



Containerboard Interlaboratory Testing Program

Participant Summary Report #643 - April 2023

[Introduction to the Containerboard Program](#)

[Explanation of Tables and Definitions of Terms](#)

Analysis	Sample	Analysis Name
201	BX17	Top to Bottom Box Compression Strength, Corrugated Boxes
202	EC15	Edgewise Compressive Strength, by T811, Corrugated Board
203	EC15	Edgewise Compressive Strength by T839, Corrugated Board
205	42H2	Bursting Strength (Mullen), 42 lb Linerboard
207	35E3	Bursting Strength (Mullen), 35 lb Linerboard
215	42H2	Ring Crush, 42 lb Linerboard
217	35E3	Ring Crush, 35 lb Linerboard
223	42H2	STFI, 42 lb Linerboard
225	35E3	STFI, 35 lb Linerboard
228	42H	Roughness - Stylus Method, 42 lb Linerboard
229	42H2	Roughness - Sheffield Method, 42 lb Linerboard
231	42H	Internal Bond, 42 lb Linerboard
234	42H	COF Inclined Plane (Slide Angle), 42 lb Linerboard
237	42H	Air Resistance, 42 lb Linerboard
240	CM12	Flat Crush Strength (CMT), 26 lb Corrugating Medium
250	CM12	Fluted Edge Crush Strength (CFC), 26 lb Corrugating Medium
255	CM12	Ring Crush (RCT), 26 lb Corrugating Medium
261	CM12	STFI, 26 lb Corrugating Medium

Collaborative Testing Services, Inc.
CONTAINERBOARD INTERLABORATORY TESTING PROGRAM

INTRODUCTION

The Interlaboratory Testing Program for Containerboard is operated and maintained by Collaborative Testing Services, Inc. (CTS), with technical guidance provided by the Containerboard Group of the American Forest & Paper Association. The tests are conducted on a monthly basis.

For these tests samples of linerboard and corrugating medium, that each have been separately randomized from narrow rolls, are distributed for testing weekly. One weight of medium (26 lb.) is used for Concora Flat Crush Strength, Corrugated Fluted Crush Strength, Ring Crush Strength, and STFI Compression. Two weights of linerboard are tested each month for Mullen Burst, Ring Crush, and STFI Compression: 42 lb. - every month; 35 lb. and 56 lb. - alternate months. The participants return their test results for analysis and receive a monthly report.

Please refer to the section, "EXPLANATION OF TABLES", for definitions of terms and guidelines to interpreting the results.

USE OF AVERAGE MEAN AS A COLLABORATIVE REFERENCE VALUE

The samples of linerboard and corrugating medium, which have been randomized and placed in sealed packages for distribution in this program, may be used as collaborative reference materials. The values most representative of each material are the Cumulative Grand Means in the latest reports, given at the bottom right of each table. Comparisons can only be made within one lot of material; therefore check your measurements against the Cumulative Grand Means with the same lot code as on the packages being tested.

Material	Lot Code	Dates in Use
26# Corrugating Medium	CM12	July 2021 - Current
	CM11	April 2019 - June 2021
35# Corrugating Medium	35E3	June 2022 - Current
	35E2	June 2020 - April 2022
42# Corrugating Medium	42H2	December 2022 - Current
	42H1	April 2022 - November 2022
56# Corrugating Medium	56G3	July 2022 - Current
	56G2	May 2021 - May 2022

ABOUT CTS

Founded in 1971, Collaborative Testing Services, Inc. (CTS) is a privately-owned company that specializes in interlaboratory tests for a wide variety of industries, including rubber, plastics, fasteners and metals, containerboard, paper, color, agriculture, hemp, and wine, as well as proficiency tests for forensic laboratories. All of the tests are designed to assist organizations in achieving and maintaining quality control objectives. Labs from the U.S., as well as more than 100 countries, currently participate in the CTS programs.

For further information, contact:
Collaborative Testing Services, Inc
21331 Gentry Drive
Sterling, VA 20166 USA
Voice: 571-434-1925
Fax: 571-434-1937
containerboard@cts-interlab.com

EXPLANATION OF TABLES

Each analysis is divided into three time spans. On the left side of the table are the individual laboratory results for each week of the month; in the center are each lab's statistical data for the month; and on the right are each lab's cumulative data for up to 16 weeks. At the bottom of the table are the consensus statistics for all the participants for each of the three time spans.

Definitions of Terms Used

Weekly Results

Laboratory Data

- | | |
|--------------|--|
| WebCode | - A six character laboratory identifier used to maintain information on a confidential basis. The WebCode is unique for each cycle and will change for each report. Your WebCode can be found in your Individual Report (Current Month Performance Report) and your datasheet. |
| Weekly Means | - The average of the test results obtained by the participant for each week that data were reported. |

Consensus Data

- | | |
|---------------|---|
| Wk Mean | - For each week, the average of the Means for all the participants, excluding those laboratories flagged with an 'X'. |
| Avg SD | - For each week, the average of the within-laboratory standard deviations (SD's) for all the participants, excluding those laboratories flagged with an 'X'. The Avg SD is an indication of the variation of measurements within an average laboratory. |
| SD btwn Labs | - For each week, the standard deviation of the laboratory Means about the Wk Mean, excluding those laboratories flagged with an 'X'. The SD LABS is an indication of the precision of measurement between the laboratories. |
| Labs Incl'd | - The number of laboratory Means included in the Wk Mean for that week. |
| Labs Excl'd | - The number of laboratory Means reported but excluded from the Wk Mean for that week because of outlying results ('X' following Mean). |
| Labs not rcvd | - The number of laboratories failing to report for that week. |

Monthly Results

Laboratory Data

- | | |
|-------|---|
| Mean | - For each laboratory, the average of all the weekly Means reported for this month. |
| CPV | - Comparative Performance Value , an indication of how well a laboratory's Mean agrees with the other participants. The CPV is a ratio indicating the number of standard deviations from the consensus mean (Monthly Mean). The closer a laboratory's CPV is to zero, the more consistent its results are with the other participants' data. |
| SD | - For each laboratory, the average of the weekly within-lab standard deviations (SD's) for all reported Weekly Means this month. |
| SD Wk | - The standard deviation among the laboratory's weekly Means, including those Means flagged with an 'X'. The SD Wks is an indication of that laboratory's ability to obtain constant results from week to week. |

Consensus Data

- | | |
|---------------|---|
| Month Mean | - The average of the Means for all the participants, excluding those laboratories flagged with an 'X,' reporting data for this month. |
| Avg SD | - For the current month, the average of the within-laboratory standard deviations (SD's) for all the participants, excluding those laboratories flagged with an 'X'. |
| SD btwn Labs | - For the current month, the standard deviation of the laboratory Means about the Month Mean, excluding those laboratories flagged with an 'X'. |
| SD btwn Group | - For the current month, the standard deviation of the laboratory Means within the group about the Month Mean, excluding those laboratories flagged with an 'X'. |
| SD btwn Wks | - For the current month, the average of the laboratory between week standard deviations (SD Wks') for all the participants, excluding those laboratories flagged with an 'X'. |

Cumulative Results

Laboratory Data

- | | |
|-------|---|
| Mean | - For each lab, the average of all the monthly Means reported for the weeks shown. |
| CPV | - Comparative Performance Value , an indication of how well a laboratory's cumulative mean agrees with the other participants. The CPV is a ratio indicating the number of standard deviations from the consensus mean (Monthly Mean). |
| SDr | - For each laboratory, the average of the weekly within-lab standard deviations (SD's) for the weeks shown. |
| SD Wk | - The standard deviation among the laboratory's weekly Means for the weeks shown, including those Means flagged with an 'X'. The SD Wks is an indication of that laboratory's ability to obtain constant results from week to week. |
| Wks | - The number of weeks included in the cumulative period. |
| Inst | - The two letter instrument code. Codes are summarized at the bottom of the last analysis page. |

Consensus Data

- | | |
|--------------|--|
| Grand Mean | - The average of the Means for all the participants, excluding those laboratories flagged with an 'X,' reporting data for the number of weeks included in the cumulative period. |
| Avg SD | - For the cumulative period, the average of the within-laboratory standard deviations (SD's) for all the participants, excluding those laboratories flagged with an 'X'. |
| SD btwn Labs | - For the cumulative period, the standard deviation of the laboratory Means about the Month Mean, excluding those laboratories flagged with an 'X'. |
| SD btwn Wks | - For the cumulative period, the average of the laboratory between week standard deviations for all the participants, excluding those laboratories flagged with an 'X'. |
| Labs Incld | - The number of laboratory Means included in the Grand Mean. |

Any laboratory that receives a 'flag' following a mean or standard deviation should refer to the chart below for an explanation of the data flag symbol:

<u>Flag</u>	<u>Explanation</u>
-------------	--------------------

Data Flags "**X**" and "*****" indicate a laboratory's performance on an average value differed from the consensus.

Data Flags "**H**" and "**L**" indicate a laboratory's performance on a standard deviation differed from the consensus.

Flags assigned to Weekly Means, Monthly Mean and Cumulative Mean:

- X** Excluded from the weekly means, monthly means and/or the cumulative mean. Immediate review of data and/or testing procedure is recommended.
- *** Included in the weekly means, monthly means and/or the cumulative mean; however, lab should review testing procedure and monitor future results.

Flags assigned to Weekly Means:

- H** Indicates high within-laboratory standard deviation. The laboratory SD for each week is not shown, but laboratory average SD and consensus average SD values are shown.
- L** Indicates low within-laboratory standard deviation. The laboratory SD for each week is not shown, but laboratory monthly average SD and consensus average SD values are shown.

Flags assigned to Monthly SD Wks and Cumulative SD Wks:

- H** Indicates high variability between weekly means (high week-to-week variation).
- L** Indicates low variability between weekly means (low week-to-week variation).



Containerboard Interlaboratory Testing Program
Analysis 201

Report #643
April 2023

Top to Bottom Box Compression Strength, Corrugated Boxes - BX17
TAPPI Official Test Method T804

WebCode	Monthly Results			Cumulative Results					
	Mean	CPV	SD	Mean	CPV	SD	Months	Months	Inst
23WZPF	987.8	1.76	33.38	910.1	1.26	55.98	4	EX	
2E98N2	781.8	-0.99	71.45	749.4	-1.82	27.30	4	LS	
3VWDF8	896.4	0.54	83.45	905.6	1.17	9.40	4	EX	
9ATVEK	836.2	-0.26	99.68	822.0	-0.43	34.63	4	LG	
9CJ9B6	753.9	-1.36	79.68	816.0	-0.54	85.71	4	LS	
9P3QP7	828.0	-0.37	60.21	840.6	-0.07	17.82	2	LG	
AB28WL	951.6	1.28	24.46	893.5	0.94	82.21	4	LG	
B7MURT	920.2	0.86	67.34	850.0	0.11	48.01	4	ER	
B8W733	819.9	-0.48	51.47	819.3	-0.48	54.77	3	LH	
BFQBV4	837.2	-0.25	75.23	840.2	-0.08	41.46	3	EX	
CHUQXM	752.1	-1.39	39.79	778.8	-1.26	60.77	4	LL	
CMPKVN	913.4	0.77	102.45	855.4	0.21	44.59	4	XX	
DAG3WT	906.5	0.68	43.17	928.6	1.61	22.03	4	ER	
DBPPFK	837.7	-0.24	92.46	845.4	0.02	36.25	4	LM	
DRXXYK	858.0	0.03	48.16	809.5	-0.67	32.76	4	EX	
DTTNJ2	809.3	-0.62	45.08	842.8	-0.03	53.68	4	ET	
L2BTRQ	862.2	0.08	15.43	827.4	-0.33	39.06	4	TB	
LHGKNN	909.1	0.71	48.99	868.6	0.46	76.25	4	LL	
P3ZVC	922.5	0.89	52.30	790.2	-1.04	89.09	4	ER	
P6HEUL	819.6	-0.49	96.20	788.3	-1.07	41.14	4	EX	
PC27BU	736.1	-1.60	22.93	852.8	0.16	80.81	4	LG	
QUWZJB	961.4	1.41	20.29	961.4	2.24 *	0.00	1	LS	
TVHYT7	782.8	-0.98	127.24 H	786.0	-1.12	55.39	4	ER	
UMALF9	786.1	-0.93	20.12	772.0	-1.39	15.92	4	EX	
WGENL3	991.7	1.81	34.34	923.9	1.52	47.68	4	LM	
ZQ97PZ	752.4	-1.39	33.00	844.4	0.00	61.76	4	ER	
ZTXDAX	897.0	0.55	38.91	877.6	0.63	39.92	4	LO	
Consensus (All Labs) Results									
Month Mean	855.96			Grand Mean	844.43				
Avg SD	63.63			Avg SD Months	52.82				
SD btwn Labs	74.77			SD btwn Labs	52.27				
Labs Incl	27			Labs Incl	27				



Containerboard Interlaboratory Testing Program
Analysis 201

Top to Bottom Box Compression Strength, Corrugated Boxes - BX17
TAPPI Official Test Method T804

Report #643
April 2023

Consensus By Method

Test Method	Group Mean	SD btwn Group	Difference from Grand Mean	Labs Included
Hot melt adhesive sealing	855.88	62.99	0.08	8
Clip sealing	853.19	82.20	2.77	18
Staple sealing	906.52	0.00	50.56	1

Key to Instrument Codes Reported by Participants

ER	Emerson 6200 Series	ET	Emerson 7200
EX	Emerson Apparatus (Model not specified)	LG	TLS / L.A.B. Validator Series
LH	L.A.B. Compression Tester Model #10610	LL	Lansmont 76-5K
LM	Lansmont 122-15k	LO	Lansmont 152-30k
LS	Lansmont Squeezer	TB	TMI Monitor/Compression Tester, Model 17-70
XX	Instrument make/model not specified by lab		



Containerboard Interlaboratory Testing Program
Analysis 202

Report #643
April 2023

Edgewise Compressive Strength, by T811, Corrugated Board - EC15
TAPPI Official Test Method T811

WebCode	Monthly Results				Cumulative Results					
	Mean	CPV	SD		Mean	CPV	SD	Months	Months	Inst
23WZPF	42.4	0.06	2.53		44.0	0.73	1.27	4		LC
3CXET7	41.8	-0.20	1.66		40.5	-1.41	1.45	3		TS
9CJ9B6	40.7	-0.69	2.19		41.8	-0.63	3.64	4		LD
AB28WL	44.0	0.73	0.93	L	43.4	0.35	0.75	4		EM
B7MURT	42.3	-0.01	2.87		42.5	-0.16	1.39	3		EN
CMPKVN	42.3	0.03	3.26		43.5	0.44	1.46	4		TS
EZR4TL	38.5	-1.62	1.29		40.4	-1.45	1.97	4		XX
JKCVEB	155.0	48.26 X	7.32 H		158.5	70.23 X	3.63	4		LD
UGGA8D	47.1	2.05 *	3.44		45.3	1.50	1.64	3		XX
UMALF9	41.5	-0.34	2.26		43.8	0.64	2.47	4		LC
Consensus (All Labs) Results										
Month Mean	42.28			Grand Mean	42.79			Avg SD Months	1.95	
Avg SD	2.41			SD btwn Labs	1.65			Labs Incl'd	9	
SD btwn Labs	2.33			Labs Incl'd	9					
Labs Incl'd	9									

Key to Instrument Codes Reported by Participants

EM	Emerson 1200 Series	EN	Emerson 2200
LC	L&W Crush Tester 48	LD	L&W Crush Tester 248
TS	TMI Digital Crush Tester, Model 17-56	XX	Instrument make/model not specified by lab



Containerboard Interlaboratory Testing Program
Analysis 203

Report #643
April 2023

Edgewise Compressive Strength by T839, Corrugated Board - EC15
TAPPI Official Test Method T839

WebCode	Monthly Results			Cumulative Results						
	Mean	CPV	SD	Mean	CPV	SD	Months	Months	Inst	
23WZPF	46.8	0.00	1.26	48.9	0.58	2.15	4	LC		
2E98N2	44.0	-0.80	1.85	43.2	-0.95	0.57	4	EM		
3CXET7	40.2	-1.83	1.94	44.6	-0.57	4.35	3	TS		
3VWDF8	44.3	-0.70	2.68	45.1	-0.46	0.75	4	CT		
73XNUM	45.5	-0.38	1.92	47.1	0.10	1.33	4	TU		
9CJ9B6	47.8	0.26	1.31	46.1	-0.17	1.48	4	LD		
9P3QP7	45.5	-0.38	2.09	45.5	-0.33	0.21	L	4	EM	
A44FNR	47.4	0.16	0.92	47.2	0.12	1.87	4	LD		
AB28WL	45.1	-0.48	1.23	44.2	-0.68	0.89	4	LY		
B7MURT	48.3	0.39	1.49	47.6	0.24	1.19	4	EN		
B8W733	51.7	1.34	1.86	47.4	0.18	4.85	H	3	EM	
BFQBV4	44.5	-0.66	0.96	44.0	-0.73	0.63	3	TL		
CMPKVN	47.0	0.04	1.48	49.1	0.63	4.32	4	TS		
DAG3WT	46.6	-0.07	1.23	47.8	0.27	1.01	4	LD		
DBPPFK	48.2	0.37	1.92	45.8	-0.25	2.39	4	TG		
DRXXYK	41.9	-1.37	2.44	42.9	-1.03	1.52	4	LD		
DTTNJ2	50.6	1.05	2.08	48.8	0.54	1.62	4	TD		
EZR4TL	39.0	-2.17 *	1.25	40.7	-1.62	2.14	4	XX		
G9CB4M	30.7	-4.48 X	1.84	36.9	-2.64 *	5.42	H	4	XX	
L2BTRQ	54.8	2.20 *	0.46	L	55.6	2.36 *	0.84	4	LD	
LHGKNN	47.6	0.20	0.73	L	46.8	0.01	0.91	4	BU	
P3ZVCC	42.7	-1.14	1.18	42.7	-1.08	0.13	L	4	LD	
PC27BU	50.8	1.10	1.49	51.3	1.23	3.23	3	MK		
PJMD6D	46.8	0.00	1.79	46.5	-0.07	0.46	4	LD		
QBM43Z	44.5	-0.64	1.85	44.3	-0.66	0.96	4	BU		
QL7T9D	49.2	0.66	1.59	49.8	0.82	0.74	4	TG		
QUWZJB	56.2	2.59 *	2.30	56.2	2.53 *	0.00	1	EM		
TVHYT7	45.9	-0.28	1.73	45.4	-0.37	0.78	4	EM		
U9L872	49.4	0.70	1.41	49.1	0.62	0.30	L	4	TH	
UMALF9	49.9	0.85	2.01	49.1	0.62	1.13	4	LC		
V6GZ2F	49.3	0.68	0.68	L	49.2	0.65	0.15	L	3	EM
WGENL3	46.8	-0.02	1.75	46.5	-0.06	1.47	4	EM		
WJZHGH	47.5	0.18	1.87	52.5	1.53	3.57	4	LC		
YEEZ3C	43.2	-1.02	1.51	46.0	-0.21	3.97	2	TD		
ZQ97PZ	47.3	0.13	2.10	46.3	-0.12	0.82	4	LD		
ZTXDAX	43.4	-0.97	2.03		43.0	-1.02	1.26	4	LD	



Containerboard Interlaboratory Testing Program
Analysis 203

Report #643
April 2023

Edgewise Compressive Strength by T839, Corrugated Board - EC15
TAPPI Official Test Method T839

Consensus (All Labs) Results

Month Mean	46.85	Grand Mean	46.75
Avg SD	1.69	Avg SD Months	2.21
SD btwn Labs	3.61	SD btwn Labs	3.74
Labs Incl'd	35	Labs Incl'd	36

Key to Instrument Codes Reported by Participants

BU	Buchel Digital Crush Tester	CT	Con-Ten
EM	Emerson 1200 Series	EN	Emerson 2200
LC	L&W Crush Tester 48	LD	L&W Crush Tester 248
LY	L&W 830	MK	Mark-10 ESM303
TD	TMI Digital Crush Tester, Model 17-09	TG	TMI Digital Crush Tester, 17-76
TH	TMI Monitor/Compression Tester, Model 17-76	TL	Tech-Lab Systems Compression
TS	TMI Digital Crush Tester, Model 17-56	TU	TMI Universal Crush Tester (TMI K440)
XX	Instrument make/model not specified by lab		



Containerboard Interlaboratory Testing Program

Analysis 205

Report #643

April 2023

Bursting Strength (Mullen), 42 lb Linerboard - 42H2

TAPPI Official Test Method T807

WebCode	Weekly Means				Monthly Results					Cumulative Results					
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst	
2AGQYA	109.8	115.2	111.8	109.7	111.6	-1.05	11.2	2.6	110.5	-1.33	10.0	5.4	16	LC	
2M3DG3	114.0	115.0	114.1	116.3	114.9	-0.30	5.8	1.1	115.5	-0.15	6.1	1.0	16	TP	
3VWDF8	120.0	119.0	H	120.0	120.4	0.97	9.8	1.5	117.6	0.37	10.6	3.0	16	XX	
7GW8BQ	121.3	120.2	118.7	123.4	120.9	1.09	9.0	2.0	121.4	1.29	9.4	2.8	16	LJ	
7JLEV M	118.0	117.5	111.4	112.8	114.9	-0.28	8.9	3.3	108.6	-1.78	9.4	4.8	16	RE	
8N24YW_AL	119.5	121.6	123.8	118.9	121.0	1.10	8.8	2.2	118.9	0.68	8.9	3.1	16	AL	
8VEAFZ	No Data	103.6 *	124.5	109.9	112.7	-0.80	7.7	10.7 H	117.0	0.22	7.4	6.0	14	TB	
92JDY8_AL	112.8	114.9	115.5	116.0	114.8	-0.31	9.7	1.4	117.4	0.32	9.4	3.1	16	AL	
9CJ9B6	117.2	117.8	H	120.1	117.5	0.30	10.2	2.1	115.9	-0.04	10.1	3.2	16	LA	
A44FNR	122.8	114.7	111.6	116.4	116.4	0.05	9.5	4.7	114.7	-0.33	9.0	4.0	16	LA	
AB28WL	121.8	120.8	124.8	122.7	122.5	1.46	8.2	1.7	123.6	1.80	8.0	2.4	16	AH	
BA776N	114.2	108.9	112.9	113.1	112.3	-0.89	7.7	2.3	112.7	-0.81	7.5	2.0	16	ME	
BQBBVL	118.4	116.6	112.4	117.0	116.1	-0.02	7.7	2.6	116.9	0.20	9.9	3.2	16	LZ	
C7YK34	120.7	115.0	118.2	115.3	117.3	0.26	7.9	2.7	117.9	0.44	9.4	3.1	16	LC	
CVXM3M	121.8	121.7	120.6	121.5	121.4	1.20	10.0	0.5 L	119.1	0.74	10.6	4.6	16	LC	
DRXXYK	114.8	118.4	111.6	116.8	115.4	-0.18	9.1	2.9	118.2	0.51	8.6	3.6	16	AH	
EH7AT4	113.8	109.4	109.6	107.1	110.0	-1.42	9.2	2.8	111.9	-1.01	9.2	3.2	16	LA	
EZR4TL	117.1	115.1	115.7	115.2	115.8	-0.09	5.5	0.9	114.9	-0.27	6.1	2.1	16	LC	
FJAWQL_AL	121.6	111.3	H	119.4	126.1 *	0.78	9.3	6.2	117.1	0.25	9.6	3.4	16	AL	
FN8CLN	119.5	123.2	117.3	121.0	120.2	0.93	9.1	2.5	119.8	0.89	9.0	2.2	16	LA	
FVQLQC_AL	115.3	116.0	118.7	No Data	116.7	0.11	8.5	1.8	115.5	-0.15	9.5	3.9	13	AL	
GALTDY	116.1	116.3	116.3	117.1 L	116.5	0.06	5.5	0.4 L	116.7	0.14	4.8	0.4 L	16	LA	
GECXT2_AL	123.5	116.6	114.4	117.5	118.0	0.42	8.4	3.9	115.9	-0.05	9.0	3.5	16	AL	
HBWKQU_AI	113.8	115.0	119.1	119.9	116.9	0.18	8.8	3.0	116.3	0.05	10.0	2.3	16	AL	
JKCVEB	103.8 *	102.9 *	103.5 *	107.4	104.4	-2.69 *	8.2	2.0	105.5	-2.54 *	8.4	3.1	16	LA	
L2BTRQ	107.1	115.4	107.1	113.8	110.8	-1.23	8.2	4.4	111.3	-1.14	8.2	3.7	16	XX	
L6HFLH	116.9	116.6	115.5	116.8	116.5	0.06	7.0	0.6	116.5	0.10	6.7	1.0	16	AH	
LDBLG6_AL	110.6	105.9 *	108.9	110.9	109.1	-1.62	6.3	2.3	111.1	-1.19	6.2	3.6	12	AL	
LHMUJU	111.0	111.5	108.1	110.9	110.4	-1.33	5.3	1.5	110.6	-1.31	8.1	3.1	16	LC	
LZPCUZ	114.2	116.0	111.4	114.0	113.9	-0.52	7.2	1.9	112.4	-0.88	8.7	3.8	16	LZ	
M6BN6L	113.8	116.8	108.9	110.3	112.5	-0.85	8.5	3.6	120.0	0.95	7.3	5.3	16	AX	
MYP9K2	127.9 *	111.3	109.8	109.4	114.6	-0.36	8.3	8.9 H	112.6	-0.83	8.7	6.3	16	LA	
MYP9K2_AL	127.9 *	121.1	126.7 * H	118.7	123.6	1.70	10.5	4.4	125.6	2.28 * 10.1	4.3	16	AL		
N3KG43_AL	122.4	115.7	125.0	No Data	121.0	1.11	11.5	4.8	117.7	0.39	9.8	3.7	15	AL	
P3ZVCC	110.3	110.4	115.7	115.5	113.0	-0.74	9.7	3.0	111.7	-1.05	9.8	3.8	16	LA	



Containerboard Interlaboratory Testing Program

Analysis 205

Report #643

April 2023

Bursting Strength (Mullen), 42 lb Linerboard - 42H2

TAPPI Official Test Method T807

WebCode	Weekly Means				Monthly Results					Cumulative Results					
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst	
PJMD6D_AL	119.5	115.2	114.9	117.6	116.8	0.15	5.4	2.2	119.6	0.85	6.4	3.0	16	AK	
PMMMB9	116.6	115.4	115.7	116.9	116.2	0.00	5.4	0.7	115.1	-0.22	5.9	1.2	16	LJ	
PQK9Y6_AL	108.1	111.7	110.8	113.2	110.9	-1.20	6.2	2.1	110.9	-1.24	6.5	2.3	16	XX	
PZDCBE	122.7	120.2	H	119.3	120.4	0.97	10.6	1.6	118.8	0.65	10.1	3.2	16	LA	
PZDCBE_AL	120.5	121.2	122.5	116.5	120.2	0.92	8.3	2.6	116.3	0.05	7.5	3.4	16	AL	
RP6G8Z	117.6	120.9	112.0	126.6 *	119.3	0.71	9.0	6.1	118.0	0.47	10.0	6.5	16	LB	
TNNT2Q	116.5	116.1	116.5	108.4	114.4	-0.41	9.8	4.0	114.1	-0.48	9.5	3.2	16	LA	
TNPJEZ	117.2	119.5	117.1	124.0	119.5	0.75	6.4	3.2	119.3	0.78	6.4	2.3	16	LA	
TTJHM4	111.3 L	113.9 L	112.5 L	115.2 L	113.2	-0.67	3.2	1.7	115.1	-0.22	3.3	1.9	16	LA	
TX9RLN_AL	102.7 *	109.7	112.0	112.8	109.3	-1.57	11.2	4.6	110.3	-1.38	8.7	4.6	16	AL	
U88EXX_AL	118.4	119.7	117.2	119.8	118.8	0.60	7.9	1.2	117.5	0.34	7.2	2.0	16	AL	
UBCDND	126.0	125.2 *L	125.3 L	125.0 L	125.4	2.11 *	3.4	0.4 L	125.9	2.37 *	3.5	0.7 L	16	AH	
UBUJM4	109.2	110.4	110.3	No DATA	110.0	-1.42	5.6	0.6	110.7	-1.29	5.9	2.1	11	XX	
UGMRJB_AL	119.6	118.5	121.5	123.0	120.7	1.03	6.9	2.0	122.3	1.49	7.8	2.0	16	AL	
UMALF9	117.7	112.8	110.8	109.8	112.8	-0.78	8.8	3.5	110.7	-1.28	8.6	6.8	16	AH	
WKBD3A_AL	116.8	111.3	117.2 H	113.1	114.6	-0.36	11.5	2.8	116.6	0.14	10.1	3.0	16	AL	
WT6HWB_AI	122.3 L	118.8	118.1 L	119.3 L	119.6	0.80	3.0	1.9	119.6	0.86	3.0	1.9	4	XX	
YZYCZM	110.1	115.1	116.3	109.1	112.7	-0.81	7.5	3.6	112.8	-0.79	8.6	2.9	16	LC	
ZQ97PZ	115.7	112.4	109.7	112.2	112.5	-0.84	9.0	2.5	115.9	-0.05	7.9	3.4	16	AH	
ZZX8E7	125.4	122.2	126.9 *	118.0	123.1	1.60	8.4	4.0	120.4	1.04	9.6	5.2	12	LC	
ZZX8E7_AL	118.5	119.6	126.0	123.9	122.0	1.33	8.7	3.6	120.9	1.16	9.3	2.7	12	AL	
Consensus (All Labs) Results															
Wk Mean	116.83	115.66	115.99	116.28	Month Mean		116.17		Grand Mean		116.07				
Avg SDr	8.59	8.40	8.06	8.18	Avg SD		8.32		Avg SD		8.40				
SD btwn Labs	5.55	4.69	5.53	5.03	SD btwn Labs		4.36		SD btwn Labs		4.16				
Labs Incld	55	56	56	53	SD btwn Wks		3.40		SD btwn Wks		3.53				
Labs Excld	0	0	0	0	Labs Incld		56		Labs Incld		56				
Labs not Rcvd	1	0	0	3											



Containerboard Interlaboratory Testing Program

Analysis 205

Bursting Strength (Mullen), 42 lb Linerboard - 42H2

TAPPI Official Test Method T807

Report #643

April 2023

Key to Instrument Codes Reported by Participants

AH	Perkins Model AH	AK	L & W Autoline 300
AL	L & W Autoline 400	AX	Perkins Mullen Tester (model not specified)
LA	L&W Bursting Strength Tester	LB	L&W Burst-O-Matic
LC	L&W Autoline (205 Enrollment)	LJ	L&W Bursting Strength Tester J-Type
LZ	L&W (model not specified)	ME	Messmer Automatic Burst Tester ME-06
RE	Regmed/Mullen Tester	TB	TMI Monitor/Burst 1000
TP	Technidyne PROFILE/Plus	XX	Instrument make/model not specified by lab



Containerboard Interlaboratory Testing Program

Analysis 207

Report #643

April 2023

Bursting Strength (Mullen), 35 lb Linerboard - 35E3

TAPPI Official Test Method T807

WebCode	Weekly Means				Monthly Results					Cumulative Results					
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst	
2AGQYA	89.9 H	87.4	87.3	83.1	86.9	-1.11	7.6	2.8	89.3	-0.56	7.9	2.9	12	LC	
2M3DG3	90.7	91.3	92.9	92.6	91.9	0.09	5.9	1.0	90.8	-0.13	6.2	1.5	12	TP	
3VWDF8	91.0	90.0	93.0	91.5	91.4	-0.04	7.7	1.3	91.6	0.09	8.1	1.9	12	XX	
7GW8BQ	87.0	92.5	91.3	93.6	91.1	-0.10	7.6	2.9	92.2	0.25	9.0	4.0	12	LJ	
7JLEVM	88.4	91.0	88.0	86.2	88.4	-0.75	6.7	2.0	82.8	-2.37 * 6.4	4.7	12	RE		
8N24YW_AL	87.5	90.3	92.2	94.6	91.2	-0.09	7.5	3.0	91.6	0.08	7.6	3.1	12	AL	
8VEAFZ	No Data	94.4	89.2	117.4 XH	100.3	2.13 *	10.3	15.0 H	95.2	1.10	8.2	9.6 H	11	TB	
92JDY8_AL	91.0	90.8	88.8	89.7	90.1	-0.36	8.0	1.0	91.2	-0.03	9.0	3.0	12	AL	
9CJ9B6	90.2	93.4	92.5	84.9	90.2	-0.31	8.7	3.8	91.0	-0.07	8.2	2.6	12	LA	
A44FNR	90.3	84.8	88.1	91.6	88.7	-0.68	9.0	3.0	88.6	-0.74	8.7	2.9	12	LA	
AB28WL	95.6	99.6	95.0	93.7	96.0	1.08	8.2	2.5	97.3	1.67	7.8	3.2	12	AH	
BA776N	94.0	90.6	88.2	96.1	92.2	0.17	7.5	3.5	92.6	0.37	7.7	3.2	12	ME	
BQBBVL	85.2	94.3	92.8	93.3	91.4	-0.03	7.7	4.2	92.2	0.26	8.1	2.9	12	LZ	
C7YK34	88.9	91.1	94.3	94.2	92.1	0.15	7.9	2.6	91.5	0.07	8.4	2.5	12	LC	
CVXM3M	95.0	91.9	92.6	96.4	94.0	0.60	8.1	2.1	92.9	0.44	8.0	3.4	12	LC	
DRXXYK	93.2	92.4	96.4	90.4	93.1	0.38	6.2	2.5	93.5	0.62	7.4	3.0	12	AH	
EH7AT4	84.8	86.8	83.6	84.5	84.9	-1.60	6.7	1.4	86.0	-1.46	8.0	1.7	12	LA	
FJAWQL_AL	87.0	91.2	95.2 H	87.2	90.1	-0.34	8.6	3.8	89.9	-0.37	8.9	3.9	12	AL	
FN8CLN	93.3	94.5	96.3 L	91.2 L	93.8	0.55	4.5	2.1	92.3	0.29	6.7	2.7	12	LA	
FVQLQC_AL	96.4	92.5	89.7	No Data	92.8	0.32	6.4	3.4	90.3	-0.26	9.0	4.1	11	AL	
GALTDY	91.1 L	91.9 L	90.7 L	91.3 L	91.3	-0.07	2.8	0.5 L	91.2	-0.02	4.6	0.5 L	12	LA	
GECXT2_AL	86.1	87.1	91.7	89.9	88.7	-0.68	8.1	2.6	90.5	-0.22	9.2	4.1	12	AL	
HBWKQU_AI	86.7	93.0	95.6	93.9	92.3	0.18	6.7	3.9	91.2	-0.01	8.6	3.0	10	AL	
JKCVEB	82.1 *	81.0 *	81.8 *	83.5	82.1	-2.28 *	6.7	1.0	82.3	-2.50 *	6.6	2.3	12	LA	
L2BTRQ	86.3	89.7	83.9	85.5	86.4	-1.24	6.6	2.5	87.5	-1.04	7.9	3.1	8	XX	
L6HFLH	90.0	90.7	91.4	91.4	90.9	-0.16	6.3	0.7	90.9	-0.10	6.4	1.1	12	AH	
LDBLG6_AL	89.0	87.9	90.2	90.8	89.5	-0.49	5.4	1.3	89.3	-0.56	5.5	2.4	12	AL	
LHMUJU	81.0 *	80.0 *	84.3	81.8 *	81.8	-2.35 *	6.0	1.8	84.3	-1.95 *	8.1	3.6	12	LC	
LZPCUZ	82.0 *	86.3	87.3	89.9	86.4	-1.24	9.2	3.3	88.8	-0.68	7.9	3.0	12	XX	
M6BN6L	95.8	103.0 *	95.5	114.9 X	102.3	2.61 *	9.5	9.1 H	99.8	2.36 *	8.8	6.0	12	AX	
MYP9K2	90.6	86.7	83.2 *	87.4	87.0	-1.10	6.2	3.0	87.4	-1.08	7.9	3.2	12	LA	
MYP9K2_AL	90.6	88.1 H	93.6 H	91.6	91.0	-0.13	11.1	2.3	89.4	-0.51	10.4	2.1	12	AL	
N3KG43_AL	95.4	102.5 *	99.4 *	No Data	99.1	1.83	6.0	3.6	96.2	1.37	7.6	4.4	11	XX	
P3ZVCC	87.9	88.0	88.8	90.1	88.7	-0.68	7.3	1.0	87.8	-0.97	9.3	2.7	12	LA	
PJMD6D_AL	92.0	93.8	89.1	95.0	92.5	0.23	7.3	2.6	94.0	0.75	7.1	1.9	12	AK	



Containerboard Interlaboratory Testing Program

Analysis 207

Bursting Strength (Mullen), 35 lb Linerboard - 35E3

TAPPI Official Test Method T807

Report #643

April 2023

WebCode	Weekly Means				Monthly Results					Cumulative Results					
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst	
PMMMB9	91.9	92.7	91.8	92.0	92.1	0.14	5.8	0.4	92.4	0.31	5.2	0.8	L	12	LJ
PQK9Y6_AL	86.9	90.1	88.4	90.9	89.1	-0.59	5.0	1.8	87.4	-1.09	5.1	1.7	12		XX
PZDCBE	95.7	99.8	99.4	*	97.9	98.2	1.62	8.4	96.5	1.46	7.9	3.0	12		LA
PZDCBE_AL	93.3	95.8	92.4	95.3	94.2	0.64	4.5	1.6	92.7	0.39	5.2	2.2	12		AL
RP6G8Z	91.7	89.9	94.2	101.8	*	94.4	0.69	9.1	94.7	0.96	9.5	3.8	12		LB
TNNT2Q	90.9	89.9	90.3	88.0	89.8	-0.42	7.6	1.3	89.4	-0.52	7.5	2.4	12		LA
TNPJEZ	99.0	*	98.8	92.2	104.2	X	98.6	1.70	95.0	1.03	5.5	4.3	12		LA
TTJHM4	90.1	L	90.0	L	92.2	L	90.9	L	93.5	0.63	2.6	3.0	12		LA
TX9RLN_AL	87.2	90.5	78.4	X	86.5	85.6	-1.42	8.2	61.2	-8.39	X	6.9	36.3	H	12
U88EXX_AL	94.8	95.2	93.6	95.9	94.9	0.81	7.4	0.9	93.1	0.52	6.8	1.9	12		AL
UBCDND	96.7	96.2	96.3	L	96.0	L	96.3	1.16	100.0	2.42	*	3.5	2.7	12	AH
UBUJM4	91.6	89.1	89.8	NO DATA	90.2	-0.33	6.1	1.3	89.7	-0.43	6.0	2.0	10		XX
UGMRJB_AL	95.8	94.3	93.7	97.1	95.2	0.90	5.9	1.5	94.0	0.76	6.1	2.4	12		AL
UMALF9	91.4	87.6	88.5	86.8	88.6	-0.71	9.3	2.0	88.6	-0.76	8.1	6.8	12		AH
WKBD3A_AL	96.7	93.3	89.7	95.1	93.7	0.53	8.6	3.0	93.9	0.73	8.1	2.3	12		AK
WT6HWB_AI	92.0	L	90.7	91.4	L	91.0	L	91.3	0.00	2.7	0.6	L	4		XX
YZYCZM	88.7	89.9	85.8	92.5	89.2	-0.56	6.0	2.8	87.6	-1.01	6.1	2.8	12		LA
ZQ97PZ	94.4	96.4	89.4	91.1	92.8	0.32	8.0	3.2	93.9	0.74	7.4	3.1	12		AH
ZZX8E7	98.4	93.8	99.3	*	95.7	96.8	1.27	7.4	90.5	-0.22	6.5	8.6	H	12	LC
Consensus (All Labs) Results															
Wk Mean	90.81	91.56	91.17	91.28	Month Mean		91.52		Grand Mean			91.28			
Avg SDr	6.85	7.17	7.08	7.59	Avg SD		7.21		Avg SD			7.45			
SD btwn Labs	4.15	4.45	4.03	4.25	SD btwn Labs		4.13		SD btwn Labs			3.59			
Labs Incld	53	54	53	48	SD btwn Wks		3.50		SD btwn Wks			3.52			
Labs Excld	0	0	1	3	Labs Incld		54		Labs Incld			53			
Labs not Rcvd	1	0	0	3											

Key to Instrument Codes Reported by Participants

AH	Perkins Model AH	AK	L & W Autoline 300
AL	L & W Autoline 400	AX	Perkins Mullen Tester (model not specified)
LA	L&W Bursting Strength Tester	LB	L&W Burst-O-Matic
LC	L&W Autoline (207 Enrollment)	LJ	L&W Bursting Strength Tester J-Type
LZ	L&W (model not specified)	ME	Messmer Automatic Burst Tester ME-06
RE	Regmed/Mullen Tester	TB	TMI Monitor/Burst 1000
TP	Technidyne PROFILE/Plus	XX	Instrument make/model not specified by lab



Containerboard Interlaboratory Testing Program
Analysis 215
Ring Crush, 42 lb Linerboard - 42H2
TAPPI Official Test Method T822

Report #643
April 2023

WebCode	Weekly Means				Monthly Results				Cumulative Results					
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst
2AGQYA	100.4	98.6	99.4	100.7	99.8	0.96	3.7	1.0	97.2	0.53	4.1	2.2	16	LD
2GTGB8	94.6 L	92.5 L	94.8 L	93.1 L	93.8	-0.38	1.2	1.1	94.1	-0.53	2.2	1.4	16	TH
2M3DG3	96.4	96.9	96.5	95.6	96.3	0.19	3.0	0.5 L	95.3	-0.13	3.0	1.2	16	TH
2VE239	94.2	99.2	93.4	100.3	96.8	0.29	3.8	3.5	95.7	0.01	4.4	6.8 H	16	LD
3Z42VU	94.1 L	95.0	94.6	94.1	94.5	-0.23	1.8	0.4 L	94.1	-0.56	1.8	0.5 L	12	MB
7JLEVM	85.1 *H	87.5 H	87.7 *H	82.7 XH	85.8	-2.17 *	10.6	2.3	89.4	-2.15 *	8.2	5.6	16	EM
8VEAFZ	No Data	No Data	104.6 *	105.2 *	104.9	2.10 *	3.9	0.4	102.2	2.23 *	3.2	5.4	13	LD
92JDY8	65.6 XH	65.6 X	66.6 XH	64.7 XH	65.6	-6.68 X	6.9	0.8	75.5	-6.87 X	6.2	11.7 H	16	LD
9CJ9B6	95.1	96.1	94.6	95.8	95.4	-0.01	2.7	0.7	94.6	-0.36	2.6	2.7	16	LD
9H7QDY	94.4	93.8	94.5	92.3	93.7	-0.39	4.2	1.0	84.7	-3.74 X	4.2	6.8 H	12	EM
AB28WL	93.1	91.9	93.2	93.6	93.0	-0.56	2.1	0.7	93.9	-0.62	2.4	1.4	16	LG
B7MURT	89.3	90.8	94.5	94.2	92.2	-0.73	3.0	2.6	93.4	-0.79	3.1	1.9	16	EN
BA776N	103.3	103.8 *	104.4 *	101.7	103.3	1.75	3.7	1.1	102.0	2.15 *	4.3	1.5	15	LX
BQBBVL	95.8	90.5	73.0 X	76.0 X	83.8	-2.61 *	3.0	11.0 H	90.4	-1.81	2.9	6.8 H	16	LC
C7YK34	100.4 H	101.5	99.8 H	103.7 H	101.3	1.31	6.4	1.8	98.4	0.92	4.4	2.6	16	MB
CVXM3M	97.9	97.5	94.1	93.9	95.9	0.09	2.7	2.1	94.9	-0.28	2.7	1.7	16	LD
DT7FAX	48.7 XH	48.1 XH	50.5 XH	49.0 XH	49.1	-10.39 X	37.4	1.0	65.4	-10.32 X	26.9	17.6 H	8	LZ
FN8CLN	98.6	94.5	96.3	95.3	96.2	0.16	3.6	1.8	96.1	0.13	3.6	1.4	7	LZ
FVQLQC	97.8 H	94.0	98.9	95.9	96.7	0.26	5.0	2.2	96.9	0.41	4.5	2.2	16	LC
GEXT2	97.7	99.7	97.3	95.4	97.5	0.46	2.5	1.7	97.2	0.53	2.4	1.5	16	LD
HBWKQU	97.2	97.9	96.7	94.3	96.5	0.23	2.3	1.6	97.0	0.44	2.7	2.3	16	LD
JKCVEB	140.4 X	146.6 X	143.2 X	140.5 X	142.7	10.57 X	4.2	2.9	128.8	11.28 X	10.6	20.2 H	16	LB
LHMUJU	94.9 L	96.4	93.3	91.7	94.1	-0.31	2.5	2.0	93.0	-0.92	2.9	1.7	16	LZ
M6BN6L	90.2	95.9	91.2	91.5	92.2	-0.73	4.1	2.5	92.1	-1.24	3.4	1.7	16	LD
N3KG43	98.7	98.4	100.4	76.5 XH	93.5	-0.44	5.4	11.4 H	96.9	0.40	4.4	5.9	16	LZ
P3ZVCC	93.8	96.3	94.5 L	96.9	95.3	-0.03	2.6	1.5	95.5	-0.06	2.8	2.4	16	LD
PJMD6D	92.9	92.4	95.9	94.6	94.0	-0.34	2.2	1.6	94.9	-0.28	2.4	2.6	16	LD
PMMMB9	95.8 L	96.0 L	96.2	96.2	96.0	0.13	1.7	0.2 L	96.2	0.19	2.4	0.4 L	16	LD
PQK9Y6	98.5	97.6	95.9	96.2	97.1	0.36	2.8	1.2	97.4	0.58	2.6	1.3	16	LD
PZDCBE	97.2	92.4	96.4	95.1	95.3	-0.05	2.9	2.1	95.6	-0.03	3.1	1.7	16	LD
QL7T9D	97.1	98.3	94.9	96.3	96.6	0.26	3.1	1.4	96.3	0.22	2.7	1.3	16	TH
RGC9L9	80.7 XH	77.3 XH	79.5 XH	106.8 *	86.1	-2.10 *	11.1	13.9 H	97.1	0.47	7.5	9.3 H	16	TU
RP6G8Z	102.7	93.2	96.6	89.7	95.5	0.02	3.3	5.5	95.5	-0.07	3.0	3.4	16	LD
TNPJEZ	93.5	95.1	91.2	94.5	93.6	-0.42	3.7	1.7	92.0	-1.25	3.4	3.6	16	LC
TTJHM4	102.8 L	102.1 L	102.5	103.3 L	102.6	1.60	1.6	0.5 L	98.1	0.83	1.3	2.8	16	TU



Containerboard Interlaboratory Testing Program

Analysis 215

Ring Crush, 42 lb Linerboard - 42H2

TAPPI Official Test Method T822

Report #643

April 2023

WebCode	Weekly Means				Monthly Results				Cumulative Results					
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst
UBCDND	96.3	96.3	95.4	96.2	96.1	0.13	2.7	0.4	95.4	-0.09	2.5	1.8	16	LD
UBUJM4	104.9 *	102.9	107.4 X	No DATA	105.1	2.15 *	3.1	2.3	101.6	2.03 *	3.3	3.2	11	TU
UMALF9	98.0	93.8	96.9	96.7	96.3	0.20	3.3	1.8	97.2	0.50	2.7	1.5	16	LC
UWTZF6	100.3	105.0 *	104.5 *	102.5	103.1	1.70	2.8	2.1	99.6	1.34	2.7	3.0	16	LD
V6GZ2F	96.3	98.8	97.5	99.4	98.0	0.57	3.0	1.4	98.0	0.79	3.1	1.4	16	EM
WJZGHG	87.8 *L	88.1	87.1 *	87.8 *	87.7	-1.74	2.6	0.4	90.4	-1.79	2.9	3.9	16	LC
WKBD3A	89.7	90.4	92.5	91.2	91.0	-1.01	3.6	1.2	92.4	-1.12	3.2	1.6	16	LD
XZG2N9	104.1	89.0 H	95.7 H	96.8	96.4	0.21	6.1	6.1	100.7	1.71	4.0	4.5	16	MB
YAPTX4	92.6	92.1	92.5	101.7	94.7	-0.16	3.1	4.6	93.6	-0.70	3.3	2.9	16	LD
YVPLQ9	94.6 L	92.8 L	95.0 L	93.6 L	94.0	-0.33	1.2	1.0	94.6	-0.37	1.8	1.2	16	TH
YZYCZM	94.8	95.2	96.0	95.5	95.4	-0.02	2.7	0.5	95.7	0.01	2.7	1.0	16	LD
Z32ZBP	98.1	95.5	95.2	98.1 H	96.7	0.28	4.7	1.6	95.4	-0.09	4.0	2.3	8	RS
ZQ97PZ	98.1	96.2	96.6	97.1	97.0	0.34	2.4	0.8	96.9	0.41	2.6	1.8	16	LD
ZZX8E7	89.7	87.8	95.7	90.9	91.0	-0.99	3.0	3.4	91.1	-1.57	3.3	2.5	12	LD
Consensus (All Labs) Results														
Wk Mean	96.11	95.44	95.92	96.31	Month Mean		95.47		Grand Mean		95.68			
Avg SDr	3.71	3.61	3.82	3.15	Avg SD		3.98		Avg SD		3.48			
SD btwn Labs	4.29	4.17	3.71	4.20	SD btwn Labs		4.47		SD btwn Labs		2.94			
Labs Incld	44	44	43	42	SD btwn Wks		3.74		SD btwn Wks		3.22			
Labs Excld	4	4	6	6	Labs Incld		46		Labs Incld		45			
Labs not Rcvd	1	1	0	1										

Key to Instrument Codes Reported by Participants

EM	Emerson 1200	EN	Emerson 2200
LB	L&W Crush Tester 240	LC	L&W Crush Tester 48
LD	L&W Crush Tester 248	LG	L&W 753
LX	L&W 506	LZ	L&W Crush Tester (model not specified)
MB	Messmer Buchel K440	RS	Regmed Digital Crush Tester CT-2000
TH	TMI Compression Tester, Model 17-76	TU	TMI Universal Crush Tester (TMI K440)



Containerboard Interlaboratory Testing Program

Analysis 217

Ring Crush, 35 lb Linerboard - 35E3

TAPPI Official Test Method T822

Report #643

April 2023

WebCode	Weekly Means				Monthly Results				Cumulative Results												
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst							
2AGQYA	80.8	81.8	79.3	81.1	80.7	-0.18	4.3	1.1	82.6	0.24	4.7	2.0	12	LD							
2GTGB8	84.1	L	83.5	L	82.9	L	83.1	L	83.4	0.60	1.1	0.5	81.0	-0.43	1.9	2.2	12	TH			
2M3DG3	80.1	79.9	80.7	80.4	80.3	-0.31	3.8	0.4	80.7	-0.57	3.7	1.1	12	TH							
2VE239	74.4	78.1	72.3	*	78.0	75.7	-1.64	4.1	2.8	72.8	-3.94	X	4.0	5.2	12	LD					
3Z42VU	80.0	80.3	L	80.8	L	80.3	80.4	-0.28	1.8	0.3	L	81.6	-0.18	1.8	1.6	12	MB				
7JLEVM	62.2	XH	71.9	*H	69.5	*H	71.5	*H	68.8	-3.66	X	8.7	4.5	77.4	-1.98	*6.9	8.5	H	12	EM	
8VEAFZ	No Data	No Data	84.7	88.3	86.5	1.51	5.7	2.5	83.9	0.81	5.4	4.5	10	LC							
92JDY8	60.1	XH	59.8	X	60.6	X	59.9	X	60.1	-6.18	X	6.7	0.3	L	66.6	-6.59	X	6.3	H	12	LD
9CJ9B6	80.1	80.1	78.7	81.6	80.1	-0.36	2.6	1.2	80.7	-0.55	2.5	1.5	12	LD							
9H7QDY	75.4	77.3	75.7	75.4	75.9	-1.58	5.5	0.9	68.7	-5.67	X	4.7	6.3	12	EM						
AB28WL	81.5	81.6	82.1	82.5	81.9	0.17	2.7	0.5	86.2	1.78	3.2	6.4	12	LG							
B7MURT	77.8	78.3	80.0	80.7	79.2	-0.63	3.7	1.4	80.5	-0.64	3.5	1.5	12	EN							
BA776N	88.8	79.7	89.0	88.5	*	86.5	1.50	4.1	4.6	85.9	1.66	5.2	5.0	12	LX						
BQBBVL	81.5	79.2	73.0	76.0	77.4	-1.14	3.3	3.7	78.7	-1.41	3.5	2.4	12	LC							
C7YK34	83.3	82.2	85.2	H	86.7	84.3	0.87	5.9	2.0	85.4	1.43	4.3	5.3	12	MB						
CVXM3M	82.2	82.5	83.2	79.8	81.9	0.17	3.1	1.5	82.5	0.22	2.8	1.6	12	LD							
DT7FAX	49.3	XH	47.8	XH	45.4	XH	48.1	XH	47.6	-9.81	X	36.2	1.6	47.6	-14.66	X	36.2	1.6	4	LZ	
FN8CLN	84.9	82.1	83.1	82.8	83.2	0.54	3.6	1.2	83.2	0.51	3.6	1.2	4	LZ							
FVQLQC	83.5	H	81.8	84.9	80.2	H	82.6	0.36	6.6	2.0	82.7	0.29	6.1	1.7	12	LC					
GEXT2	81.4	83.5	79.9	79.4	81.1	-0.08	2.5	1.9	82.8	0.35	2.7	1.9	12	LD							
HBWKQU	82.4	84.4	84.3	83.7	83.7	0.68	3.2	0.9	84.1	0.91	4.0	2.2	10	LD							
JKCVEB	102.5	XH	101.5	X	100.9	X	100.1	X	101.2	5.79	X	5.1	1.0	81.1	-0.39	11.9	14.9	H	12	LB	
LHMUJU	82.1	81.3	80.1	79.5	80.7	-0.18	4.1	1.2	80.2	-0.76	3.6	2.1	12	LZ							
M6BN6L	80.9	82.7	80.3	79.0	80.7	-0.19	4.2	1.5	80.2	-0.78	4.2	1.8	12	LD							
N3KG43	85.8	86.1	88.8	83.5	86.0	1.37	4.2	2.2	85.0	1.28	4.1	1.6	12	LZ							
P3ZVCC	77.8	83.0	82.1	80.5	80.8	-0.15	4.2	2.3	81.7	-0.13	3.9	2.1	12	LD							
PJMD6D	79.6	79.3	79.3	L	80.3	79.6	-0.50	2.6	0.5	80.1	-0.83	2.6	1.5	12	LD						
PMMMB9	81.6	82.0	82.0	81.8	81.9	0.15	3.0	0.2	L	82.5	0.20	3.2	0.5	L	12	LD					
PQK9Y6	82.4	81.6	81.9	83.6	82.4	0.30	2.8	0.9	83.3	0.53	3.0	1.1	L	12	LD						
PZDCBE	82.2	80.3	80.8	79.8	80.8	-0.17	2.5	1.0	80.5	-0.64	3.1	0.8	L	8	LD						
QL7T9D	84.2	84.0	82.3	83.4	83.5	0.62	2.6	0.8	83.3	0.53	2.6	0.9	L	12	TH						
RGC9L9	68.7	XH	68.6	XH	70.2	*H	81.6	H	72.3	-2.64	*	11.2	6.3	H	83.5	0.63	8.1	9.8	H	12	TU
RP6G8Z	89.4	*	76.2	86.3	74.4	81.6	0.06	3.3	7.4	H	81.9	-0.03	3.5	4.8	12	LC					
TNPJEZ	74.0	*	75.0	81.4	79.7	77.5	-1.11	3.5	3.6	78.7	-1.41	4.1	3.1	12	LC						
TTJHM4	84.7	L	84.7	L	85.2	L	85.0	L	84.9	1.04	0.7	0.2	L	82.9	0.38	1.1	1.8	12	TU		




Containerboard Interlaboratory Testing Program
Analysis 217
Ring Crush, 35 lb Linerboard - 35E3
TAPPI Official Test Method T822

Report #643
April 2023

WebCode	Weekly Means				Monthly Results				Cumulative Results					
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst
UBCDND	77.7	77.6	77.3	L 77.0 L	77.4	-1.15	1.9	0.3 L	77.8	-1.80	2.2	0.6 L	12	LD
UBUJM4	85.1	80.4	86.3	No DATA	83.9	0.75	4.5	3.1	83.7	0.70	3.7	2.0	10	TU
UMALF9	84.4	84.0	83.4	83.7	83.9	0.74	3.1	0.4	83.9	0.79	3.4	0.8 L	12	LC
UWTZF6	87.3	92.5 X	88.5	89.5 *	89.4	2.36 *	2.8	2.2	86.6	1.95 *	2.8	2.8	12	LD
V6GZ2F	83.3	83.8	84.0	83.5	83.7	0.67	3.4	0.3 L	82.5	0.20	3.3	1.1 L	12	EM
WJZGHG	75.9	72.9 *	74.1	75.7	74.7	-1.95 *	3.7	1.4	77.9	-1.76	5.1	3.1	12	LC
WKBD3A	80.7	76.4	81.4	80.8	79.8	-0.45	3.5	2.3	79.1	-1.24	3.8	1.6	12	LD
XZG2N9	74.0 *H	73.4 H	75.9 H	84.0	76.8	-1.31	8.0	4.9	85.8	1.62	5.6	7.3	12	MB
YAPTX4	78.9	76.3 L	78.7	83.7	79.4	-0.57	2.4	3.1	79.6	-1.04	3.8	2.0	12	LD
YVPLQ9	84.7 L	81.2 L	82.8 L	82.2 L	82.7	0.40	1.0	1.5	80.9	-0.46	1.8	2.4	12	XX
YZYCZM	87.4	83.5	83.5	83.0	84.3	0.87	4.5	2.0	84.9	1.21	3.5	1.5	12	LD
Z32ZBP	87.6	88.6 *	82.1 L	83.8	85.5	1.22	3.7	3.1	82.0	-0.02	3.8	4.6	8	RS
ZQ97PZ	82.7	84.3	83.4	83.1	83.4	0.59	2.6	0.7	82.1	0.03	2.7	1.9	12	LD
ZZX8E7	79.0	74.6	82.4	76.2	78.1	-0.96	3.3	3.4	79.2	-1.18	3.5	2.9	12	LD
Consensus (All Labs) Results														
Wk Mean	81.75	80.50	81.17	81.29	Month Mean		81.35		Grand Mean		82.02			
Avg SDr	4.00	3.91	4.21	3.94	Avg SD		4.08		Avg SD		4.26			
SD btwn Labs	3.83	3.69	4.45	3.68	SD btwn Labs		3.44		SD btwn Labs		2.34			
Labs Incld	43	43	46	45	SD btwn Wks		2.49		SD btwn Wks		4.01			
Labs Excld	5	5	3	3	Labs Incld		45		Labs Incld		45			
Labs not Rcvd	1	1	0	1										

Key to Instrument Codes Reported by Participants

EM	Emerson 1200	EN	Emerson 2200
LB	L&W Crush Tester 240	LC	L&W Crush Tester 48
LD	L&W Crush Tester 248	LG	L&W 753
LX	L&W 506	LZ	L&W Crush Tester (model not specified)
MB	Messmer Buchel K440	RS	Regmed Digital Crush Tester CT-2000
TH	TMI Compression Tester, Model 17-76	TU	TMI Universal Crush Tester (TMI K440)
XX	Instrument make/model not specified by lab		



Containerboard Interlaboratory Testing Program

Analysis 223

STFI, 42 lb Linerboard - 42H2

TAPPI Official Test Method T826

Report #643

April 2023

WebCode	Weekly Means				Monthly Results				Cumulative Results												
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst							
2AGQYA	24.3	26.2	H	25.1	25.3	H	25.2	1.02	2.5	0.8	24.4	0.53	2.1	1.3	16	LA					
2GTGB8	23.4	L	25.1	L	24.5	L	25.5	L	24.6	0.59	0.5	0.9	23.3	-0.38	1.1	1.2	16	LZ			
2M3DG3	24.2	23.9	23.8	22.8	23.7	-0.09	1.4	0.6	23.5	-0.15	1.4	0.5	16	TT							
7GW8BQ	27.4	*	27.2	*	26.9	*	27.0	*	27.1	2.37	*	2.0	0.2	26.8	2.55	*	1.9	0.5	16	LH	
8N24YW_AL	26.0	25.7	25.7	25.6	25.7	1.38	1.9	0.2	26.2	2.05	*	2.0	0.4	16	AL						
8VEAFZ	No Data	26.0	21.8	26.0	24.6	0.56	2.1	2.4	H	24.7	0.83	2.4	2.1	H	14	LW					
92JDY8	22.9	23.0	23.2	22.5	22.9	-0.65	1.7	0.3	22.7	-0.80	1.9	0.5	16	LY							
92JDY8_AL	23.7	22.9	24.1	23.6	23.6	-0.17	1.7	0.5	23.8	0.07	1.7	0.5	16	AL							
9CJ9B6	22.6	22.2	22.2	22.9	22.5	-0.97	1.9	0.3	22.9	-0.70	1.8	0.5	16	LZ							
AB28WL	24.2	23.7	24.1	25.2	24.3	0.34	1.8	0.6	24.3	0.48	1.8	0.4	16	BK							
B7MURT	22.4	21.9	21.4	*	21.9	21.9	-1.38	1.6	0.4	22.0	-1.39	1.6	0.5	16	LY						
BA776N	24.2	22.8	23.6	H	24.5	23.8	-0.03	2.4	0.8	23.1	-0.51	2.5	1.6	13	LZ						
BQBBVL	20.9	20.7	20.6	*	20.2	X	20.6	-2.31	*	1.6	0.3	20.5	-2.67	*	1.6	0.5	16	LY			
C7YK34	25.1	L	25.6	25.2	25.1	25.3	1.03	1.9	0.3	24.4	0.58	1.7	1.5	16	LA						
CVXM3M	25.1	24.0	23.4	23.4	24.0	0.12	1.6	0.8	23.8	0.06	1.7	0.5	16	LA							
DAG3WT	24.3	23.4	24.7	24.6	24.3	0.31	1.8	0.6	24.0	0.24	1.7	0.6	16	LA							
EH7AT4	23.6	24.3	25.2	24.6	24.4	0.45	1.9	0.7	23.9	0.16	2.1	0.8	16	LH							
EZR4TL	25.9	23.1	H	23.9	23.8	24.2	0.26	2.1	1.2	24.1	0.33	1.9	0.9	16	LA						
FN8CLN	22.0	22.2	21.8	22.0	22.0	-1.31	1.7	0.2	22.2	-1.23	1.7	0.4	16	LU							
FVQLQC	24.5	24.4	23.2	No Data	24.0	0.16	1.9	0.7	24.2	0.40	2.0	1.1	12	LU							
G9CB4M	22.7	22.4	23.9	22.5	L	22.9	-0.67	1.3	0.7	23.1	-0.51	1.4	0.6	16	XX						
GALTDY	24.8	24.6	24.7	24.2	24.6	0.54	1.9	0.2	24.4	0.53	1.9	0.2	16	LZ							
GECXT2_AL	23.2	21.4	24.9	23.9	23.3	-0.34	1.9	1.5	23.7	-0.04	1.6	0.8	16	AL							
HBWKQU_AI	24.1	23.7	23.8	24.1	23.9	0.08	2.1	0.2	25.1	1.10	3.0	1.1	16	AL							
HMMEZ3	22.4	L	24.5	23.5	23.1	23.4	-0.33	1.3	0.9	23.2	-0.40	1.6	0.6	16	LW						
JKCVEB	23.6	25.9	23.9	24.3	24.4	0.43	1.8	1.0	24.0	0.23	2.0	0.8	16	LH							
LDBLG6_AL	24.8	24.7	25.3	25.5	25.1	0.90	1.7	0.4	25.0	1.06	1.8	0.6	12	AL							
LHMUJU	21.2	21.6	22.7	H	21.8	21.8	-1.43	2.1	0.6	22.2	-1.21	1.6	0.9	16	LA						
LZPCUZ	22.4	22.4	22.7	22.4	22.5	-0.96	1.4	0.1	22.6	-0.93	1.4	0.5	16	LH							
M6BN6L	24.6	L	24.5	24.8	L	24.2	L	0.9	0.3	24.1	0.35	0.8	0.4	16	LH						
MYP9K2	20.5	*	20.1	*	23.4	17.9	X		20.5	-2.39	*	1.7	2.3	H							
MYP9K2_AL	20.5	*	19.7	*	22.3	19.8	X		20.6	-2.32	*	1.7	1.2								
N3KG43_AL	23.0	24.3	23.6	L	22.4	L	23.3	-0.36	1.7	0.8	23.7	-0.05	1.6	0.8	16	AL					
NJPBPQ	23.2	23.4	23.8	25.2	23.9	0.05	1.6	0.9	23.9	0.13	1.6	0.6	16	LH							
P3ZVCC	22.1	23.3	23.1	23.1	22.9	-0.65	1.9	0.5	23.0	-0.57	1.7	0.8	16	LY							



Containerboard Interlaboratory Testing Program

Analysis 223

STFI, 42 lb Linerboard - 42H2

TAPPI Official Test Method T826

Report #643

April 2023

WebCode	Weekly Means				Monthly Results				Cumulative Results					
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst
PJMD6D_AL	24.3	24.6	25.5	24.5	24.7	0.65	2.0	0.5	24.3	0.52	1.8	0.9	16	AK
PQK9Y6_AL	23.6	23.7	23.4	24.0	23.7	-0.11	1.8	0.3	23.9	0.16	1.9	0.5	16	XX
PZDCBE_AL	24.5	23.5	23.8	24.8	24.2	0.24	1.6	0.6	23.7	-0.04	1.7	0.5	16	AL
RGC9L9	27.8 *	25.1	25.1	24.5	25.6	1.30	2.0	1.5	24.9	0.98	1.8	1.3	16	LA
RP6G8Z	24.3	23.6	23.8	22.7	23.6	-0.16	1.8	0.6	28.5	3.93 X	2.3	9.8 H	16	LU
TNNT2Q	23.6	22.9	23.8	23.8	23.5	-0.19	1.6	0.4	23.4	-0.24	1.8	0.6	16	LY
TNPJEZ	24.0	24.0 H	23.7	23.9	23.9	0.06	2.0	0.1 L	23.7	0.01	1.8	0.3	16	LA
TTJHM4	21.3	21.0	21.9	22.5	21.7	-1.53	1.7	0.7	21.1	-2.19 *	1.7	0.6	16	XX
TX9RLN_AL	26.0	24.6	24.6	25.3 H	25.1	0.94	2.0	0.7	24.7	0.84	2.0	0.8	16	AL
U88EXX	25.3	22.9 H	23.3 L	20.9 *	23.1	-0.52	1.9	1.8 H	23.3	-0.38	1.7	1.0	16	LU
UBUJM4	25.5	25.5	25.6	No DATA	25.5	1.23	2.2	0.1 L	25.0	1.07	2.1	0.5	11	TT
UGMRJB_AL	24.3	23.7	23.8 L	23.4	23.8	0.00	1.4	0.4	24.2	0.37	1.7	0.5	16	AL
UMALF9	22.7	24.0	22.9	23.7	23.3	-0.36	1.5	0.6	23.5	-0.14	1.7	0.4	16	LU
UWTZF6	25.5	25.8	25.1	24.7	25.3	1.04	1.6	0.5	25.5	1.44	1.9	0.6	16	LH
VJ63LT	25.6	25.6	26.1 L	25.3	25.7	1.31	1.3	0.3	25.1	1.11	1.3	0.5	16	LH
WKBD3A_AL	25.1	23.9	23.7	24.8	24.4	0.40	1.7	0.7	24.3	0.48	1.9	0.8	16	AL
WT6HWB_AI	25.7	24.9 L	26.5 *H	25.2	25.6	1.26	2.0	0.7	25.6	1.53	2.0	0.7	4	XX
XZG2N9	23.1	28.4 *	25.2	24.5	25.3	1.05	2.0	2.2 H	24.2	0.42	1.6	1.8	16	LA
YJ9WR4	23.6 H	23.6	24.1	24.1 H	23.8	0.01	2.6	0.3	23.7	0.03	2.6	0.3	16	LY
YVPLQ9	23.5 L	24.6 L	25.0 L	25.4 L	24.6	0.57	0.6	0.8	23.2	-0.41	0.8	1.1	16	LZ
YZYCZM	25.5	26.2	23.2	25.1 L	25.0	0.84	2.0	1.3	23.9	0.11	1.7	1.0	16	LA
ZQ97PZ	23.4	23.1	23.0	24.1	23.4	-0.30	1.8	0.5	23.3	-0.37	1.9	0.6	16	LU
ZTXDAX	24.1	24.0 H	23.4 H	23.8	23.8	0.00	2.5	0.3	24.3	0.44	2.1	0.8	16	LH
ZZX8E7	20.9	19.1 *	19.8 X	21.9	20.4	-2.43 *	1.6	1.3	21.1	-2.13 *	1.6	1.8 H	12	LZ
ZZX8E7_AL	44.1 XL	43.3 XL	46.7 XL	46.4 XL	45.1	15.23 X	0.0	1.7	46.1	18.38 X	0.0	2.1 H	12	AL

Consensus (All Labs) Results									
Wk Mean				23.84	23.78	23.91	24.00	Month Mean	
Avg SDr				1.73	1.80	1.92	1.79	Avg SD	
SD btwn Labs				1.58	1.76	1.26	1.25	SD btwn Labs	
Labs Incld				58	59	58	54	SD btwn Wks	
Labs Excld				1	1	2	4	Labs Incld	
Labs not Rcvd				1	0	0	2	Labs Incld	
Grand Mean				23.82				23.72	
Avg SD				1.81				1.81	
SD btwn Labs				1.40				1.22	
SD btwn Wks				0.88				0.90	
Labs Incld				59				58	



Containerboard Interlaboratory Testing Program
Analysis 223
STFI, 42 lb Linerboard - 42H2
TAPPI Official Test Method T826

Report #643
April 2023

Key to Instrument Codes Reported by Participants

AK	L & W Autoline 300	AL	L & W Autoline 400
BK	Buchel Strip Compression Tester BK-155	LA	L&W Autoline (223 Enrollment)
LH	L&W 282	LU	L&W 52 without moisture correction(was 53)
LW	L&W 53 with moisture correction (was 53M)	LY	L&W 152 without moisture correction
LZ	L&W (model not specified)	TT	TMI Short Span Compression, 17-34 (MB K455)
XX	Instrument make/model not specified by lab		



Containerboard Interlaboratory Testing Program

Analysis 225

STFI, 35 lb Linerboard - 35E3

TAPPI Official Test Method T826

Report #643

April 2023

WebCode	Weekly Means				Monthly Results				Cumulative Results											
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst						
2AGQYA	23.2	24.1	24.1	25.3	24.2	0.66	1.6	0.8	23.9	0.52	1.6	0.7	12	LA						
2GTGB8	21.6	L	24.8	L	24.6	L	24.5	L	23.9	0.45	0.7	1.5	22.5	-0.60	1.1	1.4	12	LZ		
2M3DG3	23.3	23.6	23.4	23.1	23.3	0.07	1.3	0.2	23.4	0.11	1.4	0.3	L	12	TT					
7GW8BQ	26.6	*	26.9	*	24.8	H	26.5	*	26.2	2.06	*	2.1	0.9	26.2	2.34	*	2.0	0.7	12	LH
8N24YW_AL	25.6	25.7	25.7	25.4	25.6	1.67	1.9	0.2	25.6	1.88	2.0	0.5	12	AL						
8VEAFZ	No Data	25.8	20.5	*	26.4	*H	24.2	0.70	2.4	3.2	H	23.4	0.12	2.1	1.8	11	LW			
92JDY8	21.3	20.9	21.1	21.3	21.1	-1.49	1.8	0.2	22.0	-0.98	1.8	0.8	12	LZ						
92JDY8_AL	22.9	22.2	22.4	22.4	22.5	-0.54	1.5	0.3	22.8	-0.36	1.5	0.4	12	AL						
9CJ9B6	22.7	22.1	20.9	22.6	22.1	-0.82	1.9	0.8	22.4	-0.67	1.7	0.9	12	LZ						
AB28WL	23.4	23.5	24.5	23.8	23.8	0.40	1.7	0.5	23.8	0.39	1.8	0.4	12	LW						
B7MURT	21.4	21.9	22.0	21.6	21.7	-1.07	1.9	0.3	21.7	-1.25	1.7	0.4	12	LY						
BA776N	21.7	23.2	23.8	H	23.0	22.9	-0.23	2.3	0.9	22.7	-0.44	2.0	1.6	12	LZ					
BQBBVL	20.2	19.8	*	20.2	*	18.7	XH	19.7	-2.47	*	2.1	0.7	20.1	-2.52	*	1.7	0.8	12	LZ	
C7YK34	25.7	24.9	25.8	25.4	25.5	1.55	1.5	0.4	24.0	0.60	2.3	1.4	12	LA						
CVXM3M	23.9	23.7	24.1	23.5	23.8	0.39	1.7	0.3	23.8	0.45	1.8	0.5	12	LA						
DAG3WT	24.4	23.5	22.4	23.3	23.4	0.10	1.7	0.8	23.4	0.10	1.8	0.5	12	LA						
EH7AT4	23.2	23.8	24.0	23.8	23.7	0.32	2.0	0.4	23.8	0.40	1.9	0.7	12	LH						
EZR4TL	23.8	23.1	22.8	L	23.4	23.3	0.04	1.4	0.4	23.7	0.37	1.8	1.0	12	LA					
FN8CLN	22.3	21.0	L	21.7	21.1	*	21.5	-1.21	1.5	0.6	22.2	-0.87	1.6	0.7	12	LU				
FVQLQC	24.4	23.4	23.7	H No Data	23.8	0.41	2.3	0.5	24.1	0.63	2.0	1.4	11	LU						
G9CB4M	22.1	H	23.1	22.5	22.9	22.6	-0.43	1.9	0.4	22.4	-0.70	1.4	1.0	12	XX					
GALTDY	23.7	23.8	23.4	23.2	23.5	0.20	2.0	0.3	23.6	0.28	1.9	0.2	L	12	LA					
GECXT2_AL	20.3	23.9	L	23.5	22.7	22.6	-0.46	1.2	1.6	22.4	-0.67	1.5	1.6	12	AL					
HBWKQU_AI	24.3	21.9	23.5	22.8	H	23.1	-0.08	1.9	1.0	24.2	0.75	1.9	1.2	10	AL					
HMMEZ3	22.0	L	23.1	22.6	23.3	22.7	-0.35	1.5	0.6	22.6	-0.57	1.8	0.5	12	LW					
JKCVEB	23.4	23.2	24.0	23.1	23.4	0.12	2.0	0.4	23.7	0.33	1.8	0.6	12	LH						
LDBLG6_AL	24.4	24.5	24.2	24.7	24.4	0.85	1.6	0.2	24.2	0.78	1.8	0.7	12	AL						
LHMUJU	22.0	23.4	L	22.8	H	22.1	22.6	-0.48	2.0	0.6	22.9	-0.31	2.1	1.2	12	LA				
LZPCUZ	22.4	L	22.1	22.7	22.6	22.5	-0.56	1.5	0.3	22.5	-0.65	1.5	0.4	12	LH					
M6BN6L	24.0	24.5	L	23.2	L	23.7	L	23.8	0.42	0.8	0.5	23.8	0.40	0.8	0.5	12	LH			
MYP9K2	19.8	*	18.7	X	23.6	18.2	X	20.1	-2.23	*	1.6	2.4	H	21.1	-1.77	1.7	1.7	12	LH	
MYP9K2_AL	20.5	20.4	23.1	L	19.8	X	21.0	-1.61	1.3	1.5	21.4	-1.49	1.6	1.0	12	AL				
N3KG43_AL	21.1	20.7	23.1	22.9	22.0	-0.90	1.8	1.3	22.3	-0.80	1.9	0.8	12	XX						
NJPBPQ	22.7	22.3	22.8	24.0	23.0	-0.19	1.5	0.7	23.0	-0.20	1.5	0.6	12	LH						
P3ZVCC	22.0	22.4	22.5	23.4	22.6	-0.48	1.7	0.6	22.3	-0.81	1.6	0.7	12	LY						



Containerboard Interlaboratory Testing Program

Analysis 225

STFI, 35 Ib Linerboard - 35E3

TAPPI Official Test Method T826

Report #643

April 2023

WebCode	Weekly Means				Monthly Results				Cumulative Results					
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst
PJMD6D_AL	23.9	23.7	23.7	L 24.5	24.0	0.50	1.4	0.4	23.8	0.43	1.5	0.4	12	AK
PQK9Y6_AL	23.4	22.9	22.6	22.4	22.8	-0.29	1.6	0.4	23.3	0.04	1.7	0.5	12	XX
PZDCBE_AL	23.9	22.0	23.7	22.2	22.9	-0.22	1.9	1.0	22.9	-0.26	2.0	0.8	12	AL
RGC9L9	26.2	26.4 *	26.3 *	25.1	26.0	1.94 *	1.7	0.6	24.6	1.10	1.8	1.6	12	LA
RP6G8Z	22.2	23.2	23.5	23.2	23.0	-0.14	1.6	0.6	26.0	2.23 *	1.9	4.9 H	12	LW
TNNT2Q	22.7	23.7	23.3	24.0	23.4	0.12	1.8	0.6	23.0	-0.25	1.7	0.7	12	LU
TNPJEZ	23.1	23.8	23.6	23.4	23.5	0.16	1.6	0.3	23.0	-0.26	1.6	0.4	12	LA
TTJHM4	20.7	20.2 *	21.4	21.4	20.9	-1.63	1.7	0.6	20.9	-1.90	1.6	0.5	8	XX
TX9RLN_AL	24.2	23.6	24.8	24.0	24.2	0.64	1.6	0.5	24.2	0.72	1.9	0.5	12	AL
U88EXX	23.2	21.7	21.7 L	22.5	22.3	-0.70	1.4	0.7	22.8	-0.37	1.7	0.6	12	LU
UBUJM4	25.5	24.1	24.8	No DATA	24.8	1.10	2.1	0.7	24.5	1.00	1.9	0.5	10	TT
UGMRJB_AL	23.2	24.1 L	23.6	24.4	23.8	0.40	1.8	0.5	23.5	0.19	1.7	0.6	12	XX
UMALF9	23.2	23.3	24.3	24.2	23.8	0.36	1.8	0.6	23.7	0.38	1.7	0.6	12	LU
UWTZF6	25.5	24.2	25.5	24.6	24.9	1.19	1.8	0.7	24.8	1.27	1.8	0.5	12	LH
VJ63LT	25.0	25.0	24.9	25.2	25.0	1.25	1.4	0.2 L	25.1	1.47	1.4	0.2 L	12	LH
WKBD3A_AL	23.8	24.2	23.2	24.3	23.9	0.46	1.8	0.5	23.5	0.19	1.8	0.6	12	AK
WT6HWB_AI	26.7 *	25.6 H	25.2	26.1 *	25.9	1.88	2.0	0.6	25.9	2.13 *	2.0	0.6	4	XX
XZG2N9	22.1	20.6	21.2	23.4	21.8	-1.00	2.0	1.2	22.7	-0.42	1.8	1.3	12	LA
YJ9WR4	22.9	23.1	22.9	23.1 H	23.0	-0.16	2.4	0.1 L	23.1	-0.14	2.3	0.2 L	12	LY
YVPLQ9	21.8 L	24.7 L	23.1 L	24.9 L	23.6	0.27	0.5	1.4	22.7	-0.48	1.1	1.2	12	LZ
YZYCZM	24.0	24.1	23.8	23.6	23.9	0.44	2.0	0.2	23.3	-0.01	1.8	0.6	12	LW
ZQ97PZ	23.6	23.7	24.0	24.1	23.8	0.41	2.2	0.2	22.8	-0.40	1.9	1.0	12	LU
ZTXDAX	23.9	24.4	23.7	25.1	24.3	0.72	1.8	0.6	24.2	0.79	1.8	0.4	12	LH
ZZX8E7	21.0	17.0 XL	19.5 X	21.3	19.7	-2.50 *	1.6	2.0 H	20.5	-2.24 *	1.8	2.0	12	LZ
ZZX8E7_AL	32.7 XL	33.4 XL	32.8 XL	32.0 XL	32.7	6.68 X	0.0	0.6	33.2	7.95 X	0.0	0.9	12	AL

Consensus (All Labs) Results														
Wk Mean				Month Mean				Grand Mean				23.27		
Avg SDr				Avg SD				Avg SD				1.76		
SD btwn Labs				SD btwn Labs				SD btwn Labs				1.24		
Labs Incld				SD btwn Wks				SD btwn Wks				1.10		
Labs Excld				Labs Incld				Labs Incld				59		
Labs not Rcvd														



Containerboard Interlaboratory Testing Program
Analysis 225
STFI, 35 lb Linerboard - 35E3
TAPPI Official Test Method T826

Report #643
April 2023

Key to Instrument Codes Reported by Participants

AK	L & W Autoline 300	AL	L & W Autoline 400
LA	L&W Autoline (223 Enrollment)	LH	L&W 282
LU	L&W 52 without moisture correction (was 53)	LW	L&W 53 with moisture correction (was 53M)
LY	L&W 152 (was 52M)	LZ	L&W (model not specified)
TT	TMI Short Span Compression, 17-34 (MB K455)	XX	Instrument make/model not specified by lab



Containerboard Interlaboratory Testing Program

Analysis 228

Roughness - Stylus Method, 42 lb Linerboard - 42H

TAPPI Official Test Method T575

Report #643
April 2023

WebCode	Monthly Results			Cumulative Results					
	Mean	CPV	SD	Mean	CPV	SD	Months	Months	Inst
2AGQYA	93.6	-2.29 *	8.90	115.7	-1.59	35.01 H	4	LA	
7GW8BQ	177.9	1.62	24.40	182.9	2.16 *	5.31	4	LS	
8N24YW_AL	115.1	-1.29	15.98	118.2	-1.45	3.36	4	AL	
8VEAFZ	131.1	-0.55	14.93	128.4	-0.88	9.54	4	XX	
92JDY8	147.1	0.19	13.66	170.5	1.47	32.54 H	4	XX	
92JDY8_AL	171.2	1.31	18.07	143.0	-0.06	19.85	4	AL	
9CJ9B6	155.0	0.56	21.00	144.6	0.02	8.39	4	LS	
9P6HGM	157.7	0.69	12.81	146.2	0.12	15.58	4	LS	
B7MURT	148.6	0.26	12.74	145.8	0.09	3.86	4	EV	
BQBBVL	127.6	-0.71	4.97 L	141.0	-0.17	11.60	4	LS	
C7YK34	158.4	0.72	15.84	175.3	1.74	15.10	3	LA	
EH7AT4	141.8	-0.05	15.08	136.8	-0.41	5.83	4	EV	
FN8CLN	135.0	-0.37	8.49	142.3	-0.10	5.28	4	EV	
FVQLQC	152.1	0.43	12.35	150.1	0.33	7.91	4	EV	
GALTDY	140.5	-0.11	20.57	139.0	-0.28	1.81 L	4	LS	
LDBLG6_AL	117.5	-1.18	11.69	132.2	-0.66	12.98	3	AL	
MYP9K2_AL	134.9	-0.37	16.64	143.9	-0.02	12.60	4	AL	
N3KG43_AL	110.6	-1.50	18.12	119.7	-1.36	8.05	4	XX	
P3ZVC	148.2	0.24	14.42	146.9	0.16	2.12 L	4	EV	
PJMD6D	138.3	-0.22	20.29	140.7	-0.19	4.82	4	EV	
RGC9L9	170.1	1.26	10.70	180.9	2.05 *	21.64	4	LA	
TNPJEZ	164.4	1.00	13.66	132.9	-0.63	21.52	4	EV	
TX9RLN_AL	134.8	-0.38	22.54	123.4	-1.16	8.20	4	AL	
U88EXX	177.1	1.58	19.67	158.8	0.82	16.79	4	EV	
UGMRJB_AL	102.4	-1.88	8.17	126.3	-0.99	19.84	4	AL	
XZG2N9	167.6	1.14	22.48	170.4	1.47	2.10 L	4	LA	
YZYCZM	143.8	0.04	19.90	136.5	-0.43	5.45	4	LA	
ZQ97PZ	148.8	0.27	16.30	146.7	0.15	5.05	4	EV	
ZZX8E7	0.3	-6.61 X	0.02 L	60.1	-4.69 X	103.50 H	3	LA	
ZZX8E7_AL	133.9	-0.42	13.57	140.8	-0.19	9.21	3	AL	
Consensus (All Labs) Results									
Month Mean	142.93			Grand Mean	144.13				
Avg SD	16.14			Avg SD Months	14.22				
SD btwn Labs	21.56			SD btwn Labs	17.93				
Labs Incl'd	29			Labs Incl'd	29				



Containerboard Interlaboratory Testing Program

Analysis 228

Roughness - Stylus Method, 42 lb Linerboard - 42H2

TAPPI Official Test Method T575

Report #643

April 2023

Key to Instrument Codes Reported by Participants

AL	L & W Autoline 400	EV	Emveco Microgage Model 210-R
LA	L&W Autoline (228 Enrollment)	LS	L&W 263
XX	Instrument make/model not specified by lab		



Containerboard Interlaboratory Testing Program

Analysis 229

Roughness - Sheffield Method, 42 lb Linerboard - 42H2

TAPPI Official Test Method T538

Report #643
April 2023

WebCode	Monthly Results				Cumulative Results				
	Mean	CPV	SD		Mean	CPV	SD	Months	Months
8N24YW_AL	367.7	-0.54	15.54	H	371.1	-0.14	3.67	4	AL
92JDY8_AL	374.0	-0.10	8.54		368.2	-0.40	4.29	4	AL
9CJ9B6	391.0	1.08	13.39		382.3	0.89	6.09	4	XX
9H7QDY	410.3	2.42 *	4.35		423.0	4.59 X	12.96 H	3	TS
9P6HGM	386.7	0.78	9.23		386.7	1.28	0.00	1	LA
EZR4TL	385.0	0.66	6.99		384.1	1.05	3.97	3	XX
GECXT2_AL	385.3	0.68	10.18		385.8	1.20	3.23	4	AL
HBWKQU	370.0	-0.38	5.85		362.7	-0.90	7.79	4	PP
JKCWEB	345.8	-2.06 *	4.12		345.9	-2.44 *	0.62 L	4	LA
MYP9K2_AL	358.4	-1.18	5.56		367.5	-0.46	19.88 H	4	AL
N3KG43_AL	129.4	-17.10 X	13.62		129.4	-22.15 X	0.00	1	XX
PJMD6D	375.9	0.03	8.03		374.2	0.14	1.66	4	LA
PJMD6D_AL	374.2	-0.09	7.84		371.9	-0.06	5.13	4	AK
PQK9Y6_AL	384.7	0.64	6.69		384.2	1.06	0.69 L	4	XX
PZDCBE_AL	375.3	-0.01	13.24		378.2	0.51	2.09	4	AL
TX9RLN_AL	363.2	-0.85	6.46		359.6	-1.19	7.35	4	AL
UMALF9	380.4	0.34	6.57		379.4	0.62	1.35	4	XX
WKBD3A_AL	362.4	-0.91	11.88		364.8	-0.72	4.49	4	AL
ZZX8E7_AL	368.0	-0.52	4.00		367.8	-0.44	2.75	3	AL
Consensus (All Labs) Results									
Month Mean	375.46				Grand Mean	372.61			
Avg SD	8.88				Avg SD Months	6.47			
SD btwn Labs	14.39				SD btwn Labs	10.98			
Labs Incl'd	18				Labs Incl'd	17			

Key to Instrument Codes Reported by Participants

AK	L & W Autoline 300	AL	L & W Autoline 400
LA	L & W Autoline (229 Enrollment)	PP	Technidyne Profile/Plus
TS	TMI Monitor/Smoothness	XX	Instrument make/model not specified by lab



Containerboard Interlaboratory Testing Program

Analysis 231

Internal Bond, 42 lb Linerboard - 42H

TAPPI Official Test Method T569

Report #643

April 2023

WebCode	Monthly Results			Cumulative Results					
	Mean	CPV	SD	Mean	CPV	SD	Months	Months	Inst
92JDY8	124.0	-0.27	6.52	127.5	-0.15	8.11	4	4	TM
9P6HGM	135.0	0.43	22.89	136.4	0.44	4.66	4	4	HY
CVXM3M	125.0	-0.21	6.89	126.2	-0.24	4.47	4	4	HZ
EH7AT4	144.2	1.02	11.39	137.8	0.54	5.61	4	4	TM
EZR4TL	112.8	-0.99	8.67	112.0	-1.19	4.14	4	4	SC
FVQLQC	97.0	-2.00	*	101.9	-1.87	4.05	4	4	TM
GECXT2	58.3	-4.48	X	58.9	-4.75	X	1.34	4	LZ
HBWKQU	148.4	1.29	4.83	146.7	1.13	2.09	4	4	HY
N3KG43	102.4	-1.66	7.30	107.6	-1.49	4.09	4	4	TM
P3ZVCC	137.9	0.62	3.13	142.1	0.83	4.96	4	4	HZ
PB8WBH	147.0	1.20	3.39	144.4	0.98	3.52	4	4	TM
PJMD6D	112.8	-0.99	4.44	114.3	-1.04	3.38	4	4	TM
PQK9Y6	136.4	0.52	4.04	142.9	0.88	6.18	4	4	HY
PZDCBEBE	127.1	-0.07	4.87	124.0	-0.39	3.62	4	4	TM
TNPJEZ	121.6	-0.43	3.44	123.6	-0.42	2.90	4	4	TM
TURQU3	121.2	-0.45	2.53	119.5	-0.69	2.85	4	4	SC
TX9RLN	136.4	0.52	6.80	140.4	0.71	3.76	4	4	TM
U88EXX	115.8	-0.80	7.19	119.3	-0.70	5.65	4	4	TM
UBUJM4	120.7	-0.48	4.65	129.7	0.00	23.46	H	3	TM
UMALF9	148.7	1.31	9.04	147.9	1.22	1.66	4	4	HY
WKBD3A	118.3	-0.63	6.50	123.3	-0.44	3.31	4	4	TM
YZYCZM	157.2	1.86	8.20	163.0	2.23	*	6.01	4	HY
ZQ97PZ	131.2	0.19	9.58	124.8	-0.34	4.54	4	4	TM
Consensus (All Labs) Results									
Month Mean	128.23			Grand Mean	129.76				
Avg SD	8.00			Avg SD Months	6.66				
SD btwn Labs	15.59			SD btwn Labs	14.92				
Labs Incl	22			Labs Incl	22				

Consensus By Method

Test Method	Group Mean	SD btwn Group	Difference from Grand Mean	Labs Included
Scott Bond Type	125.98	14.35	2.25	19
Modified Scott Bond Mechanics	152.94	6.02	24.71	2

Analysis Notes

GECXT2 - Method used is not covered in this test. Data excluded from consensus calculation.



Containerboard Interlaboratory Testing Program

Analysis 231

Internal Bond, 42 lb Linerboard - 42H

TAPPI Official Test Method T569

Report #643

April 2023

Key to Instrument Codes Reported by Participants

HY	Huygen Digitized Scott Internal Bond Tester	HZ	Huygen Internal Bond Tester with AccuPress
LZ	L&W (model not specified)	SC	Scott Internal Bond Tester (Manual)
TM	TMI Monitor/Internal Bond Tester		



Containerboard Interlaboratory Testing Program

Analysis 234

COF Inclined Plane (Slide Angle), 42 lb Linerboard - 42H

TAPPI Official Test Method T815

Report #643
April 2023

WebCode	Monthly Results			Cumulative Results				
	Mean	CPV	SD	Mean	CPV	SD	Months	Months
7GW8BQ	19.5	-3.73 X	2.18	21.9	-2.26 *	3.70	4	
8N24YW	32.3	2.08 *	1.58	29.6	0.67	1.94	4	
8VEAFZ	26.8	-0.41	5.63 H	27.9	0.03	1.10	4	
92JDY8	27.2	-0.23	2.39	26.4	-0.54	1.95	4	
99HTTL	24.4	-1.50	1.95	25.8	-0.77	1.43	4	
9CJ9B6	35.3	3.45 X	1.68	31.4	1.38	3.68	4	
B7MURT	30.0	1.02	0.50 L	29.5	0.66	1.07	4	
BQBBVL	28.2	0.22	1.48	30.9	1.18	2.72	4	
C7YK34	29.8	0.95	2.17	29.3	0.58	0.34 L	4	
EH7AT4	29.2	0.69	4.91	29.6	0.68	1.08	4	
EZR4TL	25.2	-1.14	1.30	26.9	-0.35	1.32	4	
FJAWQL	24.0	-1.69	0.71	29.3	0.55	3.99	4	
FN8CLN	30.6	1.31	2.51	27.6	-0.10	2.26	4	
FVQLQC	27.0	-0.32	3.00	27.8	-0.03	2.77	4	
GALTDY	27.4	-0.14	0.55 L	27.4	-0.16	0.28 L	4	
GECXT2	28.8	0.50	3.27	23.8	-1.56	3.59	4	
HBWKQU	28.8	0.50	3.42	33.3	2.11 *	3.93	3	
J88TZ9	27.0	-0.32	2.92	27.0	-0.31	1.50	4	
M6BN6L	26.6	-0.50	0.65 L	24.9	-1.12	1.41	4	
N3KG43	30.1	1.09	1.10	30.5	1.02	0.63	4	
P3ZVCC	29.4	0.77	5.13	23.3	-1.75	4.64	4	
PJMD6D	26.4	-0.59	3.00	29.3	0.55	2.26	4	
PQK9Y6	29.4	0.77	2.07	28.6	0.30	1.05	4	
TX9RLN	30.4	1.22	3.58	30.1	0.87	3.31	4	
U88EXX	29.6	0.86	4.04	31.0	1.22	1.43	4	
UGMRJB	24.6	-1.41	1.14	25.2	-1.02	1.28	4	
UMALF9	25.8	-0.85	0.60 L	26.2	-0.61	1.34	4	
WKBD3A	24.4	-1.50	2.70	25.3	-0.98	1.76	4	
YZYCZM	26.4	-0.59	2.70	26.8	-0.41	1.18	4	
ZQ97PZ	26.0	-0.78	5.00	28.3	0.17	1.60	4	
Consensus (All Labs) Results								
Month Mean	27.71			Grand Mean	27.82			
Avg SD	2.90			Avg SD	2.33			
SD btwn Labs	2.20			SD btwn Labs	2.61			
Labs Incl'd	28			Labs Incl'd	30			



Containerboard Interlaboratory Testing Program
Analysis 234
COF Inclined Plane (Slide Angle), 42 lb Linerboard - 42H
TAPPI Official Test Method T815

Report #643
April 2023

Key to Instrument Codes Reported by Participants

ZZ Instruments No Longer Tracked



Containerboard Interlaboratory Testing Program
Analysis 237
Air Resistance, 42 lb Linerboard - 42H
TAPPI Official Test Method T460

Report #643
April 2023

WebCode	Monthly Results				Cumulative Results					
	Mean	CPV	SD		Mean	CPV	SD	Months	Months	Inst
2AGQYA	33.5	0.89	2.61		32.6	0.23	0.93	4	LA	
2VE239	30.8	-0.94	3.55		31.6	-0.68	0.56	4	GG	
7GW8BQ	34.5	1.51	4.80	H	28.5	-3.61	X	4.51	H	4
8N24YW_AL	30.3	-1.29	1.74		29.8	-2.34	*	0.83	4	AL
8VEAFZ	32.9	0.46	1.93		32.6	0.29		1.49	4	LP
92JDY8	31.5	-0.49	2.07		32.0	-0.27		0.76	4	LP
92JDY8_AL	34.1	1.28	1.68		34.6	2.16	*	0.68	4	AL
99HTTL	33.0	0.51	5.02	H	31.0	-1.25		2.22	4	XX
9CJ9B6	33.3	0.74	3.36		34.3	1.89		0.96	4	GA
9P6HGM	31.6	-0.38	1.54		31.7	-0.57		0.63	4	LP
BQBBVL	31.1	-0.77	1.10	L	31.8	-0.50		0.52	4	XX
C7YK34	30.0	-1.45	2.06		31.0	-1.26		1.05	4	LA
DAG3WT	31.4	-0.57	3.23		31.8	-0.49		0.97	4	LA
EH7AT4	32.5	0.22	1.84		32.1	-0.22		1.29	4	LP
FJAWQL_AL	33.6	0.92	2.12		32.5	0.19		0.79	4	AL
FN8CLN	30.8	-0.97	2.04		31.4	-0.83		0.64	4	LP
FVQLQC_AL	32.2	0.00	2.33		32.7	0.39		0.87	4	AL
GALTDY	32.4	0.13	1.78		32.4	0.03		0.26	L	4
GECXT2_AL	32.9	0.45	1.16		32.9	0.53		0.88	4	AL
HBWKQU	33.6	0.96	5.22	H	31.9	-0.44		1.43	4	TP
JKCVEB	27.0	-3.47	X	3.20	27.4	-4.60	X	0.62	4	LA
LDBLG6_AL	33.7	1.02	1.86		33.8	1.36		0.17	L	3
MYP9K2_AL	33.2	0.69	2.02		33.4	1.00		0.90	4	AL
N3KG43_AL	32.9	0.44	3.17		33.6	1.17		0.87	4	XX
N8EDTT	31.9	-0.20	1.01	L	34.4	1.97	*	6.75	H	4
P3ZVCC	33.9	1.14	2.75		32.9	0.57		1.05	4	LP
PJMD6D_AL	30.9	-0.85	1.50		31.9	-0.38		1.16	4	AK
PQK9Y6	34.9	1.78	3.59		32.8	0.42		1.50	4	GG
PQK9Y6_AL	30.6	-1.07	2.37		31.6	-0.66		0.70	4	XX
PZDCBE_AL	32.6	0.28	2.03		32.7	0.35		0.94	4	AL
R3CGWX	33.4	0.80	1.92		33.0	0.64		1.37	4	LP
RGC9L9	32.0	-0.14	1.65		33.1	0.77		1.35	4	LA
TX9RLN_AL	31.1	-0.77	1.56		31.7	-0.55		0.83	4	AL
U88EXX_AL	32.3	0.03	2.17		32.2	-0.10		1.22	4	AL
UBUJM4	28.7	-2.34	*	1.22	28.7	-3.39	X	0.00	1	GA
UGMRJB_AL	30.2	-1.36	1.54		30.7	-1.50		0.56	4	AL
UMALF9	31.1	-0.71	2.90		32.0	-0.31		0.57	4	TP
UWTZF6	32.5	0.20	2.37		31.0	-1.28		1.70	4	XX
WKBD3A_AL	30.8	-0.93	1.35		32.4	0.04		1.61	4	AL



Containerboard Interlaboratory Testing Program
Analysis 237
Air Resistance, 42 lb Linerboard - 42H
TAPPI Official Test Method T460

Report #643
April 2023

WebCode	Monthly Results			Cumulative Results					
	Mean	CPV	SD	Mean	CPV	SD	Months	Months	Inst
XZG2N9	31.8	-0.28	2.86	31.8	-0.48	0.46	4	4	LA
YZYCZM	33.2	0.66	1.69	32.9	0.57	1.60	4	4	LP
ZQ97PZ	35.4	2.15 *	4.09	33.6	1.19	3.26 H	4	4	GA
ZZX8E7_AL	29.6	-1.74	1.77	30.6	-1.64	1.07	3	3	XX

Consensus (All Labs) Results			
Month Mean	32.21	Grand Mean	32.32
Avg SD	2.56	Avg SD Months	1.58
SD btwn Labs	1.50	SD btwn Labs	1.07
Labs Incl'd	42	Labs Incl'd	40

Key to Instrument Codes Reported by Participants

- AK L & W Autoline 300
GA Gurley Precision #4340 Automatic Densometer
LA L&W Autoline (237 Enrollment)
TD TMI Gurley Densometer
XX Instrument make/model not specified by lab
- AL L & W Autoline 400
GG Gurley Precision #4320 Densometer
LP L&W Air Permeance Tester SE 166
TP Technidyne Profile/ plus Roughness & Porosity



Containerboard Interlaboratory Testing Program
Analysis 240

Report #643
April 2023

Flat Crush Strength (CMT), 26 lb Corrugating Medium - CM12
TAPPI Official Test Method T809

WebCode	Weekly Means				Monthly Results				Cumulative Results								
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst			
2E9WEW	62.0	58.3	58.4	60.3	59.8	0.80	3.5	1.8	58.5	0.28	3.9	2.5	16	LD			
2GTGB8	60.7	L	56.7	55.9	57.8	0.07	1.5	2.1	59.9	0.89	1.5	1.9	16	TH			
2M3DG3	56.6	58.0	60.1	57.7	H	0.18	5.1	1.5	57.9	0.02	5.5	1.0	16	TG			
3Z42VU	56.9	L	56.9	56.1	56.9	-0.35	1.7	0.4	56.5	-0.64	1.7	0.4	L	12			
4DQXQK	58.8	L	58.6	L	58.3	0.35	0.6	0.2	58.3	0.19	0.6	0.2	L	16			
7JLEVM	52.1	52.4	51.8	53.8	52.5	-1.93	*	2.2	0.9	54.2	-1.66	2.5	1.7	16	EM		
8VEAFZ	No Data	No Data	No Data	65.7	*	65.7	3.04	X	2.8	0.0	64.8	3.07	X	3.5	4.0		
92JDY8	53.4	52.2	52.2	52.8	*	52.6	-1.88		2.9	0.6	53.5	-1.94	*	3.3	1.5		
99HTTL	52.9	54.6	58.4	H	55.5	-0.86	4.8		55.4	-1.32	4.3	2.4	16	LZ			
9CJ9B6	60.8	58.7	56.0	61.1	59.2	0.57	3.4		57.9	-0.01	3.4	2.2	16	LZ			
9P6HGM	No Data	No Data	No Data	59.0	59.0	0.50	3.6		58.0	0.03	2.5	1.7	4	LD			
AB28WL	55.1	57.4	56.5	58.7	56.9	-0.27	3.5		57.7	-0.10	3.6	1.7	16	LZ			
AXDALB	58.1	57.4	56.8	57.8	57.5	-0.04	3.2		56.3	-0.70	3.4	0.9	16	LD			
B7MURT	60.2	61.1	57.4	61.2	60.0	0.87	4.3		58.9	0.44	4.3	1.9	16	EN			
BA776N	60.3	59.9	57.6	60.3	59.5	0.71	4.3		59.9	0.90	3.6	2.3	16	LD			
BJBNR8	56.3	60.1	56.6	54.6	56.9	-0.28	3.9		58.6	0.31	4.1	2.1	12	LD			
C7YK34	55.1	H	55.3	58.4	L	58.2	56.8	-0.32	4.0	1.8	54.4	-1.56	4.3	2.0	16		
CVXM3M	56.0	56.0	55.7	54.3	55.5	-0.81	2.9		56.6	-0.58	3.2	1.2	16	LD			
FVQLQC	57.3	57.8	58.9	61.7	58.9	0.49	3.9		58.6	0.31	3.5	1.9	16	LC			
G9CB4M	64.3	*	62.1	L	59.6	0.50	4.3		61.6	1.50	1.2	2.1	60.0	0.96			
GALTDY	58.0	58.1	57.7	57.8	57.9	0.10	2.3	0.2	L	58.3	0.17	1.9	0.5	L			
GECXT2	54.7	54.8	54.8	53.3	54.4	-1.23	2.6		55.4	-1.09	2.9	1.4	16	LD			
H24C4H	59.8	L	60.8	60.1	L	60.5	H	60.3	1.00	1.5	0.4	60.4	1.13	2.8	1.0	16	
HBWKQU	58.1	58.7	58.8	59.1	58.7	0.38	3.5		59.7	-0.06	3.4	1.5	15	LD			
JC6KH2	62.1	60.2	64.6	*	62.5	1.78	4.2		62.4	2.58	*	3.9	2.0	TX			
JKCWEB	53.8	54.6	H	50.7	*	52.7	*	52.9	-1.78	5.2	1.7	47.9	-4.47	X	4.1	9.1	
LZPCUZ	57.4	58.4	58.3	57.5	57.9	0.09	3.3		57.0	-0.38	3.1	0.8	16	EN			
M6BN6L	65.2	*	63.0	*	65.7	*	63.4	H	64.3	2.52	*	4.5	1.3	63.3	2.40	*	4.3
N8EDTT	57.0	58.3	58.9	58.3	58.1	0.19	4.6		59.5	0.72	3.9	2.5	16	LD			
NJPBPQ	57.3	H	62.1	59.8	59.3	0.74	5.0		59.6	0.91	4.0	1.8	16	LD			
P3ZVCC	57.7	58.2	58.0	57.5	57.8	0.08	4.1		56.9	-0.43	3.7	1.8	16	LZ			
PMMMB9	58.3	59.3	58.8	60.2	59.1	0.57	2.6		59.2	0.57	2.8	0.7	16	LD			
PQK9Y6	57.6	56.3	H	58.8	56.5	-0.14	4.8		56.9	-0.42	3.8	1.2	16	LD			
QD9PVM	56.3	55.7	56.5	57.4	56.5	-0.44	2.4		55.9	-0.90	2.7	1.4	16	TH			
R3CGWX	59.8	57.3	57.2	58.9	58.3	0.24	3.6		57.9	-0.01	3.3	1.5	16	LD			



Containerboard Interlaboratory Testing Program
Analysis 240


Report #643
April 2023

Flat Crush Strength (CMT), 26 lb Corrugating Medium - CM12
TAPPI Official Test Method T809

WebCode	Weekly Means				Monthly Results					Cumulative Results						
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst		
RGC9L9	57.4	60.8	58.8	59.1	59.0	0.53	3.9	1.4	60.1	1.01	4.0	1.1	16	TU		
RP6G8Z	48.7 *	50.2 *	57.0	57.3	53.3	-1.64	4.8	4.5 H	56.4	-0.68	4.8	3.6	16	LD		
TNNT2Q	60.3	59.7	58.9	58.0	59.2	0.60	4.0	1.0	58.6	0.30	4.4	1.6	16	LD		
TNPJEZ	57.6	57.2	58.8	58.8	58.1	0.17	3.3	0.8	59.0	0.49	3.1	1.5	16	LC		
TTJHM4	58.8 L	58.7 L	58.4 L	58.8 L	58.7	0.39	0.8	0.2 L	57.8	-0.03	1.1	0.7	16	TU		
TURQU3	56.1	54.8	55.8	58.1	56.2	-0.54	4.1	1.4	54.7	-1.42	3.5	2.3	16	LC		
TX9RLN	51.8	54.4	56.0	54.6	54.2	-1.30	3.6	1.8	55.1	-1.26	3.8	2.0	16	LD		
UGMRJB	62.1	59.5	56.6	60.6	59.7	0.78	4.5	2.3	59.5	0.73	4.3	2.1	16	LZ		
UMALF9	58.6	52.3	57.5	57.0	56.4	-0.48	3.5	2.8	57.6	-0.11	3.7	2.7	16	LC		
UWTZF6	53.6	56.8	56.1	55.9	55.6	-0.77	2.9	1.4	55.1	-1.23	2.8	2.0	16	LD		
UY2DW7	61.9	61.9	64.1 *	65.3 *	63.3	2.14 *	3.2	1.7	62.0	1.84	2.8	2.0	16	TB		
VJ63LT	54.2	55.7	56.5	55.7	55.5	-0.80	3.4	1.0	55.0	-1.27	3.3	1.0	16	LD		
XZG2N9	50.5 *	52.6	49.1 *	58.0	52.5	-1.92	4.4	3.9 H	56.3	-0.71	3.7	3.2	16	MB		
YZYCZM	56.9	57.4	58.3 L	58.5	57.8	0.05	2.8	0.8	58.6	0.34	3.3	1.0	16	XX		
ZQ97PZ	54.1	54.4	52.4	54.3	53.8	-1.44	2.8	0.9	56.4	-0.64	3.7	2.8	16	LD		
ZTXDAX	59.5	59.0	64.8 *	59.2	60.6	1.13	4.3	2.8	61.5	1.61	4.1	2.5	16	LD		
ZZX8E7	56.7	56.5	55.6	58.8	56.9	-0.28	3.3	1.3	57.9	0.00	3.7	1.6	12	LD		
Consensus (All Labs) Results																
Wk Mean	57.37	57.42	57.56	58.26	Month Mean		57.64		Grand Mean		57.88					
Avg SDr	3.69	3.65	3.42	3.58	Avg SD		3.59		Avg SD		3.47					
SD btwn Labs	3.38	2.84	3.18	2.82	SD btwn Labs		2.65		SD btwn Labs		2.24					
Labs Incld	50	50	50	52	SD btwn Wks		1.67		SD btwn Wks		1.83					
Labs Excld	0	0	0	0	Labs Incld		51		Labs Incld		50					
Labs not Rcvd	2	2	2	0												

Key to Instrument Codes Reported by Participants

EM	Emerson 1200 Series	EN	Emerson 2200 Series
LC	L&W Crush Tester 48	LD	L&W Crush Tester 248
LZ	L&W Crush Tester (model not specified)	MB	Messmer Buchel K440
TB	TMI Monitor/Compression Tester, 17-70	TG	TMI Compression Tester, Model 17-10
TH	TMI Compression Tester, Model 17-76	TU	TMI Universal Crush Tester (TMI K440)
TX	TMI Crush Tester (model not specified)	XX	Instrument make/model not specified by lab



Containerboard Interlaboratory Testing Program
Analysis 250

Report #643
April 2023

Fluted Edge Crush Strength (CFC), 26 lb Corrugating Medium - CM12
TAPPI Official Test Method T843

WebCode	Weekly Means				Monthly Results				Cumulative Results					
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst
2GTGB8	64.5 L	62.3	62.3 L	63.6 *	63.2	-0.88	1.3	1.1	64.1	-1.80	2.8	1.4	16	TH
3Z42VU	69.4	69.1 L	69.1	69.2	69.2	0.27	1.7	0.2 L	69.1	0.11	1.8	1.6	12	MB
8VEAFZ	No Data	No Data	No Data	72.7	72.7	0.94	3.7	0.0	69.6	0.33	3.7	1.7	12	LD
92JDY8	54.7 *	55.4 *	54.5 *	53.9 X	54.6	-2.52 *	2.9	0.6	58.0	-4.14 X	4.6	2.5	16	LD
AB28WL	64.6	65.3	66.3	67.9	66.0	-0.34	3.1	1.4	66.8	-0.74	3.3	1.7	16	LZ
FVQLQC	69.4	72.0	71.0	68.7	70.3	0.47	3.3	1.5	69.3	0.22	4.2	1.9	16	LC
G9CB4M	71.8 L	73.8 L	70.0 L	71.5 L	71.8	0.76	1.2	1.6	71.2	0.95	1.3	1.4	16	XX
GALTDY	68.5	68.0	67.9	67.8	68.1	0.05	2.2	0.3	68.5	-0.10	1.9	0.5 L	16	LD
GECXT2	69.8	68.0	69.6	72.5	70.0	0.41	3.3	1.8	70.7	0.74	3.1	1.3	16	LD
HBWKQU	71.9	69.3	70.0	71.2	70.6	0.53	3.2	1.2	70.3	0.61	3.9	1.4	15	LD
JKCVEB	55.9 * H	55.3 * H	55.5 * H	53.6 XH	55.1	-2.44 *	8.7	1.0	64.5	-1.67	7.4	15.5 H	16	LD
N8EDTT	73.5	73.5	72.4	74.1	73.4	1.07	3.9	0.7	73.1	1.68	3.6	2.0	16	LD
PQK9Y6	73.6	74.0	73.7	71.4	73.2	1.03	3.3	1.2	72.2	1.32	3.8	1.6	16	LD
R3CGWX	70.6	72.9	70.8	69.5	70.9	0.60	2.9	1.4	68.8	0.00	3.2	1.8	16	LD
RP6G8Z	65.7	62.2	72.5	69.7	67.5	-0.05	3.0	4.5 H	67.8	-0.38	3.4	3.4	16	LD
TX9RLN	72.1	68.6	69.3	70.6	70.2	0.45	3.4	1.5	70.0	0.46	3.5	1.8	16	LD
UGMRJB	66.2	62.8 H	64.2	66.9	65.0	-0.53	4.4	1.9	63.9	-1.87	4.6	2.8	16	LZ
UMALF9	70.4	67.8	71.4	72.1	70.4	0.50	3.3	1.9	69.9	0.43	3.0	2.2	16	LC
YZYCZM	68.7	67.6	67.0	72.1	68.8	0.20	4.0	2.3	70.0	0.49	3.7	1.5	16	XX
ZZX8E7	62.5	65.3	65.0	67.4	65.1	-0.52	3.0	2.0	66.8	-0.78	3.8	2.6	12	XX

Consensus (All Labs) Results							
Wk Mean		67.58	67.01	67.49	69.93	Month Mean	
Avg SDr		3.57	3.78	3.32	2.92	Avg SD	
SD btwn Labs		5.33	5.54	5.31	2.60	SD btwn Labs	
Labs Incld		19	19	19	18	SD btwn Wks	
Labs Excld		0	0	0	2	Labs Incld	
Labs not Rcvd		1	1	1	0	Grand Mean	
						68.77	
						Avg SD	
						3.69	
						SD btwn Labs	
						2.59	
						SD btwn Wks	
						4.02	
						Labs Incld	
						19	

Key to Instrument Codes Reported by Participants

LC	L&W Crush Tester 48	LD	L&W Crush Tester 248
LZ	L&W Crush Tester (model not specified)	MB	Messmer Buchel K440
TH	TMI Compression Tester, Model 17-76	XX	Instrument make/model not specified by lab



Containerboard Interlaboratory Testing Program

Analysis 255

Ring Crush (RCT), 26 lb Corrugating Medium - CM12

TAPPI Official Test Method T822

Report #643

April 2023

WebCode	Weekly Means				Monthly Results					Cumulative Results					
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst	
2E9WEW	47.1	47.4	45.5	47.7 *	46.9	1.54	2.6	1.0	46.7	1.39	3.2	1.5	16	EM	
2GTGB8	45.0 L	45.7	43.7 L	45.2 L	44.9	0.34	1.4	0.9	43.9	-0.23	1.7	1.0	16	TH	
3Z42VU	43.0	43.6	44.0	43.9	43.6	-0.42	1.6	0.4	43.5	-0.45	1.6	0.8	12	MB	
4DQXQK	44.5 L	44.8 L	44.6 L	44.5 L	44.6	0.16	0.4	0.1 L	44.6	0.14	0.5	0.1 L	16	LD	
7JLEVW	34.9 XH	40.6 H	37.1 *H	38.7 X	37.8	-3.86 X	5.4	2.4	41.9	-1.41	4.7	3.8 H	16	EM	
9CJ9B6	45.4	40.3	42.1 L	42.9	42.7	-0.97	2.8	2.1	42.2	-1.19	2.8	2.6	16	LD	
AXDALB	46.1	44.8	46.4 L	45.5	45.7	0.82	2.0	0.7	45.1	0.45	2.4	1.0	16	LC	
BA776N	43.3	48.4	49.6 H	46.8	47.0	1.60	4.0	2.7	46.7	1.36	3.4	2.0	16	LZ	
BJBNR8	46.2	45.9	44.0 H	41.7	44.5	0.09	4.2	2.1	43.6	-0.42	4.3	2.0	12	LD	
C7YK34	54.1 XH	49.6 *	52.0 *	51.9 X	51.9	4.48 X	4.8	1.9	46.9	1.50	4.2	4.0 H	16	MB	
CVXM3M	42.8	42.8	44.0	44.8	43.6	-0.43	2.6	1.0	44.2	-0.04	2.9	1.1	16	LD	
DAG3WT	41.8	41.8	40.1	42.5	41.6	-1.63	3.0	1.0	43.3	-0.60	3.1	1.8	16	LD	
GECXT2	43.9	44.5	43.3	42.2	43.5	-0.52	3.7	1.0	44.2	-0.07	2.9	1.3	16	LD	
H24C4H	40.7 *	39.6	40.4	42.9	40.9	-2.02 *	2.2	1.4	41.3	-1.71	2.6	1.2	16	XX	
HBWKQU	45.6	45.6	45.3	43.3 H	44.9	0.36	3.6	1.1	45.7	0.81	3.2	1.4	16	LD	
JC6KH2	47.1	45.2	48.0	45.2	46.4	1.21	4.0	1.4	47.6	1.91 *	3.4	2.1	16	LZ	
N8EDTT	43.6	45.1	46.0	44.2	44.7	0.23	2.9	1.0	44.8	0.30	3.2	1.3	16	LD	
PMMMB9	44.3	43.6	43.9	44.4	44.0	-0.17	2.1	0.4	44.2	-0.07	2.5	0.4 L	16	LD	
PQK9Y6	46.7	47.7	44.0	44.8	45.8	0.88	2.8	1.7	46.1	1.01	2.8	0.9	16	LD	
QD9PVM	37.2 X	38.0 *	37.1 *	37.2 X	37.4	-4.13 X	2.3	0.4	35.8	-4.91 X	2.4	1.9	16	TH	
QL7T9D	43.4	44.6	43.4	44.0	43.8	-0.29	3.1	0.6	44.2	-0.09	3.5	1.2	16	TH	
R3CGWX	46.4	43.9	44.4	43.3	44.5	0.09	3.2	1.4	42.3	-1.13	3.4	1.6	16	LD	
TTJHM4	45.5 L	45.3	45.2 L	45.3 L	45.3	0.58	1.0	0.2 L	44.7	0.20	0.9	0.5	16	TU	
UMALF9	45.5 H	43.5	40.7	45.7	43.8	-0.29	4.3	2.3	45.0	0.37	3.3	1.9	16	LC	
UWTZF6	47.1 H	47.7	47.1	45.9	46.9	1.54	3.3	0.8	46.2	1.08	3.0	0.9	16	LD	
UY2DW7	41.4	40.7 L	40.7	40.7 *	40.9	-2.05 *	1.9	0.4	40.9	-1.98 *	2.6	1.4	16	XX	
YZYCZM	44.3	43.5	47.5	44.4	44.9	0.35	3.2	1.8	44.1	-0.11	3.5	1.3	16	XX	
ZTXDAX	43.1	43.7	46.3	45.1	44.5	0.13	2.5	1.4	44.7	0.24	2.9	1.2	16	LD	
ZZX8E7	45.0	40.6	43.3	40.9 *	42.5	-1.11	3.5	2.1	42.1	-1.25	3.8	1.4	12	LD	

Consensus (All Labs) Results

Wk Mean	44.57	44.08	44.12	44.15	Month Mean	44.33	Grand Mean	44.31
Avg SDr	2.66	3.49	3.13	2.75	Avg SD	2.93	Avg SD	3.08
SD btwn Labs	1.80	2.78	3.29	1.70	SD btwn Labs	1.69	SD btwn Labs	1.74
Labs Incld	26	29	29	26	SD btwn Wks	1.37	SD btwn Wks	1.72
Labs Excld	3	0	0	3	Labs Incld	26	Labs Incld	28
Labs not Rcvd	0	0	0	0				



Containerboard Interlaboratory Testing Program

Analysis 255

Ring Crush (RCT), 26 lb Corrugating Medium - CM12

TAPPI Official Test Method T822

Report #643

April 2023

Key to Instrument Codes Reported by Participants

EM	Emerson 1200 Series	LC	L&W Crush Tester 48
LD	L&W Crush Tester 248	LZ	L&W Crush Tester (model not specified)
MB	Messmer Buchel K440	TH	TMI Compression Tester, Model 17-76
TU	TMI Universal Crush Tester (TMI K440)	XX	Instrument make/model not specified by lab



Containerboard Interlaboratory Testing Program

Analysis 261

STFI, 26 lb Corrugating Medium - CM12

TAPPI Official Test Method T826

Report #643

April 2023

WebCode	Weekly Means				Monthly Results				Cumulative Results										
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst					
2GTGB8	13.7	L	14.6	L	15.6	L	15.4	L	14.8	1.06	0.5	0.9	13.5	-0.84	0.6	0.9	16	LZ	
2M3DG3	13.9		14.1		13.5		13.6		13.8	-0.29	1.1	0.3	13.6	-0.60	1.1	0.5	16	TT	
9CJ9B6	13.6		12.9		12.4		13.2		13.0	-1.28	1.1	0.5	13.3	-1.14	1.0	0.6	16	LZ	
9P6HGM	No Data			No Data			13.0		13.0	-1.26	0.8	0.0	13.4	-1.01	0.8	0.3	4	LH	
AXDALB	13.5		14.4		14.2		14.0		14.0	0.02	1.1	0.4	14.3	0.59	1.2	0.5	16	LH	
C7YK34	14.8	H	15.2		15.6		15.1	H	15.2	1.54	1.6	0.3	14.5	0.82	1.4	0.8	16	LA	
CKXWJ2	14.9	L	14.4		14.1		14.4		14.4	0.58	0.8	0.3	14.6	0.99	0.9	0.3	16	XX	
DAG3WT	14.1	L	13.2	L	14.6		13.5		13.9	-0.20	0.8	0.6	14.3	0.55	1.0	0.8	16	LH	
G9CB4M	14.1		13.2		12.6		13.2		13.3	-0.93	1.1	0.6	13.2	-1.34	1.0	0.6	16	XX	
GALTDY	14.6		14.7		14.3		14.6		14.6	0.74	1.2	0.2	14.5	0.78	1.2	0.2	16	LA	
GECXT2	14.4		13.7		13.7		16.1	*	14.5	0.62	1.1	1.1	14.1	0.26	0.9	0.7	16	LA	
HBWKQU	13.5	L	13.3		13.7		12.9		13.3	-0.88	1.0	0.3	13.6	-0.62	1.0	0.4	16	LB	
LHMUJU	12.8		13.4	L	12.9		13.3		13.1	-1.20	0.9	0.3	13.5	-0.79	1.1	0.6	16	LA	
LZPCUZ	13.0		13.6		13.2		13.5		13.3	-0.89	0.9	0.3	13.3	-1.11	0.9	0.3	16	LH	
M6BN6L	14.1	L	14.1		14.3		14.6		14.3	0.38	0.7	0.2	14.4	0.73	0.6	0.3	16	LH	
RGC9L9	13.0	H	16.2	XH	17.9	XH	14.6		15.4	1.89	2.3	2.1 H	15.4	2.24 *	1.6	1.0	16	LA	
TX9RLN	13.4		14.0		14.5		13.6		13.9	-0.16	1.1	0.5	14.1	0.12	1.1	0.6	16	LA	
UMALF9	14.2		14.5		14.3		14.5		14.3	0.46	1.0	0.2	14.1	0.27	1.0	0.3	16	LU	
WKBD3A	14.7		14.6		15.0		14.6		14.7	0.96	1.2	0.2	14.5	0.81	1.1	0.4	16	LA	
XZG2N9	13.0	H	13.0	H	15.9	H	14.2		14.0	0.03	1.6	1.4	14.5	0.89	1.3	2.3 H	16	LA	
ZQ97PZ	13.9		13.4		14.8		13.9		14.0	0.00	0.9	0.6	13.8	-0.28	1.1	0.4	16	LU	
ZTXDAX	15.1		14.6		14.5		14.5		14.7	0.90	1.1	0.3	14.4	0.68	1.1	0.3	16	XX	
ZZX8E7	13.5		11.1	X	11.5	*	13.6		12.4	-2.08	*	0.9	1.3	12.8	-2.00 *	1.0	1.2	12	LZ
Consensus (All Labs) Results																			
Wk Mean	13.89	13.95	14.06	14.08	Month Mean				14.00	Grand Mean				13.98					
Avg SDr	1.21	1.10	1.09	0.98	Avg SD				1.13	Avg SD				1.07					
SD btwn Labs	0.68	0.66	1.10	0.80	SD btwn Labs				0.76	SD btwn Labs				0.61					
Labs Incld	22	20	21	23	SD btwn Wks				0.76	SD btwn Wks				0.75					
Labs Excld	0	2	1	0	Labs Incld				23	Labs Incld				23					
Labs not Rcvd	1	1	1	0															



Containerboard Interlaboratory Testing Program

Analysis 261

STFI, 26 lb Corrugating Medium - CM12

TAPPI Official Test Method T826

Report #643

April 2023

Key to Instrument Codes Reported by Participants

LA	L&W Autoline	LB	L&W Model 152
LH	L&W 282	LU	L&W 52 without moisture correction (was 53)
LZ	L&W (model not specified)	TT	TMI Short Span Compression, 17-34 (MB K455)
XX	Instrument make/model not specified by lab		

End of Report