



Containerboard Interlaboratory Testing Program

Participant Summary Report #654 - March 2024

[Introduction to the Containerboard Program](#)

[Explanation of Tables and Definitions of Terms](#)

Analysis	Sample	Analysis Name
201	BX18	Top to Bottom Box Compression Strength, Corrugated Boxes
202	EC16	Edgewise Compressive Strength, by T811, Corrugated Board
203	EC16	Edgewise Compressive Strength by T839, Corrugated Board
205	42H3	Bursting Strength (Mullen), 42 lb Linerboard
206	52J1	Bursting Strength (Mullen), 52 lb Linerboard
215	42H3	Ring Crush, 42 lb Linerboard
216	52J1	Ring Crush, 52 lb Linerboard
223	42H3	STFI, 42 lb Linerboard
224	52J1	STFI, 52 lb Linerboard
228	42H	Roughness - Stylus Method, 42 lb Linerboard
229	42H3	Roughness - Sheffield Method, 42 lb Linerboard
231	42H	Internal Bond, 42 lb Linerboard
234	42H	COF Inclined Plane (Slide Angle), 42 lb Linerboard
237	42H	Air Resistance, 42 lb Linerboard
240	CM13	Flat Crush Strength (CMT), 26 lb Corrugating Medium
250	CM13	Fluted Edge Crush Strength (CFC), 26 lb Corrugating Medium
255	CM13	Ring Crush (RCT), 26 lb Corrugating Medium
261	CM13	STFI, 26 lb Corrugating Medium

**Collaborative Testing Services, Inc.
CONTAINERBOARD INTERLABORATORY TESTING PROGRAM**

INTRODUCTION

The Interlaboratory Testing Program for Containerboard is operated and maintained by Collaborative Testing Services, Inc. (CTS), with technical guidance provided by the Containerboard Group of the American Forest & Paper Association. The tests are conducted on a monthly basis.

For these tests samples of linerboard and corrugating medium, that each have been separately randomized from narrow rolls, are distributed for testing weekly. One weight of medium (26 lb.) is used for Concora Flat Crush Strength, Corrugated Fluted Crush Strength, Ring Crush Strength, and STFI Compression. Two weights of linerboard are tested each month for Mullen Burst, Ring Crush, and STFI Compression: 42 lb. - every month; 35 lb. and 56 lb. - alternate months. The participants return their test results for analysis and receive a monthly report.

Please refer to the section, "EXPLANATION OF TABLES", for definitions of terms and guidelines to interpreting the results.

USE OF AVERAGE MEAN AS A COLLABORATIVE REFERENCE VALUE

The samples of linerboard and corrugating medium, which have been randomized and placed in sealed packages for distribution in this program, may be used as collaborative reference materials. The values most representative of each material are the Cumulative Grand Means in the latest reports, given at the bottom right of each table. Comparisons can only be made within one lot of material; therefore check your measurements against the Cumulative Grand Means with the same lot code as on the packages being tested.

Material	Lot Code	Dates in Use
26# Corrugating Medium	CM13	September 2023 - Current
	CM12	June 2022 - August 2023
35# Corrugating Medium	35E3	June 2022 - Current
	35E2	June 2020 - April 2022
42# Corrugating Medium	42H3	October 2023 - Current
	42H1	April 2022 - November 2022
52# Corrugating Medium	52J1	November 2023 - Current
	56G2	May 2021 - May 2022

ABOUT CTS

Founded in 1971, Collaborative Testing Services, Inc. (CTS) is a privately-owned company that specializes in interlaboratory tests for a wide variety of industries including rubber, plastics, fasteners and metals, containerboard, paper, color, agriculture, hemp, and wine, as well as proficiency tests for forensic laboratories. All of the tests are designed to assist organizations in achieving and maintaining quality control objectives. Labs from the U.S., as well as more than 100 countries, currently participate in the CTS programs.

For further information, contact:
Collaborative Testing Services, Inc
21331 Gentry Drive
Sterling, VA 20166 USA
Voice: 571-434-1925
Fax: 571-434-1937
containerboard@cts-interlab.com

EXPLANATION OF TABLES

Each analysis is divided into three time spans. On the left side of the table are the individual laboratory results for each week of the month; in the center are each lab's statistical data for the month; and on the right are each lab's cumulative data for up to 16 weeks. At the bottom of the table are the consensus statistics for all the participants for each of the three time spans.

Definitions of Terms Used

Weekly Results

Laboratory Data

- | | |
|--------------|--|
| WebCode | - A six character laboratory identifier used to maintain information on a confidential basis. The WebCode is unique for each cycle and will change for each report. Your WebCode can be found in your Individual Report (Current Month Performance Report) and your datasheet. |
| Weekly Means | - The average of the test results obtained by the participant for each week that data were reported. |

Consensus Data

- | | |
|---------------|---|
| Wk Mean | - For each week, the average of the Means for all the participants, excluding those laboratories flagged with an 'X'. |
| Avg SD | - For each week, the average of the within-laboratory standard deviations (SD's) for all the participants, excluding those laboratories flagged with an 'X'. The Avg SD is an indication of the variation of measurements within an average laboratory. |
| SD btwn Labs | - For each week, the standard deviation of the laboratory Means about the Wk Mean, excluding those laboratories flagged with an 'X'. The SD LABS is an indication of the precision of measurement between the laboratories. |
| Labs Incl'd | - The number of laboratory Means included in the Wk Mean for that week. |
| Labs Excl'd | - The number of laboratory Means reported but excluded from the Wk Mean for that week because of outlying results ('X' following Mean). |
| Labs not rcvd | - The number of laboratories failing to report for that week. |

Monthly Results

Laboratory Data

- | | |
|-------|---|
| Mean | - For each laboratory, the average of all the weekly Means reported for this month. |
| CPV | - Comparative Performance Value , an indication of how well a laboratory's Mean agrees with the other participants. The CPV is a ratio indicating the number of standard deviations from the consensus mean (Monthly Mean). The closer a laboratory's CPV is to zero, the more consistent its results are with the other participants' data. |
| SD | - For each laboratory, the average of the weekly within-lab standard deviations (SD's) for all reported Weekly Means this month. |
| SD Wk | - The standard deviation among the laboratory's weekly Means, including those Means flagged with an 'X'. The SD Wks is an indication of that laboratory's ability to obtain constant results from week to week. |

Consensus Data

- | | |
|---------------|---|
| Month Mean | - The average of the Means for all the participants, excluding those laboratories flagged with an 'X,' reporting data for this month. |
| Avg SD | - For the current month, the average of the within-laboratory standard deviations (SD's) for all the participants, excluding those laboratories flagged with an 'X'. |
| SD btwn Labs | - For the current month, the standard deviation of the laboratory Means about the Month Mean, excluding those laboratories flagged with an 'X'. |
| SD btwn Group | - For the current month, the standard deviation of the laboratory Means within the group about the Month Mean, excluding those laboratories flagged with an 'X'. |
| SD btwn Wks | - For the current month, the average of the laboratory between week standard deviations (SD Wks') for all the participants, excluding those laboratories flagged with an 'X'. |

Cumulative Results

Laboratory Data

- | | |
|-------|---|
| Mean | - For each lab, the average of all the monthly Means reported for the weeks shown. |
| CPV | - Comparative Performance Value , an indication of how well a laboratory's cumulative mean agrees with the other participants. The CPV is a ratio indicating the number of standard deviations from the consensus mean (Monthly Mean). |
| SDr | - For each laboratory, the average of the weekly within-lab standard deviations (SD's) for the weeks shown. |
| SD Wk | - The standard deviation among the laboratory's weekly Means for the weeks shown, including those Means flagged with an 'X'. The SD Wks is an indication of that laboratory's ability to obtain constant results from week to week. |
| Wks | - The number of weeks included in the cumulative period. |
| Inst | - The two letter instrument code. Codes are summarized at the bottom of the last analysis page. |

Consensus Data

- | | |
|--------------|--|
| Grand Mean | - The average of the Means for all the participants, excluding those laboratories flagged with an 'X,' reporting data for the number of weeks included in the cumulative period. |
| Avg SD | - For the cumulative period, the average of the within-laboratory standard deviations (SD's) for all the participants, excluding those laboratories flagged with an 'X'. |
| SD btwn Labs | - For the cumulative period, the standard deviation of the laboratory Means about the Month Mean, excluding those laboratories flagged with an 'X'. |
| SD btwn Wks | - For the cumulative period, the average of the laboratory between week standard deviations for all the participants, excluding those laboratories flagged with an 'X'. |
| Labs Incld | - The number of laboratory Means included in the Grand Mean. |

Any laboratory that receives a 'flag' following a mean or standard deviation should refer to the chart below for an explanation of the data flag symbol:

<u>Flag</u>	<u>Explanation</u>
-------------	--------------------

Data Flags "**X**" and "*****" indicate a laboratory's performance on an average value differed from the consensus.

Data Flags "**H**" and "**L**" indicate a laboratory's performance on a standard deviation differed from the consensus.

Flags assigned to Weekly Means, Monthly Mean and Cumulative Mean:

- X** Excluded from the weekly means, monthly means and/or the cumulative mean. Immediate review of data and/or testing procedure is recommended.
- *** Included in the weekly means, monthly means and/or the cumulative mean; however, lab should review testing procedure and monitor future results.

Flags assigned to Weekly Means:

- H** Indicates high within-laboratory standard deviation. The laboratory SD for each week is not shown, but laboratory average SD and consensus average SD values are shown.
- L** Indicates low within-laboratory standard deviation. The laboratory SD for each week is not shown, but laboratory monthly average SD and consensus average SD values are shown.

Flags assigned to Monthly SD Wks and Cumulative SD Wks:

- H** Indicates high variability between weekly means (high week-to-week variation).
- L** Indicates low variability between weekly means (low week-to-week variation).



Containerboard Interlaboratory Testing Program
Analysis 201

Report #654
March 2024

Top to Bottom Box Compression Strength, Corrugated Boxes - BX18
TAPPI Official Test Method T804

WebCode	Monthly Results			Cumulative Results					
	Mean	CPV	SD	Mean	CPV	SD	Months	Months	Inst
3UJ2H3	478.9	-1.72	13.51	513.4	-2.39 *	31.89	3	LL	
4PGJHE	542.2	-0.52	37.43	542.2	-1.22	0.00	1	LG	
4VT8HB	570.5	0.02	31.60	571.6	-0.01	7.82	3	ER	
7K3NQA	542.4	-0.51	46.79	562.5	-0.39	18.94	3	EX	
9AXLQH	552.6	-0.32	36.62	583.2	0.46	30.50	3	LG	
9ZPK8V	565.6	-0.07	45.11	582.1	0.42	18.38	3	LG	
A9DVVV	623.0	1.01	63.92	595.5	0.96	23.80	3	LG	
BYTFRZ	546.7	-0.43	47.52	570.3	-0.07	33.29	2	ER	
DDV6TH	520.1	-0.94	54.45	534.8	-1.52	23.05	3	EX	
EA4RXT	609.8	0.76	27.01	611.7	1.63	5.24	3	LO	
GTKE7Y	583.0	0.26	47.06	579.2	0.30	3.60 L	3	EX	
JHZDQN	536.3	-0.63	37.76	574.8	0.12	34.60	3	LM	
JJ78HU	524.6	-0.85	40.93	573.3	0.06	42.19	3	LM	
KUYAZT	537.2	-0.61	18.43	568.2	-0.15	30.42	3	EX	
LMVMLX	569.8	0.01	42.86	595.0	0.94	32.79	3	LS	
MBKA7J	501.9	-1.28	35.31	538.2	-1.38	32.94	3	LG	
NT28BN	592.8	0.44	61.88	584.0	0.49	7.79	3	ER	
NV348N	556.8	-0.24	43.47	551.1	-0.85	13.73	3	ER	
Q3AG3P	547.3	-0.42	34.85	578.8	0.28	28.90	3	EX	
RH4AMQ	704.8	2.56 *	27.11	705.5	5.46 X	1.70 L	3	LS	
UF63VP	594.1	0.47	14.52	603.0	1.27	13.74	3	ET	
UZCBAN	497.3	-1.37	45.91	547.2	-1.01	44.77	3	TB	
VD2X8F	603.6	0.65	51.20	569.3	-0.11	32.65	3	ES	
XLZ7DJ	602.0	0.62	27.31	586.9	0.61	38.25	3	LS	
YBK CZ6	620.0	0.96	39.35	609.7	1.54	12.91	3	EX	
YHJXPJ	1,019.1	8.52 X	45.44	921.4	14.29 X	203.30 H	3	LG	
Z8DFQL	684.0	2.17 *	8.27 L	681.7	4.49 X	8.16	3	ER	
Consensus (All Labs) Results									
Month Mean	569.52			Grand Mean	571.92				
Avg SD	40.14			Avg SD Months	27.18				
SD btwn Labs	52.75			SD btwn Labs	24.45				
Labs Incl	26			Labs Incl	24				



Containerboard Interlaboratory Testing Program
Analysis 201

Report #654
March 2024

Top to Bottom Box Compression Strength, Corrugated Boxes - BX18
TAPPI Official Test Method T804

Consensus By Method

Test Method	Group Mean	SD btwn Group	Difference from Grand Mean	Labs Included
Hot melt adhesive sealing	543.42	51.79	26.10	8
Clip sealing	575.06	44.51	5.54	17
Staple sealing	684.02	0.00	114.50	1

Key to Instrument Codes Reported by Participants

ER	Emerson 6200 Series	ES	Emerson 8510
ET	Emerson 7200	EX	Emerson Apparatus (Model not specified)
LG	TLS / L.A.B. Validator Series	LL	Lansmont 76-5K
LM	Lansmont 122-15k	LO	Lansmont 152-30k
LS	Lansmont Squeezer	TB	TMI Monitor/Compression Tester, Model 17-70



Containerboard Interlaboratory Testing Program
Analysis 202

Report #654
March 2024

Edgewise Compressive Strength, by T811, Corrugated Board - EC16
TAPPI Official Test Method T811

WebCode	Monthly Results				Cumulative Results					
	Mean	CPV	SD		Mean	CPV	SD	Months	Months	Inst
4G8TFB	40.7	-1.79	2.93		40.7	-1.79	0.00	1	TS	
4GMEMR	149.7	29.14 X	8.38 H		149.7	29.14 X	0.00	1	LD	
7K3NQA	46.8	-0.04	2.94		46.8	-0.04	0.00	1	LC	
93FMBX	44.5	-0.69	4.58		44.5	-0.69	0.00	1	TS	
9AXLQH	47.5	0.14	0.85 L		47.5	0.14	0.00	1	EX	
BYTFRZ	42.6	-1.25	7.05 H		42.6	-1.25	0.00	1	EN	
FQXDM7	52.4	1.54	1.74		52.4	1.54	0.00	1	XX	
LMVMLX	47.6	0.16	2.90		47.6	0.16	0.00	1	LD	
XLZ7DJ	50.1	0.88	1.80		50.1	0.88	0.00	1	EM	
YBK CZ6	48.9	0.54	3.50		48.9	0.54	0.00	1	LC	
ZFP RJD	48.8	0.51	1.28 L		48.8	0.51	0.00	1	XX	
Consensus (All Labs) Results										
Month Mean	46.97				Grand Mean	46.97				
Avg SD	3.42				Avg SD Months	0.00				
SD btwn Labs	3.53				SD btwn Labs	3.53				
Labs Incl'd	10				Labs Incl'd	10				

Key to Instrument Codes Reported by Participants

- | | | | |
|----|--|----|---------------------------------------|
| EM | Emerson 1200 Series | EN | Emerson 2200 |
| EX | Emerson (model not specified) | LC | L&W Crush Tester 48 |
| LD | L&W Crush Tester 248 | TS | TMI Digital Crush Tester, Model 17-56 |
| XX | Instrument make/model not specified by lab | | |



Containerboard Interlaboratory Testing Program
Analysis 203

Report #654
March 2024

Edgewise Compressive Strength by T839, Corrugated Board - EC16
TAPPI Official Test Method T839

WebCode	Monthly Results			Cumulative Results					
	Mean	CPV	SD	Mean	CPV	SD	Months	Months	Inst
4G8TFB	50.7	0.28	2.98	50.7	0.28	0.00	1	TS	
4PGJHE	45.5	-1.06	2.65	45.5	-1.06	0.00	1	EM	
4VT8HB	46.8	-0.74	1.39	46.8	-0.74	0.00	1	LD	
62PJRC	52.0	0.61	0.87	52.0	0.61	0.00	1	BU	
64GH7B	56.2	1.67	2.50	56.2	1.67	0.00	1	TG	
7K3NQA	53.3	0.93	2.27	53.3	0.93	0.00	1	LC	
7UV6RK	50.3	0.16	0.72	50.3	0.16	0.00	1	LD	
93FMBX	47.1	-0.66	3.14	47.1	-0.66	0.00	1	TS	
9AXLQH	47.9	-0.44	2.26	47.9	-0.44	0.00	1	LY	
9ZPK8V	53.0	0.86	1.58	53.0	0.86	0.00	1	MK	
BYTFRZ	48.8	-0.21	1.83	48.8	-0.21	0.00	1	EN	
C7GYJ7	57.2	1.93 *	1.64	57.2	1.93 *	0.00	1	LC	
EA4RXT	44.9	-1.22	4.23	44.9	-1.22	0.00	1	LD	
G7NY73	54.0	1.11	0.93	54.0	1.11	0.00	1	EM	
GTKE7Y	43.9	-1.48	1.96	43.9	-1.48	0.00	1	TL	
JHZDQN	42.0	-1.96 *	1.13	42.0	-1.96 *	0.00	1	EM	
JJ78HU	47.3	-0.60	2.24	47.3	-0.60	0.00	1	TG	
JRXPW3	51.9	0.56	4.48	51.9	0.56	0.00	1	TE	
KUYAZT	48.5	-0.29	2.56	48.5	-0.29	0.00	1	LD	
LMVMLX	47.2	-0.63	2.15	47.2	-0.63	0.00	1	LD	
NT28BN	48.4	-0.33	2.74	48.4	-0.33	0.00	1	LD	
NV348N	48.7	-0.26	1.30	48.7	-0.26	0.00	1	EM	
P8B4GM	43.7	-1.52	2.93	43.7	-1.52	0.00	1	IX	
RH4AMQ	57.9	2.11 *	3.03	57.9	2.11 *	0.00	1	EM	
UF63VP	48.6	-0.26	2.18	48.6	-0.26	0.00	1	TD	
UZCBAN	51.8	0.54	0.75	51.8	0.54	0.00	1	LD	
VD2X8F	48.4	-0.32	2.08	48.4	-0.32	0.00	1	LD	
VHBMKB	48.1	-0.40	1.58	48.1	-0.40	0.00	1	TU	
VPAABP	49.7	0.01	3.21	49.7	0.01	0.00	1	TD	
VT8TE9	55.4	1.46	1.23	55.4	1.46	0.00	1	TH	
YBK CZ6	50.1	0.12	2.26	50.1	0.12	0.00	1	LC	
YHJXPJ	47.2	-0.62	3.23	47.2	-0.62	0.00	1	EM	
Z8DFQL	55.9	1.60	2.08	55.9	1.60	0.00	1	LD	
ZFPRJD	48.1	-0.39	1.33	48.1	-0.39	0.00	1	XX	
ZJ7Y8C	47.4	-0.59	1.94	47.4	-0.59	0.00	1	TD	



Containerboard Interlaboratory Testing Program
Analysis 203

Edgewise Compressive Strength by T839, Corrugated Board - EC16
TAPPI Official Test Method T839

Report #654
March 2024

Consensus (All Labs) Results

Month Mean	49.65	Grand Mean	49.65
Avg SD	2.33	Avg SD Months	0.00
SD btwn Labs	3.90	SD btwn Labs	3.90
Labs Incl'd	35	Labs Incl'd	35

Key to Instrument Codes Reported by Participants

BU	Buchel Digital Crush Tester	EM	Emerson 1200 Series
EN	Emerson 2200	IX	Instron (model not specified)
LC	L&W Crush Tester 48	LD	L&W Crush Tester 248
LY	L&W 830	MK	Mark-10 ESM303
TD	TMI Digital Crush Tester, Model 17-09	TE	TMI Monitor/Compression Tester, Model 17-60
TG	TMI Digital Crush Tester, 17-76	TH	TMI Monitor/Compression Tester, Model 17-76
TL	Tech-Lab Systems Compression	TS	TMI Digital Crush Tester, Model 17-56
TU	TMI Universal Crush Tester (TMI K440)	XX	Instrument make/model not specified by lab



Containerboard Interlaboratory Testing Program

Analysis 205

Report #654

March 2024

Bursting Strength (Mullen), 42 lb Linerboard - 42H3

TAPPI Official Test Method T807

WebCode	Weekly Means				Monthly Results					Cumulative Results					
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst	
2RFNLB	113.4	115.7	114.0	114.6	114.4	-0.30	6.7	1.0	111.7	-0.87	6.5	4.1	16	LJ	
3W983Z	111.7	110.4	114.2	106.0	110.5	-1.17	7.5	3.4	112.5	-0.67	9.1	3.1	16	XX	
3XJALD_AL	119.2	117.4	118.6	113.2	117.1	0.31	10.7	2.7	115.6	0.10	9.8	3.0	12	AL	
48MN7Q_AL	118.2	117.0	115.2	106.5	114.2	-0.34	8.5	5.3	117.4	0.54	9.5	4.2	13	AL	
4DX7T7_AL	115.6	114.8	113.4	113.3	114.3	-0.32	10.1	1.1	115.0	-0.06	10.0	3.1	16	AL	
4GMEMR	105.0 *	107.1 *	104.9 *	101.1 *	104.5	-2.54 *	7.3	2.5	103.0	-3.01 X	8.6	3.5	16	LA	
4VT8HB	105.1 *H	115.6	113.3	113.2	111.8	-0.89	11.2	4.6	110.2	-1.24	9.8	3.1	16	LZ	
69WHP4	118.9	119.4	117.8	119.1	118.8	0.70	10.0	0.7	118.4	0.79	8.8	1.7	16	LB	
6KLPHR_AL	108.6	110.6	113.6	110.3	110.8	-1.12	5.8	2.1	109.6	-1.40	6.5	2.0	12	XX	
6RZVUP_AL	109.6 H	117.3	118.8	116.8	115.6	-0.02	10.7	4.1	115.9	0.16	9.2	3.6	14	AL	
7K3NQA	110.4	113.6	115.2	112.5	112.9	-0.63	8.5	2.0	111.8	-0.85	8.6	2.1	16	AH	
868V82	119.1	118.0	121.1	116.9	118.8	0.69	10.1	1.8	114.4	-0.22	10.3	4.6	16	LZ	
9AXLQH	111.7	122.2	123.8	130.0 *	121.9	1.40	8.9	7.6 H	122.0	1.65	9.5	3.9	16	AX	
9WWTLZ_AL	124.0	122.1	125.1 *	123.6	123.7	1.81	8.1	1.2	123.4	2.00 *	7.6	2.0	16	AL	
A39WJ7_AL	117.3	111.6	113.3	112.4	113.6	-0.47	10.0	2.5	111.8	-0.86	10.8	3.4	16	AL	
ABYHMH	108.7	112.7	No Data	No Data	110.7	-1.14	7.9	2.8	109.6	-1.40	8.7	2.8	12	LJ	
ABYHMH_AI	122.6	125.8 *	No Data	No Data	124.2	1.92	11.2	2.3	122.0	1.66	13.5	4.0	12	AL	
B39NFZ	111.9	113.8	115.8	113.7	113.8	-0.44	7.3	1.6	112.3	-0.74	9.0	2.4	16	LC	
BCTMJ3	119.2	118.7	115.5	118.4	117.9	0.50	10.5	1.6	120.2	1.21	10.4	4.1	16	LC	
BXW9J9	114.7	116.2	115.4	115.1	115.4	-0.08	5.4	0.6	115.5	0.05	5.2	0.6 L	16	LA	
CHCDGH_AL	117.2	No Data	No Data	No Data	117.2	0.32	9.0	0.0	116.7	0.36	8.4	3.6	13	AL	
DDV6TH	119.1 L	119.1	119.5	120.1	119.5	0.85	7.7	0.5 L	117.5	0.55	8.7	3.0	12	XX	
E8QNW3	114.8	114.1	116.0	116.9	115.5	-0.06	5.6	1.2	115.6	0.09	5.5	1.1	16	TP	
EAW9MN	114.0	112.1	120.0	115.3	115.4	-0.08	10.1	3.4	110.6	-1.14	9.0	4.7	16	LA	
ERJ2XU	123.2	116.0	118.8	119.6	119.4	0.83	9.8	3.0	117.4	0.53	9.7	3.4	16	LA	
ERJ2XU_AL	119.0	118.4	118.4	121.1	119.2	0.79	6.3	1.3	117.0	0.43	8.0	2.6	16	AL	
EYWAYV	114.5	116.9	120.2	119.8	117.9	0.48	9.6	2.7	115.4	0.03	10.1	2.9	16	LA	
G9GZYT	No Data	117.4	120.0	110.7	116.0	0.07	11.2	4.8	113.2	-0.52	9.1	3.1	15	ME	
GFDN4Q_AL	117.8	113.9	108.5	114.0	113.6	-0.49	8.1	3.8	113.1	-0.52	9.3	2.5	16	AL	
H29RH4	122.7 L	122.0	122.2	121.0	122.0	1.41	3.9	0.7	118.3	0.74	3.3	3.6	16	AH	
HRKTRX_AL	120.2	118.1	121.0	126.0	121.3	1.27	9.3	3.3	118.8	0.88	10.0	3.4	12	AL	
JRXPW3	119.0	116.7	118.6	116.7	117.8	0.46	10.6	1.2	116.4	0.28	10.1	3.1	16	LC	
JWH7EV_AL	126.7 *	121.1	116.4	128.5 *	123.2	1.69	10.0	5.5	125.5	2.53 *	11.1	4.6	16	AL	
KUYAZT	116.0	109.6	111.2	108.0	111.2	-1.02	8.2	3.5	111.2	-1.00	9.5	3.3	16	AH	
LKDWNM	120.6	120.0	120.4	115.5 L	119.1	0.77	5.4	2.4	116.5	0.30	5.8	6.6	16	LA	



Containerboard Interlaboratory Testing Program

Analysis 205

Bursting Strength (Mullen), 42 lb Linerboard - 42H3

TAPPI Official Test Method T807

Report #654

March 2024

WebCode	Weekly Means				Monthly Results					Cumulative Results						
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst		
LMVMLX	111.1	120.6	110.7	117.8	115.1	-0.15	10.8	4.9	116.1	0.21	9.3	3.4	16	LA		
LY8Q9G_AL	99.6	XH	108.3	105.8 *	105.0	104.7	-2.49	*	16.7	3.7	108.0	-1.80	12.4	3.4	16	AL
NT28BN	120.6	114.8	116.3	119.4	117.8	0.46	7.4	2.7	117.7	0.61	8.9	3.0	16	AH		
PLTW6U	115.5	117.6	117.3	117.0	116.8	0.25	9.1	0.9	118.5	0.80	9.1	3.7	16	LC		
PLTW6U_AL	118.6	119.8	120.3	117.8	119.1	0.77	9.9	1.1	118.8	0.86	9.7	2.1	16	AL		
Q2ZFGQ	116.3	116.0	116.3	117.4	116.5	0.18	6.3	0.6	115.5	0.05	6.1	1.1	16	AH		
TMDD2J	106.7	116.0	109.7	112.9	111.3	-1.00	7.2	4.0	108.8	-1.58	8.0	4.7	16	LC		
TUUHLJ	108.3 L	108.8 L	109.2 L	109.3 L	108.9	-1.54	1.9	0.5 L	108.8	-1.60	2.8	3.6	16	LA		
UQPCJH	118.2	122.7	121.2	120.6	120.7	1.12	10.9	1.9	121.5	1.53	10.4	3.0	16	LJ		
UZCBAN	111.4	108.6	107.6	106.1	108.4	-1.65	8.2	2.2	107.6	-1.88	8.0	3.9	16	XX		
VD2X8F	114.2	117.7	115.2	116.2	115.8	0.02	9.2	1.5	115.7	0.10	9.6	3.3	16	LA		
VWG89G	121.4	114.0	117.4	120.0 L	118.2	0.56	7.5	3.2	115.5	0.06	8.7	4.6	16	TB		
X6FFDJ	134.9 X	135.3 X	130.6 X	128.7 *	132.4	3.77	X	7.9	3.2	129.9	3.61 X	9.3	4.2	16	AX	
XTRKQD_AL	118.8	113.8	110.8	112.2	113.9	-0.41	8.4	3.5	115.0	-0.07	9.6	3.5	16	AL		
YJT8FV	109.8	109.8	110.4 L	110.6	110.2	-1.26	4.7	0.4 L	111.9	-0.83	4.8	2.7	8	LA		
Z8DFQL	119.1	113.3	113.9	116.7	115.8	0.01	7.6	2.7	116.2	0.24	8.5	3.6	16	LA		
ZFPRJD	117.0	114.8	115.7	114.8	115.6	-0.03	8.8	1.0	114.8	-0.11	7.8	1.8	12	LC		
Consensus (All Labs) Results																
Wk Mean	115.85	115.84	115.79	115.77	Month Mean			115.72	Grand Mean			115.25				
Avg SDr	8.85	8.61	8.55	8.41	Avg SD			8.86	Avg SD			8.91				
SD btwn Labs	5.08	4.18	4.59	6.05	SD btwn Labs			4.42	SD btwn Labs			4.06				
Labs Incld	49	50	48	49	SD btwn Wks			2.92	SD btwn Wks			3.38				
Labs Excld	2	1	1	0	Labs Incld			51	Labs Incld			50				
Labs not Rcvd	1	1	3	3												

Key to Instrument Codes Reported by Participants

AH	Perkins Model AH	AL	L & W Autoline 400
AX	Perkins Mullen Tester (model not specified)	LA	L&W Bursting Strength Tester
LB	L&W Burst-O-Matic	LC	L&W Autoline (205 Enrollment)
LJ	L&W Bursting Strength Tester J-Type	LZ	L&W (model not specified)
ME	Messmer Automatic Burst Tester ME-06	TB	TMI Monitor/Burst 1000
TP	Technidyne PROFILE/Plus	XX	Instrument make/model not specified by lab



Containerboard Interlaboratory Testing Program

Analysis 206

Bursting Strength (Mullen), 52 lb Linerboard - 52J1

TAPPI Official Test Method T807

Report #654

March 2024

WebCode	Weekly Means				Monthly Results					Cumulative Results					
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst	
2RFNLB	108.4	112.7	109.8	109.0	110.0	-0.27	10.2	1.9	111.8	0.36	8.6	2.9	12	LJ	
3W983Z	113.1	111.0	113.0	109.0	111.5	0.18	10.6	1.9	110.4	-0.10	10.5	3.1	12	XX	
3XJALD_AL	115.3	106.9	106.3	106.9	108.8	-0.62	11.4	4.3	109.3	-0.45	11.8	3.3	8	AL	
48MN7Q_AL	116.4 L	110.5	112.2	117.5 L	114.1	0.98	7.8	3.3	109.8	-0.28	12.7	5.2	11	AL	
4DX7T7_AL	109.0	115.9	101.7	108.2	108.7	-0.66	13.0	5.8	112.0	0.40	12.3	5.1	12	AL	
4GMEMR	109.8	103.0	107.7	102.7	105.8	-1.53	13.5	3.5	103.5	-2.26	*12.8	3.1	12	LA	
4VT8HB	104.3	107.9	104.1	106.3	105.6	-1.58	11.1	1.8	107.4	-1.05	11.3	2.7	12	LZ	
69WHP4	90.1 X	90.9 X	93.8 X	92.5 XL	91.8	-5.73	X	8.0	1.6	107.2	-1.09	9.9	12.4 H	12	LB
6KLPHR_AL	104.5	107.3	108.8	101.8 *	105.6	-1.59	8.9	3.1	105.7	-1.57	8.6	2.3	12	XX	
6RZVUP_AL	110.7	110.6	110.2	111.6	110.8	-0.03	10.9	0.6 L	108.0	-0.84	10.9	3.2	10	AL	
7K3NQA	102.4	113.4	108.9	109.0	108.4	-0.74	13.1	4.5	107.9	-0.89	12.2	4.2	12	AH	
868V82	108.4	109.3	119.5 *	117.7	113.7	0.86	13.9	5.7	114.5	1.20	11.3	5.3	12	LZ	
8GVPV8	100.6 *	116.2	115.1	112.7	111.2	0.08	9.5	7.2	110.2	-0.15	13.2	6.7	7	LA	
9AXLQH	121.6 *	119.8 *	121.5 *	116.1 H	119.8	2.66	*	14.9	2.6	117.7	2.19	*13.3	3.2	12	LA
9WWTLZ_AL	121.7 *	117.0	113.7	118.3	117.7	2.05	*	7.9	3.3	117.7	2.21	*8.8	3.2	12	AL
A39WJ7_AL	106.3 H	109.1	103.9	109.3	107.2	-1.12	14.4	2.6	109.5	-0.38	12.9	3.8	12	AL	
B39NFZ	108.5	106.8	102.0	108.0	106.3	-1.37	7.3	3.0	107.8	-0.92	8.5	3.3	12	LA	
BCTMJ3	115.9	116.1	110.8	115.0	114.4	1.06	10.7	2.5	113.8	0.98	13.7	3.6	12	LC	
BXW9J9	110.9 L	111.1 L	110.8 L	112.1 L	111.2	0.10	3.8	0.6 L	111.2	0.17	7.6	0.9 L	12	LA	
CHCDGH_AL	113.7	No Data	No Data	No Data	113.7	0.83	11.5	0.0	110.1	-0.19	8.6	3.8	8	AL	
DDV6TH	114.1	109.9	109.5	114.3	112.0	0.32	6.5	2.6	113.4	0.87	9.2	3.1	8	XX	
E8QNW3	112.4	111.0 L	111.9	109.7	111.3	0.11	6.2	1.2	112.8	0.67	6.2	2.2	12	TP	
EA9WMN	108.5	114.9	111.6	111.8	111.7	0.24	12.4	2.6	109.5	-0.39	11.1	3.4	12	LA	
ERJ2XU	110.5	112.1	114.2	118.5	113.8	0.88	9.2	3.5	114.6	1.24	9.2	4.4	8	LA	
ERJ2XU_AL	107.2	112.5	104.3	111.6	108.9	-0.60	10.1	3.9	111.9	0.38	9.7	5.2	8	AL	
EYWAYV	117.0	115.3	104.5	114.6	112.9	0.59	13.9	5.6	110.3	-0.12	13.4	5.4	12	LA	
G9GZYT	No Data	107.3	112.7	110.4	110.1	-0.23	8.8	2.7	109.6	-0.34	10.1	2.2	11	LA	
GFDN4Q_AL	110.5	109.1	109.2	111.6	110.1	-0.24	10.7	1.2	109.4	-0.40	11.6	2.7	12	AL	
H29RH4	132.7 XL	132.5 XL	132.2 XL	132.5 XL	132.5	6.49	X	2.9	0.2 L	130.5	6.23	X 3.3	2.4	12	AH
HRKTRX_AL	115.8	115.9	120.2 *	118.6	117.6	2.02	*	11.4	2.2	113.7	0.95	10.4	4.4	12	AL
JRXPW3	107.4	114.8	111.6	111.1	111.2	0.10	11.1	3.0	110.6	-0.03	10.9	5.1	12	XX	
JWH7EV_AL	112.6	105.7	111.6	110.7	110.1	-0.22	12.3	3.1	111.7	0.33	10.6	4.0	12	AL	
KUYAZT	110.8	104.4	106.0	108.0	107.3	-1.08	13.0	2.8	107.5	-1.01	12.3	2.7	12	AH	
LKDWNM	112.7	113.8	115.4 L	115.2	114.3	1.02	5.8	1.3	113.5	0.87	7.5	2.7	12	LA	
LMVMLX	113.9	107.0 H	114.3	112.0	111.8	0.27	21.7	3.3	113.4	0.84	14.8	4.4	12	LA	



Containerboard Interlaboratory Testing Program

Analysis 206

Bursting Strength (Mullen), 52 lb Linerboard - 52J1

TAPPI Official Test Method T807

Report #654

March 2024

WebCode	Weekly Means				Monthly Results					Cumulative Results						
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst		
LY8Q9G_AL	107.7	102.4 *	104.1	106.0	105.1	-1.75	12.2	2.3	104.0	-2.11 *11.8	3.0	12	AL			
NT28BN	122.0 *	108.2	112.8	112.1	113.8	0.87	10.6	5.8	114.5	1.19	10.8	4.0	12	AH		
PLTW6U	116.0	115.7	109.3	102.4	110.9	-0.01	14.4	6.4	110.8	0.03	13.1	4.3	12	LC		
PLTW6U_AL	104.9	117.1	102.4 H	116.2	110.1	-0.22	19.9	7.6 H	110.9	0.07	15.9	4.6	12	XX		
Q2ZFGQ	108.0	108.9 L	107.9	111.3	109.0	-0.56	7.1	1.6	111.5	0.26	11.2	4.5	12	AH		
TMDD2J	112.1	113.8	113.6	115.6	113.8	0.86	11.0	1.4	112.3	0.52	9.5	2.7	12	LC		
TUUHLJ	116.1 L	116.3 L	115.2 L	113.9 L	115.4	1.35	1.8	1.1	116.9	1.94 *	2.3	2.3	12	LA		
UQPCJH	110.0	110.2	106.6	120.1	111.7	0.25	12.1	5.8	109.5	-0.39	13.9	5.1	12	LZ		
UZCBAN	113.2	110.7	107.7	99.9 *	107.9	-0.90	9.6	5.8	107.0	-1.15	9.4	4.2	12	XX		
VD2X8F	119.7	110.2	107.4	110.8	112.0	0.34	12.0	5.3	110.9	0.07	11.2	5.5	12	LA		
VWG89G	108.8	107.1	114.3	109.5	109.9	-0.29	14.4	3.1	113.1	0.77	11.9	5.8	12	TB		
XTRKQD_AL	105.5	101.2 *	111.7	113.7	108.0	-0.86	10.1	5.7	108.4	-0.73	11.5	4.2	12	XX		
YJT8FV	105.2 L	106.1 L	105.7 L	105.7 L	105.7	-1.57	3.6	0.3 L	105.7	-1.59	3.6	0.3 L	4	LA		
Z8DFQL	108.3	114.4	111.2	109.7	110.9	0.00	11.1	2.6	110.5	-0.06	12.8	3.3	12	XX		
Consensus (All Labs) Results																
Wk Mean	111.13	110.88	110.15	111.22	Month Mean		110.88		Grand Mean		110.70					
Avg SDr	11.27	12.42	11.27	10.55	Avg SD		11.39		Avg SD		11.04					
SD btwn Labs	5.01	4.34	4.67	4.66	SD btwn Labs		3.33		SD btwn Labs		3.18					
Labs Incld	46	46	46	46	SD btwn Wks		3.77		SD btwn Wks		4.28					
Labs Excld	2	2	2	2	Labs Incld		47		Labs Incld		48					
Labs not Rcvd	1	1	1	1												

Key to Instrument Codes Reported by Participants

AH	Perkins Model AH	AL	L & W Autoline 400
LA	L&W Bursting Strength Tester	LB	L&W Burst-O-Matic
LC	L&W Autoline (206 Enrollment)	LJ	L&W Bursting Strength Tester J-Type
LZ	L&W (model not specified)	TB	TMI Monitor/Burst 1000
TP	Technidyne PROFILE/Plus	XX	Instrument make/model not specified by lab



Containerboard Interlaboratory Testing Program
Analysis 215
Ring Crush, 42 lb Linerboard - 42H3
TAPPI Official Test Method T822

Report #654
March 2024

WebCode	Weekly Means				Monthly Results				Cumulative Results												
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst							
2RFNLB	94.0	94.3	96.0	96.2	L	95.1	-0.08	2.4	1.1	95.1	-0.08	2.6	0.8	L	16	LD					
3KZVW7	99.3	95.5	L	100.6	95.7	97.8	0.69	2.5	2.6	95.1	-0.09	3.2	3.1	L	16	LD					
3XJALD	92.2	L	97.4	95.3	L	96.5	95.3	-0.01	2.7	2.2	95.5	0.06	2.5	1.3	L	12	LD				
48MN7Q	96.6	98.1	98.1	99.2		98.0	0.76	3.4	1.1	98.1	1.08	3.4	1.1	L	16	LC					
4DX7T7	96.4	94.5	92.5	94.1		94.4	-0.29	4.1	1.6	95.1	-0.09	4.0	2.4	L	16	LD					
4GMEMR	100.9	H	100.0	H	101.1	H	100.6	H	100.6	1.53	20.6	0.5	L	96.8	0.57	21.2	3.6	16	LB		
4VT8HB	92.2	93.1	L	90.8	91.5	91.9	-1.02	2.9	1.0	93.8	-0.59	3.2	2.0	L	16	LD					
64GH7B	100.5	97.8	100.0	98.8		99.3	1.13	2.8	1.2	96.7	0.52	2.9	1.9	L	16	TH					
69WHP4	97.6	93.5	97.7	97.5		96.5	0.34	4.4	2.0	96.6	0.52	4.4	2.4	L	16	LD					
6KLPHR	No Data	No Data	No Data	98.4		98.4	0.88	2.6	0.0	92.5	-1.08	2.5	2.8	L	9	LD					
7K3NQA	96.6	L	98.4	L	97.4	L	93.8		96.6	0.34	2.1	2.0		95.9	0.24	2.5	1.3	16	LC		
868V82	101.8	91.1	101.8	H	94.5		97.3	0.55	6.5	5.4		94.7	-0.24	4.4	6.3	L	16	LC			
8VF6X7	88.6	*	89.4	89.2	89.4		89.1	-1.82	3.3	0.4	L	90.5	-1.87	3.4	1.6	L	16	EM			
9AXLQH	95.9	96.8	98.2	L	97.4		97.1	0.49	2.5	1.0		95.9	0.22	2.3	2.0	L	16	LG			
A39WJ7	69.6	XH	68.2	XH	69.5	XH	68.7	XH	69.0	-7.69	X	10.1	0.7	69.9	-9.81	X	7.8	2.1	16	LD	
B39NFZ	93.4	L	93.5	92.0	93.3		93.0	-0.68	2.8	0.7		92.8	-0.99	2.7	0.8	L	16	LD			
BCTMJ3	93.8	91.3	93.3	92.3		92.7	-0.79	2.3	1.1		94.5	-0.32	2.3	1.5	L	16	LD				
BYTFRZ	90.5	87.7	*L	85.0	*	87.7	*		87.7	-2.23	*	2.6	2.2	92.4	-1.13	2.7	3.3	L	16	LC	
C7GYJ7	94.8	94.1	94.3	94.6		94.4	-0.28	3.5	0.3	L	94.9	-0.15	3.3	1.4	L	16	LC				
E8QNW3	96.1	96.0	95.1	96.5		95.9	0.16	2.5	0.6	L	96.1	0.31	3.3	1.8	L	16	TH				
ERJ2XU	97.9	95.5	99.0	95.6		97.0	0.47	3.4	1.7		96.0	0.26	3.2	1.9	L	16	LD				
G7NY73	93.4	93.1	92.6	95.4		93.6	-0.51	4.0	1.2		96.2	0.33	3.5	2.7	L	16	EM				
G9GZYT	No Data	104.2	*	97.8	105.3	*	102.5	2.06	*	4.5	4.0	101.3	2.30	*	5.0	5.2	15	LX			
H29RH4	95.7	93.6	L	94.0	93.8	L	94.3	-0.33	2.2	1.0		94.9	-0.16	2.0	1.6	L	16	LD			
JRXPW3	93.8	82.2	XH	99.8	96.9		93.2	-0.65	10.6	7.7	H	96.8	0.59	6.5	6.1	L	16	MB			
JWH7EV	74.7	XH	72.4	XH	106.6	*	104.5	*		89.5	-1.70	6.6	18.5	H	91.3	-1.55	6.2	12.5	H	16	LZ
LKDWNM	87.7	*	88.7	87.4	95.8		89.9	-1.60	2.9	4.0		89.4	-2.27	*	3.8	4.9	L	16	LC		
LMVMLX	95.4	L	95.5	92.6	92.7	L	94.0	-0.39	2.7	1.6		94.7	-0.24	2.5	1.5	L	16	LD			
MYRHKL	107.8	X	97.7	H	101.6	100.0		101.8	1.87	6.8	4.3		100.9	2.14	*	6.9	3.0	L	TU		
NT28BN	95.3	94.9	92.9	93.8		94.2	-0.35	2.5	1.1		94.2	-0.43	2.7	1.3	L	16	LD				
NTB6TQ	99.7	97.8	99.4	102.1	L	99.8	1.27	3.6	1.8		99.8	1.73	4.0	2.0	L	16	MB				
PLTW6U	100.7	97.7	88.5	93.0		95.0	-0.12	4.0	5.4		93.5	-0.72	3.2	5.0	L	16	LD				
PTNY86	102.5	*	98.8	101.6	102.3		101.3	1.72	2.8	1.7		100.4	1.96	*	3.0	1.7	L	16	LD		
TMDD2J	91.4	89.3	94.1	90.7		91.4	-1.16	2.4	2.0		92.8	-0.97	3.4	2.5	L	16	LD				
TUUHLJ	97.6	L	97.3	L	97.8	L	97.5	L		97.5	0.62	1.1	0.2	L	94.8	-0.20	1.6	1.9	L	TU	



Containerboard Interlaboratory Testing Program

Analysis 215

Ring Crush, 42 lb Linerboard - 42H3

TAPPI Official Test Method T822

Report #654

March 2024

WebCode	Weekly Means				Monthly Results				Cumulative Results											
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst						
VBPU8P	95.7	L	97.6	L	97.6	L	97.2	L	97.0	0.48	1.6	0.9	96.4	0.44	1.2	1.1	L	12	MZ	
VWG89G	94.0		99.4		96.8		96.0		96.6	0.34	3.5	2.2	93.9	-0.55	3.2	3.7		16	LD	
X6FFDJ	93.5		96.4		94.1		92.6		94.2	-0.36	3.7	1.6	96.0	0.25	4.2	16.0	H	16	LD	
XHZVGJ	91.5	L	91.1	L	91.2		91.6		91.3	-1.18	2.0	0.3	L	94.6	-0.29	2.5	3.5		8	LD
XTRKQD	97.6		95.8		97.7	L	97.5		97.2	0.51	2.4	0.9	99.2	1.50	2.7	2.2		16	LD	
YJT8FV	93.6	L	92.9	L	94.5	L	94.0		93.8	-0.48	1.6	0.7	93.0	-0.89	1.6	1.7		8	LZ	
ZJ7Y8C	94.9	L	94.2	L	94.8	L	94.9	L	94.7	-0.19	1.7	0.3	L	95.0	-0.11	1.7	0.4	L	12	MB
Consensus (All Labs) Results																				
Wk Mean	95.49		95.10		95.76		95.88		Month Mean		95.39		Grand Mean		95.31					
Avg SD _r	4.32		4.73		4.83		4.56		Avg SD		4.89		Avg SD		4.77					
SD btwn Labs	3.49		3.46		4.44		3.77		SD btwn Labs		3.44		SD btwn Labs		2.59					
Labs Incl _d	37		38		40		41		SD btwn Wks		3.80		SD btwn Wks		4.20					
Labs Excl _d	3		3		1		1		Labs Incl _d		41		Labs Incl _d		41					
Labs not Rcvd	2		1		1		0													

Key to Instrument Codes Reported by Participants

EM	Emerson 1200	LB	L&W Crush Tester 240
LC	L&W Crush Tester 48	LD	L&W Crush Tester 248
LG	L&W 753	LX	L&W 506
LZ	L&W Crush Tester (model not specified)	MB	Messmer Buchel K440
MZ	Messmer Buchel (model not specified)	TH	TMI Compression Tester, Model 17-76
TU	TMI Universal Crush Tester (TMI K440)		



Containerboard Interlaboratory Testing Program
Analysis 216
Ring Crush, 52 lb Linerboard - 52J1
TAPPI Official Test Method T822

Report #654
March 2024

WebCode	Weekly Means				Monthly Results					Cumulative Results					
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst	
2RFNLB	126.9	126.1	126.8	126.6	126.6	-0.32	4.0	0.4	125.4	-0.55	4.1	2.1	12	LD	
3KZVW7	133.2	125.6	131.2	128.7	129.7	0.52	3.8	3.3	129.6	0.67	4.0	2.3	8	LD	
3XJALD	129.9	130.0	129.5	121.3	127.7	-0.03	4.2	4.2	127.4	0.04	3.4	2.9	8	LD	
48MN7Q	135.9	136.1	137.4	* 135.0	136.1	2.26	*	4.2	1.0	136.1	2.56	*	4.3	1.8	LC
4DX7T7	128.3	130.0	130.7	128.8	129.4	0.45	4.5	1.1	130.0	0.81	4.0	1.7	12	LD	
4GMEMR	96.5 XH	95.7 XH	106.3 XH	104.4 XH	100.7	-7.33	X	20.7	5.4	97.2	-8.77	X	19.6	6.1	LB
4VT8HB	126.4	125.8	128.8	124.8	126.4	-0.36	3.5	1.7	127.5	0.06	3.7	1.9	12	LD	
64GH7B	127.0	125.4	129.4	131.0	128.2	0.11	4.7	2.5	126.3	-0.29	4.4	2.4	12	TH	
69WHP4	83.1 X	81.4 X	83.1 X	82.4 X	82.5	-12.26	X	4.5	0.8	113.5	-4.00	X	4.6	23.0 H	12
6KLPHR	No Data	No Data	No Data	128.1	128.1	0.08	4.0	0.0	123.6	-1.08	4.6	2.2	9	LD	
7K3NQA	129.9	128.4	126.6	129.5	128.6	0.23	3.3	1.5	128.7	0.42	3.3	1.5	12	LC	
868V82	118.5	135.2	134.2	127.2	128.8	0.27	4.2	7.7	124.2	-0.88	5.5	7.3	12	LC	
8VF6X7	122.2	123.0	123.6	H 123.8	123.2	-1.24	5.9	0.7	120.4	-2.00	*	5.2	3.3	12	
9AXLQH	127.9	128.3	125.7	126.8	127.2	-0.17	3.5	1.2	127.4	0.04	3.7	2.5	12	LY	
A39WJ7	84.3 XH	85.0 XH	85.9 XH	86.9 XH	85.5	-11.44	X	12.6	1.1	83.0	-12.89	X	11.7	2.1	12
B39NFZ	126.2	126.2	126.1	124.6	125.8	-0.54	3.5	0.8	125.6	-0.47	3.7	1.1	L	12	
BCTMJ3	122.8 L	119.9	120.8	L 121.2	121.2	-1.79	1.8	1.2	124.7	-0.75	2.5	3.6	12	LD	
BYTFRZ	117.9	113.7 *L	111.6 X	114.9 *	114.5	-3.58	X	3.1	2.6	123.5	-1.09	3.7	7.1	12	LC
C7GYJ7	126.9	122.7	130.7	124.9	126.3	-0.40	4.1	3.4	124.9	-0.69	3.8	2.5	12	LC	
E8QNW3	127.7	127.0	125.4	128.9	127.3	-0.14	4.7	1.4	125.9	-0.41	4.1	2.6	12	TH	
ERJ2XU	131.9	128.5	131.1	128.7	130.1	0.62	3.8	1.7	129.2	0.58	3.9	1.7	8	LD	
G7NY73	125.0	123.5	123.4	125.2	124.3	-0.94	4.6	1.0	125.2	-0.59	3.7	1.1	L	12	
G9GZYT	No Data	140.6 *	115.1 XH	138.7 *	131.5	1.00	11.2	14.2 H	134.7	2.18	*	8.4	8.2	10	
H29RH4	122.7	122.8	122.6	122.2	122.6	-1.40	2.9	0.3	L	122.0	-1.54	2.6	0.8	L	12
JRXPW3	112.5 *H	112.2 *H	127.9	H 124.0	119.1	-2.34	*	11.4	8.0 H	123.4	-1.13	9.2	6.8	12	MB
JWH7EV	100.6 XH	96.3 XH	125.6 H	140.6 *	115.8	-3.25	X	11.0	21.0 H	122.5	-1.38	8.9	16.3 H	12	LZ
LKDWNM	118.5	120.0	120.5	122.7	120.4	-1.99	*	3.8	1.7	123.3	-1.15	4.0	3.7	12	LC
LMVMLX	125.7	126.5	125.1	126.1	125.8	-0.52	3.8	0.6	L	127.3	0.00	3.6	1.6	12	LD
MYRHKL	136.0	127.4	131.4	133.0	131.9	1.13	4.6	3.6	130.0	0.80	4.7	2.5	12	TU	
NT28BN	127.3 L	125.6	125.6	127.5	126.5	-0.35	4.4	1.0	125.6	-0.47	3.6	1.5	12	LD	
NTB6TQ	133.3	130.5 L	127.8	133.1	131.2	0.92	3.5	2.6	130.2	0.86	4.2	3.5	12	MB	
PLTW6U	142.2 *	132.6	122.6	123.5	130.2	0.67	4.7	9.2 H	129.3	0.60	5.0	6.5	12	LD	
PTNY86	134.0	127.9	131.2	133.4	131.6	1.05	3.9	2.7	131.9	1.34	3.9	2.3	12	LD	
TMDD2J	124.2	127.2	130.4	129.5	127.8	0.02	4.1	2.8	129.4	0.62	4.8	3.0	12	LD	
TUUHLJ	131.4 L	131.1 L	130.8 L	L 130.9	131.0	0.88	1.0	0.2	L	128.4	0.32	1.6	2.5	12	TU



Containerboard Interlaboratory Testing Program
Analysis 216
Ring Crush, 52 lb Linerboard - 52J1
TAPPI Official Test Method T822

Report #654
March 2024

WebCode	Weekly Means				Monthly Results				Cumulative Results						
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst	
VBPU8P	134.1 L	130.2	133.0 L	133.7	132.8	1.35	1.8	1.8	129.7	0.71	1.2	3.8	12	MZ	
VWG89G	128.6	134.3	139.7 X	132.8	133.8	1.64	6.1	4.6	129.0	0.51	5.0	5.2	12	LD	
XHZVGJ	124.7	123.4	125.8	125.8	124.9	-0.77	2.8	1.1	124.9	-0.68	2.8	1.1 L	4	LD	
XTRKQD	128.9	130.2	127.1	130.4	129.1	0.37	2.7	1.5	132.0	1.39	3.1	2.7	12	LD	
YJT8FV	125.7	125.5	127.9	128.5 L	126.9	-0.23	3.3	1.5	126.9	-0.10	3.3	1.5	4	LZ	
ZJ7Y8C	127.8 L	127.2 L	127.8	127.3 L	127.5	-0.07	1.8	0.3 L	129.8	0.73	1.7	4.1	12	MB	
Consensus (All Labs) Results															
Wk Mean	127.48	126.96	127.78	127.99	Month Mean		127.77	Grand Mean		127.26					
Avg SDr	4.61	4.58	3.82	4.21	Avg SD		4.62	Avg SD		4.45					
SD btwn Labs	5.81	5.55	3.80	4.98	SD btwn Labs		3.69	SD btwn Labs		3.43					
Labs Incld	35	36	34	38	SD btwn Wks		3.93	SD btwn Wks		4.42					
Labs Excld	4	4	6	3	Labs Incld		36	Labs Incld		38					
Labs not Rcvd	2	1	1	0											

Key to Instrument Codes Reported by Participants

EM	Emerson 1200	LB	L&W Crush Tester 240
LC	L&W Crush Tester 48	LD	L&W Crush Tester 248
LY	L&W Crush Tester 958	LZ	L&W Crush Tester (model not specified)
MB	Messmer Buchel K440	MZ	Messmer Buchel (model not specified)
TH	TMI Compression Tester, Model 17-76	TU	TMI Universal Crush Tester (TMI K440)



Containerboard Interlaboratory Testing Program

Analysis 223

STFI, 42 lb Linerboard - 42H3

TAPPI Official Test Method T826

Report #654

March 2024

WebCode	Weekly Means				Monthly Results				Cumulative Results					
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst
3W983Z	23.4	23.1	23.4	22.1	23.0	-0.55	1.6	0.6	22.7	-0.92	1.6	0.7	16	LH
3XJALD_AL	23.1	24.1	24.3	24.6 H	24.0	0.44	2.3	0.7	23.4	-0.35	2.1	0.7	12	AL
48MN7Q	23.7	22.9 H	22.6	24.6	23.5	-0.10	2.0	0.9	23.3	-0.39	2.0	0.8	13	LU
4DX7T7_AL	23.9	24.3	23.9	22.9	23.8	0.19	1.9	0.6	23.8	0.06	1.8	0.3 L	16	AL
4GMEMR	23.2	23.2	23.6	21.6	22.9	-0.66	2.0	0.9	23.7	-0.08	2.1	1.0	16	LH
4VT8HB	23.4	23.2	23.7	23.1	23.3	-0.22	1.7	0.3	23.3	-0.41	1.7	1.1	16	LY
69WHP4	24.7	25.1	25.0	24.9	24.9	1.30	1.9	0.2	26.0	2.06 *	2.0	4.3 H	16	LU
6KLPHR_AL	22.5	23.1	23.0	22.7	22.8	-0.73	1.6	0.3	23.5	-0.21	2.0	0.8	12	XX
6RZVUP	23.6	24.0	21.8	23.6	23.2	-0.31	1.8	1.0	23.2	-0.47	1.6	0.6	14	LU
7K3NQA	22.5	23.3	23.1	23.3	23.1	-0.49	1.6	0.4	23.2	-0.48	1.7	0.4	16	LU
868V82	22.4	19.4 X	21.4 *H	20.8 *	21.0	-2.50 *	2.0	1.3	21.2	-2.30 *	1.6	1.8	16	LY
9AXLQH	24.4	24.4 L	24.0	22.4	23.8	0.23	1.6	1.0	23.8	0.07	1.6	0.8	16	BK
9WWTLZ_AL	23.9	23.2	23.6	24.0	23.7	0.10	1.7	0.3	23.5	-0.22	1.7	0.6	16	AL
A39WJ7	22.9	23.3	23.1	22.9	23.1	-0.49	2.1	0.2	22.9	-0.77	2.0	0.7	16	LY
A39WJ7_AL	22.3	22.7	21.8	21.9	22.2	-1.35	1.6	0.4	23.0	-0.70	1.7	0.6	16	AL
A6K4AZ	22.0	23.2	23.8	23.0	23.0	-0.55	1.7	0.8	22.8	-0.83	1.6	0.6	16	LW
ABYHMH	21.4	22.1	No Data	No Data	21.8	-1.76	2.0	0.5	22.4	-1.23	1.6	0.8	12	LH
B39NFZ	24.1	23.9	24.6	24.2	24.2	0.60	1.8	0.3	23.3	-0.43	6.4	0.7	16	LA
BCTMJ3	22.1	22.8	23.8	21.6	22.6	-0.97	1.8	1.0	22.9	-0.80	1.6	0.8	16	LA
BXW9J9	24.1	24.1	23.7	23.8	23.9	0.34	2.1	0.2	23.9	0.12	2.0	0.2 L	16	LZ
BYTFRZ	21.6 L	21.3 *	21.7	22.6	21.8	-1.73	1.7	0.6	22.1	-1.47	1.6	0.5	16	LZ
EA4RXT	24.3	23.6	24.5	24.0	24.1	0.54	2.0	0.4	23.9	0.18	1.9	0.6	16	LH
EAW9MN	24.8 H	23.9	25.8	24.5	24.8	1.15	2.4	0.8	24.4	0.61	2.1	0.6	16	LH
ERJ2XU_AL	23.4	23.6	23.2	24.0	23.5	-0.02	1.8	0.3	23.8	0.02	1.8	0.6	16	AL
EYWAYV	24.4	24.7	24.2	25.2	24.6	1.02	1.8	0.4	23.7	-0.01	1.8	0.9	16	LY
G9GZYT	No Data	26.6 XH	24.4 H	27.0 XH	26.0	2.37 *	4.2	1.4	25.0	1.10	2.7	2.6	15	LZ
GFDN4Q_AL	31.0 X	30.6 X	30.6 X	31.9 X	31.0	7.21 X	2.1	0.6	30.4	6.11 X	2.4	0.9	16	AL
HRKTRX_AL	23.4	23.4	26.0 *	24.8	24.4	0.79	2.0	1.2	25.9	1.94 *	1.9	1.4	12	AL
JRXPW3	23.6	23.5	24.2	23.5	23.7	0.13	1.7	0.3	24.7	0.86	1.7	0.8	16	LA
JWH7EV_AL	23.2	22.3	23.4	23.5	23.1	-0.46	2.0	0.6	22.5	-1.17	1.7	0.6	16	AL
K4NXWG	24.0	24.8	24.5	24.0	24.3	0.72	1.5	0.4	24.4	0.55	1.8	0.6	16	XX
L6FDKX	24.6 H	24.2	24.6	25.2	24.7	1.05	2.3	0.4	24.8	0.92	1.8	0.7	16	LA
LKDWNM	24.5	23.3	23.6	24.4	24.0	0.37	1.7	0.6	24.1	0.31	1.7	0.4	16	LA
LMVMLX	23.7	23.8	23.1	22.3	23.2	-0.35	1.5	0.7	23.2	-0.49	1.8	0.4 L	16	LZ
LY8Q9G_AL	23.3	24.6	25.1	24.1	24.3	0.69	2.0	0.8	24.0	0.27	1.9	0.8	16	AL



Containerboard Interlaboratory Testing Program

Analysis 223

STFI, 42 lb Linerboard - 42H3

TAPPI Official Test Method T826

Report #654

March 2024

WebCode	Weekly Means				Monthly Results				Cumulative Results					
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst
M9TDGP	24.0	23.3	22.9	23.1	23.3	-0.27	1.3	0.5	23.3	-0.42	1.3	0.5	4	LZ
MYRHKL	26.3 *	25.3	25.1	No DATA	25.6	1.94 *	1.9	0.6	25.1	1.21	1.8	0.7	15	LA
NT28BN	22.5	21.9	23.0	22.8	22.6	-0.97	2.0	0.5	23.1	-0.57	1.7	0.6	16	LU
NTB6TQ	23.9	23.4	24.2	L	24.1	0.33	1.5	0.4	23.8	0.09	1.6	0.7	16	LA
PLTW6U	25.6	24.2	22.7	23.3	24.0	0.39	1.4	1.3	23.1	-0.60	1.7	1.3	16	LZ
PLTW6U_AL	47.9 XL	48.6 XL	47.2 XL	45.8 XL	47.4	23.07 X	0.0	1.2	46.1	20.41 X 0.0	1.6	16	AL	
PTNY86	26.0 *	22.2	22.9	22.0	23.3	-0.29	1.4	1.8 H	25.0	1.19	1.7	1.4	16	LH
Q7ATZB	25.0	24.8	25.2	25.0	25.0	1.40	1.6	0.2	25.1	1.21	1.5	0.3	L 16	LH
T2DNKB	23.0 L	22.5 L	23.1	23.2	23.0	-0.59	2.3	0.3	22.8	-0.84	2.5	0.5	12	LH
TMDD2J	23.4	23.5	23.2	22.9 L	23.3	-0.30	1.3	0.2	24.0	0.24	1.6	1.0	16	LA
TUUHLJ	22.5	21.8	22.1	21.9	22.1	-1.44	1.5	0.3	21.3	-2.28 *	1.6	0.8	16	XX
TWWFWC	25.7	23.7	24.0	24.7	24.5	0.93	2.1	0.9	24.0	0.23	1.8	1.2	12	LU
UQPCJH	23.2	25.6 *	24.0 H	23.9	24.2	0.58	2.4	1.0	24.4	0.63	2.2	0.7	16	LH
VBUU8P	25.5 L	25.2 L	25.9 *	24.4	25.2	1.63	1.1	0.6	26.0	2.02 *	0.8	0.9	8	LZ
VWG89G	23.5	23.1	22.7	25.5	23.7	0.10	2.1	1.2	23.8	0.09	2.1	0.7	16	LW
X6FFDJ	25.6 L	50.5 XL	23.9 L	24.6 L	31.2	7.35 X	0.0	12.9 H	26.5	2.50 *	1.8	6.6 H	16	LH
XTRKQD_AL	23.2	22.1 L	22.2	23.1	22.6	-0.89	1.5	0.5	23.3	-0.40	1.5	0.9	16	AL
Z8DFQL	23.6	25.1	25.1	23.2	24.2	0.66	1.2	1.0	25.1	1.21	1.7	0.8	16	LA
ZFPRJD	20.7 *	23.4 L	21.0 *	20.8 *L	21.5	-2.03 *	1.6	1.3	22.8	-0.87	2.1	1.2	16	LA
Consensus (All Labs) Results														
Wk Mean	23.63	23.55	23.65	23.44	Month Mean				23.57	Grand Mean				23.75
Avg SDr	1.82	1.80	1.78	1.87	Avg SD				1.89	Avg SD				2.00
SD btwn Labs	1.19	0.99	1.14	1.15	SD btwn Labs				1.03	SD btwn Labs				1.09
Labs Incld	51	49	51	49	SD btwn Wks				0.75	SD btwn Wks				1.39
Labs Excld	2	5	2	3	Labs Incld				51	Labs Incld				52
Labs not Rcvd	1	0	1	2										

Key to Instrument Codes Reported by Participants

AL	L & W Autoline 400	BK	Buchel Strip Compression Tester BK-155
LA	L&W Autoline (223 Enrollment)	LH	L&W 282
LU	L&W 52 without moisture correction(was 53)	LW	L&W 53 with moisture correction (was 53M)
LY	L&W 152 without moisture correction	LZ	L&W (model not specified)
XX	Instrument make/model not specified by lab		



Containerboard Interlaboratory Testing Program

Analysis 224

STFI, 52 lb Linerboard - 52J1

TAPPI Official Test Method T826

Report #654

March 2024

WebCode	Weekly Means				Monthly Results				Cumulative Results							
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst		
3W983Z	32.3	31.8	31.9	30.7	31.7	-0.98	2.1	0.7	31.5	-1.45	2.0	0.5	12	LH		
3XJALD_AL	33.1	34.2	34.4	H 35.2	34.2	1.02	2.5	0.9	33.2	0.20	2.4	1.2	8	XX		
48MN7Q	35.0	31.3	33.6	31.2	32.8	-0.13	2.4	1.8	33.5	0.46	2.4	1.2	11	LU		
4DX7T7_AL	33.3	33.7	33.1	33.7	33.4	0.40	2.4	0.3	33.4	0.37	2.3	0.4	L 12	AL		
4GMEMR	33.5	32.9	31.9	H 32.3	32.6	-0.25	2.7	0.7	32.4	-0.56	2.8	1.2	12	LH		
4VT8HB	33.5	33.5	32.9	32.6	33.1	0.16	2.3	0.5	32.5	-0.47	2.2	1.5	12	LZ		
69WHP4	24.7	XL 24.3	X 24.8	X 24.6	24.6	-6.53	X 1.7	0.2	L	31.4	-1.58	1.9	5.0	H 12	LU	
6KLPHR_AL	32.6	L 32.4	32.8	32.3	32.5	-0.32	2.1	0.2	32.5	-0.49	2.2	0.5	12	XX		
6RZVUP	32.9	31.5	31.9	H 32.1	32.1	-0.65	2.7	0.6	32.9	-0.06	2.4	1.5	10	LU		
7K3NQA	31.9	32.0	33.5	32.8	32.6	-0.29	2.2	0.8	32.9	-0.09	2.3	0.7	12	LU		
868V82	32.2	28.2	X 31.5	28.6 *	30.1	-2.20	*	2.6	2.0	29.7	-3.23	X 2.4	2.4	12	LW	
9AXLQH	34.7	31.7	34.8	34.0	33.8	0.69	2.6	1.4	33.8	0.77	2.5	1.0	12	BK		
9WWTLZ_AL	31.6	32.4	32.6	32.5	32.3	-0.50	2.3	0.5	31.9	-1.05	2.9	2.3	12	AL		
A39WJ7	31.7	32.1	31.2	31.8	31.7	-0.97	2.2	0.3	31.1	-1.80	2.3	0.5	12	LY		
A39WJ7_AL	32.6	31.6	32.9	32.1	32.3	-0.49	1.9	0.5	32.5	-0.49	2.2	0.5	12	AL		
A6K4AZ	32.0	H 32.8	31.9	32.3	32.3	-0.53	3.0	0.4	31.8	-1.14	2.5	0.8	12	LW		
B39NFZ	32.7	H 32.6	32.7	L 32.7	32.7	-0.19	2.5	0.0	L	32.8	-0.15	2.4	0.6	12	LW	
BCTMJ3	31.1	31.5	31.7	32.4	31.7	-0.99	2.0	0.5	32.4	-0.62	2.0	0.8	12	LU		
BXW9J9	32.7	32.6	33.0	32.8	32.8	-0.11	2.5	0.2	L	32.0	-0.98	2.6	0.8	12	LZ	
BYTFRZ	31.7	30.2	31.2	32.4	31.4	-1.20	2.0	0.9	31.4	-1.52	2.0	0.6	12	LZ		
EA4RXT	34.0	33.8	33.5	33.9	33.8	0.69	2.4	0.2	L	34.0	0.95	2.3	0.8	12	LH	
EAW9MN	36.0	33.0	35.8	35.4	35.0	1.66	2.3	1.4	34.5	1.43	2.5	1.1	12	LH		
ERJ2XU_AL	33.4	32.3	32.9	31.9	32.6	-0.25	2.1	0.7	32.6	-0.34	2.4	0.8	8	AL		
EYWAYV	33.2	35.2	33.6	33.9	34.0	0.83	2.1	0.8	33.2	0.18	2.4	1.1	12	LU		
G9GZYT	No Data	33.0	24.4	X 35.7	H	31.1	-1.47	5.8	5.9	H	32.2	-0.73	3.6	3.0	11	LZ
GFDN4Q_AL	39.7	X 41.5	XH 42.5	X 43.0	X	41.6	6.85	X 2.7	1.5	41.0	7.72	X 2.5	1.2	12	AL	
HRKTRX_AL	30.7	32.5	35.4	32.6	32.8	-0.11	2.1	2.0	34.5	1.51	2.3	1.8	12	AL		
JRXPW3	34.6	31.6	L 33.2	32.0	32.9	-0.05	2.5	1.3	33.9	0.84	2.4	1.2	12	LA		
JWH7EV_AL	32.0	33.4	32.0	34.2	32.9	-0.02	2.0	1.1	31.8	-1.16	2.1	1.1	12	AL		
K4NXWG	32.1	33.3	33.5	32.9	32.9	0.02	2.5	0.6	33.3	0.32	2.2	0.9	12	XX		
L6FDKX	34.4	33.3	34.9	34.5	34.3	1.08	1.8	0.7	34.9	1.82	2.2	1.0	12	LA		
LKDWNM	35.6	31.2	34.4	H 34.9	34.0	0.87	2.2	1.9	34.5	1.48	2.3	1.3	12	LA		
LMVMLX	33.0	33.8	32.6	32.6	33.0	0.06	2.2	0.6	32.9	-0.10	2.2	0.7	12	LZ		
LY8Q9G_AL	33.3	34.2	33.9	No Data	33.8	0.69	2.3	0.5	33.3	0.35	2.2	0.7	11	AL		
MYRHKL	35.5	35.7	*	35.0	No Data	35.4	1.95	*	2.0	0.4	35.1	2.01	*	2.3	1.2	LA



Containerboard Interlaboratory Testing Program

Analysis 224

STFI, 52 Ib Linerboard - 52J1

TAPPI Official Test Method T826

Report #654

March 2024

WebCode	Weekly Means				Monthly Results				Cumulative Results											
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst						
NT28BN	31.7	33.0	31.9	32.7	32.3	-0.47	2.6	0.6	32.0	-0.98	2.4	0.6	12	LU						
NTB6TQ	32.3	33.6	33.9	L	32.9	33.2	0.21	2.1	0.7	33.0	-0.03	2.2	1.0	12	LA					
PLTW6U	34.9	33.1	31.8	31.9	32.9	-0.01	2.4	1.4	31.8	-1.13	2.3	2.5	12	LZ						
PLTW6U_AL	45.3	XL	41.5	XL	40.7	XL	42.4	XL	42.5	7.50	X	0.0	2.0	XX						
PTNY86	34.4	29.3	*	29.4	*	30.2	30.8	-1.65	2.2	2.4	33.1	0.13	2.3	2.2	12	LH				
Q7ATZB	34.3	34.4	34.5	34.8	34.5	1.23	1.9	0.2	34.8	1.73	2.0	1.2	12	LH						
T2DNKB	30.6	L	32.4	L	31.4	L	31.0	31.4	-1.23	2.8	0.8	32.5	-0.51	3.4	2.5	12	LH			
TMDD2J	35.9	35.8	*	36.2	*	37.0	*	36.2	2.60	*	2.3	0.5	34.6	1.57	2.2	1.7	12	LA		
TUUHLJ	30.7	30.3	29.9	*	30.5	30.4	-2.02	*	1.8	0.3	29.5	-3.41	X	1.9	1.1	12	XX			
TWWFWC	34.0	33.3	33.5	H	34.7	33.9	0.74	2.4	0.6	33.0	0.05	2.5	1.1	8	LU					
UQPCJH	34.3	33.0	34.6	34.6	34.1	0.93	2.6	0.8	33.7	0.65	2.6	0.7	12	LZ						
VBUU8P	34.9	L	35.2	L	34.5	L	35.4	L	35.0	1.60	0.9	0.4	34.4	1.38	0.7	0.9	8	LZ		
VWG89G	32.5	33.4	32.4	33.4	32.9	0.01	2.6	0.5	33.5	0.52	2.9	0.9	12	LW						
XTRKQD_AL	32.5	31.5	L	35.0	33.6	L	33.2	0.20	1.8	1.5	33.2	0.16	1.9	1.1	12	XX				
Z8DFQL	37.2	*L	35.8	*	36.9	*	37.0	*	36.7	2.99	X	2.0	0.6	32.9	-0.12	2.0	3.6	H	12	LA
ZFPRJD	34.6	30.4	H	32.0	L	31.9	L	32.2	-0.55	2.3	1.8	31.6	-1.34	1.9	2.8	12	LA			
Consensus (All Labs) Results																				
Wk Mean	33.26	32.80	33.15	33.06	Month Mean				32.92	Grand Mean				32.99						
Avg SDr	2.38	2.27	2.18	2.62	Avg SD				2.41	Avg SD				2.35						
SD btwn Labs	1.53	1.46	1.56	1.71	SD btwn Labs				1.27	SD btwn Labs				1.03						
Labs Incld	47	47	47	46	SD btwn Wks				1.31	SD btwn Wks				1.59						
Labs Excld	3	4	4	3	Labs Incld				47	Labs Incld				47						
Labs not Rcvd	1	0	0	2																

Key to Instrument Codes Reported by Participants

AL	L & W Autoline 400	BK	Buchel Strip Compression Tester BK-155
LA	L&W Autoline (224 Enrollment)	LH	L&W 282
LU	L&W 52 without moisture correction (was 53)	LW	L&W 53 with moisture correction (was 53M)
LY	L&W 152 with moisture correction	LZ	L&W (model not specified)
XX	Instrument make/model not specified by lab		



Containerboard Interlaboratory Testing Program

Analysis 228

Roughness - Stylus Method, 42 lb Linerboard - 42H

TAPPI Official Test Method T575

Report #654
March 2024

WebCode	Monthly Results			Cumulative Results					
	Mean	CPV	SD	Mean	CPV	SD	Months	Months	Inst
4DX7T7	179.3	2.49 *	16.13	148.0	0.59	20.91	4	LS	
4VT8HB	141.9	0.15	11.23	154.6	1.14	18.83	4	EV	
6RZVUP	171.4	1.99 *	18.64	160.2	1.61	18.77	4	EV	
868V82	247.7	6.76 X	31.01 H	226.3	7.12 X	27.38	4	LS	
9WWTLZ_AL	141.9	0.15	14.61	133.6	-0.61	12.10	4	AL	
A39WJ7	123.1	-1.02	15.85	120.6	-1.70	27.46	4	XX	
B39NFZ	145.8	0.40	14.92	137.7	-0.27	6.12	4	LA	
BXW9J9	144.0	0.28	18.04	143.5	0.21	1.12 L	4	LS	
BYTFRZ	151.5	0.75	16.29	148.0	0.59	7.88	4	EV	
DDV6TH	152.8	0.83	11.01	143.5	0.21	8.49	4	LS	
EAW9MN	133.8	-0.36	10.18	135.5	-0.45	1.88 L	4	EV	
GFDN4Q_AL	119.4	-1.25	15.75	149.6	0.73	21.29	4	AL	
HRKTRX_AL	119.6	-1.24	14.36	121.9	-1.59	7.20	3	AL	
JRXPW3	130.3	-0.57	19.05	149.0	0.67	12.80	4	LA	
JWH7EV_AL	115.0	-1.53	13.66	117.1	-1.99 *	11.64	4	AL	
L6FDKX	153.3	0.86	21.42	150.5	0.80	8.00	4	XX	
LKDWNM	150.5	0.69	22.66	145.7	0.40	4.85	3	EV	
LMVMLX	131.1	-0.52	20.91	135.3	-0.47	4.34	4	LS	
LY8Q9G_AL	130.6	-0.56	21.87	143.0	0.17	20.43	4	AL	
MYRHKL	135.9	-0.23	11.21	140.7	-0.02	6.40	4	LA	
NT28BN	145.7	0.39	4.73 L	145.7	0.40	1.50 L	4	EV	
NTB6TQ	140.9	0.09	20.75	146.4	0.45	9.36	4	LA	
PLTW6U	0.3	-8.69 X	0.02 L	44.1	-8.08 X	87.57 H	4	LA	
PLTW6U_AL	127.6	-0.74	22.36	161.3	1.70	28.87 H	4	AL	
TMDD2J	154.0	0.91	28.74 H	143.9	0.25	22.55	4	LA	
UQPCJH	122.4	-1.07	13.17	122.9	-1.51	2.44	4	LS	
VWG89G	125.1	-0.90	12.99	125.2	-1.31	5.26	4	XX	
Consensus (All Labs) Results									
Month Mean	139.47			Grand Mean	140.93				
Avg SD	17.18			Avg SD Months	14.22				
SD btwn Labs	16.01			SD btwn Labs	11.98				
Labs Incl	25			Labs Incl	25				



Containerboard Interlaboratory Testing Program

Analysis 228

Roughness - Stylus Method, 42 lb Linerboard - 42H

TAPPI Official Test Method T575

Report #654

March 2024

Key to Instrument Codes Reported by Participants

AL	L & W Autoline 400	EV	Emveco Microgage Model 210-R
LA	L&W Autoline (228 Enrollment)	LS	L&W 263
XX	Instrument make/model not specified by lab		



Containerboard Interlaboratory Testing Program

Analysis 229

Roughness - Sheffield Method, 42 lb Linerboard - 42H3

TAPPI Official Test Method T538

Report #654

March 2024

WebCode	Monthly Results			Cumulative Results					
	Mean	CPV	SD	Mean	CPV	SD	Months	Months	Inst
3XJALD	370.4	0.16	7.41	370.4	-0.05	0.95	3	3	PP
4DX7T7_AL	369.4	0.01	17.73	367.7	-0.50	9.81	4	4	AL
4GMEMR	344.1	-3.88	5.72	343.2	-4.72	5.72	4	4	LA
6KLPHR_AL	378.6	1.42	5.34	380.6	1.71	6.00	3	3	XX
7K3NQA	373.8	0.69	4.13	374.2	0.62	1.14	4	4	XX
8VF6X7	357.0	-1.90	*	364.7	-1.03	5.87	4	4	TS
A39WJ7_AL	369.6	0.04	9.99	367.7	-0.51	2.01	4	4	AL
ERJ2XU_AL	373.1	0.58	8.08	371.4	0.14	1.15	4	4	AL
HRKTRX_AL	361.7	-1.17	6.40	361.6	-1.55	4.85	3	3	AL
LMVMLX	377.4	1.23	8.49	377.4	1.16	2.29	4	4	XX
LY8Q9G_AL	362.9	-0.99	4.98	362.7	-1.37	3.51	4	4	AL
PLTW6U_AL	363.7	-0.86	9.44	369.3	-0.23	4.46	4	4	AL
XTRKQD_AL	368.2	-0.17	8.23	373.8	0.55	4.93	4	4	AL
ZFPRJD	375.5	0.95	10.18	376.8	1.06	5.91	4	4	XX
Consensus (All Labs) Results									
Month Mean	369.33			Grand Mean	370.64				
Avg SD	8.97			Avg SD Months	4.76				
SD btwn Labs	6.51			SD btwn Labs	5.81				
Labs Incl'd	13			Labs Incl'd	13				

Key to Instrument Codes Reported by Participants

AL L & W Autoline 400

PP Technidyne Profile/Plus

XX Instrument make/model not specified by lab

LA L & W Autoline (229 Enrollment)

TS TMI Monitor/Smoothness



Containerboard Interlaboratory Testing Program

Analysis 231

Internal Bond, 42 lb Linerboard - 42H

TAPPI Official Test Method T569

Report #654

March 2024

WebCode	Monthly Results			Cumulative Results								
	Mean	CPV	SD	Mean	CPV	SD	Months	Months	Inst			
3XJALD	146.6	0.85	6.35	146.9	1.05	1.42	L	3	HY			
48MN7Q	109.8	-1.47	6.38	112.3	-1.31	2.14		4	TM			
4DX7T7	115.9	-1.09	2.16	111.9	-1.33	7.25		4	TM			
4VT8HB	150.0	1.07	8.54	134.1	0.18	26.16	H	4	HZ			
6KLPHR	157.4	1.54	8.79	159.2	1.89	1.80		3	HY			
6RZVUP	106.8	-1.66	4.66	111.9	-1.33	4.91		3	TM			
7K3NQA	146.0	0.81	6.56	147.6	1.09	1.60		4	HY			
8PYZD7	147.0	0.88	18.64	H	125.0	-0.44	19.10	H	3	TM		
A39WJ7	123.4	-0.61	2.70	123.7	-0.53	4.73		4	TM			
B39NFZ	138.8	0.36	9.98	154.6	1.57	11.84		4	HY			
BCTMJ3	132.8	-0.02	4.55	134.9	0.23	2.90		4	HZ			
DDV6TH	142.6	0.60	8.02	141.4	0.68	2.57		4	HY			
EAW9MN	142.4	0.59	5.86	138.0	0.44	4.78		4	TM			
ERJ2XU	123.3	-0.62	6.77	125.0	-0.44	2.38		4	TM			
JWH7EV	135.2	0.13	13.29	118.4	-0.89	11.35		4	TM			
LKDWNM	126.8	-0.40	5.63	122.9	-0.58	2.90		4	TM			
LY8Q9G	153.6	1.30	20.95	H	142.2	0.73	14.88		4	TM		
NT28BN	129.4	-0.23	4.62	129.6	-0.13	1.24	L	4	TM			
T2DNKB	129.0	-0.26	4.69	132.0	0.04	4.24		2	HY			
XTRKQD	138.7	0.36	4.72	142.5	0.75	2.64		4	LZ			
ZFPRJD	99.4	-2.13	*	5.27				106.9	-1.67	10.15	4	SC
Consensus (All Labs) Results												
Month Mean	133.09			Grand Mean	131.46							
Avg SD	8.89			Avg SD Months	9.34							
SD btwn Labs	15.83			SD btwn Labs	14.71							
Labs Incl'd	21			Labs Incl'd	21							

Consensus By Method

Test Method	Group Mean	SD btwn Group	Difference from Grand Mean	Labs Included
Scott Bond Type	131.10	17.29	1.99	16
Modified Scott Bond Mechanics	141.16	4.16	8.07	3



Containerboard Interlaboratory Testing Program

Analysis 231

Internal Bond, 42 lb Linerboard - 42H

TAPPI Official Test Method T569

Report #654

March 2024

Key to Instrument Codes Reported by Participants

HY	Huygen Digitized Scott Internal Bond Tester	HZ	Huygen Internal Bond Tester with AccuPress
LZ	L&W (model not specified)	SC	Scott Internal Bond Tester (Manual)
TM	TMI Monitor/Internal Bond Tester		



Containerboard Interlaboratory Testing Program

Analysis 234

COF Inclined Plane (Slide Angle), 42 lb Linerboard - 42H

TAPPI Official Test Method T815

Report #654

March 2024

WebCode	Monthly Results			Cumulative Results				
	Mean	CPV	SD	Mean	CPV	SD	Months	Months
3XJALD	29.6	1.02	2.07	30.2	1.08	0.87	3	
48MN7Q	27.8	0.37	3.27	29.5	0.81	2.34	4	
4DX7T7	23.2	-1.29	1.48	24.1	-1.16	0.93	4	
4VT8HB	25.1	-0.60	3.51	28.5	0.45	7.85	H	4
6KLPHR	28.4	0.59	2.30	29.6	0.86	2.25		3
6MHW4	25.8	-0.35	1.92	26.0	-0.48	0.19	L	4
6RZVUP	30.8	1.46	3.11	31.9	1.71	1.79		3
7K3NQA	24.6	-0.80	0.63	L	25.4	-0.67	1.21	4
868V82	28.4	0.59	1.34	29.1	0.68	0.70		4
9WWTLZ	24.8	-0.71	2.17	21.9	-1.96	*	1.97	4
A39WJ7	22.6	-1.51	1.95	24.8	-0.90	1.68		4
ANFVUY	26.6	-0.06	2.51	25.8	-0.55	2.12		4
B39NFZ	26.6	-0.06	3.97	25.4	-0.70	0.91		4
BXW9J9	26.8	0.01	0.84	27.2	-0.04	0.34	L	4
BYTFRZ	29.8	1.09	3.37	29.7	0.88	1.18		4
DDV6TH	28.8	0.73	1.30	28.5	0.46	0.35	L	4
E8QNW3	30.7	1.42	6.57	H	28.7	0.51	2.04	
EA9WMN	29.7	1.07	1.56	28.1	0.31	1.81		4
GFDN4Q	22.8	-1.45	1.71	24.1	-1.14	1.47		4
HRKTRX	26.3	-0.17	4.15	29.9	0.98	3.19		3
JWH7EV	28.9	0.78	3.47	30.2	1.10	1.55		4
LMVMLX	31.8	1.82	1.44	31.4	1.50	3.51		4
LY8Q9G	28.3	0.57	3.37	29.7	0.91	1.17		4
NT28BN	27.2	0.16	3.49	26.2	-0.41	3.74		4
T2DNKB	26.8	0.01	1.92	26.8	-0.19	1.48		3
UQPCJH	21.0	-2.09	*	2.00	21.7	-2.06	*	0.55
VWG89G	25.4	-0.50	2.19		27.9	0.24	2.02	
X6FFDJ	21.7	-1.83	5.17		26.5	-0.30	3.63	
XTRKQD	25.8	-0.35	1.35		26.6	-0.23	1.58	
ZFPRJD	27.0	0.08	1.22		22.7	-1.69	2.93	

Consensus (All Labs) Results			
Month Mean	26.77	Grand Mean	27.26
Avg SD	2.83	Avg SD Months	2.40
SD btwn Labs	2.76	SD btwn Labs	2.73
Labs Incl'd	30	Labs Incl'd	30



Containerboard Interlaboratory Testing Program
Analysis 234
COF Inclined Plane (Slide Angle), 42 lb Linerboard - 42H
TAPPI Official Test Method T815

Report #654
March 2024

Key to Instrument Codes Reported by Participants

ZZ Instruments No Longer Tracked



Containerboard Interlaboratory Testing Program

Analysis 237

Air Resistance, 42 lb Linerboard - 42H

TAPPI Official Test Method T460

Report #654

March 2024

WebCode	Monthly Results			Cumulative Results					
	Mean	CPV	SD	Mean	CPV	SD	Months	Months	Inst
3XJALD	31.4	-0.99	3.20	34.1	1.14	2.38	H	3	TP
48MN7Q_AL	30.9	-1.30	1.86	33.1	0.22	1.46		4	AL
4DX7T7_AL	31.6	-0.81	3.75	32.5	-0.34	0.96		4	AL
4GMEMR	36.2	2.55 *	4.02	34.1	1.13	1.38		4	LA
4VT8HB	32.5	-0.16	2.57	32.1	-0.68	0.53		4	LP
6KLPHR	32.9	0.15	2.84	32.7	-0.17	1.07		3	TP
6KLPHR_AL	32.2	-0.40	1.70	31.9	-0.84	0.26		3	XX
6MHW4	31.5	-0.88	3.25	32.8	-0.09	1.03		4	TD
6RZVUP_AL	32.1	-0.47	2.40	32.2	-0.63	0.30		4	AL
7K3NQA	30.9	-1.30	2.94	33.4	0.54	1.79		4	TP
7TFEEL	33.4	0.51	1.70	34.0	1.07	0.85		4	LP
868V82	24.8	-5.84 X	2.53	25.4	-6.75 X	0.97		4	XX
9WWTLZ_AL	31.2	-1.12	2.04	30.5	-2.16 *	0.62		4	AL
A39WJ7	32.8	0.10	1.97	33.5	0.55	0.99		4	LP
A39WJ7_AL	34.0	0.93	2.13	34.5	1.45	0.46		4	AL
B39NFZ	33.6	0.66	2.17	33.4	0.48	0.63		4	LP
BXW9J9	32.3	-0.30	2.00	32.4	-0.40	0.37		4	LP
CHCDGH_AL	32.8	0.05	1.93	33.6	0.69	0.73		4	AL
DDV6TH	32.1	-0.48	2.37	32.8	-0.03	0.92		4	LP
EAW9MN	32.0	-0.51	3.27	32.7	-0.15	0.96		4	LP
ERJ2XU_AL	32.8	0.08	2.44	33.4	0.46	0.81		4	AL
GFDN4Q_AL	38.6	4.33 X	1.73	36.5	3.33 X	1.57		4	AL
HRKTRX_AL	32.3	-0.33	2.86	31.8	-0.96	0.44		3	AL
JRXPW3	28.0	-3.49 X	1.60	30.5	-2.09 *	1.75		4	LA
JWH7EV_AL	31.5	-0.88	2.04	31.7	-1.04	0.82		4	AL
L6FDKX	34.1	1.07	2.78	32.9	0.01	1.02		4	XX
LMVMLX	32.4	-0.22	3.17	32.8	-0.01	1.08		4	GA
LY8Q9G_AL	31.4	-0.99	3.34	31.8	-0.99	0.52		4	AL
MYRHKL	32.9	0.14	2.31	32.9	0.06	1.20		4	LA
NT28BN	32.4	-0.22	3.10	34.3	1.29	1.54		4	GA
NTB6TQ	34.4	1.22	1.14 L	33.1	0.20	1.39		4	LA
PLTW6U_AL	33.3	0.47	2.97	32.2	-0.62	1.03		4	XX
PTNY86	33.6	0.66	2.99	34.1	1.13	1.19		4	XX
TMDD2J	35.0	1.67	2.54	33.5	0.57	1.84		4	LA
UQPCJH	30.7	-1.47	3.82	25.1	-6.96 X	3.79 H		4	TD
VWG89G	34.5	1.34	2.39	34.5	1.50	0.28		4	LP
XJGJ6C	30.9	-1.35	1.79	30.1	-2.48 *	1.24		4	LP
XTRKQD_AL	35.0	1.70	1.10 L	34.5	1.53	0.95		4	AL
YJT8FV	31.7	-0.74	2.06	32.4	-0.45	0.92		2	XX



Containerboard Interlaboratory Testing Program

Analysis 237

Air Resistance, 42 lb Linerboard - 42H

TAPPI Official Test Method T460

Report #654

March 2024

WebCode	Monthly Results			Cumulative Results					Inst
	Mean	CPV	SD	Mean	CPV	SD	Months	Months	
Z8DFQL	34.9	1.62	2.94	33.0	0.11	1.50	4	4	LP
Consensus (All Labs) Results									
Month Mean	32.71			Grand Mean	32.85				
Avg SD	2.63			Avg SD Months	1.11				
SD btwn Labs	1.35			SD btwn Labs	1.11				
Labs Incl'd	37			Labs Incl'd	37				

Key to Instrument Codes Reported by Participants

AL	L & W Autoline 400	GA	Gurley Precision #4340 Automatic Densometer
LA	L&W Autoline (237 Enrollment)	LP	L&W Air Permeance Tester SE 166
TD	TMI Gurley Densometer	TP	Technidyne Profile/ plus Roughness & Porosity
XX	Instrument make/model not specified by lab		



Containerboard Interlaboratory Testing Program
Analysis 240

Report #654
March 2024

Flat Crush Strength (CMT), 26 lb Corrugating Medium - CM13
TAPPI Official Test Method T809

WebCode	Weekly Means				Monthly Results					Cumulative Results					
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst	
2RFNLB	60.8	60.3	59.4	57.3	59.5	0.70	3.5	1.6	59.3	0.81	3.4	1.2	16	LD	
3AY969	57.4	55.1	55.2	56.2	56.0	-0.76	3.3	1.1	56.0	-0.86	3.3	1.1	4	LD	
3RRYEZ	66.6 X	67.1 X	68.5 XH	67.7 X	67.5	4.08 X	4.8	0.8	68.1	5.31 X	4.7	2.7	16	TX	
3W983Z	57.7	56.9	57.4	56.2	57.0	-0.31	2.8	0.6	57.2	-0.25	3.0	1.0	16	EM	
48MN7Q	60.4	60.6	No Data	No Data	60.5	1.14	5.2	0.1	59.0	0.68	3.8	1.5	14	LC	
4GMEMR	51.8 *	53.0	53.4	53.7	53.0	-2.02 *	4.8	0.9	53.2	-2.28 *	4.3	1.6	16	LD	
4VT8HB	55.9	57.2	56.3	56.0	56.4	-0.60	4.8	0.6	56.6	-0.57	4.1	1.8	16	LZ	
69WHP4	56.0	57.9	57.7	58.5	57.5	-0.12	4.6	1.0	58.3	0.30	4.4	3.1	16	LD	
6KLPHR	59.1	56.4	57.6	60.7	58.5	0.28	3.2	1.9	57.1	-0.30	3.4	1.9	12	LD	
6MHWT4	54.3	55.0	57.8	54.9	55.5	-0.96	4.1	1.6	56.2	-0.74	4.2	2.1	16	LZ	
7K3NQA	57.8	58.9	56.7	59.2	58.2	0.16	4.2	1.2	59.0	0.66	4.1	2.3	16	LC	
7TFEEL	57.1	56.2	59.2	56.9	57.3	-0.18	4.2	1.3	58.3	0.31	3.6	1.3	16	LD	
8BEUED	57.1	56.4	57.0	55.9	56.6	-0.49	1.9	0.5	56.7	-0.49	2.1	0.5 L	12	TH	
8GVPV8	52.4	51.0 *	54.7	54.2	53.1	-1.98 *	3.9	1.7	53.3	-2.23 *	3.6	1.6	11	TH	
9AXLQH	57.1	59.1	58.6	56.4	57.8	0.01	3.2	1.3	58.1	0.21	3.3	1.4	16	LZ	
9WWTLZ	59.1	58.4 H	54.6	55.1	56.8	-0.41	5.5	2.3	56.7	-0.50	4.0	1.6	16	LZ	
A39WJ7	54.0	54.9	55.9	53.7	54.6	-1.33	4.2	0.9	55.2	-1.23	4.4	1.3	16	LD	
B39NFZ	62.0	58.2	60.0	61.4	60.4	1.10	4.1	1.7	60.0	1.18	3.8	1.4	16	XX	
BCTMJ3	57.3	58.2	57.8	57.7	57.7	-0.01	2.9	0.4	57.5	-0.08	3.0	1.7	13	LD	
BXW9J9	58.0	58.3	57.7	58.9	58.2	0.19	1.9	0.5	58.0	0.18	2.1	0.5 L	16	LD	
BYTFRZ	54.6	55.4	59.5	54.8	56.1	-0.73	3.8	2.3	56.2	-0.76	4.0	3.1	16	EN	
CTYALP	58.8 L	58.9 L	58.6 L	58.6 L	58.7	0.40	1.5	0.1 L	58.5	0.42	0.9	0.2 L	16	LD	
DDV6TH	57.9	59.1	58.2	57.2 L	58.1	0.13	2.0	0.8	57.5	-0.06	2.7	1.6	15	LD	
EA4RXT	57.7	60.1	60.6	60.7	59.8	0.83	4.5	1.4	59.2	0.76	4.3	2.1	16	LD	
EYWAYV	59.5 H	61.6	61.2	62.3	61.2	1.42	4.9	1.2	57.3	-0.19	4.2	3.3	16	LD	
FGPZ9M	60.8 H	63.6 *	58.2 H	56.3 H	59.7	0.83	7.4	3.2 H	61.6	2.00 *	6.1	2.5	15	LD	
G9GZYT	57.2	55.8	59.9	60.0 H	58.2	0.18	4.5	2.1	59.4	0.89	4.3	2.4	16	LD	
GBDC8Q	54.0	58.6	58.1	56.4	56.8	-0.43	3.4	2.1	57.3	-0.20	3.7	2.4	16	LD	
GEZYZE	63.1 *	64.3 *	64.1 *	63.7 *	63.8	2.52 *	2.9	0.6	61.5	1.98 *	3.2	1.9	16	TB	
JRXPW3	53.7	57.3	54.9	55.7	55.4	-1.00	4.7	1.5	56.8	-0.46	4.6	2.3	16	MB	
K4NXWG	59.1	58.1	59.2	58.7	58.8	0.42	2.6	0.5	59.7	1.01	2.7	0.7	16	LD	
KFY9MR	59.5	59.9	61.8	58.9	60.0	0.95	4.3	1.2	60.4	1.41	4.0	3.7	16	LD	
LKDWNM	59.0	59.5 L	58.1	56.8	58.4	0.24	2.7	1.2	58.7	0.52	2.7	1.6	16	LC	
LMVMLX	60.7	61.7	60.8	60.3	60.9	1.30	2.9	0.6	58.5	0.43	4.2	2.8	8	LZ	
LY8Q9G	57.5	59.1	60.7	57.7	58.8	0.41	2.8	1.5	56.7	-0.47	3.7	1.8	16	LD	



Containerboard Interlaboratory Testing Program
Analysis 240

Report #654
March 2024

Flat Crush Strength (CMT), 26 lb Corrugating Medium - CM13
TAPPI Official Test Method T809

WebCode	Weekly Means				Monthly Results					Cumulative Results						
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst		
M28MT9	50.1 *H	48.9 X	49.3 X	37.2 XH	46.4	-4.80 X	7.4	6.1 H	47.1	-5.39 X	6.6	4.3 H	8	TC		
MYRHKL	59.3	56.4	59.4	62.9	59.5	0.73	3.7	2.7	59.1	0.75	4.5	2.5	16	TU		
NT28BN	55.8	55.3	53.9	55.6	55.2	-1.11	3.5	0.9	55.3	-1.22	3.7	1.8	16	LD		
PLTW6U	57.0	59.0	54.5	57.6	57.0	-0.33	4.1	1.9	57.2	-0.22	3.9	2.3	16	LD		
PTNY86	56.6	53.4	56.7	56.3	55.8	-0.85	3.2	1.6	56.4	-0.63	3.1	1.6	16	LD		
Q7ATZB	57.8	54.2	52.2 *	53.9	54.5	-1.36	3.2	2.4	54.8	-1.48	3.1	1.5	16	LD		
TUUHLJ	55.6 L	54.6 L	54.8 L	54.7 L	54.9	-1.20	0.8	0.5	55.6	-1.04	1.5	1.4	16	TU		
UBWLL2	63.1 *	62.1	61.6	62.9	62.4	1.95 *	2.7	0.7	60.8	1.60	3.0	1.7	16	LC		
VBUU8P	55.1 L	54.0 L	58.7 L	55.9	55.9	-0.78	1.4	2.0	55.9	-0.89	1.4	2.0	4	XX		
VWG89G	59.1	62.8	59.0	59.5	60.1	0.98	3.7	1.8	60.1	1.24	3.7	1.8	16	LD		
WKWRT8	58.9	55.0	57.1	60.8	58.0	0.07	4.1	2.5	64.4	3.42 X	4.2	4.4 H	16	LD		
X6FFDJ	61.6	58.6	63.4 *	63.6 *	61.8	1.68	3.7	2.3	59.5	0.95	3.5	4.4 H	16	LD		
XJG6C	59.0	58.3	57.6	60.6	58.8	0.45	3.7	1.3	58.9	0.61	3.2	1.9	16	LD		
XTRKQD	54.7	54.5 L	50.9 *	56.2	54.1	-1.55	2.3	2.2	54.3	-1.69	3.2	1.6	16	LD		
ZJ7Y8C	56.8 L	56.5 L	56.1	56.1	56.4	-0.58	1.5	0.3	57.5	-0.09	1.7	1.0	12	MB		
Consensus (All Labs) Results																
Wk Mean	57.53	57.70	57.80	57.82	Month Mean		57.78		Grand Mean		57.66					
Avg SDr	3.66	3.94	3.79	3.49	Avg SD		3.72		Avg SD		3.59					
SD btwn Labs	2.78	2.86	2.73	2.73	SD btwn Labs		2.38		SD btwn Labs		1.96					
Labs Incld	49	48	47	47	SD btwn Wks		1.52		SD btwn Wks		2.00					
Labs Excld	1	2	2	2	Labs Incld		48		Labs Incld		47					
Labs not Rcvd	0	0	1	1												

Key to Instrument Codes Reported by Participants

EM	Emerson 1200 Series	EN	Emerson 2200 Series
LC	L&W Crush Tester 48	LD	L&W Crush Tester 248
LZ	L&W Crush Tester (model not specified)	MB	Messmer Buchel K440
TB	TMI Monitor/Compression Tester, 17-70	TC	TMI Monitor/Compression Tester, 17-37
TH	TMI Compression Tester, Model 17-76	TU	TMI Universal Crush Tester (TMI K440)
TX	TMI Crush Tester (model not specified)	XX	Instrument make/model not specified by lab



Containerboard Interlaboratory Testing Program
Analysis 250

Report #654
March 2024

Fluted Edge Crush Strength (CFC), 26 lb Corrugating Medium - CM13
TAPPI Official Test Method T843

WebCode	Weekly Means				Monthly Results				Cumulative Results					
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst
48MN7Q	71.5	69.7	No Data	No Data	70.6	1.15	4.7	1.3	70.7	1.29	4.4	2.4	14	LC
4GMEMR	66.0 H	69.8 H	78.4 *H	68.4 H	70.6	1.16	10.7	5.4 H	59.4	-1.81	8.7	7.2 H	16	LD
69WHP4	65.4	68.2	66.1	67.5	66.8	0.04	3.9	1.2	66.1	0.04	3.5	1.9	16	LD
6KLPHR	67.8	66.9	66.1	67.4	67.0	0.10	4.1	0.7	69.0	0.82	3.9	1.8	12	LD
7K3NQA	67.6	68.3	69.5 L	68.5	68.5	0.53	2.9	0.8	69.0	0.83	3.0	1.5	16	LC
7TFFEL	61.5	66.7	64.6	65.4	64.6	-0.62	3.5	2.2	65.0	-0.27	3.3	1.5	16	LD
9AXLQH	67.0	65.1	68.2	66.9	66.8	0.04	3.0	1.3	66.0	0.01	3.5	1.4	16	LZ
9WWTLZ	65.5	57.0 *	63.2	63.4	62.3	-1.30	3.4	3.7	62.4	-0.98	4.2	2.8	16	LZ
A39WJ7	58.7 *	57.9 *	59.2	57.7 X	58.4	-2.44 *	3.9	0.7	57.3	-2.36 *	5.6	1.6	16	LD
B39NFZ	69.7	69.5	68.5	69.3	69.3	0.76	2.6	0.5	68.6	0.73	3.0	1.1	16	XX
BXW9J9	67.1 L	66.8	67.9	67.1	67.2	0.16	2.0	0.5	67.2	0.34	2.1	0.6 L	16	LD
LY8Q9G	65.7	67.7	67.8	67.0	67.1	0.11	3.5	1.0	67.1	0.30	3.5	1.7	16	LD
PLTW6U	65.3	65.9	65.4	63.4	65.0	-0.49	4.6	1.1	64.8	-0.32	3.9	2.0	16	XX
VBUU8P	61.0	62.5	59.2 L	62.3 *	61.3	-1.59	1.9	1.5	61.3	-1.29	1.9	1.5	4	XX
VWG89G	69.2	69.9	67.9	67.4	68.6	0.56	3.5	1.2	67.5	0.41	3.7	1.7	16	LD
XJGJ6C	70.2	71.4	72.1 L	69.5	70.8	1.21	3.6	1.2	70.2	1.15	4.1	2.0	16	LD
XTRKQD	69.2	69.7 L	73.2	71.0	70.8	1.20	2.9	1.8	69.7	1.03	3.1	2.6	16	LD
YJT8FV	66.4	65.4 L	66.2 L	69.6 L	66.9	0.06	1.5	1.9	65.8	-0.05	1.7	1.7	8	LZ
ZJ7Y8C	64.7 L	64.3 L	64.4 L	64.8	64.6	-0.63	1.7	0.3 L	66.4	0.11	1.7	1.4	12	MB
Consensus (All Labs) Results														
Wk Mean	66.29	66.45	67.10	66.99	Month Mean	66.68	Grand Mean		65.96					
Avg SDr	3.97	4.00	4.36	3.75	Avg SD	4.04	Avg SD		3.94					
SD btwn Labs	3.24	3.89	4.59	2.42	SD btwn Labs	3.40	SD btwn Labs		3.66					
Labs Incld	19	19	18	17	SD btwn Wks	1.89	SD btwn Wks		2.42					
Labs Excld	0	0	0	1	Labs Incld	19	Labs Incld		19					
Labs not Rcvd	0	0	1	1										

Key to Instrument Codes Reported by Participants

LC L&W Crush Tester 48

LZ L&W Crush Tester (model not specified)

XX Instrument make/model not specified by lab

LD L&W Crush Tester 248

MB Messmer Buchel K440



Containerboard Interlaboratory Testing Program

Analysis 255

Ring Crush (RCT), 26 lb Corrugating Medium - CM13

TAPPI Official Test Method T822

Report #654

March 2024

WebCode	Weekly Means				Monthly Results				Cumulative Results					
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst
2RFNLB	42.6	41.5	43.7	42.2	42.5	0.17	3.6	0.9	42.7	0.21	3.1	1.0	16	LD
3AY969	44.8	44.7	44.5	44.8	44.7	1.46	2.6	0.1 L	44.3	1.15	3.0	0.9	8	LC
3RRYEZ	45.7	43.9	43.2	40.2	43.2	0.61	3.9	2.3	43.3	0.55	3.4	1.8	16	LZ
64GH7B	43.2	41.6 L	42.9	41.6	42.3	0.06	2.4	0.9	41.3	-0.61	2.7	1.6	16	TH
6KLPHR	40.7	41.8	42.0	42.6	41.8	-0.27	3.3	0.8	44.5	1.28	3.4	2.4	12	LD
7K3NQA	45.4	45.4	42.0	43.6	44.1	1.10	3.4	1.7	42.5	0.12	2.9	2.1	16	LC
7TFFEL	41.2 H	41.1	38.3 *	39.6	40.0	-1.28	3.7	1.4	40.4	-1.15	3.6	1.3	16	LD
8BEUED	32.4 X	33.6 X	35.9 X	38.4	35.0	-4.21 X	3.5	2.6 H	36.0	-3.84 X	2.8	1.7	12	TH
B39NFZ	40.9	40.4	44.3	41.6	41.8	-0.24	2.6	1.7	41.3	-0.60	3.1	1.5	16	XX
BCTMJ3	42.4	42.2	42.8	43.3	42.6	0.25	1.9	0.5	43.6	0.74	2.8	1.3	16	LD
CTYALP	45.0 L	45.0 L	45.3 L	45.3 L	45.2	1.72	0.8	0.2 L	44.7	1.42	0.8	0.4 L	16	LD
DEAQ46	26.0 X	27.4 X	24.6 X	24.1 X	25.5	-9.78 X	2.3	1.5	25.6	-10.06 X	2.0	1.3	8	XX
EA4RXT	44.2	43.4	43.8	46.1 *	44.4	1.27	3.4	1.2	44.1	1.04	3.1	1.2	16	LD
FGPZ9M	41.3	41.0	42.2	41.5	41.5	-0.42	3.7	0.5	42.4	0.04	3.9	1.8	14	LD
G9GZYT	40.8	45.0	44.6	45.9 *H	44.1	1.09	3.7	2.2	44.2	1.12	4.0	2.0	15	LZ
GBDC8Q	40.1 L	44.3	42.2	41.0	41.9	-0.19	2.9	1.8	43.5	0.68	4.8	2.5	16	LD
GEZYZE	40.4	41.5	40.5	41.8	41.0	-0.69	2.1	0.7	39.6	-1.67	2.1	1.0	16	XX
JRXPW3	38.3	36.8 *	40.1	39.7	38.7	-2.05 *	3.7	1.5	40.6	-1.04	4.1	2.8	16	MB
KFY9MR	46.1	43.3	41.4 H	42.0	43.2	0.58	3.8	2.1	43.6	0.75	3.9	2.6	16	EM
LMVMLX	42.1	40.0	41.2	40.4	40.9	-0.76	2.7	0.9	40.5	-1.11	3.2	1.1	16	LD
M28MT9	43.9 H	40.7 H	45.8 H	41.7 H	43.0	0.47	7.0	2.3	42.8	0.25	6.5	1.6	8	TC
PLTW6U	42.7 H	41.6	40.1	41.7	41.5	-0.40	4.2	1.1	41.1	-0.76	4.1	1.9	16	LD
PTNY86	45.2	47.0 *	45.0	44.3	45.4	1.85	2.6	1.2	44.9	1.57	2.6	1.3	16	LD
TUUHLJ	38.8 L	38.7 L	39.1 L	39.1 L	38.9	-1.93 *	0.9	0.2 L	39.4	-1.75	1.1	1.4	16	TU
UBWLL2	41.6	41.9	41.7	42.2	41.8	-0.22	2.2	0.3	40.4	-1.17	2.8	1.1	16	XX
VBUU8P	43.9 L	42.7	43.2 L	43.0	43.2	0.58	1.7	0.5	44.1	1.08	1.3	1.1	8	MZ
WKWRT8	42.6	42.8 L	38.2 *	41.1	41.2	-0.61	2.1	2.1	40.4	-1.20	2.5	1.4	16	LD
X6FFDJ	40.1	43.1	41.2	39.2	40.9	-0.79	3.6	1.7	40.9	-0.88	3.6	1.7	4	XX
XJGJ6C	38.4	39.7 H	39.3	41.1	39.6	-1.53	4.2	1.1	41.1	-0.73	3.1	1.4	16	LD
XTRKQD	44.2	42.4	42.0	43.8	43.1	0.54	2.4	1.1	43.9	0.95	3.1	1.1	16	LD
Z8DFQL	41.7	42.6	43.3	42.5 L	42.5	0.18	1.9	0.6	42.5	0.12	2.7	1.2	16	LD
ZJ7Y8C	41.1	41.4	41.4	41.3	41.3	-0.53	1.7	0.2 L	41.6	-0.44	1.7	0.5	12	MB



Containerboard Interlaboratory Testing Program

Analysis 255

Ring Crush (RCT), 26 lb Corrugating Medium - CM13

TAPPI Official Test Method T822


Report #654

March 2024

Consensus (All Labs) Results								
Wk Mean	42.30	42.25	42.16	42.01	Month Mean	42.21	Grand Mean	42.34
Avg SDr	3.55	3.06	2.85	3.20	Avg SD	3.18	Avg SD	3.29
SD btwn Labs	2.19	2.12	2.04	1.96	SD btwn Labs	1.70	SD btwn Labs	1.66
Labs Incld	30	30	30	31	SD btwn Wks	1.31	SD btwn Wks	1.60
Labs Excld	2	2	2	1	Labs Incld	30	Labs Incld	30
Labs not Rcvd	0	0	0	0				

Key to Instrument Codes Reported by Participants

EM	Emerson 1200 Series	LC	L&W Crush Tester 48
LD	L&W Crush Tester 248	LZ	L&W Crush Tester (model not specified)
MB	Messmer Buchel K440	MZ	Messmer Buchel (model not specified)
TC	TMI Monitor/Compression Tester, 17-37	TH	TMI Compression Tester, Model 17-76
TU	TMI Universal Crush Tester (TMI K440)	XX	Instrument make/model not specified by lab



Containerboard Interlaboratory Testing Program

Analysis 261

STFI, 26 lb Corrugating Medium - CM13

TAPPI Official Test Method T826

Report #654

March 2024

WebCode	Weekly Means				Monthly Results				Cumulative Results					
	Week 1	Week 2	Week 3	Week 4	Mean	CPV	SD	SD Wks	Mean	CPV	SD	SD Wks	Wks	Inst
3AY969	13.9	13.9	14.4	13.5	13.9	0.51	1.0	0.4	13.8	0.11	1.1	0.4	8	LH
3W983Z	13.1	13.4	13.5	13.4	13.4	-0.72	1.0	0.2	13.1	-1.19	1.0	0.4	16	LH
4DX7T7	14.0	13.5	14.1	14.4	14.0	0.64	1.1	0.4	14.0	0.54	1.1	0.4	16	LA
7K3NQA	12.9	13.5	13.6	13.5	13.4	-0.61	1.1	0.3	13.5	-0.33	1.0	0.3	16	LU
A39WJ7	12.5 * H	12.9	13.1 H	12.5 H	12.8	-1.93 *	1.5	0.3	12.9	-1.57	1.3	0.3	16	LB
BCTMJ3	14.5	13.4	14.1	13.2	13.8	0.24	1.2	0.6	13.8	0.21	1.2	0.6	4	XX
BXW9J9	13.9	13.6	13.9	13.8	13.8	0.19	1.2	0.2	13.8	0.20	1.1	0.2	16	LA
DDV6TH	13.2	13.3	13.5 L	13.4	13.4	-0.68	0.9	0.1	13.3	-0.92	0.9	0.2	15	LH
E8QNW3	14.3	14.4 H	13.5	13.8	14.0	0.65	1.2	0.4	13.6	-0.20	1.1	0.5	16	TT
EA4RXT	13.8	14.3	14.3	14.2	14.2	1.00	1.1	0.2	13.8	0.27	1.0	0.3	16	XX
G9GZYT	13.3 L	12.4 *L	15.9 X	12.2 *L	13.4	-0.54	0.5	1.7 H	13.3	-0.92	1.1	1.2	16	XX
JRXPW3	14.0	14.3	14.2	14.1	14.1	0.97	0.9	0.1	14.2	0.95	1.2	0.3	16	LA
L6FDKX	14.3	13.9	14.1 L	14.1	14.1	0.88	0.8	0.2	14.5	1.74	1.0	0.6	16	XX
LMVMLX	13.9 H	13.2	13.8	13.5	13.6	-0.20	1.3	0.3	13.4	-0.56	1.1	0.4	16	LZ
LY8Q9G	13.8	13.7	13.8	14.2	13.9	0.40	1.1	0.2	13.9	0.44	1.2	0.4	16	LA
M28MT9	12.6	13.4	13.3	12.6	13.0	-1.50	1.0	0.5	13.2	-1.10	1.1	0.6	8	TS
MYRHKL	14.2	14.2	14.7	No DATA	14.4	1.44	1.2	0.3	14.7	2.00 *	1.2	0.5	15	LA
NT28BN	13.4	12.9	13.1	12.8	13.1	-1.33	1.4	0.2	13.4	-0.58	1.2	0.3	16	LU
NTB6TQ	14.1 H	13.0	13.2	13.1	13.4	-0.69	1.4	0.5	13.2	-1.03	1.3	0.5	16	LA
PLTW6U	14.9	14.6	12.9	13.9	14.1	0.78	1.0	0.9	13.4	-0.54	1.1	0.8	16	LZ
T6CYEQ	13.5	14.4	14.1	13.3	13.8	0.29	1.2	0.5	14.0	0.57	1.2	0.4	16	TX
TUUHLJ	13.5 H	13.9 H	14.2 H	13.8 H	13.9	0.34	1.9	0.3	12.9	-1.66	1.4	0.8	12	XX
TWWFWC	14.5	13.6	13.3	13.6	13.8	0.15	1.3	0.5	13.7	0.06	1.1	0.5	12	LU
VBUU8P	14.9 L	14.5 L	14.5 L	14.4 L	14.6	1.88	0.3	0.2	14.4	1.46	0.3	0.3	8	LZ
X6FFDJ	15.0 L	21.3 XL	13.8 L	14.0 L	16.0	4.95 X	0.0	3.6 H	14.5	1.69	1.1	1.9 H	16	LH
XTRKQD	14.1	13.8	13.4	13.4	13.7	-0.04	0.9	0.3	13.6	-0.23	0.8	0.4	16	LA
Z8DFQL	13.0 L	12.5 L	12.7 *L	12.5 L	12.7	-2.15 *	0.5	0.2	14.0	0.59	1.0	1.0	16	LH
Consensus (All Labs) Results														
Wk Mean	13.82	13.64	13.73	13.51	Month Mean				13.69	Grand Mean				13.70
Avg SDr	1.07	1.08	1.21	1.13	Avg SD				1.12	Avg SD				1.10
SD btwn Labs	0.67	0.61	0.52	0.61	SD btwn Labs				0.47	SD btwn Labs				0.48
Labs Incld	27	26	26	26	SD btwn Wks				0.50	SD btwn Wks				0.64
Labs Excld	0	1	1	0	Labs Incld				26	Labs Incld				27
Labs not Rcvd	0	0	0	1										



Containerboard Interlaboratory Testing Program

Analysis 261

STFI, 26 lb Corrugating Medium - CM13

TAPPI Official Test Method T826

Report #654

March 2024

Key to Instrument Codes Reported by Participants

LA	L&W Autoline	LB	L&W Model 152
LH	L&W 282	LU	L&W 52 without moisture correction (was 53)
LZ	L&W (model not specified)	TS	TMI Monitor/STFI Compression Tester, 17-33
TT	TMI Short Span Compression, 17-34 (MB K455)	TX	TMI (model not specified)
XX	Instrument make/model not specified by lab		

End of Report