

Rubber Interlaboratory Testing Program

Summary Report #213- 3rd Qtr 2022

[About the Rubber Program](#), [About CTS](#)

[Key for Web Summary Report](#)

Analysis	Analysis Name	Analysis	Analysis Name
605	Tensile Strength: Precured Rubber Samples	674	ODR Vulcanization Charac.: Maximum Torque
606	Ultimate Elongation: Precured Rubber Samples	684	MDR Vulcanization Charac.: Cure Time 10%
607	Stress at 300% Elongation: Precured Samples	685	MDR Vulcanization Charac.: Scorch Time, Ts1
608	Stress at 100% Elongation: Precured Samples	686	MDR Vulcanization Charac.: Cure Time 50%
620	Hardness (Type A): Precured Rubber Samples	687	MDR Vulcanization Charac.: Cure Time 90%
621	Density: Precured Rubber Samples @ 25C	688	MDR Vulcanization Charac.: Minimum Torque
625	Hardness (Shore D/Type D)	689	MDR Vulcanization Charac.: Maximum Torque
630	Tensile Strength: Participant-Cured Rubber	690	RPA Rheological Properties: Part A - G' at 20Hz
631	Ultimate Elongation: Participant-Cured Samples	691	RPA Rheological Properties: Part A - G" at 20Hz
632	Tensile Stress at 300% Elongation: Lab-Cured	695	RPA Rheological Properties: Part B - G' at 1.0Hz
633	Tensile Stress at 100% Elongation: Lab-Cured	696	RPA Rheological Properties: Part B - G" at 1.0Hz
635	Compression Set		
640	O-Ring Tensile Strength at Break		
641	O-Ring Ultimate Elongation		
642	O-Ring Stress at 100% Elongation		
647	O-Ring Hardness (Shore A/Type A)		
648	O-Ring Hardness (Shore M)		
649	O-Ring Density		
650	O-Ring Compression Set		
660	Mooney Viscosity (4-minute readings)		
661	Mooney Viscosity (8-minute butyl readings)		
662	Mooney Stress Relaxation: i80		
663	Mooney Stress Relaxation: X30		
664	Mooney Stress Relaxation: Area under curve		
669	ODR Vulcanization Charac.: Cure Time 10%		
670	ODR Vulcanization Charac.: Scorch Time, Ts1		
671	ODR Vulcanization Charac.: Cure Time 50%		
672	ODR Vulcanization Charac.: Cure Time 90%		
673	ODR Vulcanization Charac.: Minimum Torque		

ABOUT THE PROGRAM

The Collaborative Reference Program for RUBBER, which was initiated in 1969, is operated and maintained by Collaborative Testing Services, Inc. (CTS), with technical guidance provided by the Rubber Division of the American Chemical Society. The program allows laboratories to compare periodically the level and uniformity of their testing with that of other participating laboratories. It also provides a realistic assessment of the state of rubber testing proficiency.

For each test there are summary statistics and a graphical representation of the data. Also shown are notes concerning specific laboratory results, as well as significant findings related to instrument types or other testing variations. Please refer to the section KEY TO TABLES AND GRAPHS for an explanation of terms and guidelines to interpreting the results.

ABOUT CTS

Founded in 1971, CTS is a privately-owned company that specializes in interlaboratory tests for a wide variety of industrial sectors, including rubber, plastics, fasteners and metals, containerboard, paper and color, as well as proficiency tests for forensic laboratories. All of the tests are designed to assist organizations in achieving and maintaining quality control objectives. Labs from the U.S., as well as more than 80 countries, currently participate in CTS programs.

If there are any questions on the report or testing program, please contact:

**Collaborative Testing Services, Inc.
21331 Gentry Drive
Sterling, Virginia 20166 USA**

+1-571-434-1925
FAX #: +1-571-434-1937
rubber@cts-interlab.com

Office Hours: 8:00 a.m. - 4:30 p.m. ET

Key for Web Summary Report (Page 1 of 2)

WebCode	Assigned laboratory identification number (temporary) used to ensure lab confidentiality while permitting a lab to locate its data in the Rubber Report published on the CTS Web site. The WebCode for each analysis can be found in the Performance Analysis Report mailed to each participant.
Lab Mean	Tensile & Hardness: the average of the median values obtained for each sample. All other tests: the average of the test results obtained by the participant.
Grand Mean	The average of the LAB MEANS for all included participants. Laboratories flagged with an X or an M (see DATA FLAG column) are excluded from the GRAND MEAN.
Difference from Grand Mean	The difference of the LAB MEAN from the GRAND MEAN.
Between-Lab Standard Deviation	An indication of the precision of measurement between the laboratories. The greater the spread of the LAB MEANS about the GRAND MEAN, the larger the BETWEEN-LAB STANDARD DEVIATION (and vice versa).
Comparative Performance Value	An indication of how well a laboratory's results agree with the other participants. The CPV is a ratio indicating the number of standard deviations from the GRAND MEAN. The closer a laboratory's COMPARATIVE PERFORMANCE VALUE is to zero, the more consistent its results are with the other participants' data (and vice versa). The critical value for each CPV will vary depending on the number of labs participating in a test.
Inst Code	If instruments are tracked in a test, a code indicating the manufacturer of the instrument used to perform the test (see separate INSTRUMENT CODE LIST for each test section).
Data Flag	DATA FLAGS are assigned based on the simultaneous analysis of both samples tested. Refer to the following chart for an explanation of each symbol:

<u>DATA FLAG</u>	<u>STATISTICALLY INCLUDED/EXCLUDED</u>	<u>ACTION REQUIRED</u>
*	INCLUDED	CAUTION - review testing procedure and monitor future results. Results fall outside 95% ellipse but within a 99% ellipse that is calculated but not drawn.
X	EXCLUDED	STOP - immediate review of data and/or testing procedure is required. Results fall outside the 99% ellipse. See specific notes following each table for more information on why the data is excluded.
M	EXCLUDED	PROCEED - lab was unable to report data for at least one sample. However, a lab receiving two or more M flags for a test may need to stop and review its testing procedures.

Graph - For each laboratory, the LAB MEAN for the first sample (x-axis) is plotted against the LAB MEAN for the second sample (y-axis) with each point representing a laboratory. The horizontal and vertical cross-hairs are the GRAND MEANS for each sample. When 20 or more laboratories are in the statistics, an ellipse is also drawn so that 95% of the time a randomly selected laboratory will be included inside the ellipse. Plotted data flags are explained above.

Common Problems Highlighted in Footnotes

1. ***Extreme data*** - The laboratory's results for one or both samples are so inconsistent with those of the other participants that the lab mean(s) fall outside the plot. (The data usually vary by more than three standard deviations from the grand mean.) The participant is advised to immediately review his data and/or testing procedure.
 2. ***Systematic bias*** - The laboratory's results are either consistently high or low for both samples when compared to the other participants (the plotted point falls near the top or bottom of the ellipse). This indicates that the participant is performing the test with a constant bias. Causes of systematic errors include improper calibration, the particular make/model of equipment or a modification to the testing procedure.
 3. ***Inconsistency in testing between samples/sample sets*** - The laboratory's results indicate that there are differences in the way the two samples tested (the plotted point falls to the side of the ellipse). This type of error may be attributed to the analyst deviating from the procedure when testing one of the samples or a material interaction occurrence with the instrument or room conditions. The inconsistency is reflected in the CPVs for the two samples, such as a +1.5 CPV for sample A and a -2.2 CPV for sample B. CTS also will specify if the laboratory's data for one sample are high/low compared to the other participants. If this inconsistency is slight, the lab's plotted point will be an * that falls on the edge of the ellipse.
 4. ***Inconsistency in testing within a sample*** - The laboratory's within-lab standard deviation for a specified sample is high when compared to the other participants, often causing the lab's plotted point to fall outside of the ellipse.
 5. ***Data appeared to be off by a factor of # and was corrected by CTS*** - In tests that involve computations, the results reported to CTS may be off by a factor. If this factor can easily be determined, CTS may correct the data and flag the participant. Occasionally CTS will correct a laboratory's results even though the data are still high or low when compared to the other participants. This is done so that the laboratory may be alerted to other possible errors in its testing procedure.
 6. ***Data for two samples (or two tests) appeared to be switched by the lab, and the error was corrected by CTS.***
-

Labs flagged with an * are not typically included in the footnotes of a data table. These labs may locate their position in the control ellipse and use the definitions above to help identify the type of testing error. An * should serve as a caution flag, a "yellow light", to a lab. If this error is repeated in future rounds, a lab may need to stop and review its testing procedures. The initial data flag is not cause for alarm. Interlaboratory tests conducted at regular intervals permit a lab to recognize trends in testing.



Rubber Interlaboratory Testing Program

Analysis 605

Report #213

3rd Qtr 2022

Tensile Strength (psi)

WebCode	Data Flag	Sample C21-C22			Sample C23-C24		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2JUWC2		3,264.5	-76.7	-0.52	3,187.5	-134.8	-0.88
2KZLB6		3,208.0	-133.2	-0.91	3,166.5	-155.8	-1.01
2X9AJ2		3,535.0	193.8	1.33	3,470.0	147.7	0.96
2XQBAB		3,308.1	-33.1	-0.23	3,469.9	147.7	0.96
2ZWXME		3,486.5	145.3	0.99	3,375.5	53.2	0.35
32NYH6		3,415.7	74.4	0.51	3,393.9	71.6	0.47
38PD7R		3,319.0	-22.2	-0.15	3,354.5	32.2	0.21
3BT3UU		3,238.0	-103.2	-0.71	3,233.8	-88.5	-0.58
3J3TUC		3,408.5	67.3	0.46	3,272.5	-49.8	-0.32
3KWG9Z		3,323.3	-18.0	-0.12	3,369.5	47.2	0.31
3M4GRL		3,159.7	-181.6	-1.24	2,997.2	-325.0	-2.11
3U29XV		3,270.5	-70.7	-0.48	3,324.5	2.2	0.01
3VZCUQ		3,569.5	228.3	1.56	3,537.5	215.2	1.40
47V837		3,196.0	-145.2	-0.99	3,146.0	-176.3	-1.15
6QVM4U		3,495.0	153.8	1.05	3,440.0	117.7	0.76
72VHVX		3,440.0	98.8	0.68	3,480.0	157.7	1.02
7MNN4L		3,415.7	74.4	0.51	3,394.6	72.4	0.47
7QU6H4		3,188.1	-153.2	-1.05	3,242.1	-80.2	-0.52
87JGNJ		3,471.0	129.8	0.89	3,395.5	73.2	0.48
8DG8AU		3,141.8	-199.4	-1.36	3,076.9	-245.4	-1.59
8ECRZZ		3,157.5	-183.7	-1.26	3,151.0	-171.3	-1.11
8R3LDT		3,391.1	49.9	0.34	3,303.5	-18.8	-0.12
8TVBVN		3,285.0	-56.2	-0.38	3,360.0	37.7	0.25
99KXHT		3,435.0	93.8	0.64	3,522.0	199.7	1.30
9KZRUL		3,385.2	44.0	0.30	3,325.7	3.5	0.02
9PPCVF	X	2,182.8	-1,158.4	-7.92	2,422.2	-900.1	-5.85
9TRBBE		3,455.0	113.8	0.78	3,435.0	112.7	0.73
9ZQRPR		3,257.5	-83.7	-0.57	3,356.5	34.2	0.22
ARTL6N		3,334.4	-6.8	-0.05	3,307.6	-14.7	-0.10
AYA3TR	*	2,943.5	-397.7	-2.72	3,023.3	-299.0	-1.94
BD6YC3		3,334.5	-6.7	-0.05	3,280.5	-41.8	-0.27
BZHRGM		3,373.0	31.8	0.22	3,328.5	6.2	0.04
C3837U		3,547.6	206.4	1.41	3,396.1	73.8	0.48
CCEZWJ		3,380.0	38.8	0.27	3,375.0	52.7	0.34
CL3NVR		3,118.3	-222.9	-1.52	3,002.3	-320.0	-2.08
CN7L4Y		3,244.2	-97.1	-0.66	3,177.0	-145.3	-0.94
CPXMYP		3,293.5	-47.7	-0.33	3,299.0	-23.3	-0.15
DEB7QE		3,142.0	-199.2	-1.36	3,120.0	-202.3	-1.31



Rubber Interlaboratory Testing Program

Analysis 605

Report #213

3rd Qtr 2022

Tensile Strength (psi)

WebCode	Data Flag	Sample C21-C22			Sample C23-C24		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
DF34XL		3,320.5	-20.7	-0.14	3,320.5	-1.8	-0.01
DGHJCM		3,314.1	-27.1	-0.19	3,234.4	-87.9	-0.57
DLXVBP		3,231.5	-109.7	-0.75	3,269.0	-53.3	-0.35
E3ZQLV		3,350.8	9.6	0.07	3,374.5	52.2	0.34
EX7VJM	*	3,784.1	442.8	3.03	3,709.4	387.1	2.51
FGCQQK		3,253.5	-87.7	-0.60	3,219.0	-103.3	-0.67
FT78FL	X	4,142.2	801.0	5.48	4,043.9	721.6	4.69
G47U8H		3,451.0	109.8	0.75	3,511.0	188.7	1.23
GGRELJ		3,388.0	46.8	0.32	3,372.5	50.2	0.33
H36LBH		3,295.3	-45.9	-0.31	3,205.4	-116.9	-0.76
H3NM2R		3,487.3	146.1	1.00	3,432.8	110.5	0.72
HMPKFD		3,343.1	1.9	0.01	3,292.4	-29.9	-0.19
J7KD2B		3,188.0	-153.3	-1.05	3,237.3	-85.0	-0.55
J8UK44		3,352.6	11.3	0.08	3,346.2	23.9	0.16
JFA3ZK		3,497.6	156.4	1.07	3,499.1	176.8	1.15
JM8RJA		3,289.0	-52.2	-0.36	3,155.5	-166.8	-1.08
JN2F36		3,333.0	-8.2	-0.06	3,319.5	-2.8	-0.02
JNZPRF		3,314.5	-26.7	-0.18	3,269.0	-53.3	-0.35
KGF2EQ		3,688.5	347.3	2.38	3,657.7	335.5	2.18
KNXGXM	X	2,367.0	-974.2	-6.66	2,397.6	-924.7	-6.01
L63YTR		3,157.0	-184.2	-1.26	3,134.0	-188.3	-1.22
L7XM8G		3,270.2	-71.0	-0.49	3,338.7	16.4	0.11
LAWX8M		3,447.6	106.3	0.73	3,490.4	168.1	1.09
LH43N7		3,257.4	-83.9	-0.57	3,269.5	-52.8	-0.34
LRBCKC		3,261.9	-79.3	-0.54	3,404.8	82.5	0.54
LW4ELQ		3,325.7	-15.5	-0.11	3,294.6	-27.7	-0.18
M3BM7R		3,406.6	65.4	0.45	3,368.9	46.6	0.30
M7TJW3		3,514.7	173.5	1.19	3,423.0	100.8	0.65
MFCZK4		3,095.5	-245.7	-1.68	3,106.9	-215.4	-1.40
MX24AK		3,420.8	79.6	0.54	3,390.2	67.9	0.44
NMUTCT	*	3,626.0	284.7	1.95	3,401.2	78.9	0.51
NVM7A8		3,152.4	-188.9	-1.29	3,274.1	-48.2	-0.31
NVQJ2B		3,358.0	16.8	0.11	3,365.5	43.2	0.28
P2RFXF		3,542.5	201.3	1.38	3,520.5	198.2	1.29
PYXREK		3,378.8	37.5	0.26	3,352.8	30.5	0.20
Q8Q7XW	X	3,229.3	-111.9	-0.77	2,919.6	-402.6	-2.62
QZQRAA		3,438.5	97.3	0.67	3,333.5	11.2	0.07



Rubber Interlaboratory Testing Program

Analysis 605

Report #213

3rd Qtr 2022

Tensile Strength (psi)

WebCode	Data Flag	Sample C21-C22			Sample C23-C24		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
RFYZQ4	*	3,323.6	-17.7	-0.12	3,540.4	218.1	1.42
RNVVR9	*	3,019.5	-321.7	-2.20	3,131.0	-191.3	-1.24
TLX7HC		3,216.5	-124.7	-0.85	3,244.5	-77.8	-0.51
UEXZMA		3,442.5	101.3	0.69	3,443.5	121.2	0.79
V8W642		3,414.0	72.8	0.50	3,332.0	9.7	0.06
VDHZ2Y		3,451.4	110.2	0.75	3,508.5	186.3	1.21
VMQUXD		3,242.5	-98.7	-0.68	3,058.5	-263.8	-1.71
VNHUT3		3,192.8	-148.5	-1.02	3,199.6	-122.7	-0.80
VNXWZB		3,314.1	-27.1	-0.19	3,324.3	2.0	0.01
VVGDE7		3,473.0	131.7	0.90	3,573.8	251.5	1.63
W49VN9		3,129.2	-212.0	-1.45	3,119.1	-203.2	-1.32
WC3ZGA	*	3,091.0	-250.2	-1.71	2,931.5	-390.8	-2.54
WU46KC	X	2,910.0	-431.2	-2.95	2,555.0	-767.3	-4.98
WVGLYB		3,586.0	244.8	1.67	3,609.0	286.7	1.86
WVXT38		3,373.8	32.6	0.22	3,339.7	17.4	0.11
X3DWPZ		3,375.8	34.6	0.24	3,417.8	95.6	0.62
X48J4P		3,324.6	-16.6	-0.11	3,306.6	-15.7	-0.10
XAU6FH		3,334.1	-7.1	-0.05	3,375.6	53.4	0.35
XD8AMC		3,436.7	95.5	0.65	3,313.4	-8.9	-0.06
XFEKK2		3,173.5	-167.7	-1.15	3,041.0	-281.3	-1.83
YY7ZGG		3,492.5	151.3	1.03	3,578.5	256.2	1.66
ZK6GMW		3,365.0	23.8	0.16	3,255.0	-67.3	-0.44
ZMURC6		3,158.2	-183.0	-1.25	3,053.8	-268.5	-1.74
ZRNP3G		3,612.9	271.7	1.86	3,571.6	249.3	1.62
ZV8YXZ		3,406.5	65.3	0.45	3,362.5	40.2	0.26

Grand Means	Summary Statistics
3,341.23 psi	3,322.27 psi
Stnd Dev Btwn Labs	
146.20 psi	153.92 psi
Statistics based on 95 of 100 reporting participants	



Rubber Interlaboratory Testing Program
Analysis 605
Tensile Strength (psi)

Report #213

3rd Qtr 2022

Summary Statistics in SI Units	
Grand Means	
23.037 MPa	22.910 MPa
Stnd Dev Btwn Labs	
1.008 MPa	1.060 MPa

Statistics based on 95 of 100 reporting participants

Samples C21-C22: Polyisoprene compound, batch #1 & C23-C24: Polyisoprene compound, batch #2

Comments on Assigned Data Flags for Test #605

9PPCVF (X) - Data for all samples are low. Possible Systematic Error. Inconsistent within the determinations of sample group C23-C24.

FT78FL (X) - Data for all samples are high. Possible Systematic Error.

KNXGXM (X) - Data for all samples are low. Possible Systematic Error.

Q8Q7XW (X) - Inconsistent in testing between samples. Inconsistent within the determinations of sample group C23-C24.

WU46KC (X) - Data for all samples are low. Possible Systematic Error. Inconsistent within the determinations of sample group C21-C22.



Rubber Interlaboratory Testing Program

Analysis 605


Report #213

3rd Qtr 2022

Tensile Strength (psi)

Grand Mean Sample C21-C22 = 3,341.23 psi

Grand Mean Sample C23-C24 = 3,322.27 psi





Rubber Interlaboratory Testing Program

Analysis 606

Report #213

3rd Qtr 2022

Ultimate Elongation (percent)

WebCode	Data Flag	Sample C21-C22			Sample C23-C24		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2JUWC2		680.0	32.2	1.06	667.5	19.8	0.64
2KZLB6		627.5	-20.3	-0.66	627.0	-20.7	-0.67
2X9AJ2		692.5	44.7	1.46	697.0	49.3	1.60
2XQBAB		631.2	-16.6	-0.54	634.4	-13.3	-0.43
2ZWXME		649.5	1.7	0.06	647.5	-0.2	-0.01
32NYH6		672.0	24.2	0.79	670.0	22.3	0.72
38PD7R		651.5	3.7	0.12	643.5	-4.2	-0.14
3BT3UU		626.5	-21.3	-0.70	626.0	-21.7	-0.70
3J3TUC		676.0	28.2	0.92	664.5	16.8	0.55
3KWG9Z		656.7	8.9	0.29	664.6	16.9	0.55
3M4GRL		637.2	-10.6	-0.35	617.6	-30.1	-0.98
3U29XV		639.5	-8.3	-0.27	642.5	-5.2	-0.17
3VZCUQ		685.0	37.2	1.22	693.0	45.3	1.47
47V837		606.0	-41.8	-1.37	622.5	-25.2	-0.82
6QVM4U		676.5	28.7	0.94	670.5	22.8	0.74
72VHVX		624.0	-23.8	-0.78	641.0	-6.7	-0.22
7MNN4L		674.5	26.7	0.87	661.0	13.3	0.43
7QU6H4		639.0	-8.8	-0.29	646.5	-1.2	-0.04
87JGNJ		673.5	25.7	0.84	666.5	18.8	0.61
8DG8AU		613.7	-34.1	-1.12	634.1	-13.6	-0.44
8ECRZZ		669.0	21.2	0.69	672.0	24.3	0.79
8R3LDT		603.6	-44.1	-1.45	595.1	-52.5	-1.70
8TVBVN		665.0	17.2	0.56	649.5	1.8	0.06
99KXHT		622.0	-25.8	-0.85	646.0	-1.7	-0.05
9KZRUL		608.5	-39.3	-1.29	623.5	-24.2	-0.78
9PPCVF	X	905.5	257.7	8.44	957.5	309.8	10.05
9TRBBE		650.0	2.2	0.07	645.0	-2.7	-0.09
9ZQRPR	X	538.5	-109.3	-3.58	544.0	-103.7	-3.36
ARTL6N		709.5	61.7	2.02	690.0	42.3	1.37
AYA3TR		608.4	-39.4	-1.29	592.3	-55.4	-1.80
BD6YC3		625.0	-22.8	-0.75	607.0	-40.7	-1.32
BZHHRGM		645.5	-2.3	-0.08	677.5	29.8	0.97
C3837U		686.3	38.5	1.26	674.8	27.1	0.88
CCEZWJ		636.5	-11.3	-0.37	640.0	-7.7	-0.25
CL3NVR		656.1	8.3	0.27	644.1	-3.6	-0.12
CN7L4Y		642.5	-5.3	-0.17	651.0	3.3	0.11
CPXMYP		671.0	23.2	0.76	685.0	37.3	1.21
DEB7QE		661.0	13.2	0.43	655.0	7.3	0.24



Rubber Interlaboratory Testing Program

Analysis 606

Report #213

3rd Qtr 2022

Ultimate Elongation (percent)

WebCode	Data Flag	Sample C21-C22			Sample C23-C24		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
DF34XL		638.5	-9.3	-0.30	628.5	-19.2	-0.62
DGHJCM		600.4	-47.4	-1.55	592.8	-54.9	-1.78
DLXVBP		632.0	-15.8	-0.52	633.0	-14.7	-0.48
E3ZQLV		687.6	39.8	1.30	687.4	39.7	1.29
EX7VJM		680.6	32.8	1.08	688.1	40.4	1.31
FGCQQK		623.5	-24.3	-0.80	635.0	-12.7	-0.41
FT78FL		646.2	-1.6	-0.05	655.4	7.7	0.25
G47U8H		651.5	3.7	0.12	661.5	13.8	0.45
GGRELJ		694.0	46.2	1.51	677.5	29.8	0.97
H36LBH	*	611.0	-36.8	-1.21	649.0	1.3	0.04
H3NM2R		648.0	0.2	0.01	665.5	17.8	0.58
HMPKFD		664.0	16.2	0.53	675.0	27.3	0.89
J7KD2B		663.5	15.7	0.51	664.0	16.3	0.53
J8UK44		653.9	6.1	0.20	644.4	-3.3	-0.11
JM8RJA	*	661.5	13.7	0.45	622.0	-25.7	-0.83
JN2F36		626.0	-21.8	-0.71	620.0	-27.7	-0.90
JNZPRF		621.0	-26.8	-0.88	627.0	-20.7	-0.67
KGF2EQ		582.2	-65.6	-2.15	580.2	-67.5	-2.19
KNXGXM		637.6	-10.2	-0.33	612.0	-35.7	-1.16
L63YTR		632.0	-15.8	-0.52	618.5	-29.2	-0.95
L7XM8G	X	758.7	110.9	3.63	787.5	139.8	4.54
LAWX8M		597.1	-50.7	-1.66	621.2	-26.5	-0.86
LH43N7		624.1	-23.7	-0.78	652.2	4.5	0.14
LRBCKC		591.5	-56.3	-1.84	609.5	-38.2	-1.24
LW4ELQ		669.8	22.0	0.72	674.7	27.0	0.88
M3BM7R		632.0	-15.8	-0.52	652.0	4.3	0.14
M7TJW3		671.9	24.1	0.79	683.5	35.8	1.16
MFCZK4		640.3	-7.5	-0.25	659.8	12.1	0.39
MX24AK		669.1	21.3	0.70	657.1	9.4	0.31
NMUTCT		670.0	22.2	0.73	637.0	-10.7	-0.35
NVM7A8		666.5	18.7	0.61	688.5	40.8	1.32
NVQJ2B		636.5	-11.3	-0.37	647.0	-0.7	-0.02
P2RFXF		672.0	24.2	0.79	664.5	16.8	0.55
PYXREK		673.5	25.7	0.84	662.5	14.8	0.48
Q8Q7XW	*	616.5	-31.3	-1.03	585.0	-62.7	-2.03
QZQRAA		695.5	47.7	1.56	705.5	57.8	1.88
RFYZQ4		671.0	23.2	0.76	643.0	-4.7	-0.15



Rubber Interlaboratory Testing Program

Analysis 606

Report #213

3rd Qtr 2022

Ultimate Elongation (percent)

WebCode	Data Flag	Sample C21-C22			Sample C23-C24		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
RNVVR9	X	512.0	-135.8	-4.45	533.0	-114.7	-3.72
TLX7HC		640.0	-7.8	-0.26	651.5	3.8	0.12
UEXZMA		643.5	-4.3	-0.14	658.5	10.8	0.35
V8W642		680.0	32.2	1.06	671.0	23.3	0.76
VDHZ2Y		663.8	16.0	0.52	665.7	18.0	0.58
VMQUXD		594.5	-53.3	-1.75	577.5	-70.2	-2.28
VNHUT3		680.0	32.2	1.06	691.5	43.8	1.42
VVGDE7		611.5	-36.3	-1.19	601.0	-46.7	-1.52
W49VN9		637.5	-10.3	-0.34	637.5	-10.2	-0.33
WC3ZGA	*	575.0	-72.8	-2.38	568.5	-79.2	-2.57
WU46KC	X	595.5	-52.3	-1.71	533.5	-114.2	-3.71
WVGLYB		648.5	0.7	0.02	656.5	8.8	0.29
WVXT38		660.1	12.3	0.40	646.8	-0.9	-0.03
X3DWPZ		667.5	19.7	0.65	670.0	22.3	0.72
X48J4P		687.3	39.5	1.29	683.0	35.3	1.15
XAU6FH		662.3	14.5	0.47	660.4	12.7	0.41
XD8AMC		687.5	39.7	1.30	678.3	30.7	0.99
XFEKK2	*	726.5	78.7	2.58	719.5	71.8	2.33
YY7ZGG		636.5	-11.3	-0.37	627.5	-20.2	-0.66
ZK6GMW		665.0	17.2	0.56	663.5	15.8	0.51
ZMURC6		618.5	-29.3	-0.96	620.2	-27.5	-0.89
ZRNP3G	*	569.5	-78.3	-2.57	570.5	-77.2	-2.50
ZV8YXZ		645.5	-2.3	-0.08	652.0	4.3	0.14

Grand Means	Summary Statistics
647.79 percent	647.69 percent
Stnd Dev Btwn Labs	
30.52 percent	
30.82 percent	
Statistics based on 93 of 98 reporting participants	

Samples C21-C22: Polyisoprene compound, batch #1 & C23-C24: Polyisoprene compound, batch #2

Comments on Assigned Data Flags for Test #606

9PPCVF (X) - Data for all samples are high. Inconsistent within the determinations of sample group C23-C24.

9ZQRPR (X) - Data for all samples are low. Possible Systematic Error.

L7XM8G (X) - Data for all samples are high. Possible Systematic Error.

RNVVR9 (X) - Data for all samples are low. Possible Systematic Error.

WU46KC (X) - Data for sample group C23-C24 are low.



Rubber Interlaboratory Testing Program

Analysis 606


Report #213

3rd Qtr 2022

Ultimate Elongation (percent)

Grand Mean Sample C21-C22 = 647.79 percent

Grand Mean Sample C23-C24 = 647.69 percent





Rubber Interlaboratory Testing Program

Analysis 607

Report #213

3rd Qtr 2022

Stress at 300% Elongation (psi)

WebCode	Data Flag	Sample C21-C22			Sample C23-C24		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2JUWC2		766.5	-67.0	-1.02	754.0	-71.2	-1.04
2KZLB6		845.0	11.5	0.18	845.5	20.3	0.30
2X9AJ2		774.1	-59.3	-0.91	706.7	-118.5	-1.74
2XQBAB		877.6	44.1	0.67	881.0	55.8	0.82
2ZWXME		889.0	55.5	0.85	874.5	49.3	0.72
32NYH6		863.0	29.5	0.45	871.0	45.8	0.67
38PD7R		802.5	-31.0	-0.47	825.0	-0.2	0.00
3J3TUC		760.5	-73.0	-1.12	753.5	-71.7	-1.05
3KWG9Z		856.2	22.8	0.35	829.9	4.7	0.07
3M4GRL	*	803.7	-29.8	-0.46	897.8	72.6	1.07
3U29XV		822.5	-11.0	-0.17	847.0	21.8	0.32
3VZCUQ		784.5	-49.0	-0.75	776.5	-48.7	-0.71
47V837		834.5	1.0	0.02	769.0	-56.2	-0.82
6QVM4U		837.5	4.0	0.06	831.5	6.3	0.09
72VHVX		956.3	122.8	1.88	910.1	84.9	1.25
7MNN4L		831.1	-2.4	-0.04	832.5	7.3	0.11
7QU6H4		787.3	-46.2	-0.71	814.3	-10.9	-0.16
87JGNJ		807.5	-26.0	-0.40	790.0	-35.2	-0.52
8DG8AU		887.5	54.0	0.83	799.5	-25.7	-0.38
8ECRZZ		728.8	-104.6	-1.60	749.9	-75.3	-1.11
8R3LDT	*	990.2	156.8	2.40	1,005.8	180.6	2.65
8TVBVN		700.5	-133.0	-2.03	744.5	-80.7	-1.18
99KXHT		875.0	41.5	0.64	851.0	25.8	0.38
9KZRUL		921.0	87.5	1.34	867.3	42.1	0.62
9PPCVF	X	456.9	-376.6	-5.76	477.9	-347.3	-5.10
9TRBBE		815.0	-18.5	-0.28	817.0	-8.2	-0.12
9ZQRPR	X	1,153.0	319.5	4.89	1,166.5	341.3	5.01
ARTL6N		780.3	-53.1	-0.81	811.5	-13.7	-0.20
AYA3TR	*	978.4	145.0	2.22	1,019.0	193.8	2.84
BD6YC3		870.0	36.5	0.56	853.5	28.3	0.42
BZHRCM		816.0	-17.5	-0.27	740.5	-84.7	-1.24
C3837U		776.9	-56.6	-0.87	766.3	-58.9	-0.86
CCEZWJ		853.0	19.5	0.30	888.0	62.8	0.92
CL3NVR		794.1	-39.4	-0.60	731.0	-94.2	-1.38
CN7L4Y		819.8	-13.7	-0.21	763.2	-62.0	-0.91
CPXMYP		757.0	-76.5	-1.17	732.0	-93.2	-1.37
DEB7QE		739.5	-94.0	-1.44	723.0	-102.2	-1.50
DF34XL		884.5	51.0	0.78	838.8	13.6	0.20



Rubber Interlaboratory Testing Program

Analysis 607

Report #213

3rd Qtr 2022

Stress at 300% Elongation (psi)

WebCode	Data Flag	Sample C21-C22			Sample C23-C24		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
DGHJCM		935.5	102.1	1.56	954.4	129.2	1.90
DLXVBP		827.0	-6.5	-0.10	852.5	27.3	0.40
E3ZQLV		704.0	-129.5	-1.98	750.8	-74.4	-1.09
EX7VJM	X	681.0	-152.5	-2.33	905.8	80.6	1.18
FGCQQK		822.0	-11.5	-0.18	798.0	-27.2	-0.40
FT78FL		969.4	135.9	2.08	974.0	148.8	2.18
G47U8H		792.5	-41.0	-0.63	783.5	-41.7	-0.61
GGRELJ		803.0	-30.5	-0.47	809.0	-16.2	-0.24
H36LBH	X	928.2	94.8	1.45	791.9	-33.3	-0.49
H3NM2R		860.7	27.2	0.42	790.9	-34.3	-0.50
HMPKFD		775.2	-58.2	-0.89	730.3	-94.9	-1.39
J7KD2B		732.4	-101.0	-1.55	737.5	-87.7	-1.29
J8UK44		819.5	-14.0	-0.21	839.1	13.9	0.20
JM8RJA		768.0	-65.5	-1.00	812.0	-13.2	-0.19
JN2F36		898.9	65.5	1.00	899.4	74.2	1.09
JNZPRF		885.0	51.6	0.79	915.0	89.8	1.32
KGF2EQ	X	1,092.9	259.4	3.97	1,116.1	290.9	4.27
KNXGXM	X	615.6	-217.8	-3.33	713.4	-111.8	-1.64
L63YTR		839.0	5.5	0.08	860.5	35.3	0.52
LAWX8M		911.6	78.1	1.20	915.9	90.7	1.33
LH43N7	X	981.1	147.6	2.26	865.7	40.5	0.59
LRBCKC		955.8	122.4	1.87	913.0	87.8	1.29
LW4ELQ		787.6	-45.9	-0.70	763.6	-61.6	-0.90
M3BM7R	*	910.5	77.0	1.18	810.5	-14.7	-0.22
M7TJW3		814.1	-19.4	-0.30	780.5	-44.7	-0.66
MFCZK4		754.3	-79.2	-1.21	729.9	-95.3	-1.40
MX24AK		787.5	-45.9	-0.70	828.3	3.1	0.05
NMUTCT		921.0	87.5	1.34	834.0	8.8	0.13
NVM7A8		751.0	-82.5	-1.26	743.2	-82.0	-1.20
NVQJ2B		870.5	37.0	0.57	841.0	15.8	0.23
P2RFXF		818.0	-15.5	-0.24	835.5	10.3	0.15
PYXREK		803.7	-29.8	-0.46	826.6	1.4	0.02
Q8Q7XW		886.9	53.5	0.82	921.7	96.5	1.42
QZQRAA		831.0	-2.5	-0.04	764.0	-61.2	-0.90
RFYZQ4	X	778.9	-54.6	-0.84	923.9	98.7	1.45
RNVVR9	X	1,176.5	343.0	5.25	1,172.0	346.8	5.09
V8W642		791.5	-42.0	-0.64	781.0	-44.2	-0.65



Rubber Interlaboratory Testing Program

Analysis 607

Report #213

3rd Qtr 2022

Stress at 300% Elongation (psi)

WebCode	Data Flag	Sample C21-C22			Sample C23-C24		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
VDHZ2Y		831.5	-2.0	-0.03	856.2	31.0	0.45
VMQUXD		903.0	69.5	1.06	894.0	68.8	1.01
VNHUT3		747.9	-85.6	-1.31	719.4	-105.8	-1.55
VVGDE7		877.0	43.5	0.67	879.5	54.3	0.80
W49VN9		823.1	-10.4	-0.16	809.3	-15.9	-0.23
WC3ZGA		980.0	146.5	2.24	956.5	131.3	1.93
WU46KC		862.5	29.0	0.44	903.0	77.8	1.14
WVGLYB		882.0	48.5	0.74	866.0	40.8	0.60
WVXT38		813.6	-19.9	-0.30	826.2	1.0	0.02
X3DWPZ		788.3	-45.2	-0.69	779.6	-45.6	-0.67
X48J4P		724.8	-108.7	-1.66	763.9	-61.3	-0.90
XAU6FH		823.7	-9.7	-0.15	844.3	19.1	0.28
XD8AMC		782.5	-51.0	-0.78	755.7	-69.5	-1.02
YY7ZGG		856.5	23.0	0.35	883.5	58.3	0.86
ZK6GMW		815.0	-18.5	-0.28	784.0	-41.2	-0.60
ZMURC6		864.4	31.0	0.47	826.7	1.5	0.02
ZV8YXZ		887.0	53.5	0.82	836.5	11.3	0.17

Summary Statistics	
Grand Means	
	833.45 psi
Stnd Dev Btwn Labs	
	65.36 psi
	825.20 psi
Statistics based on 83 of 92 reporting participants	

Summary Statistics in SI Units	
Grand Means	
	5.7464 MPa
Stnd Dev Btwn Labs	
	0.4506 MPa
	5.6900 MPa
Statistics based on 83 of 92 reporting participants	

Samples C21-C22: Polyisoprene compound, batch #1 & C23-C24: Polyisoprene compound, batch #2



Rubber Interlaboratory Testing Program

Analysis 607

Report #213

3rd Qtr 2022

Stress at 300% Elongation (psi)

Comments on Assigned Data Flags for Test #607

9PPCVF (X) - Data for all samples are low. Possible Systematic Error.

9ZQRPR (X) - Data for all samples are high. Possible Systematic Error. Inconsistent within the determinations of sample group C21-C22.

EX7VJM (X) - Inconsistent in testing between samples.

H36LBH (X) - Inconsistent in testing between samples.

KGF2EQ (X) - Data for all samples are high. Possible Systematic Error.

KNXGXM (X) - Data for sample group C21-C22 are low.

LH43N7 (X) - Inconsistent in testing between samples. Inconsistent within the determinations of sample group C21-C22.

RFYZQ4 (X) - Inconsistent in testing between samples.

RNVVR9 (X) - Data for all samples are high. Possible Systematic Error. Inconsistent within the determinations of sample group C21-C22.



Rubber Interlaboratory Testing Program

Analysis 607


Report #213

3rd Qtr 2022

Stress at 300% Elongation (psi)

Grand Mean Sample C21-C22 = 833.45 psi

Grand Mean Sample C23-C24 = 825.20 psi





Rubber Interlaboratory Testing Program

Analysis 608

Report #213

3rd Qtr 2022

Stress at 100% Elongation (psi)

WebCode	Data Flag	Sample C21-C22			Sample C23-C24		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2JUWC2		186.5	-1.2	-0.09	180.0	-5.9	-0.42
2KZLB6		194.5	6.8	0.48	191.0	5.1	0.36
2X9AJ2	*	207.7	20.0	1.42	184.4	-1.5	-0.10
2XQBAB		197.5	9.8	0.70	195.8	9.9	0.70
2ZWXME		191.0	3.3	0.23	194.5	8.6	0.61
32NYH6	*	222.0	34.3	2.44	225.5	39.6	2.80
38PD7R		187.5	-0.2	-0.02	193.5	7.6	0.54
3J3TUC		177.5	-10.2	-0.73	175.5	-10.4	-0.73
3KWG9Z		192.0	4.3	0.31	188.5	2.6	0.18
3M4GRL		170.4	-17.3	-1.23	173.3	-12.6	-0.89
3U29XV		181.5	-6.2	-0.44	190.0	4.1	0.29
3VZCUQ		174.5	-13.2	-0.94	175.5	-10.4	-0.73
47V837		186.5	-1.2	-0.09	175.5	-10.4	-0.73
6QVM4U		189.5	1.8	0.13	191.0	5.1	0.36
72VHVX		217.9	30.2	2.15	205.4	19.5	1.38
7MNN4L		195.1	7.4	0.52	194.4	8.5	0.60
7QU6H4		174.7	-13.0	-0.93	181.0	-4.9	-0.35
87JGNJ		180.0	-7.7	-0.55	179.0	-6.9	-0.49
8DG8AU		185.0	-2.7	-0.19	170.5	-15.4	-1.09
8ECRZZ		185.6	-2.1	-0.15	196.5	10.6	0.75
8R3LDT		200.7	13.0	0.93	205.7	19.8	1.40
8TVBVN		167.0	-20.7	-1.48	174.0	-11.9	-0.84
99KXHT		188.0	0.3	0.02	181.0	-4.9	-0.35
9KZRUL		176.9	-10.8	-0.77	183.5	-2.4	-0.17
9PPCVF		166.1	-21.6	-1.54	179.1	-6.8	-0.48
9TRBBE		177.5	-10.2	-0.73	174.0	-11.9	-0.84
9ZQRPR		207.0	19.3	1.37	207.5	21.6	1.53
ARTL6N		175.5	-12.2	-0.87	180.6	-5.3	-0.38
AYA3TR		211.4	23.7	1.69	213.6	27.7	1.95
BD6YC3		190.0	2.3	0.16	183.0	-2.9	-0.20
BZHRCM		183.5	-4.2	-0.30	172.0	-13.9	-0.98
C3837U		179.9	-7.8	-0.56	180.6	-5.3	-0.37
CCEZWJ		188.0	0.3	0.02	195.5	9.6	0.68
CL3NVR		175.5	-12.2	-0.87	161.7	-24.2	-1.71
CN7L4Y		182.3	-5.4	-0.39	170.3	-15.6	-1.10
CPXMYP		175.0	-12.7	-0.91	172.0	-13.9	-0.98
DEB7QE		171.0	-16.7	-1.19	165.5	-20.4	-1.44
DF34XL		200.0	12.3	0.88	193.5	7.6	0.54



Rubber Interlaboratory Testing Program

Analysis 608

Report #213

3rd Qtr 2022

Stress at 100% Elongation (psi)

WebCode	Data Flag	Sample C21-C22			Sample C23-C24		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
DGHJCM		192.2	4.5	0.32	196.5	10.6	0.75
DLXVBP		177.5	-10.2	-0.73	181.0	-4.9	-0.35
E3ZQLV		167.1	-20.6	-1.47	178.7	-7.2	-0.51
EX7VJM		201.4	13.7	0.97	195.5	9.6	0.68
FGCQQK		184.0	-3.7	-0.26	186.0	0.1	0.01
FT78FL		207.7	20.0	1.42	216.3	30.4	2.15
G47U8H		175.5	-12.2	-0.87	178.0	-7.9	-0.56
GGRELJ		198.0	10.3	0.73	198.0	12.1	0.86
H36LBH		192.9	5.2	0.37	172.6	-13.3	-0.94
H3NM2R		189.6	1.8	0.13	177.7	-8.2	-0.58
HMPKFD		179.1	-8.6	-0.61	172.6	-13.3	-0.94
J7KD2B	*	150.1	-37.6	-2.68	150.1	-35.8	-2.53
J8UK44		184.9	-2.8	-0.20	190.7	4.8	0.34
JM8RJA		174.0	-13.7	-0.98	181.0	-4.9	-0.35
JN2F36		193.7	6.0	0.43	193.1	7.2	0.51
JNZPRF	X	175.0	-12.7	-0.91	209.0	23.1	1.63
KGF2EQ		220.5	32.7	2.33	219.0	33.1	2.34
KNXGXM	X	127.2	-60.5	-4.31	142.1	-43.8	-3.10
L63YTR		190.5	2.8	0.20	192.5	6.6	0.47
L7XM8G		171.0	-16.7	-1.19	172.7	-13.2	-0.93
LAWX8M		201.6	13.9	0.99	208.1	22.2	1.57
LH43N7	X	222.3	34.5	2.46	198.2	12.3	0.87
LRBCKC		198.7	11.0	0.78	184.9	-1.0	-0.07
LW4ELQ		173.3	-14.4	-1.03	166.8	-19.1	-1.35
M3BM7R		197.5	9.8	0.70	177.5	-8.4	-0.59
M7TJW3		171.5	-16.3	-1.16	164.0	-21.9	-1.55
MFCZK4		170.4	-17.3	-1.23	167.5	-18.4	-1.30
MX24AK		184.7	-3.0	-0.21	190.4	4.5	0.32
NMUTCT	X	246.6	58.9	4.19	203.1	17.2	1.21
NVM7A8		176.2	-11.6	-0.82	174.0	-11.9	-0.84
NVQJ2B		190.5	2.8	0.20	187.0	1.1	0.08
P2RFXF		185.0	-2.7	-0.19	189.0	3.1	0.22
PYXREK		178.6	-9.2	-0.65	181.7	-4.2	-0.30
Q8Q7XW		190.0	2.3	0.16	196.5	10.6	0.75
QZQRAA		201.5	13.8	0.98	190.0	4.1	0.29
RFYZQ4	X	176.9	-10.8	-0.77	215.4	29.5	2.08
RNVVR9		209.0	21.3	1.52	202.0	16.1	1.14



Rubber Interlaboratory Testing Program

Analysis 608

Report #213

3rd Qtr 2022

Stress at 100% Elongation (psi)

WebCode	Data Flag	Sample C21-C22			Sample C23-C24		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
UEXZMA		187.5	-0.2	-0.02	173.5	-12.4	-0.88
V8W642		184.5	-3.2	-0.23	183.0	-2.9	-0.20
VDHZ2Y		187.2	-0.6	-0.04	191.0	5.1	0.36
VMQUXD		201.5	13.8	0.98	198.0	12.1	0.86
VNHUT3		180.6	-7.1	-0.51	174.5	-11.4	-0.80
VVGDE7		188.5	0.8	0.06	189.0	3.1	0.22
W49VN9		194.4	6.6	0.47	192.2	6.3	0.44
WC3ZGA	*	227.0	39.3	2.80	220.5	34.6	2.45
WU46KC		188.5	0.8	0.06	204.5	18.6	1.31
WVGLYB		187.5	-0.2	-0.02	186.5	0.6	0.04
WVXT38		177.0	-10.7	-0.76	180.1	-5.8	-0.41
X3DWPZ		176.9	-10.8	-0.77	176.9	-8.9	-0.63
X48J4P		163.3	-24.5	-1.74	169.7	-16.2	-1.15
XAU6FH	X	172.4	-15.3	-1.09	203.1	17.2	1.21
XD8AMC		179.8	-7.9	-0.56	170.4	-15.5	-1.09
YY7ZGG		220.5	32.8	2.34	216.5	30.6	2.16
ZK6GMW		191.0	3.3	0.23	184.5	-1.4	-0.10
ZMURC6		189.3	1.6	0.11	183.5	-2.4	-0.17
ZRNP3G		193.6	5.9	0.42	178.4	-7.5	-0.53
ZV8YXZ		197.5	9.8	0.70	186.0	0.1	0.01

Summary Statistics

Grand Means

187.71 psi

185.89 psi

Stnd Dev Btwn Labs

14.03 psi

14.15 psi

Statistics based on 89 of 95 reporting participants

Summary Statistics in SI Units

Grand Means

1.2942 MPa

1.2800 MPa

Stnd Dev Btwn Labs

0.0968 MPa

0.1000 MPa

Statistics based on 89 of 95 reporting participants

Samples C21-C22: Polyisoprene compound, batch #1 & C23-C24: Polyisoprene compound, batch #2



Rubber Interlaboratory Testing Program
Analysis 608
Stress at 100% Elongation (psi)

Report #213

3rd Qtr 2022

Comments on Assigned Data Flags for Test #608

JNZPRF (X) - Inconsistent in testing between samples. Inconsistent within the determinations of sample group C23-C24.

KNXGXM (X) - Data for all samples are low. Possible Systematic Error.

LH43N7 (X) - Inconsistent in testing between samples. Inconsistent within the determinations of sample group C21-C22.

NMUTCT (X) - Data for sample group C21-C22 are high. Inconsistent within the determinations of sample group C21-C22.

RFYZQ4 (X) - Inconsistent in testing between samples.

XAU6FH (X) - Inconsistent in testing between samples.



Rubber Interlaboratory Testing Program

Analysis 608


Report #213

3rd Qtr 2022

Stress at 100% Elongation (psi)

Grand Mean Sample C21-C22 = 187.71 psi

Grand Mean Sample C23-C24 = 185.89 psi





Rubber Interlaboratory Testing Program

Report #213

Analysis 620

3rd Qtr 2022

Hardness (Shore A/Type A)

WebCode	Data Flag	Sample C21-C22			Sample C23-C24			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
2JUWC2		47.00	-0.54	-0.35	46.00	-1.65	-1.10	BT
2KZLB6		50.50	2.96	1.93	51.00	3.35	2.23	XX
2X9AJ2		48.25	0.71	0.46	47.50	-0.15	-0.10	HH
2XQBAB		47.25	-0.29	-0.19	47.40	-0.25	-0.17	BT
2ZWXME		48.20	0.66	0.43	47.95	0.30	0.20	BT
32NYH6		47.00	-0.54	-0.35	47.50	-0.15	-0.10	BT
38PD7R		47.05	-0.49	-0.32	47.40	-0.25	-0.17	BT
3BT3UU		47.00	-0.54	-0.35	47.50	-0.15	-0.10	BT
3J3TUC		48.50	0.96	0.62	48.50	0.85	0.57	BT
3KGW9Z		47.50	-0.04	-0.03	47.25	-0.40	-0.27	BT
3M4GRL		47.00	-0.54	-0.35	47.00	-0.65	-0.43	BT
3U29XV		49.50	1.96	1.28	49.50	1.85	1.23	HH
3VZCUQ		48.55	1.01	0.66	49.40	1.75	1.17	BT
47V837		49.00	1.46	0.95	49.50	1.85	1.23	BT
4GBUER	X	56.50	8.96	5.84	56.00	8.35	5.56	HH
6QVM4U		47.98	0.44	0.29	47.56	-0.09	-0.06	BT
72VHVX	X	46.50	-1.04	-0.68	49.00	1.35	0.90	BT
73MQNY		46.50	-1.04	-0.68	47.50	-0.15	-0.10	BT
7MNN4L		46.85	-0.69	-0.45	48.45	0.80	0.53	BT
7QU6H4		47.15	-0.39	-0.26	47.55	-0.10	-0.07	BT
87JGNJ		49.05	1.51	0.98	48.80	1.15	0.77	BT
8DG8AU		48.25	0.71	0.46	47.85	0.20	0.13	BT
8ECRZZ		45.95	-1.59	-1.04	46.80	-0.85	-0.57	BT
8R3LDT		50.00	2.46	1.60	51.00	3.35	2.23	HH
8TVBVN		49.50	1.96	1.28	49.00	1.35	0.90	BT
8VJ7Y9		50.50	2.96	1.93	50.00	2.35	1.57	HH
92JTKG		46.45	-1.09	-0.71	45.75	-1.90	-1.27	BT
99KXHT		48.00	0.46	0.30	47.50	-0.15	-0.10	BT
9KZRUL		47.30	-0.24	-0.16	46.70	-0.95	-0.63	BT
9PPCVF		46.10	-1.44	-0.94	47.80	0.15	0.10	BT
9TRBBE		51.00	3.46	2.25	50.50	2.85	1.90	BT
9ZQRPR	*	45.00	-2.54	-1.66	47.00	-0.65	-0.43	BT
ARTL6N		49.00	1.46	0.95	49.80	2.15	1.43	BT
AYA3TR		48.00	0.46	0.30	48.50	0.85	0.57	BT
BD6YC3		47.85	0.31	0.20	47.40	-0.25	-0.17	HH
BZHHRGM		47.50	-0.04	-0.03	46.50	-1.15	-0.77	BT
C3837U		49.30	1.76	1.15	48.90	1.25	0.83	XX
CCEZWJ		49.00	1.46	0.95	49.50	1.85	1.23	HH



Rubber Interlaboratory Testing Program

Analysis 620

Report #213

3rd Qtr 2022

Hardness (Shore A/Type A)

WebCode	Data Flag	Sample C21-C22			Sample C23-C24			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
CK7B9Y		46.80	-0.74	-0.48	46.25	-1.40	-0.93	BT
CL3NVR		47.95	0.41	0.27	47.90	0.25	0.17	BT
CMXCC3		47.70	0.16	0.10	46.85	-0.80	-0.53	BT
CPXMYP		49.00	1.46	0.95	50.00	2.35	1.57	HH
DEB7QE		47.50	-0.04	-0.03	47.00	-0.65	-0.43	BT
DF34XL		46.00	-1.54	-1.01	46.00	-1.65	-1.10	HH
DGHJCM		50.00	2.46	1.60	50.00	2.35	1.57	HH
DLXVBP		48.25	0.71	0.46	49.10	1.45	0.97	BT
E3ZQLV		47.10	-0.44	-0.29	47.45	-0.20	-0.13	BT
EX7VJM		45.75	-1.79	-1.17	45.85	-1.80	-1.20	BT
FGCQQK		45.00	-2.54	-1.66	46.50	-1.15	-0.77	BT
FT78FL	X	43.00	-4.54	-2.96	45.50	-2.15	-1.43	HH
G47U8H		48.50	0.96	0.62	48.00	0.35	0.23	HH
GGRELJ		48.00	0.46	0.30	48.00	0.35	0.23	BT
H36LBH		44.20	-3.34	-2.18	44.65	-3.00	-2.00	BT
H3NM2R		49.45	1.91	1.24	48.80	1.15	0.77	BT
HMPKFD		48.35	0.81	0.53	48.30	0.65	0.43	BT
J7KD2B		49.00	1.46	0.95	49.00	1.35	0.90	BT
J8UK44		48.00	0.46	0.30	47.00	-0.65	-0.43	BT
JCLPW9		49.00	1.46	0.95	49.00	1.35	0.90	BT
JFA3ZK		45.25	-2.29	-1.50	46.00	-1.65	-1.10	BT
JM8RJA		47.70	0.16	0.10	48.70	1.05	0.70	BT
JN2F36		44.50	-3.04	-1.98	44.50	-3.15	-2.10	BT
JNZPRF		47.00	-0.54	-0.35	47.50	-0.15	-0.10	HH
KGF2EQ		45.90	-1.64	-1.07	46.05	-1.60	-1.07	BT
KNXGXM		47.55	0.01	0.00	48.55	0.90	0.60	BT
L63YTR		46.00	-1.54	-1.01	45.00	-2.65	-1.77	HH
L7XM8G		47.90	0.36	0.23	48.95	1.30	0.87	BT
LAWX8M	*	43.50	-4.04	-2.64	44.00	-3.65	-2.43	BT
LH43N7		48.55	1.01	0.66	48.80	1.15	0.77	BT
LRBCKC		48.25	0.71	0.46	48.35	0.70	0.47	BT
LW4ELQ		48.50	0.96	0.62	48.00	0.35	0.23	BT
M3BM7R		46.50	-1.04	-0.68	46.50	-1.15	-0.77	HH
M7TJW3		50.50	2.96	1.93	50.50	2.85	1.90	HH
MFCZK4		46.20	-1.34	-0.88	45.70	-1.95	-1.30	XX
MX24AK		48.30	0.76	0.49	48.55	0.90	0.60	BT
NMUTCT		45.00	-2.54	-1.66	45.00	-2.65	-1.77	BT



Rubber Interlaboratory Testing Program

Analysis 620

Report #213

3rd Qtr 2022

Hardness (Shore A/Type A)

WebCode	Data Flag	Sample C21-C22			Sample C23-C24			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
NVM7A8		49.85	2.31	1.50	48.90	1.25	0.83	BT
NVQJ2B		48.25	0.71	0.46	48.00	0.35	0.23	BT
P2RFXF		46.50	-1.04	-0.68	47.25	-0.40	-0.27	BT
PXNQAD		48.15	0.61	0.40	48.00	0.35	0.23	BT
PYXREK		47.85	0.31	0.20	48.25	0.60	0.40	BT
Q8Q7XW	X	42.75	-4.79	-3.13	45.45	-2.20	-1.47	BT
QZQRAA		49.15	1.61	1.05	48.75	1.10	0.73	BT
RFYZQ4		47.50	-0.04	-0.03	47.00	-0.65	-0.43	BT
RNVVR9	X	53.50	5.96	3.88	51.50	3.85	2.56	HH
UEXZMA		48.45	0.91	0.59	48.05	0.40	0.27	BT
V8W642		46.00	-1.54	-1.01	47.00	-0.65	-0.43	BT
VDHZ2Y		46.50	-1.04	-0.68	46.70	-0.95	-0.63	BT
VMQUXD		44.40	-3.14	-2.05	44.80	-2.85	-1.90	BT
VNHUT3		47.60	0.06	0.04	46.85	-0.80	-0.53	BT
VNXWZB		45.50	-2.04	-1.33	45.50	-2.15	-1.43	BT
VVGDE7		46.50	-1.04	-0.68	47.50	-0.15	-0.10	XX
W49VN9		47.00	-0.54	-0.35	47.00	-0.65	-0.43	HH
WC3ZGA	X	53.50	5.96	3.88	53.50	5.85	3.90	HH
WU46KC		47.50	-0.04	-0.03	47.00	-0.65	-0.43	BT
WVGLYB		47.50	-0.04	-0.03	47.00	-0.65	-0.43	BT
WVXT38		45.50	-2.04	-1.33	46.00	-1.65	-1.10	BT
X3DWPZ		47.00	-0.54	-0.35	47.50	-0.15	-0.10	BT
X48J4P		46.50	-1.04	-0.68	47.00	-0.65	-0.43	BT
XAU6FH		48.00	0.46	0.30	48.00	0.35	0.23	HH
XFEKK2	X	56.50	8.96	5.84	54.50	6.85	4.56	HH
YY7ZGG		45.45	-2.09	-1.36	46.55	-1.10	-0.73	BT
ZD3EC6		48.00	0.46	0.30	48.00	0.35	0.23	HH
ZK6GMW		50.50	2.96	1.93	51.00	3.35	2.23	BT
ZMURC6		48.50	0.96	0.62	49.00	1.35	0.90	BT
ZRNP3G		45.25	-2.29	-1.50	44.90	-2.75	-1.83	BT
ZV8YXZ		46.65	-0.89	-0.58	45.95	-1.70	-1.13	BT

Grand Means	Summary Statistics
47.543 Type A	47.652 Type A
Stnd Dev Btwn Labs 1.534 Type A	1.500 Type A

Statistics based on 99 of 106 reporting participants



Rubber Interlaboratory Testing Program
Analysis 620
Hardness (Shore A/Type A)

Report #213

3rd Qtr 2022

Samples C21-C22: Polyisoprene compound, batch #1 & C23-C24: Polyisoprene compound, batch #2

Comments on Assigned Data Flags for Test #620

4GBUER (X) - Data for all samples are high. Possible Systematic Error.

72VHVX (X) - Inconsistent in testing between samples.

FT78FL (X) - Data for sample group C21-C22 are low.

Q8Q7XW (X) - Data for sample group C21-C22 are low.

RNVVR9 (X) - Data for sample group C21-C22 are high. Inconsistent within the determinations of sample group C21-C22.

WC3ZGA (X) - Data for all samples are high. Possible Systematic Error.

XFEKK2 (X) - Data for all samples are high. Possible Systematic Error.

Key to Instrument Codes Reported by Participants

BT Benchtop **HH** Handheld

XX Specify Benchtop or Handheld Instrument

Results by Reading Time (as reported by laboratory)

Reading Time	Sample C21-C22 Polyisoprene compound, batch #1			Sample C23-C24 Polyisoprene compound, batch #2			Labs Incl / Rpt
	Group Mean	Btwn Lab STD	Diff from GM	Group Mean	Btwn Lab STD	Diff from GM	
Reading time not reported	50.50	0.00	2.96	51.00	0.00	3.35	1 1
Readings taken within 0 - 5 seconds	47.80	1.45	0.26	47.90	1.48	0.25	68 73
Readings taken at 5 seconds	47.03	1.53	-0.51	47.13	1.26	-0.52	11 13
Readings taken after 5+ seconds	46.87	1.11	-0.68	46.68	1.17	-0.97	9 9
Maximum hardness indicator used	47.25	1.36	-0.29	47.44	0.98	-0.21	8 10



Rubber Interlaboratory Testing Program

Analysis 620


Report #213

3rd Qtr 2022

Hardness (Shore A/Type A)

Grand Mean Sample C21-C22 = 47.543 Type A

Grand Mean Sample C23-C24 = 47.652 Type A





Rubber Interlaboratory Testing Program

Analysis 621

Report #213

3rd Qtr 2022

Density

WebCode	Data Flag	Sample C21-C22			Sample C23-C24		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2JUWC2		1.135	0.003	0.92	1.134	0.002	0.66
2KZLB6		1.134	0.002	0.75	1.134	0.002	0.52
2X9AJ2		1.134	0.002	0.75	1.134	0.002	0.52
2XQBAB	X	1.115	-0.016	-5.48	1.117	-0.014	-4.12
2ZWXME		1.134	0.002	0.67	1.133	0.001	0.28
32NYH6		1.130	-0.002	-0.70	1.131	-0.001	-0.27
3BT3UU		1.130	-0.002	-0.58	1.129	-0.003	-0.77
3J3TUC		1.133	0.001	0.25	1.133	0.001	0.38
3KWG9Z		1.132	0.001	0.19	1.133	0.001	0.28
3M4GRL		1.137	0.005	1.77	1.137	0.005	1.38
3U29XV		1.128	-0.004	-1.28	1.129	-0.003	-0.74
3VZCUQ		1.132	0.000	0.07	1.133	0.001	0.41
4GBUER		1.136	0.004	1.44	1.136	0.004	1.28
72VHVX		1.135	0.003	1.09	1.136	0.004	1.24
73MQNY		1.130	-0.002	-0.75	1.132	0.000	0.09
7MNN4L		1.133	0.001	0.27	1.135	0.003	0.81
7QU6H4		1.133	0.002	0.52	1.134	0.002	0.64
87JGNJ		1.133	0.001	0.45	1.135	0.003	0.92
8DG8AU		1.130	-0.001	-0.50	1.129	-0.003	-0.74
8ECRZZ		1.133	0.001	0.47	1.131	0.000	-0.09
8R3LDT		1.128	-0.003	-1.11	1.127	-0.005	-1.40
8TVBVN		1.134	0.002	0.75	1.134	0.002	0.66
99KXHT	X	1.118	-0.014	-4.59	1.116	-0.016	-4.53
9PPCVF		1.128	-0.004	-1.25	1.125	-0.007	-2.06
9TRBBE		1.134	0.002	0.59	1.134	0.002	0.52
9ZQRPR		1.128	-0.004	-1.36	1.127	-0.004	-1.24
ARTL6N		1.135	0.003	1.09	1.135	0.003	0.81
BD6YC3		1.131	0.000	-0.11	1.131	-0.001	-0.27
CCEZWJ		1.137	0.005	1.59	1.137	0.005	1.38
CK7B9Y		1.131	-0.001	-0.25	1.129	-0.003	-0.77
CL3NVR		1.132	0.000	-0.08	1.132	0.000	-0.05
CPXMYP	*	1.130	-0.002	-0.58	1.125	-0.007	-1.91
DEB7QE	X	1.136	0.004	1.27	1.145	0.014	3.91
DF34XL		1.131	-0.001	-0.23	1.134	0.002	0.55
DLXVBP		1.132	0.000	-0.03	1.134	0.002	0.69
E3ZQLV		1.134	0.002	0.75	1.133	0.001	0.38
EX7VJM		1.129	-0.002	-0.80	1.132	0.000	0.13
FGCQQK		1.134	0.002	0.59	1.132	0.000	-0.05



Rubber Interlaboratory Testing Program

Analysis 621

Report #213

3rd Qtr 2022

Density

WebCode	Data Flag	Sample C21-C22			Sample C23-C24		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
G47U8H		1.128	-0.004	-1.25	1.129	-0.003	-0.91
GGRELJ		1.131	-0.001	-0.31	1.133	0.001	0.36
H36LBH		1.135	0.003	1.09	1.134	0.002	0.66
H3NM2R	X	1.127	-0.005	-1.66	1.132	0.001	0.15
HMPKFD		1.130	-0.002	-0.58	1.133	0.001	0.38
J7KD2B		1.131	-0.001	-0.25	1.131	-0.001	-0.19
JFA3ZK		1.136	0.004	1.44	1.136	0.005	1.32
JM8RJA	X	1.113	-0.019	-6.24	1.115	-0.017	-4.77
JN2F36		1.128	-0.004	-1.41	1.128	-0.004	-1.05
JNZPRF		1.132	0.001	0.22	1.130	-0.001	-0.41
KNXGXM		1.128	-0.004	-1.25	1.129	-0.003	-0.77
L63YTR	X	1.116	-0.016	-5.41	1.115	-0.017	-4.77
L7XM8G		1.131	-0.001	-0.25	1.133	0.001	0.38
LAWX8M	X	1.109	-0.023	-7.57	1.127	-0.005	-1.48
LRBCKC	X	1.118	-0.014	-4.58	1.122	-0.010	-2.77
LW4ELQ		1.137	0.005	1.75	1.137	0.005	1.52
M3BM7R		1.133	0.001	0.29	1.133	0.001	0.32
MFCZK4		1.133	0.002	0.57	1.134	0.002	0.66
MX24AK		1.131	-0.001	-0.35	1.131	-0.001	-0.17
NMUTCT	*	1.134	0.002	0.59	1.129	-0.003	-0.77
NVM7A8		1.133	0.001	0.30	1.133	0.001	0.32
NVQJ2B	X	1.122	-0.010	-3.41	1.127	-0.005	-1.34
P2RFXF		1.132	0.000	0.09	1.134	0.002	0.66
PXNQAD		1.137	0.005	1.59	1.136	0.004	1.24
PYXREK		1.133	0.001	0.27	1.133	0.001	0.38
Q8Q7XW		1.131	0.000	-0.15	1.133	0.001	0.39
QZQRAA		1.133	0.002	0.57	1.134	0.002	0.54
RFYZQ4		1.132	0.000	0.04	1.132	0.001	0.18
RNVVR9		1.135	0.003	0.94	1.134	0.003	0.78
UEXZMA		1.136	0.004	1.42	1.135	0.003	0.95
V8W642		1.132	0.000	-0.08	1.135	0.003	0.81
VNHUT3	*	1.123	-0.009	-2.88	1.124	-0.008	-2.16
VVGDE7		1.131	-0.001	-0.25	1.131	-0.001	-0.34
WC3ZGA		1.131	0.000	-0.11	1.130	-0.002	-0.44
WU46KC	*	1.124	-0.008	-2.58	1.122	-0.010	-2.91
WVGLYB	X	1.096	-0.036	-11.90	1.098	-0.034	-9.78
WVXT38	X	1.130	-0.002	-0.58	1.120	-0.012	-3.34



Rubber Interlaboratory Testing Program

Analysis 621

Report #213

3rd Qtr 2022

Density

WebCode	Data Flag	Sample C21-C22			Sample C23-C24		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
X48J4P		1.126	-0.006	-1.94	1.123	-0.009	-2.47
XAU6FH	*	1.126	-0.006	-1.91	1.122	-0.010	-2.77
YY7ZGG		1.128	-0.004	-1.35	1.128	-0.003	-0.94
ZD3EC6		1.135	0.003	1.09	1.134	0.002	0.52
ZK6GMW		1.132	0.000	0.00	1.133	0.001	0.34
ZMURC6		1.130	-0.002	-0.75	1.130	-0.002	-0.62

Summary Statistics	
Grand Means	
1.1317 g/cm^3 (Mg/m^3)	1.1317 g/cm^3 (Mg/m^3)
Snd Dev Btwn Labs	
0.0030 g/cm^3 (Mg/m^3)	0.0035 g/cm^3 (Mg/m^3)
Statistics based on 70 of 81 reporting participants	

Samples C21-C22: Polyisoprene compound, batch #1 & C23-C24: Polyisoprene compound, batch #2

Comments on Assigned Data Flags for Test #621

2XQBAB (X) - Data for all samples are low. Possible Systematic Error.

99KXHT (X) - Data for all samples are low. Possible Systematic Error.

DEB7QE (X) - Data for sample group C23-C24 are high. Inconsistent within the determinations of sample group C23-C24.

H3NM2R (X) - Inconsistent in testing between samples.

JM8RJA (X) - Data for all samples are low. Possible Systematic Error.

L63YTR (X) - Data for all samples are low. Possible Systematic Error. Inconsistent within the determinations of sample group C21-C22.

LAWX8M (X) - Data for sample group C21-C22 are low. Inconsistent within the determinations of sample group C23-C24.

LRBCKC (X) - Data for all samples are low. Possible Systematic Error. Inconsistent within the determinations of sample group C21-C22.

NVQJ2B (X) - Data for sample group C21-C22 are low. Inconsistent in testing between samples.

WVGLYB (X) - Data for all Samples are low.

WVXT38 (X) - Data for sample group C23-C24 are low.



Rubber Interlaboratory Testing Program

Analysis 621


Density

Report #213

3rd Qtr 2022

Grand Mean Sample C21-C22 = 1.1317 g/cm³
(Mg/m³)

Grand Mean Sample C23-C24 = 1.1317 g/cm³
(Mg/m³)





Rubber Interlaboratory Testing Program

Analysis 625

Report #213

3rd Qtr 2022

Hardness (Shore D/Type D)

WebCode	Data Flag	Sample HC21-HC22			Sample HC23-HC24			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
22PPXZ	X	67.95	14.80	4.67	55.05	-11.87	-4.44	HH
4GBUER		53.50	0.35	0.11	69.25	2.33	0.87	HH
7QU6H4		53.95	0.80	0.25	67.40	0.48	0.18	BT
92JTKG	X	37.55	-15.60	-4.92	65.10	-1.82	-0.68	BT
9TRBBE		52.00	-1.15	-0.36	66.50	-0.42	-0.16	BT
AYA3TR		54.00	0.85	0.27	67.00	0.08	0.03	XX
BBLK93		57.00	3.85	1.21	69.75	2.83	1.06	BT
CK7B9Y		49.00	-4.15	-1.31	63.95	-2.97	-1.11	BT
CL3NVR		52.40	-0.75	-0.24	66.85	-0.07	-0.03	BT
CMXCC3		52.15	-1.00	-0.32	66.50	-0.42	-0.16	BT
DF4U9B		48.05	-5.10	-1.61	62.20	-4.72	-1.76	BT
DLXVBP		50.45	-2.70	-0.85	65.05	-1.87	-0.70	BT
DUQ7KK		54.65	1.50	0.47	65.85	-1.07	-0.40	BT
EHAJ8D		48.30	-4.85	-1.53	62.25	-4.67	-1.74	BT
G2X2VV	X	45.50	-7.65	-2.41	51.50	-15.42	-5.76	HH
HEVFMC		55.70	2.55	0.80	68.95	2.03	0.76	BT
JM8RJA	X	93.20	40.05	12.63	93.70	26.78	10.01	BT
KNX8DH		57.75	4.60	1.45	69.65	2.73	1.02	BT
L63YTR		56.50	3.35	1.06	70.00	3.08	1.15	HH
MFCZK4		49.20	-3.95	-1.25	64.50	-2.42	-0.90	XX
PH8T8X		54.00	0.85	0.27	68.65	1.73	0.65	HH
PWRB2M		54.00	0.85	0.27	68.50	1.58	0.59	BT
RKRCA8		50.50	-2.65	-0.84	65.50	-1.42	-0.53	XX
RNVVR9		56.00	2.85	0.90	70.50	3.58	1.34	HH
T6X8F4		56.50	3.35	1.06	69.00	2.08	0.78	HH
TTKQ97		57.00	3.85	1.21	70.50	3.58	1.34	BT
VQQ349		58.10	4.95	1.56	70.25	3.33	1.24	HH
WVGLYB		53.00	-0.15	-0.05	65.00	-1.92	-0.72	HH
WVXT38		50.00	-3.15	-0.99	63.50	-3.42	-1.28	BT
ZRNP3G		48.20	-4.95	-1.56	62.85	-4.07	-1.52	BT

Grand Means		Summary Statistics	
		53.150	Type D
Stnd Dev Btwn Labs		3.172	Type D
Statistics based on 26 of 30 reporting participants			



Rubber Interlaboratory Testing Program
Analysis 625
Hardness (Shore D/Type D)

Report #213

3rd Qtr 2022

Samples HC21-HC22: Hardness Disc, batch #1 & HC23-HC24: Hardness Disc, batch #2

Comments on Assigned Data Flags for Test #625

22PPXZ (X) - Data for sample group HC21-HC22 are high and data for sample group HC23-HC24 are low.
Inconsistent in testing between sample groups. Inconsistent within the determinations of sample group HC23-HC24.

92JTKG (X) - Data for sample group HC21-HC22 are low.

G2X2W (X) - Data for sample group HC23-HC24 are low. Inconsistent within the determinations of sample group HC23-HC24.

JM8RJA (X) - Extreme Data.

Key to Instrument Codes Reported by Participants

BT Benchtop **HH** Handheld

XX Specify Benchtop or Handheld Instrument



Rubber Interlaboratory Testing Program

Report #213


Analysis 625

3rd Qtr 2022

Hardness (Shore D/Type D)

Grand Mean Sample HC21-HC22 = 53.150 Type D

Grand Mean Sample HC23-HC24 = 66.919 Type D





Rubber Interlaboratory Testing Program

Analysis 630

Report #213

3rd Qtr 2022

Tensile Strength: Precured vs. Lab-Cured Samples (psi)

WebCode	Data Flag	Sample C21-C22			Sample L21-L22		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2KZLB6		3,208.0	-115.0	-0.69	2,863.5	-21.3	-0.08
2X9AJ2		3,535.0	212.0	1.27	2,740.0	-144.8	-0.53
2XQBAB		3,308.1	-14.9	-0.09	2,823.2	-61.6	-0.23
38PD7R		3,319.0	-4.0	-0.02	2,921.0	36.2	0.13
3J3TUC		3,408.5	85.5	0.51	3,058.0	173.2	0.64
3VZCUQ		3,569.5	246.5	1.47	3,231.5	346.7	1.27
72VHVX	*	3,440.0	117.0	0.70	2,085.0	-799.8	-2.94
7QU6H4		3,188.1	-134.9	-0.81	2,952.4	67.6	0.25
8ECRZZ		3,157.5	-165.5	-0.99	2,852.2	-32.6	-0.12
8R3LDT		3,391.1	68.1	0.41	3,005.4	120.6	0.44
ARTL6N		3,334.4	11.5	0.07	2,955.2	70.4	0.26
BD6YC3		3,334.5	11.5	0.07	2,922.0	37.2	0.14
CCEZWJ		3,380.0	57.0	0.34	2,865.0	-19.8	-0.07
CL3NVR		3,118.3	-204.6	-1.22	2,821.0	-63.8	-0.23
CN7L4Y		3,244.2	-78.8	-0.47	2,897.6	12.8	0.05
DEB7QE		3,142.0	-181.0	-1.08	3,044.5	159.7	0.59
DLXVBP		3,231.5	-91.5	-0.55	3,172.5	287.7	1.06
EX7VJM	*	3,784.1	461.1	2.75	3,358.4	473.6	1.74
FT78FL	X	4,142.2	819.3	4.89	2,996.1	111.3	0.41
G47U8H		3,451.0	128.0	0.76	2,709.5	-175.3	-0.64
H3NM2R		3,487.3	164.3	0.98	2,883.9	-0.9	0.00
HMPKFD		3,343.1	20.2	0.12	2,908.0	23.2	0.09
JM8RJA		3,289.0	-34.0	-0.20	3,085.5	200.7	0.74
LH43N7		3,257.4	-65.6	-0.39	3,077.4	192.6	0.71
LW4ELQ		3,325.7	2.8	0.02	2,343.1	-541.7	-1.99
M3BM7R		3,406.6	83.6	0.50	3,236.4	351.6	1.29
MX24AK		3,420.8	97.8	0.58	3,137.8	253.0	0.93
NVM7A8		3,152.4	-170.6	-1.02	3,067.9	183.1	0.67
PYXREK		3,378.8	55.8	0.33	2,778.0	-106.8	-0.39
W49VN9		3,129.2	-193.7	-1.16	2,724.6	-160.2	-0.59
WC3ZGA		3,091.0	-232.0	-1.39	3,014.5	129.7	0.48
WU46KC		2,910.0	-413.0	-2.47	2,575.0	-309.8	-1.14
WVGLYB		3,586.0	263.0	1.57	3,107.0	222.2	0.82
X48J4P		3,324.6	1.7	0.01	2,300.4	-584.4	-2.15
XAU6FH		3,334.1	11.1	0.07	2,566.1	-318.7	-1.17



Rubber Interlaboratory Testing Program

Analysis 630

Report #213

3rd Qtr 2022

Tensile Strength: Precured vs. Lab-Cured Samples (psi)

Summary Statistics

Grand Means

3,322.96 psi

2,884.80 psi

Stnd Dev Btwn Labs

167.42 psi

272.23 psi

Statistics based on 34 of 35 reporting participants

Summary Statistics in SI Units

Grand Means

22.911 MPa

19.890 MPa

Stnd Dev Btwn Labs

1.154 MPa

1.880 MPa

Statistics based on 34 of 35 reporting participants

Samples C21-C22: Polyisoprene compound, batch #1 & L21-L22: Polyisoprene compound, batch #1

Comments on Assigned Data Flags for Test #630

FT78FL (X) - Data for sample group C21-C22 are high.



Rubber Interlaboratory Testing Program

Analysis 630


Report #213

3rd Qtr 2022

Tensile Strength: Precured vs. Lab-Cured Samples (psi)

Grand Mean Sample C21-C22 = 3,322.96 psi

Grand Mean Sample L21-L22 = 2,884.80 psi





Rubber Interlaboratory Testing Program

Analysis 631

Report #213

3rd Qtr 2022

Ultimate Elongation: Precured vs. Lab-Cured Samples (percent)

WebCode	Data Flag	Sample C21-C22			Sample L21-L22		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2KZLB6		627.5	-22.6	-0.80	567.0	-26.7	-0.87
2X9AJ2		692.5	42.4	1.51	666.0	72.3	2.36
2XQBAB		631.2	-18.9	-0.67	589.1	-4.6	-0.15
38PD7R		651.5	1.4	0.05	546.5	-47.2	-1.54
3J3TUC		676.0	25.9	0.92	594.0	0.3	0.01
3VZCUQ		685.0	34.9	1.24	632.0	38.3	1.25
72VHVX		624.0	-26.1	-0.93	580.5	-13.2	-0.43
7QU6H4		639.0	-11.1	-0.40	573.0	-20.7	-0.67
8ECRZZ		669.0	18.9	0.67	617.5	23.8	0.78
8R3LDT		603.6	-46.5	-1.65	548.1	-45.6	-1.49
ARTL6N		709.5	59.4	2.11	624.5	30.8	1.00
BD6YC3		625.0	-25.1	-0.89	584.5	-9.2	-0.30
CCEZWJ		636.5	-13.6	-0.48	585.0	-8.7	-0.28
CL3NVR		656.1	6.0	0.21	590.4	-3.3	-0.11
CN7L4Y		642.5	-7.6	-0.27	583.5	-10.2	-0.33
DEB7QE		661.0	10.9	0.39	599.5	5.8	0.19
DLXVBP		632.0	-18.1	-0.64	600.5	6.8	0.22
EX7VJM		680.6	30.5	1.08	629.4	35.7	1.16
FT78FL		646.2	-3.9	-0.14	608.6	14.9	0.48
G47U8H		651.5	1.4	0.05	580.5	-13.2	-0.43
H3NM2R		648.0	-2.1	-0.08	593.0	-0.7	-0.02
HMPKFD		664.0	13.9	0.49	593.0	-0.7	-0.02
JM8RJA		661.5	11.4	0.40	604.5	10.8	0.35
LH43N7		624.1	-26.1	-0.93	590.3	-3.5	-0.11
LW4ELQ		669.8	19.7	0.70	576.9	-16.8	-0.55
M3BM7R		632.0	-18.1	-0.64	583.0	-10.7	-0.35
MX24AK		669.1	19.0	0.67	615.5	21.8	0.71
NVM7A8		666.5	16.4	0.58	639.5	45.8	1.49
PYXREK		673.5	23.4	0.83	612.5	18.8	0.61
W49VN9		637.5	-12.6	-0.45	601.5	7.8	0.25
WC3ZGA	*	575.0	-75.1	-2.67	541.5	-52.2	-1.70
WU46KC	*	595.5	-54.6	-1.94	500.0	-93.7	-3.05
WVGLYB		648.5	-1.6	-0.06	595.0	1.3	0.04
X48J4P		687.3	37.1	1.32	611.2	17.5	0.57
XAU6FH		662.3	12.1	0.43	622.2	28.5	0.93



Rubber Interlaboratory Testing Program

Analysis 631

Report #213

3rd Qtr 2022

Ultimate Elongation: Precured vs. Lab-Cured Samples (percent)

Summary Statistics

Grand Means

650.14 percent

593.70 percent

Stnd Dev Btwn Labs

28.14 percent

30.69 percent

Statistics based on 35 of 35 reporting participants

Samples C21-C22: Polyisoprene compound, batch #1 & L21-L22: Polyisoprene compound, batch #1



Rubber Interlaboratory Testing Program

Analysis 631


Report #213

3rd Qtr 2022

Ultimate Elongation: Precured vs. Lab-Cured Samples (percent)

Grand Mean Sample C21-C22 = 650.14 percent

Grand Mean Sample L21-L22 = 593.70 percent





Rubber Interlaboratory Testing Program

Analysis 632

Report #213

3rd Qtr 2022

Stress at 300% Elongation: Precured vs. Lab-Cured Samples (psi)

WebCode	Data Flag	Sample C21-C22			Sample L21-L22		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2KZLB6		845.0	14.7	0.19	894.5	-11.0	-0.10
2X9AJ2		774.1	-56.2	-0.72	788.5	-117.0	-1.09
2XQBAB		877.6	47.3	0.61	887.9	-17.6	-0.16
38PD7R		802.5	-27.8	-0.36	974.0	68.5	0.64
3J3TUC		760.5	-69.8	-0.90	919.5	14.0	0.13
3VZCUQ		784.5	-45.8	-0.59	889.5	-16.0	-0.15
72VHVX	*	956.3	126.0	1.63	634.1	-271.3	-2.54
7QU6H4		787.3	-43.0	-0.55	962.2	56.7	0.53
8ECRZZ		728.8	-101.5	-1.31	847.0	-58.4	-0.55
8R3LDT		990.2	159.9	2.06	1,098.4	193.0	1.80
ARTL6N		780.3	-50.0	-0.64	876.8	-28.7	-0.27
BD6YC3		870.0	39.7	0.51	900.0	-5.5	-0.05
CCEZWJ		853.0	22.7	0.29	912.0	6.5	0.06
CL3NVR		794.1	-36.2	-0.47	876.8	-28.7	-0.27
CN7L4Y		819.8	-10.5	-0.14	937.0	31.5	0.29
DEB7QE		739.5	-90.8	-1.17	929.0	23.5	0.22
DLXVBP		827.0	-3.3	-0.04	940.5	35.0	0.33
EX7VJM		681.0	-149.3	-1.93	1,005.8	100.4	0.94
FT78FL		969.4	139.1	1.79	817.7	-87.7	-0.82
G47U8H		792.5	-37.8	-0.49	819.5	-86.0	-0.80
H3NM2R		860.7	30.4	0.39	857.9	-47.6	-0.45
HMPKFD		775.2	-55.1	-0.71	916.6	11.2	0.10
JM8RJA		768.0	-62.3	-0.80	926.0	20.5	0.19
LH43N7		981.1	150.8	1.95	1,040.8	135.3	1.27
LW4ELQ		787.6	-42.7	-0.55	810.8	-94.7	-0.89
M3BM7R		910.5	80.2	1.04	1,050.5	145.0	1.36
MX24AK		787.5	-42.8	-0.55	937.3	31.9	0.30
NVM7A8		751.0	-79.3	-1.02	838.5	-67.0	-0.63
PYXREK		803.7	-26.6	-0.34	807.5	-98.0	-0.92
W49VN9		823.1	-7.2	-0.09	803.5	-101.9	-0.95
WC3ZGA		980.0	149.7	1.93	1,023.5	118.0	1.10
WU46KC	*	862.5	32.2	0.42	1,190.0	284.5	2.66
WVGLYB		882.0	51.7	0.67	958.5	53.0	0.50
X48J4P	M	724.8	-105.5	-1.36	687.0	-218.4	-2.04
XAU6FH		823.7	-6.6	-0.08	713.5	-191.9	-1.79



Rubber Interlaboratory Testing Program

Analysis 632

Report #213

3rd Qtr 2022

Stress at 300% Elongation: Precured vs. Lab-Cured Samples (psi)

Grand Means

830.29 psi

905.45 psi

Stnd Dev Btwn Labs

77.49 psi

106.97 psi

Statistics based on 34 of 35 reporting participants

Summary Statistics in SI Units

Grand Means

5.7246 MPa

6.2400 MPa

Stnd Dev Btwn Labs

0.5343 MPa

0.7400 MPa

Statistics based on 34 of 35 reporting participants

Samples C21-C22: Polyisoprene compound, batch #1 & L21-L22: Polyisoprene compound, batch #1

Comments on Assigned Data Flags for Test #632

X48J4P (M) - Missing data for sample L21.



Rubber Interlaboratory Testing Program

Analysis 632


Report #213

3rd Qtr 2022

Stress at 300% Elongation: Precured vs. Lab-Cured Samples (psi)

Grand Mean Sample C21-C22 = 830.29 psi

Grand Mean Sample L21-L22 = 905.45 psi





Rubber Interlaboratory Testing Program

Analysis 633

Report #213

3rd Qtr 2022

Stress at 100% Elongation: Precured vs. Lab-Cured Samples (psi)

WebCode	Data Flag	Sample C21-C22			Sample L21-L22		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2KZLB6		194.5	7.7	0.53	205.5	0.5	0.02
2X9AJ2		207.7	20.9	1.43	212.2	7.2	0.31
2XQBAB		197.5	10.7	0.73	209.0	4.0	0.17
38PD7R		187.5	0.7	0.04	215.0	10.0	0.44
3J3TUC		177.5	-9.3	-0.64	208.5	3.5	0.15
3VZCUQ		174.5	-12.3	-0.85	202.5	-2.5	-0.11
72VHVX	X	217.9	31.1	2.14	305.7	100.7	4.37
7QU6H4		174.7	-12.1	-0.83	213.8	8.8	0.38
8ECRZZ		185.6	-1.2	-0.08	222.6	17.7	0.77
8R3LDT		200.7	13.9	0.95	229.2	24.2	1.05
ARTL6N		175.5	-11.3	-0.78	192.2	-12.8	-0.56
BD6YC3		190.0	3.2	0.22	184.5	-20.5	-0.89
CCEZWJ		188.0	1.2	0.08	198.5	-6.5	-0.28
CL3NVR		175.5	-11.3	-0.78	195.1	-9.9	-0.43
CN7L4Y		182.3	-4.5	-0.31	209.1	4.1	0.18
DEB7QE		171.0	-15.8	-1.09	203.5	-1.5	-0.06
DLXVBP		177.5	-9.3	-0.64	206.5	1.5	0.07
EX7VJM		201.4	14.5	1.00	220.6	15.6	0.68
FT78FL	*	207.7	20.8	1.43	174.5	-30.5	-1.32
G47U8H		175.5	-11.3	-0.78	182.0	-23.0	-1.00
H3NM2R		189.6	2.7	0.19	185.8	-19.2	-0.83
HMPKFD		179.1	-7.7	-0.53	211.8	6.8	0.29
JM8RJA		174.0	-12.8	-0.88	209.5	4.5	0.20
LH43N7		222.3	35.4	2.43	239.6	34.6	1.50
LW4ELQ		173.3	-13.5	-0.93	166.8	-38.2	-1.66
M3BM7R		197.5	10.7	0.73	230.5	25.5	1.11
MX24AK		184.7	-2.1	-0.15	221.7	16.7	0.73
NVM7A8		176.2	-10.7	-0.73	200.5	-4.5	-0.19
PYXREK		178.6	-8.3	-0.57	176.1	-28.9	-1.26
W49VN9		194.4	7.5	0.52	198.7	-6.3	-0.27
WC3ZGA	*	227.0	40.2	2.76	237.0	32.0	1.39
WU46KC	*	188.5	1.7	0.11	271.5	66.5	2.89
WVGLYB		187.5	0.7	0.04	205.0	0.0	0.00
X48J4P		163.3	-23.6	-1.62	152.3	-52.7	-2.29
XAU6FH		172.4	-14.5	-0.99	177.7	-27.3	-1.19



Rubber Interlaboratory Testing Program

Analysis 633

Report #213

3rd Qtr 2022

Stress at 100% Elongation: Precured vs. Lab-Cured Samples (psi)

Grand Means

186.85 psi

204.97 psi

Stnd Dev Btwn Labs

14.56 psi

23.03 psi

Statistics based on 34 of 35 reporting participants

Summary Statistics in SI Units

Grand Means

1.2883 MPa

1.4100 MPa

Stnd Dev Btwn Labs

0.1004 MPa

0.1600 MPa

Statistics based on 34 of 35 reporting participants

Samples C21-C22: Polyisoprene compound, batch #1 & L21-L22: Polyisoprene compound, batch #1

Comments on Assigned Data Flags for Test #633

72VHVX (X) - Data for sample group L21-L22 are high. Inconsistent within the determinations of sample group L21-L22.



Rubber Interlaboratory Testing Program

Analysis 633


Report #213

3rd Qtr 2022

Stress at 100% Elongation: Precured vs. Lab-Cured Samples (psi)

Grand Mean Sample C21-C22 = 186.85 psi

Grand Mean Sample L21-L22 = 204.97 psi





Rubber Interlaboratory Testing Program

Analysis 635

Report #213

3rd Qtr 2022

Compression Set Method B

WebCode	Data Flag	Sample P21			Sample P22		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2JUWC2		28.10	-1.26	-0.43	27.97	-1.20	-0.40
2ZWXME		27.77	-1.59	-0.54	26.29	-2.87	-0.96
32NYH6		26.67	-2.69	-0.92	27.00	-2.16	-0.72
3BT3UU		24.00	-5.36	-1.83	24.00	-5.16	-1.73
3J3TUC		29.67	0.31	0.11	29.00	-0.16	-0.06
7QU6H4		32.59	3.23	1.10	31.90	2.74	0.91
8DG8AU		26.50	-2.86	-0.98	26.03	-3.13	-1.05
8R3LDT		25.43	-3.93	-1.34	26.12	-3.05	-1.02
8TVBVN		29.00	-0.36	-0.12	29.33	0.17	0.06
99KXHT		32.67	3.31	1.13	33.67	4.50	1.51
9NVNDK		28.13	-1.23	-0.42	28.43	-0.73	-0.24
9TRBBE		27.00	-2.36	-0.81	26.00	-3.16	-1.06
9VWZB3		30.35	0.99	0.34	30.50	1.34	0.45
9ZQRPR		25.33	-4.03	-1.37	27.00	-2.16	-0.72
BD6YC3		31.70	2.34	0.80	31.70	2.54	0.85
CCEZWJ		31.33	1.97	0.67	30.33	1.17	0.39
DEB7QE		25.60	-3.76	-1.28	25.17	-4.00	-1.34
DLXVBP		30.67	1.31	0.45	29.67	0.50	0.17
EHP3TV		27.23	-2.13	-0.73	25.57	-3.60	-1.20
G47U8H		31.00	1.64	0.56	31.67	2.50	0.84
GGRELJ		26.00	-3.36	-1.15	26.33	-2.83	-0.95
H36LBH		28.33	-1.03	-0.35	28.67	-0.50	-0.17
H3NM2R		34.37	5.01	1.71	34.80	5.64	1.88
J8UK44		33.80	4.44	1.52	33.58	4.41	1.47
JM8RJA		28.33	-1.03	-0.35	28.00	-1.16	-0.39
LAWX8M		29.67	0.31	0.11	28.33	-0.83	-0.28
LH43N7	X	34.83	5.47	1.87	30.60	1.44	0.48
M3BM7R		29.45	0.09	0.03	31.26	2.09	0.70
MFCZK4		29.03	-0.33	-0.11	29.57	0.40	0.13
MX24AK		30.97	1.61	0.55	29.77	0.60	0.20
PYXREK		33.00	3.64	1.24	32.33	3.17	1.06
Q8Q7XW	*	32.41	3.06	1.04	29.85	0.69	0.23
QJ4LLG		31.67	2.31	0.79	31.67	2.50	0.84
QZQRAA		25.33	-4.03	-1.37	25.00	-4.16	-1.39
RFYZQ4		34.46	5.10	1.74	34.50	5.34	1.78
RNVVR9		34.43	5.07	1.73	35.23	6.07	2.03
UEXZMA		26.13	-3.23	-1.10	26.63	-2.53	-0.85
V8W642		28.67	-0.69	-0.24	28.33	-0.83	-0.28



Rubber Interlaboratory Testing Program

Analysis 635

Report #213

3rd Qtr 2022

Compression Set Method B

WebCode	Data Flag	Sample P21			Sample P22		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
WVGLYB		33.23	3.87	1.32	32.37	3.20	1.07
X3DWPZ		27.49	-1.87	-0.64	27.80	-1.36	-0.46
ZVPQA6		26.83	-2.53	-0.86	25.23	-3.93	-1.31

Summary Statistics	
Grand Means	
29.359 % Compression	29.165 % Compression
Stnd Dev Btwn Labs	
2.929 % Compression	2.990 % Compression
Statistics based on 40 of 41 reporting participants	

Samples P21: EPDM compound, batch #1 & P22: EPDM compound, batch #1

Comments on Assigned Data Flags for Test #635

LH43N7 (X) - Inconsistent in testing between samples.



Rubber Interlaboratory Testing Program

Report #213


Analysis 635

3rd Qtr 2022

Compression Set Method B

Grand Mean Sample P21 = 29.359 % Compression

Grand Mean Sample P22 = 29.165 % Compression





Rubber Interlaboratory Testing Program

Analysis 640

Report #213

3rd Qtr 2022

O-Ring Tensile Strength at Break (psi)

WebCode	Data Flag	Sample RC21			Sample RC22		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2ZWXME		2,461.6	45.2	0.96	2,459.8	31.3	0.64
7QU6H4		2,482.6	66.2	1.41	2,491.0	62.5	1.27
87JGNJ		2,442.6	26.2	0.56	2,471.4	42.9	0.87
8BVE8Y		2,434.0	17.6	0.38	2,394.9	-33.6	-0.68
9ZQRPR		2,484.2	67.8	1.45	2,490.0	61.5	1.25
BD6YC3		2,415.2	-1.2	-0.03	2,323.8	-104.7	-2.13
DLXVBP		2,337.8	-78.6	-1.68	2,409.4	-19.1	-0.39
GGRELJ		2,378.2	-38.2	-0.82	2,455.0	26.5	0.54
H3NM2R		2,354.6	-61.8	-1.32	2,392.0	-36.5	-0.74
JGXMGN		2,357.4	-59.0	-1.26	2,391.8	-36.7	-0.74
P2RFXF		2,437.4	21.0	0.45	2,419.2	-9.3	-0.19
PYXREK		2,438.4	22.0	0.47	2,488.1	59.6	1.21
QZQRAA		2,415.6	-0.8	-0.02	2,422.6	-5.9	-0.12
V8W642		2,390.2	-26.2	-0.56	2,389.6	-38.9	-0.79

Grand Means		Summary Statistics	
2,416.42	psi	2,428.47	psi
Stnd Dev Btwn Labs		46.88	psi
Statistics based on 14 of 14 reporting participants			

Samples RC21: Nitrile O-Ring & RC22: Nitrile O-Ring



Rubber Interlaboratory Testing Program

Analysis 640


Report #213

3rd Qtr 2022

O-Ring Tensile Strength at Break (psi)

Grand Mean Sample RC21 = 2,416.42 psi

Grand Mean Sample RC22 = 2,428.47 psi



If fewer than 20 laboratories are included in an analysis, a control ellipse will not be drawn on the two-sample plot.



Rubber Interlaboratory Testing Program

Analysis 641

Report #213

3rd Qtr 2022

O-Ring Ultimate Elongation (%)

WebCode	Data Flag	Sample RC21			Sample RC22		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2ZWXME		416.6	3.8	0.16	416.6	-0.3	-0.01
7QU6H4		433.4	20.6	0.86	445.2	28.3	1.16
87JGNJ		413.0	0.2	0.01	422.2	5.3	0.22
8BVE8Y		416.0	3.2	0.13	408.2	-8.7	-0.36
9ZQRPR		430.8	18.0	0.75	418.6	1.7	0.07
BD6YC3		426.8	14.0	0.58	403.4	-13.5	-0.55
DLXVBP		439.4	26.6	1.11	460.2	43.3	1.77
GGRELJ		355.6	-57.2	-2.38	372.6	-44.3	-1.81
H3NM2R		408.2	-4.6	-0.19	423.2	6.3	0.26
JGXMGN		410.6	-2.2	-0.09	423.0	6.1	0.25
P2RFXF		429.0	16.2	0.67	424.8	7.9	0.32
PYXREK		420.1	7.3	0.30	435.0	18.1	0.74
QZQRAA		365.6	-47.2	-1.96	368.4	-48.5	-1.99
V8W642		413.8	1.0	0.04	414.8	-2.1	-0.08

Grand Means		Summary Statistics	
		412.78 percent	416.87 percent
Stnd Dev Btwn Labs		24.05 percent	24.42 percent
Statistics based on 14 of 14 reporting participants			

Samples RC21: Nitrile O-Ring & RC22: Nitrile O-Ring



Rubber Interlaboratory Testing Program

Analysis 641


Report #213

3rd Qtr 2022

O-Ring Ultimate Elongation (%)

Grand Mean Sample RC21 = 412.78 percent

Grand Mean Sample RC22 = 416.87 percent



If fewer than 20 laboratories are included in an analysis, a control ellipse will not be drawn on the two-sample plot.



Rubber Interlaboratory Testing Program

Analysis 642

Report #213

3rd Qtr 2022

O-Ring Stress at 100% Elongation (psi)

WebCode	Data Flag	Sample RC21			Sample RC22		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2ZWXME		457.6	-13.5	-0.18	456.4	-16.2	-0.22
7QU6H4		475.2	4.1	0.06	470.6	-2.0	-0.03
87JGNJ		476.6	5.5	0.07	480.6	8.0	0.11
8BVE8Y		548.8	77.7	1.05	526.5	53.9	0.72
9ZQRPR	X	3,074.4	2,603.3	35.04	3,146.4	2,673.8	35.56
BD6YC3		565.6	94.5	1.27	582.4	109.8	1.46
DLXVBP		300.6	-170.5	-2.30	301.4	-171.2	-2.28
GGRELJ		558.6	87.5	1.18	568.6	96.0	1.28
H3NM2R		384.7	-86.4	-1.16	384.4	-88.1	-1.17
JGXMGN		442.2	-28.9	-0.39	440.4	-32.2	-0.43
P2RFXF		439.2	-31.9	-0.43	459.0	-13.6	-0.18
PYXREK		467.2	-3.9	-0.05	468.7	-3.9	-0.05
QZQRAA		541.4	70.3	0.95	542.6	70.0	0.93
V8W642		466.6	-4.5	-0.06	462.0	-10.6	-0.14

Grand Means		Summary Statistics	
471.10	psi	472.58	psi
Stnd Dev Btwn Labs		74.29	psi
75.19 psi Statistics based on 13 of 14 reporting participants			

Samples RC21: Nitrile O-Ring & RC22: Nitrile O-Ring

Comments on Assigned Data Flags for Test #642

9ZQRPR (X) - Extreme data.



Rubber Interlaboratory Testing Program

Analysis 642


O-Ring Stress at 100% Elongation (psi)

Report #213

3rd Qtr 2022

Grand Mean Sample **RC21** = 471.10 psi

Grand Mean Sample **RC22** = 472.58 psi



If fewer than 20 laboratories are included in an analysis, a control ellipse will not be drawn on the two-sample plot.



Rubber Interlaboratory Testing Program

Analysis 647

Report #213

3rd Qtr 2022

O-Ring Hardness (Shore A)

WebCode	Data Flag	Sample RC21			Sample RC22		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2ZWXME		64.40	-3.52	-1.36	64.80	-3.40	-1.33
73MQNY		70.40	2.48	0.96	70.80	2.60	1.02
7QU6H4		69.12	1.20	0.47	69.78	1.58	0.62
87JGNJ		68.96	1.04	0.40	69.04	0.84	0.33
8BVE8Y		66.00	-1.92	-0.74	66.00	-2.20	-0.86
97UP4X		61.84	-6.08	-2.36	61.60	-6.60	-2.58
9ZQRPR		66.40	-1.52	-0.59	66.60	-1.60	-0.63
BD6YC3		65.46	-2.46	-0.95	66.86	-1.34	-0.52
DLXVBP		68.16	0.24	0.09	68.46	0.26	0.10
GGRELJ		70.40	2.48	0.96	70.80	2.60	1.02
H3NM2R		67.42	-0.50	-0.19	68.70	0.50	0.19
JGXMGN		70.00	2.08	0.81	69.00	0.80	0.31
P2RFXF		67.10	-0.82	-0.32	67.42	-0.78	-0.31
PYXREK		69.80	1.88	0.73	70.00	1.80	0.70
QZQRAA		70.84	2.92	1.13	70.56	2.36	0.92
V8W642		70.40	2.48	0.96	70.80	2.60	1.02

Summary Statistics	
Grand Means	
67.919 Type A	68.201 Type A
Stnd Dev Btwn Labs	
2.579 Type A	2.558 Type A
Statistics based on 16 of 16 reporting participants	

Samples RC21: Nitrile O-Ring & RC22: Nitrile O-Ring



Rubber Interlaboratory Testing Program

Analysis 647


O-Ring Hardness (Shore A)

Report #213

3rd Qtr 2022

Grand Mean Sample **RC21** = 67.919 Type A

Grand Mean Sample **RC22** = 68.201 Type A



If fewer than 20 laboratories are included in an analysis, a control ellipse will not be drawn on the two-sample plot.



Rubber Interlaboratory Testing Program

Analysis 648

Report #213

3rd Qtr 2022

O-Ring Hardness (Shore M)

WebCode	Data Flag	Sample RC21			Sample RC22		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2ZWXME		76.52	1.20	0.80	77.04	1.52	1.13
7QU6H4		74.80	-0.52	-0.35	75.40	-0.12	-0.09
87JGNJ		73.40	-1.92	-1.28	74.00	-1.52	-1.13
8BVE8Y		73.60	-1.72	-1.15	73.40	-2.12	-1.58
9ZQRPR		75.92	0.60	0.40	76.08	0.56	0.41
BD6YC3		74.36	-0.96	-0.64	74.56	-0.96	-0.72
GGRELJ		75.46	0.14	0.09	75.72	0.20	0.15
JGXMGN		73.60	-1.72	-1.15	74.40	-1.12	-0.84
PYXREK		77.60	2.28	1.52	77.00	1.48	1.10
QZQRAA		75.84	0.52	0.34	75.58	0.06	0.04
V8W642		77.44	2.12	1.41	77.58	2.06	1.53

Grand Means		Summary Statistics	
75.322	Type M	75.524	Type M
1.503	Type M	1.345	Type M
Statistics based on 11 of 11 reporting participants			

Samples RC21: Nitrile O-Ring & RC22: Nitrile O-Ring



Rubber Interlaboratory Testing Program

Analysis 648


O-Ring Hardness (Shore M)

Report #213

3rd Qtr 2022

Grand Mean Sample **RC21** = 75.322 Type M

Grand Mean Sample **RC22** = 75.524 Type M



If fewer than 20 laboratories are included in an analysis, a control ellipse will not be drawn on the two-sample plot.



Rubber Interlaboratory Testing Program

Analysis 649

O-Ring Density

Report #213

3rd Qtr 2022

WebCode	Data Flag	Sample RC21			Sample RC22		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2ZWXME		1.212	-0.001	-0.40	1.208	-0.005	-0.84
73MQNY		1.215	0.002	0.71	1.216	0.004	0.61
7QU6H4		1.218	0.005	1.92	1.216	0.003	0.51
87JGNJ		1.212	-0.001	-0.52	1.214	0.001	0.15
8BVE8Y		1.217	0.003	1.23	1.216	0.004	0.61
97UP4X		1.213	0.000	-0.18	1.208	-0.004	-0.73
9ZQRPR	*	1.208	-0.005	-1.96	1.193	-0.019	-3.33
BD6YC3		1.213	0.000	-0.03	1.213	0.000	0.02
DLXVBP		1.216	0.003	1.14	1.218	0.006	1.00
GGRELJ		1.214	0.001	0.31	1.215	0.002	0.35
H3NM2R		1.213	0.000	0.06	1.214	0.001	0.16
JGXMGN		1.210	-0.004	-1.37	1.214	0.001	0.23
P2RFXF		1.215	0.002	0.56	1.215	0.002	0.37
PYXREK		1.211	-0.003	-1.04	1.214	0.002	0.31
QZQRAA		1.214	0.000	0.11	1.214	0.001	0.16
V8W642		1.212	-0.001	-0.55	1.215	0.002	0.41

Summary Statistics

Grand Means

1.2133 g/cm³ (Mg/m³)

1.2126 g/cm³ (Mg/m³)

Stnd Dev Btwn Labs

0.0027 g/cm³ (Mg/m³)

0.0058 g/cm³ (Mg/m³)

Statistics based on 16 of 16 reporting participants

Samples RC21: Nitrile O-Ring & RC22: Nitrile O-Ring



Rubber Interlaboratory Testing Program

Analysis 649


O-Ring Density

Report #213

3rd Qtr 2022

Grand Mean Sample **RC21** = 1.2133 g/cm³
(Mg/m³)

Grand Mean Sample **RC22** = 1.2126 g/cm³
(Mg/m³)



If fewer than 20 laboratories are included in an analysis, a control ellipse will not be drawn on the two-sample plot.



Rubber Interlaboratory Testing Program

Analysis 650

Report #213

3rd Qtr 2022

O-Ring Compression Set Method B

WebCode	Data Flag	Sample RC23			Sample RC24		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2ZWXME		10.540	1.900	1.49	10.597	1.904	1.55
7QU6H4		9.703	1.064	0.83	10.677	1.984	1.62
87JGNJ		9.800	1.160	0.91	8.800	0.108	0.09
9ZQRPR		9.000	0.360	0.28	9.000	0.308	0.25
BD6YC3		8.800	0.160	0.13	8.800	0.108	0.09
DLXVBP		9.233	0.594	0.47	9.200	0.508	0.41
GGRELJ		9.000	0.360	0.28	9.000	0.308	0.25
H3NM2R		8.800	0.160	0.13	8.800	0.108	0.09
JGXMGN		7.333	-1.306	-1.02	7.333	-1.359	-1.11
PYXREK		8.000	-0.640	-0.50	7.000	-1.692	-1.38
QZQRAA		7.667	-0.973	-0.76	8.333	-0.359	-0.29
V8W642		5.800	-2.840	-2.23	6.767	-1.926	-1.57

Summary Statistics	
Grand Means	
8.6397 % Compression	8.6922 % Compression
Stnd Dev Btwn Labs	
1.2749 % Compression	1.2282 % Compression
Statistics based on 12 of 12 reporting participants	

Samples RC23: Nitrile O-Ring & RC24: Nitrile O-Ring



Rubber Interlaboratory Testing Program

Analysis 650


Report #213

3rd Qtr 2022

O-Ring Compression Set Method B

Grand Mean Sample **RC23** = 8.6397 % Compression

Grand Mean Sample **RC24** = 8.6922 % Compression



If fewer than 20 laboratories are included in an analysis, a control ellipse will not be drawn on the two-sample plot.

**Rubber Interlaboratory Testing Program**

Report #213

Analysis 660

3rd Qtr 2022

Mooney Viscosity: 4-minute readings (ML 1 + 4)

WebCode	Data Flag	Sample U21-U22			Sample U23-U24			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
2JUWC2		47.76	0.05	0.06	53.59	0.71	0.65	MR
2KZLB6		47.33	-0.38	-0.45	51.38	-1.50	-1.38	XX
2X9AJ2	X	53.66	5.94	7.10	59.04	6.15	5.66	MR
2XQBAB		47.88	0.16	0.20	52.82	-0.07	-0.06	MR
37VPMW		48.70	0.99	1.18	54.05	1.17	1.07	MR
38PD7R		47.98	0.27	0.33	52.92	0.03	0.03	MR
3VZCUQ		48.58	0.87	1.04	53.80	0.92	0.84	MR
4VV AJD		46.60	-1.11	-1.33	51.35	-1.53	-1.41	MR
72VHVX		48.57	0.86	1.03	54.87	1.98	1.82	MV
86L7TF	*	48.48	0.76	0.91	51.28	-1.60	-1.48	MR
8ECRZZ		49.66	1.95	2.33	54.19	1.30	1.20	XX
ARTL6N	*	47.45	-0.26	-0.31	55.25	2.37	2.18	MR
C3837U		47.87	0.16	0.19	53.12	0.23	0.21	MR
CCEZWJ		48.37	0.66	0.78	52.83	-0.05	-0.05	MR
CL3NVR		46.62	-1.09	-1.31	52.35	-0.53	-0.49	MR
CN7L4Y		47.75	0.04	0.05	52.90	0.02	0.02	MR
DEB7QE		46.60	-1.12	-1.33	51.65	-1.23	-1.13	MV
DLXVBP		48.32	0.61	0.72	53.75	0.87	0.80	ML
E7XANT		46.44	-1.27	-1.51	51.77	-1.11	-1.02	MV
EX7VJM		46.15	-1.56	-1.86	51.52	-1.37	-1.26	MV
G2FT4F		48.50	0.79	0.94	53.92	1.03	0.95	MR
G47U8H		46.90	-0.81	-0.97	52.57	-0.32	-0.29	MP
H36LBH		48.29	0.58	0.69	54.34	1.46	1.34	MR
JM8RJA		46.83	-0.88	-1.05	51.95	-0.93	-0.86	MM
KZQZED		47.31	-0.40	-0.48	53.79	0.91	0.83	TA
M3BM7R		49.17	1.46	1.75	55.01	2.13	1.95	ML
MX24AK		46.18	-1.53	-1.83	52.08	-0.80	-0.74	MR
NLFJZ8		47.79	0.08	0.09	52.93	0.05	0.05	MR
NVM7A8		47.37	-0.34	-0.41	52.02	-0.87	-0.80	MR
PXNQAD		47.50	-0.21	-0.25	51.33	-1.55	-1.43	MV
UVMCUA		48.07	0.36	0.43	53.87	0.99	0.91	MR
V8W642		47.23	-0.48	-0.57	52.08	-0.80	-0.74	MR
VDHZ2Y		46.40	-1.31	-1.57	51.51	-1.37	-1.26	MR
VNHUT3		47.96	0.24	0.29	53.32	0.43	0.40	TA
W49VN9		47.74	0.03	0.03	52.90	0.01	0.01	MV
WC3ZGA		47.95	0.24	0.29	52.85	-0.03	-0.03	MR
X48J4P		48.27	0.56	0.67	52.59	-0.29	-0.27	TV
XUJN9F		47.65	-0.06	-0.07	51.92	-0.97	-0.89	MR



Rubber Interlaboratory Testing Program

Analysis 660

Report #213

3rd Qtr 2022

Mooney Viscosity: 4-minute readings (ML 1 + 4)

WebCode	Data Flag	Sample U21-U22			Sample U23-U24			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
YP4FFA		47.69	-0.02	-0.03	52.95	0.07	0.06	MV
ZD3EC6		48.82	1.11	1.32	53.15	0.27	0.25	MR

Grand Means	Summary Statistics
47.710 ML 1 + 4	52.884 ML 1 + 4
Stnd Dev Btwn Labs	1.087 ML 1 + 4
Statistics based on 39 of 40 reporting participants	

Samples U21-U22: SBR & U23-U24: Butyl

Comments on Assigned Data Flags for Test #660

2X9AJ2 (X) - Data for all samples are high. Inconsistent within the determinations of both sample groups.

Key to Instrument Codes Reported by Participants

ML	Alpha Technologies/Monsanto model not specified	MM	Alpha Technologies Model 1xxx or OSM
MP	Monsanto Compact Mooney Viscometer	MR	Alpha Technologies Model MV2000/MV2000E
MV	MonTech	TA	TA Instruments (any model)
TV	Tech Pro Visc Tech (any model)	XX	Instrument make/model not specified by lab



Rubber Interlaboratory Testing Program

Analysis 660


Report #213

3rd Qtr 2022

Mooney Viscosity: 4-minute readings (ML 1 + 4)

Grand Mean Sample U21-U22 = 47.710 ML 1 + 4

Grand Mean Sample U23-U24 = 52.884 ML 1 + 4





Rubber Interlaboratory Testing Program

Analysis 661

Report #213

3rd Qtr 2022

Mooney Viscosity: 4-min NBR/SBR & 8-min butyl readings (ML)

WebCode	Data Flag	Sample U21-U22			Sample U23-U24			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
2JUWC2		47.76	0.09	0.10	51.09	0.58	0.58	MR
2KZLB6		47.33	-0.34	-0.39	48.92	-1.60	-1.62	XX
2X9AJ2	X	53.66	5.98	6.87	54.88	4.37	4.42	MR
2XQBAB		47.88	0.20	0.23	50.39	-0.12	-0.12	MR
37VPMW		48.70	1.03	1.18	51.15	0.64	0.64	MR
38PD7R		47.98	0.31	0.36	50.75	0.24	0.24	MR
3VZCUQ		48.58	0.91	1.04	51.08	0.57	0.58	MR
4VV AJD		46.60	-1.07	-1.23	49.30	-1.21	-1.23	MR
72VHVX		48.57	0.90	1.03	51.90	1.39	1.40	MV
8ECRZZ	*	49.66	1.99	2.28	50.43	-0.08	-0.08	XX
ARTL6N		47.45	-0.22	-0.26	52.40	1.89	1.91	MR
C3837U		47.87	0.19	0.22	50.73	0.22	0.22	MR
CCEZWJ		48.37	0.69	0.80	52.25	1.74	1.76	MR
CL3NVR		46.62	-1.06	-1.21	49.78	-0.73	-0.74	MR
CN7L4Y		47.75	0.08	0.09	50.87	0.35	0.36	MR
DEB7QE		46.60	-1.08	-1.24	49.45	-1.07	-1.08	MV
DLXVBP		48.32	0.64	0.74	51.12	0.60	0.61	ML
E7XANT		46.44	-1.23	-1.41	50.09	-0.42	-0.43	MV
EX7VJM		46.15	-1.52	-1.75	48.92	-1.59	-1.61	MV
G2FT4F		48.50	0.83	0.95	51.12	0.60	0.61	MR
G47U8H		46.90	-0.77	-0.89	48.95	-1.56	-1.58	MP
H36LBH		48.29	0.62	0.71	51.44	0.93	0.94	MR
JM8RJA		46.83	-0.84	-0.96	51.83	1.32	1.34	MR
KZQZED		47.31	-0.36	-0.42	51.19	0.68	0.68	TA
M3BM7R		49.17	1.50	1.72	52.04	1.53	1.54	ML
MX24AK		46.18	-1.49	-1.71	49.74	-0.77	-0.78	MR
NLFJZ8		47.79	0.11	0.13	50.15	-0.36	-0.37	MR
NVM7A8		47.37	-0.31	-0.35	49.33	-1.18	-1.19	MR
PXNQAD		47.50	-0.17	-0.20	49.28	-1.23	-1.24	MV
V8W642		47.23	-0.44	-0.50	49.73	-0.78	-0.79	MR
VDHZ2Y		46.40	-1.27	-1.46	49.23	-1.28	-1.29	MR
W49VN9		47.74	0.07	0.07	50.77	0.26	0.26	MV
WC3ZGA		47.95	0.28	0.32	50.50	-0.01	-0.01	MR
X48J4P		48.27	0.60	0.68	50.15	-0.36	-0.37	TV
YP4FFA		47.69	0.02	0.02	51.03	0.52	0.53	MV
ZD3EC6		48.82	1.14	1.31	50.83	0.32	0.32	MR



Rubber Interlaboratory Testing Program

Analysis 661

Report #213

3rd Qtr 2022

Mooney Viscosity: 4-min NBR/SBR & 8-min butyl readings (ML)

Summary Statistics

Grand Means

47.673 ML 1 + 8

50.513 ML 1 + 8

Stnd Dev Btwn Labs

0.871 ML 1 + 8

0.988 ML 1 + 8

Statistics based on 35 of 36 reporting participants

Samples U21-U22: SBR & U23-U24: Butyl

Comments on Assigned Data Flags for Test #661

2X9AJ2 (X) - Data for all samples are high. Inconsistent within the determinations of sample group U21-U22.

Key to Instrument Codes Reported by Participants

ML	Alpha Technologies/Monsanto model not specified	MP	Monsanto Compact Mooney Viscometer
MR	Alpha Technologies Model MV2000/MV2000E	MV	Montech
TA	TA Instruments (any model)	TV	Tech Pro Visc Tech (any model)
XX	Instrument make/model not specified by lab		



Rubber Interlaboratory Testing Program

Analysis 661


Report #213

3rd Qtr 2022

Mooney Viscosity: 4-min NBR/SBR & 8-min butyl readings (ML)

Grand Mean Sample U21-U22 = 47.673 ML 1 + 8

Grand Mean Sample U23-U24 = 50.513 ML 1 + 8





Rubber Interlaboratory Testing Program

Analysis 662

Report #213

3rd Qtr 2022

Mooney Stress Relaxation: t80 (seconds)

WebCode	Data Flag	Sample U21-U22			Sample U23-U24			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
2KZLB6		12.28	0.44	0.16	5.750	-0.289	-0.53	XX
2X9AJ2		8.20	-3.64	-1.31	6.233	0.194	0.36	MR
38PD7R		12.94	1.10	0.40	5.847	-0.193	-0.35	MR
72VHVX	X	547.63	535.80	193.33	546.033	539.994	993.83	MV
8ECRZZ		13.83	2.00	0.72	7.333	1.294	2.38	XX
ARTL6N		13.00	1.16	0.42	6.000	-0.039	-0.07	MR
CL3NVR		12.81	0.97	0.35	6.030	-0.009	-0.02	MR
DEB7QE		9.93	-1.90	-0.69	5.205	-0.834	-1.54	MV
DLXVBP		13.75	1.91	0.69	6.157	0.117	0.22	ML
EX7VJM		5.14	-6.70	-2.42	5.090	-0.949	-1.75	MV
G2FT4F		13.10	1.26	0.46	6.367	0.327	0.60	MR
H36LBH	X	41.46	29.62	10.69	10.038	3.999	7.36	MR
M3BM7R		14.40	2.56	0.92	6.452	0.413	0.76	ML
MX24AK		13.07	1.23	0.44	6.207	0.167	0.31	MR
NVM7A8		12.36	0.52	0.19	5.765	-0.274	-0.50	MR
PXNQAD		5.77	-6.07	-2.19	5.200	-0.839	-1.54	MV
W49VN9		12.00	0.16	0.06	6.000	-0.039	-0.07	MV
WC3ZGA		12.82	0.98	0.35	6.017	-0.023	-0.04	MR
X48J4P	X	11.11	-0.73	-0.26	11.095	5.056	9.30	TV
XUJN9F		12.90	1.06	0.38	6.600	0.561	1.03	MR
ZD3EC6		14.77	2.93	1.06	6.453	0.414	0.76	MR

Grand Means		Summary Statistics	
		11.836 seconds	6.0392 seconds
Stnd Dev Btwn Labs		2.771 seconds	0.5433 seconds
Statistics based on 18 of 21 reporting participants			

Samples U21-U22: SBR & U23-U24: Butyl

Comments on Assigned Data Flags for Test #662

72VHVX (X) - Extreme Data.

H36LBH (X) - Extreme Data.

X48J4P (X) - Data for sample group U23-U24 are high.



Rubber Interlaboratory Testing Program

Analysis 662

Report #213

3rd Qtr 2022

Mooney Stress Relaxation: t80 (seconds)

Key to Instrument Codes Reported by Participants

ML	Alpha Technologies/Monsanto model not specified	MR	Alpha Technologies Model MV2000/MV2000E
MV	MonTech	TV	Tech Pro Visc Tech (any model)
XX	Instrument make/model not specified by lab		



Rubber Interlaboratory Testing Program

Report #213


Analysis 662

3rd Qtr 2022

Mooney Stress Relaxation: t₈₀ (seconds)

Grand Mean Sample U21-U22 = 11.836 seconds

Grand Mean Sample U23-U24 = 6.0392 seconds



If fewer than 20 laboratories are included in an analysis, a control ellipse will not be drawn on the two-sample plot.



Rubber Interlaboratory Testing Program

Analysis 663

Report #213

3rd Qtr 2022

Mooney Stress Relaxation: X30 (percent)

WebCode	Data Flag	Sample U21-U22			Sample U23-U24			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
2KZLB6		85.97	-0.29	-0.10	94.63	0.50	0.44	XX
2X9AJ2		87.68	1.42	0.47	92.74	-1.39	-1.22	MR
38PD7R		85.46	-0.79	-0.26	94.09	-0.04	-0.04	MR
72VHVX		88.88	2.62	0.86	94.38	0.25	0.22	MV
8ECRZZ		85.00	-1.26	-0.41	92.62	-1.52	-1.34	XX
ARTL6N	X	1,468.18	1,381.92	453.59	715.04	620.91	546.82	MR
CL3NVR		85.70	-0.56	-0.18	94.68	0.55	0.48	MR
DEB7QE		87.44	1.19	0.39	95.68	1.54	1.36	MV
DLXVBP	X	14.95	-71.31	-23.40	6.35	-87.79	-77.31	ML
EX7VJM		89.04	2.78	0.91	96.26	2.13	1.88	MV
G2FT4F		85.43	-0.82	-0.27	93.83	-0.30	-0.26	MR
H36LBH	*	77.39	-8.87	-2.91	91.99	-2.15	-1.89	MR
M3BM7R		84.75	-1.51	-0.50	93.06	-1.08	-0.95	ML
MX24AK		85.48	-0.78	-0.26	93.75	-0.38	-0.34	MR
NVM7A8		86.03	-0.23	-0.08	95.13	1.00	0.88	MR
PXNQAD		92.72	6.46	2.12	95.62	1.49	1.31	MV
W49VN9		86.00	-0.26	-0.08	94.50	0.37	0.32	MV
WC3ZGA		85.57	-0.69	-0.23	93.88	-0.25	-0.22	MR
X48J4P		89.45	3.19	1.05	94.27	0.13	0.12	TV
ZD3EC6		84.67	-1.59	-0.52	93.29	-0.85	-0.75	MR

Summary Statistics

Grand Means

86.257 percent

94.134 percent

Stnd Dev Btwn Labs

3.047 percent

1.135 percent

Statistics based on 18 of 20 reporting participants

Samples U21-U22: SBR & U23-U24: Butyl

Comments on Assigned Data Flags for Test #663

ARTL6N (X) - Extreme Data.

DLXVBP (X) - Extreme Data.

Key to Instrument Codes Reported by Participants

ML Alpha Technologies/Monsanto model not specified

MR Alpha Technologies Model MV2000/MV2000E

MV Montech

TV Tech Pro Visc Tech (any model)

XX Instrument make/model not specified by lab



Rubber Interlaboratory Testing Program


Report #213

3rd Qtr 2022

Mooney Stress Relaxation: X30 (percent)

Grand Mean Sample U21-U22 = 86.257 percent

Grand Mean Sample **U23-U24** = 94.134 percent



If fewer than 20 laboratories are included in an analysis, a control ellipse will not be drawn on the two-sample plot.



Rubber Interlaboratory Testing Program

Analysis 664

Report #213

3rd Qtr 2022

Mooney Stress Relaxation: Area under curve (M-s)

WebCode	Data Flag	Sample U21-U22			Sample U23-U24			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
2KZLB6		715.1	14.6	0.15	312.2	-42.2	-0.59	XX
2X9AJ2		650.4	-50.1	-0.51	455.3	100.9	1.41	MR
38PD7R		754.3	53.8	0.55	347.2	-7.3	-0.10	MR
72VHVX		539.0	-161.6	-1.64	337.8	-16.6	-0.23	MV
8ECRZZ		808.4	107.9	1.10	464.8	110.4	1.54	XX
ARTL6N		751.5	51.0	0.52	440.9	86.5	1.21	MR
CL3NVR		721.5	21.0	0.21	323.2	-31.3	-0.44	XX
DEB7QE		617.9	-82.6	-0.84	241.2	-113.2	-1.58	MV
DLXVBP		781.7	81.1	0.83	381.0	26.6	0.37	ML
EX7VJM		529.3	-171.3	-1.74	213.8	-140.6	-1.96	MV
G2FT4F		769.0	68.5	0.70	379.0	24.6	0.34	MR
H36LBH		741.4	40.9	0.42	344.1	-10.3	-0.14	MR
M3BM7R		854.4	153.9	1.57	472.5	118.0	1.65	ML
MX24AK		722.4	21.8	0.22	364.1	9.7	0.13	MR
NVM7A8		710.7	10.2	0.10	286.8	-67.6	-0.94	MR
PXNQAD	X	330.0	-370.5	-3.77	245.2	-109.2	-1.52	MV
W49VN9		700.8	0.2	0.00	320.1	-34.3	-0.48	MV
WC3ZGA		746.7	46.1	0.47	362.3	7.9	0.11	MR
X48J4P		495.2	-205.3	-2.09	333.3	-21.1	-0.30	TV

Grand Means		Summary Statistics	
		700.53 M-s	354.43 M-s
Std Dev Btwn Labs		98.23 M-s	71.63 M-s
Statistics based on 18 of 19 reporting participants			

Samples U21-U22: SBR & U23-U24: Butyl

Comments on Assigned Data Flags for Test #664

PXNQAD (X) - Data for sample group U21-U22 are low.

Key to Instrument Codes Reported by Participants

ML	Alpha Technologies/Monsanto model not specified	MR	Alpha Technologies Model MV2000/MV2000E
MV	MonTech	TV	Tech Pro Visc Tech (any model)
XX	Instrument make/model not specified by lab		



Rubber Interlaboratory Testing Program

Analysis 664


Report #213

3rd Qtr 2022

Mooney Stress Relaxation: Area under curve (M-s)

Grand Mean Sample U21-U22 = 700.53 M-s

Grand Mean Sample U23-U24 = 354.43 M-s



If fewer than 20 laboratories are included in an analysis, a control ellipse will not be drawn on the two-sample plot.



Rubber Interlaboratory Testing Program

Analysis 669

Report #213

3rd Qtr 2022

ODR Vulcanization-Cure Time 10% (minutes)

WebCode	Data Flag	Sample Y21-Y22			Sample Y23-Y24		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2XQBAB		1.562	-0.144	-1.59	3.327	-0.202	-1.30
72VHVX		1.748	0.043	0.47	3.468	-0.060	-0.39
8R3LDT		1.752	0.046	0.51	3.515	-0.013	-0.09
DEB7QE		1.677	-0.029	-0.32	3.750	0.222	1.43
FT78FL		1.790	0.084	0.93	3.582	0.053	0.34

Grand Means		Summary Statistics	
Stnd Dev Btwn Labs	1.7057 minutes	3.5283 minutes	
	0.0903 minutes	0.1553 minutes	
Statistics based on 5 of 5 reporting participants			

Samples Y21-Y22: EPDM compound, batch #1 & Y23-Y24: EPDM compound, batch #2



Rubber Interlaboratory Testing Program

Report #213


Analysis 669

3rd Qtr 2022

ODR Vulcanization-Cure Time 10% (minutes)

Grand Mean Sample Y21-Y22 = 1.7057 minutes

Grand Mean Sample Y23-Y24 = 3.5283 minutes



If fewer than 20 laboratories are included in an analysis, a control ellipse will not be drawn on the two-sample plot.



Rubber Interlaboratory Testing Program

Analysis 670

Report #213

3rd Qtr 2022

ODR Vulcanization-Scorch Time, Ts1 (minutes)

WebCode	Data Flag	Sample Y21-Y22			Sample Y23-Y24		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2XQBAB		1.190	-0.092	-1.36	2.602	-0.044	-0.31
72VHVX		1.340	0.058	0.87	2.517	-0.129	-0.92
8R3LDT		1.318	0.037	0.54	2.573	-0.072	-0.51
DEB7QE		1.230	-0.052	-0.77	2.880	0.235	1.67
FT78FL		1.330	0.048	0.72	2.655	0.010	0.07

Grand Means		Summary Statistics	
1.2817 minutes		2.6453 minutes	
Stnd Dev Btwn Labs		0.1404 minutes	
0.0674 minutes		Statistics based on 5 of 5 reporting participants	

Samples Y21-Y22: EPDM compound, batch #1 & Y23-Y24: EPDM compound, batch #2



Rubber Interlaboratory Testing Program

Analysis 670


Report #213

3rd Qtr 2022

ODR Vulcanization-Schorch Time, Ts1 (minutes)

Grand Mean Sample Y21-Y22 = 1.2817 minutes

Grand Mean Sample Y23-Y24 = 2.6453 minutes



If fewer than 20 laboratories are included in an analysis, a control ellipse will not be drawn on the two-sample plot.



Rubber Interlaboratory Testing Program

Analysis 671

Report #213

3rd Qtr 2022

ODR Vulcanization-Cure Time 50% (minutes)

WebCode	Data Flag	Sample Y21-Y22			Sample Y23-Y24		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2XQBAB		3.110	-0.113	-0.86	6.170	-0.429	-1.26
72VHVX		3.088	-0.134	-1.02	6.400	-0.199	-0.58
8R3LDT		3.290	0.067	0.51	7.040	0.441	1.30
DEB7QE		3.218	-0.004	-0.03	6.810	0.211	0.62
FT78FL		3.407	0.184	1.40	6.573	-0.025	-0.07

Grand Means		Summary Statistics	
3.2228 minutes		6.5987 minutes	
0.1317 minutes		0.3403 minutes	
Statistics based on 5 of 5 reporting participants			

Samples Y21-Y22: EPDM compound, batch #1 & Y23-Y24: EPDM compound, batch #2



Rubber Interlaboratory Testing Program

Report #213


Analysis 671

3rd Qtr 2022

ODR Vulcanization-Cure Time 50% (minutes)

Grand Mean Sample Y21-Y22 = 3.2228 minutes

Grand Mean Sample Y23-Y24 = 6.5987 minutes



If fewer than 20 laboratories are included in an analysis, a control ellipse will not be drawn on the two-sample plot.



Rubber Interlaboratory Testing Program

Analysis 672

Report #213

3rd Qtr 2022

ODR Vulcanization-Cure Time 90% (minutes)

WebCode	Data Flag	Sample Y21-Y22			Sample Y23-Y24		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2XQBAB		18.37	5.71	1.71	15.92	2.62	1.68
72VHVX		10.68	-1.99	-0.59	12.17	-1.13	-0.72
8R3LDT		10.36	-2.31	-0.69	12.93	-0.37	-0.23
DEB7QE		11.00	-1.66	-0.50	13.36	0.07	0.04
FT78FL		12.91	0.25	0.07	12.10	-1.20	-0.77

Grand Means		Summary Statistics	
12.662 minutes		13.296 minutes	
Stnd Dev Btwn Labs		1.558 minutes	
Statistics based on 5 of 5 reporting participants			

Samples Y21-Y22: EPDM compound, batch #1 & Y23-Y24: EPDM compound, batch #2



Rubber Interlaboratory Testing Program

Report #213


Analysis 672

3rd Qtr 2022

ODR Vulcanization-Cure Time 90% (minutes)

Grand Mean Sample Y21-Y22 = 12.662 minutes

Grand Mean Sample Y23-Y24 = 13.296 minutes



If fewer than 20 laboratories are included in an analysis, a control ellipse will not be drawn on the two-sample plot.



Rubber Interlaboratory Testing Program

Analysis 673

Report #213

3rd Qtr 2022

ODR Vulcanization: Minimum Torque (lbf.in)

WebCode	Data Flag	Sample Y21-Y22			Sample Y23-Y24		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2XQBAB		10.992	2.098	1.28	16.28	4.22	1.36
72VHVX		7.818	-1.075	-0.65	9.98	-2.08	-0.67
8R3LDT		7.378	-1.515	-0.92	8.55	-3.51	-1.13
DEB7QE		10.323	1.430	0.87	13.94	1.88	0.61
FT78FL		7.955	-0.938	-0.57	11.54	-0.52	-0.17

Grand Means	Summary Statistics
8.8933 lbf.in	12.057 lbf.in
Stnd Dev Btwn Labs	3.091 lbf.in
Statistics based on 5 of 5 reporting participants	

Grand Means	Summary Statistics in SI Units
10.048 dN.m	13.622 dN.m
Stnd Dev Btwn Labs	3.493 dN.m
Statistics based on 5 of 5 reporting participants	

Samples Y21-Y22: EPDM compound, batch #1 & Y23-Y24: EPDM compound, batch #2



Rubber Interlaboratory Testing Program

Analysis 673


Report #213

3rd Qtr 2022

ODR Vulcanization: Minimum Torque (lbf.in)

Grand Mean Sample Y21-Y22 = 8.8933 lbf.in

Grand Mean Sample Y23-Y24 = 12.057 lbf.in



If fewer than 20 laboratories are included in an analysis, a control ellipse will not be drawn on the two-sample plot.



Rubber Interlaboratory Testing Program

Analysis 674

Report #213

3rd Qtr 2022

ODR Vulcanization: Maximum Torque (lbf.in)

WebCode	Data Flag	Sample Y21-Y22			Sample Y23-Y24		
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV
2XQBAB		45.70	0.02	0.01	41.76	2.86	1.01
72VHVX		48.44	2.76	0.84	39.72	0.82	0.29
8R3LDT		40.11	-5.57	-1.70	34.16	-4.74	-1.67
DEB7QE		46.55	0.86	0.26	39.71	0.81	0.29
FT78FL		47.62	1.93	0.59	39.14	0.25	0.09

Grand Means	Summary Statistics
45.682 lbf.in	38.896 lbf.in
Stnd Dev Btwn Labs	2.831 lbf.in
Statistics based on 5 of 5 reporting participants	

Grand Means	Summary Statistics in SI Units
51.613 dN.m	43.947 dN.m
Stnd Dev Btwn Labs	3.198 dN.m
Statistics based on 5 of 5 reporting participants	

Samples Y21-Y22: EPDM compound, batch #1 & Y23-Y24: EPDM compound, batch #2



Rubber Interlaboratory Testing Program

Analysis 674


Report #213

3rd Qtr 2022

ODR Vulcanization: Maximum Torque (lbf.in)

Grand Mean Sample Y21-Y22 = 45.682 lbf.in

Grand Mean Sample Y23-Y24 = 38.896 lbf.in



If fewer than 20 laboratories are included in an analysis, a control ellipse will not be drawn on the two-sample plot.

**Rubber Interlaboratory Testing Program**

Report #213

Analysis 684

3rd Qtr 2022

MDR Vulcanization-Cure Time 10% (minutes)

WebCode	Data Flag	Sample Y25-Y26			Sample Y27-Y28			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
2JUWC2		2.783	0.170	1.62	2.840	0.192	1.82	MC
2KZLB6		2.550	-0.063	-0.60	2.573	-0.074	-0.70	XX
2UPA8R		2.593	-0.020	-0.19	2.635	-0.013	-0.12	ME
2X9AJ2		2.788	0.175	1.66	2.813	0.166	1.57	MX
2XQBAB		2.457	-0.157	-1.49	2.475	-0.173	-1.63	MC
38PD7R		2.753	0.140	1.33	2.770	0.122	1.16	MC
3J3TUC		2.525	-0.088	-0.84	2.581	-0.067	-0.63	MC
3VZCUQ		2.613	0.000	0.00	2.650	0.002	0.02	MC
72VHVX		2.425	-0.188	-1.79	2.508	-0.139	-1.32	MM
7MNN4L		2.540	-0.073	-0.70	2.610	-0.038	-0.36	MC
7QU6H4		2.692	0.078	0.74	2.710	0.062	0.59	MC
86L7TF		2.767	0.153	1.46	2.757	0.109	1.03	MC
8ECRZZ		2.632	0.018	0.17	2.635	-0.013	-0.12	ME
ARTL6N		2.608	-0.005	-0.05	2.630	-0.018	-0.17	MC
C3837U		2.781	0.167	1.59	2.782	0.134	1.27	MC
DEB7QE		2.517	-0.097	-0.92	2.580	-0.068	-0.64	XX
DLXVBP	*	2.600	-0.013	-0.13	2.745	0.097	0.92	ME
E7XANT	*	2.362	-0.252	-2.39	2.337	-0.311	-2.94	MC
EX7VJM		2.435	-0.178	-1.70	2.482	-0.166	-1.57	MR
G47U8H		2.745	0.132	1.25	2.783	0.136	1.28	ME
H36LBH		2.645	0.032	0.30	2.665	0.017	0.16	MD
H3NM2R		2.682	0.068	0.65	2.728	0.081	0.76	MC
HMPKFD		2.847	0.234	2.22	2.895	0.247	2.33	MC
L63YTR		2.673	0.060	0.57	2.718	0.071	0.67	XX
LH43N7		2.505	-0.108	-1.03	2.522	-0.126	-1.19	MC
M3BM7R		2.627	0.014	0.13	2.572	-0.075	-0.71	MM
MX24AK		2.562	-0.052	-0.49	2.593	-0.054	-0.51	MD
NDLE87		2.600	-0.013	-0.13	2.637	-0.011	-0.10	MM
NVM7A8		2.635	0.022	0.21	2.680	0.032	0.31	MC
PNZVDH		2.502	-0.112	-1.06	2.607	-0.041	-0.39	MP
PXNQAD		2.563	-0.050	-0.48	2.610	-0.038	-0.36	MM
PYXREK		2.587	-0.027	-0.25	2.638	-0.009	-0.09	ME
QJ4LLG		2.600	-0.013	-0.13	2.688	0.041	0.38	ME
V8W642		2.638	0.025	0.24	2.600	-0.048	-0.45	MC
VDHZ2Y		2.652	0.038	0.36	2.673	0.026	0.24	MC
VNHUT3		2.670	0.057	0.54	2.678	0.031	0.29	MP
W49VN9		2.643	0.030	0.28	2.602	-0.046	-0.44	MC
WC3ZGA		2.553	-0.060	-0.57	2.602	-0.046	-0.44	ME



Rubber Interlaboratory Testing Program

Analysis 684

Report #213

3rd Qtr 2022

MDR Vulcanization-Cure Time 10% (minutes)

WebCode	Data Flag	Sample Y25-Y26			Sample Y27-Y28			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
WVGLYB		2.608	-0.005	-0.05	2.703	0.056	0.53	MC
X48J4P	X	2.902	0.288	2.74	2.747	0.099	0.94	MM
YY7ZGG		2.592	-0.022	-0.21	2.618	-0.029	-0.28	ME
ZD3EC6		2.600	-0.013	-0.13	2.630	-0.018	-0.17	MC

Grand Means		Summary Statistics	
2.6134 minutes		2.6477 minutes	
Stnd Dev Btwn Labs		0.1052 minutes	
		0.1057 minutes	
Statistics based on 41 of 42 reporting participants			

Samples Y25-Y26: EPDM compound, batch #1 & Y27-Y28: EPDM compound, batch #2

Comments on Assigned Data Flags for Test #684

X48J4P (X) - Data for sample group Y25-Y26 are high. Inconsistent within the determinations of sample group Y27-Y28.

Key to Instrument Codes Reported by Participants

MC	Alpha Technologies [Monsanto] MDR 2000 or 2000E	MD	Alpha Tech. Rubber Process Analyzer (RPA 2000)
ME	Alpha Tech. MDR Premiere	MM	MonTech MDR 3000
MP	Alpha Technologies [Monsanto] MDR 2000P	MR	MonTech D-RPA 3000
MX	Rebuilt MonTech Alpha	XX	Instrument model not specified by lab



Rubber Interlaboratory Testing Program

Analysis 684


Report #213

3rd Qtr 2022

MDR Vulcanization-Cure Time 10% (minutes)

Grand Mean Sample Y25-Y26 = 2.6134 minutes

Grand Mean Sample Y27-Y28 = 2.6477 minutes



**Rubber Interlaboratory Testing Program**

Report #213

Analysis 685

3rd Qtr 2022

MDR Vulcanization-Scorch Time, Ts1 (minutes)

WebCode	Data Flag	Sample Y25-Y26			Sample Y27-Y28			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
2JUWC2		2.793	0.208	1.34	2.837	0.221	1.43	MC
2KZLB6		2.548	-0.037	-0.24	2.588	-0.027	-0.17	XX
2UPA8R		2.675	0.090	0.58	2.675	0.060	0.39	ME
2X9AJ2		2.713	0.128	0.83	2.802	0.186	1.21	MX
2XQBAB		2.467	-0.118	-0.76	2.505	-0.110	-0.71	MC
38PD7R		2.705	0.120	0.77	2.743	0.128	0.83	MC
3J3TUC		2.444	-0.141	-0.91	2.500	-0.115	-0.74	MC
3M4GRL		2.342	-0.243	-1.57	2.372	-0.244	-1.57	MC
3VZCUQ		2.740	0.155	1.00	2.742	0.126	0.82	MC
72VHVX		2.517	-0.068	-0.44	2.588	-0.027	-0.17	MM
7MNN4L		2.545	-0.040	-0.26	2.590	-0.025	-0.16	MC
7QU6H4		2.772	0.187	1.20	2.758	0.143	0.93	MC
86L7TF		2.642	0.057	0.36	2.607	-0.009	-0.06	MC
8ECRZZ		2.657	0.072	0.46	2.648	0.033	0.21	ME
ARTL6N		2.450	-0.135	-0.87	2.477	-0.139	-0.90	MC
C3837U		2.725	0.140	0.90	2.740	0.125	0.81	MC
CCEZWJ	*	2.122	-0.463	-2.98	2.168	-0.447	-2.89	MR
CL3NVR		2.428	-0.158	-1.01	2.509	-0.106	-0.69	MC
DEB7QE		2.805	0.220	1.42	2.828	0.213	1.38	XX
DLXVBP	X	2.505	-0.080	-0.52	2.708	0.093	0.60	ME
E7XANT	*	2.272	-0.313	-2.02	2.247	-0.369	-2.38	MC
EX7VJM	X	3.395	0.810	5.21	3.428	0.813	5.26	MR
G47U8H		2.675	0.090	0.58	2.737	0.121	0.79	ME
H36LBH		2.423	-0.162	-1.04	2.422	-0.194	-1.25	MD
H3NM2R		2.588	0.003	0.02	2.593	-0.022	-0.14	MC
HMPKFD		2.895	0.309	1.99	2.903	0.288	1.86	MC
L63YTR		2.595	0.010	0.06	2.615	0.000	0.00	XX
LH43N7		2.321	-0.264	-1.70	2.316	-0.299	-1.93	MC
M3BM7R		2.658	0.073	0.47	2.620	0.005	0.03	MM
MX24AK		2.757	0.172	1.10	2.802	0.186	1.21	MD
NDLE87		2.712	0.127	0.81	2.720	0.105	0.68	MM
NVM7A8		2.662	0.077	0.49	2.687	0.071	0.46	MC
PNZVDH	*	2.492	-0.093	-0.60	2.630	0.015	0.10	MP
PXNQAD		2.448	-0.137	-0.88	2.488	-0.127	-0.82	MM
PYXREK		2.647	0.062	0.40	2.688	0.073	0.47	ME
QJ4LLG		2.492	-0.093	-0.60	2.562	-0.054	-0.35	ME
V8W642		2.663	0.078	0.50	2.628	0.013	0.08	MC
VDHZ2Y		2.623	0.038	0.25	2.648	0.033	0.21	MC



Rubber Interlaboratory Testing Program

Analysis 685

Report #213

3rd Qtr 2022

MDR Vulcanization-Scorch Time, Ts1 (minutes)

WebCode	Data Flag	Sample Y25-Y26			Sample Y27-Y28			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
VNHUT3		2.612	0.027	0.17	2.640	0.025	0.16	MP
W49VN9		2.595	0.010	0.06	2.592	-0.024	-0.15	MC
WC3ZGA		2.665	0.080	0.51	2.755	0.140	0.90	ME
WVGLYB		2.543	-0.042	-0.27	2.655	0.040	0.26	MC
X48J4P	X	3.055	0.470	3.03	2.838	0.223	1.44	MM
YY7ZGG		2.545	-0.040	-0.26	2.583	-0.032	-0.21	XX
ZD3EC6		2.603	0.018	0.12	2.630	0.015	0.10	MC

Grand Means		Summary Statistics	
Stnd Dev Btwn Labs	2.5851 minutes	2.6152 minutes	
	0.1553 minutes	0.1546 minutes	
Statistics based on 42 of 45 reporting participants			

Samples Y25-Y26: EPDM compound, batch #1 & Y27-Y28: EPDM compound, batch #2

Comments on Assigned Data Flags for Test #685

DLXVBP (X) - Inconsistent in testing between samples. Inconsistent within the determinations of sample group Y25-Y26.

EX7VJM (X) - Data for all samples are high. Possible Systematic Error.

X48J4P (X) - Data for sample group Y25-Y26 are high. Inconsistent within the determinations of sample group Y27-Y28.

Key to Instrument Codes Reported by Participants

MC	Alpha Technologies [Monsanto] MDR 2000 or 2000E	MD	Alpha Tech. Rubber Process Analyzer (RPA 2000)
ME	Alpha Tech. MDR Premiere	MM	MonTech MDR 3000
MP	Alpha Technologies [Monsanto] MDR 2000P	MR	MonTech D-RPA 3000
MX	Rebuilt MonTech Alpha	XX	Instrument model not specified by lab



Rubber Interlaboratory Testing Program

Analysis 685


Report #213

3rd Qtr 2022

MDR Vulcanization-Scorch Time, Ts1 (minutes)

Grand Mean Sample Y25-Y26 = 2.5851 minutes

Grand Mean Sample Y27-Y28 = 2.6152 minutes



**Rubber Interlaboratory Testing Program**

Report #213

Analysis 686

3rd Qtr 2022

MDR Vulcanization-Cure Time 50% (minutes)

WebCode	Data Flag	Sample Y25-Y26			Sample Y27-Y28			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
2JUWC2		6.060	0.312	1.61	6.208	0.319	1.57	MC
2KZLB6		5.562	-0.186	-0.96	5.628	-0.261	-1.28	XX
2UPA8R		5.682	-0.066	-0.34	5.782	-0.108	-0.53	ME
2X9AJ2		5.742	-0.006	-0.03	5.932	0.042	0.21	MX
2XQBAB		5.393	-0.354	-1.83	5.453	-0.436	-2.14	MC
38PD7R		6.048	0.301	1.55	6.107	0.217	1.07	MC
3J3TUC		5.770	0.022	0.11	5.947	0.058	0.28	MC
3M4GRL		5.377	-0.371	-1.91	5.508	-0.381	-1.87	MC
3VZCUQ		5.777	0.029	0.15	5.848	-0.041	-0.20	MC
72VHVX	X	4.998	-0.749	-3.86	5.273	-0.616	-3.03	MM
7MNN4L		5.825	0.077	0.40	6.055	0.166	0.81	MC
7QU6H4		5.915	0.167	0.86	6.083	0.194	0.95	MC
86L7TF		5.862	0.114	0.59	5.868	-0.021	-0.10	MC
8ECRZZ		5.818	0.071	0.36	5.950	0.061	0.30	ME
ARTL6N		5.847	0.099	0.51	5.983	0.094	0.46	MC
C3837U		6.022	0.274	1.41	6.048	0.159	0.78	MC
CCEZWJ		5.633	-0.114	-0.59	5.877	-0.013	-0.06	MR
CL3NVR		5.973	0.225	1.16	6.119	0.229	1.13	MC
DEB7QE		5.323	-0.424	-2.19	5.475	-0.414	-2.04	XX
DLXVBP		5.860	0.112	0.58	6.140	0.251	1.23	ME
E7XANT		5.555	-0.193	-0.99	5.668	-0.221	-1.09	MC
EX7VJM		5.478	-0.269	-1.39	5.598	-0.291	-1.43	MR
G47U8H		6.017	0.269	1.39	6.208	0.319	1.57	ME
H36LBH		5.748	0.001	0.00	5.870	-0.019	-0.10	MD
H3NM2R		5.750	0.002	0.01	5.937	0.047	0.23	MC
HMPKFD		6.042	0.294	1.51	6.153	0.264	1.29	MC
L63YTR		5.927	0.179	0.92	6.130	0.241	1.18	XX
LH43N7		5.492	-0.256	-1.32	5.643	-0.246	-1.21	MC
M3BM7R		5.844	0.096	0.49	5.847	-0.043	-0.21	MM
MX24AK		5.740	-0.008	-0.04	5.898	0.009	0.04	MD
NDLE87		5.817	0.069	0.36	6.033	0.144	0.71	MM
NVM7A8		5.715	-0.033	-0.17	5.895	0.006	0.03	MC
PNZVDH		5.580	-0.168	-0.86	5.858	-0.031	-0.15	MP
PXNQAD		5.502	-0.246	-1.27	5.627	-0.263	-1.29	MM
PYXREK		5.620	-0.128	-0.66	5.827	-0.063	-0.31	ME
QJ4LLG		5.692	-0.056	-0.29	5.930	0.041	0.20	ME
V8W642		5.867	0.119	0.61	5.908	0.019	0.09	MC
VDHZ2Y		5.852	0.104	0.54	6.070	0.181	0.89	MC



Rubber Interlaboratory Testing Program

Analysis 686

Report #213

3rd Qtr 2022

MDR Vulcanization-Cure Time 50% (minutes)

WebCode	Data Flag	Sample Y25-Y26			Sample Y27-Y28			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
VNHUT3		5.945	0.197	1.02	6.015	0.126	0.62	MC
W49VN9		5.737	-0.011	-0.06	5.757	-0.133	-0.65	MC
WC3ZGA		5.487	-0.261	-1.34	5.687	-0.203	-1.00	ME
WVGLYB		5.703	-0.044	-0.23	5.968	0.079	0.39	MC
X48J4P	X	5.922	0.174	0.90	5.765	-0.124	-0.61	MM
YY7ZGG		5.970	0.222	1.14	6.113	0.224	1.10	ME
ZD3EC6		5.587	-0.161	-0.83	5.590	-0.299	-1.47	MC

Summary Statistics	
Grand Means	
5.7477 minutes	5.8894 minutes
Stnd Dev Btwn Labs	
0.1942 minutes	0.2035 minutes
Statistics based on 43 of 45 reporting participants	

Samples Y25-Y26: EPDM compound, batch #1 & Y27-Y28: EPDM compound, batch #2

Comments on Assigned Data Flags for Test #686

72VHVX (X) - Data for all samples are low. Possible Systematic Error.

X48J4P (X) - Inconsistent in testing between samples. Inconsistent within the determinations of sample group Y27-Y28.

Key to Instrument Codes Reported by Participants

MC	Alpha Technologies [Monsanto] MDR 2000 or 2000E	MD	Alpha Tech. Rubber Process Analyzer (RPA 2000)
ME	Alpha Tech. MDR Premiere	MM	MonTech MDR 3000
MP	Alpha Technologies [Monsanto] MDR 2000P	MR	MonTech D-RPA 3000
MX	Rebuilt MonTech Alpha	XX	Instrument model not specified by lab



Rubber Interlaboratory Testing Program

Analysis 686


Report #213

3rd Qtr 2022

MDR Vulcanization-Cure Time 50% (minutes)

Grand Mean Sample Y25-Y26 = 5.7477 minutes

Grand Mean Sample Y27-Y28 = 5.8894 minutes



**Rubber Interlaboratory Testing Program**

Report #213

Analysis 687

3rd Qtr 2022

MDR Vulcanization-Cure Time 90% (minutes)

WebCode	Data Flag	Sample Y25-Y26			Sample Y27-Y28			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
2JUWC2		10.050	0.507	1.41	10.257	0.599	1.81	MC
2KZLB6		9.590	0.047	0.13	9.453	-0.205	-0.62	XX
2UPA8R		9.278	-0.265	-0.74	9.320	-0.338	-1.02	ME
2X9AJ2		9.455	-0.088	-0.24	9.720	0.062	0.19	MX
2XQBAB	*	10.530	0.987	2.74	10.283	0.625	1.89	MC
38PD7R		10.210	0.667	1.86	10.200	0.542	1.64	MC
3J3TUC		9.678	0.135	0.38	9.781	0.123	0.37	MC
3M4GRL		9.232	-0.311	-0.87	9.295	-0.363	-1.10	MC
3VZCUQ		9.458	-0.085	-0.24	9.465	-0.193	-0.58	MC
72VHVX	X	7.852	-1.691	-4.70	8.192	-1.466	-4.43	MM
7MNN4L		9.420	-0.123	-0.34	9.700	0.042	0.13	MC
7QU6H4		9.447	-0.096	-0.27	9.703	0.045	0.14	MC
86L7TF		9.713	0.170	0.47	9.695	0.037	0.11	MC
8ECRZZ		9.578	0.035	0.10	9.657	-0.001	0.00	ME
ARTL6N		9.268	-0.275	-0.76	9.378	-0.280	-0.85	MC
C3837U		10.092	0.549	1.53	10.043	0.385	1.16	MC
CCEZWJ		9.487	-0.056	-0.16	9.822	0.164	0.49	MR
CL3NVR		9.686	0.143	0.40	9.808	0.149	0.45	MC
DEB7QE		8.932	-0.611	-1.70	9.127	-0.531	-1.61	XX
DLXVBP		9.720	0.177	0.49	9.820	0.162	0.49	ME
E7XANT		9.325	-0.218	-0.61	9.322	-0.336	-1.02	MC
EX7VJM		8.877	-0.666	-1.85	9.118	-0.540	-1.63	MR
G47U8H		9.873	0.330	0.92	9.942	0.284	0.86	ME
H36LBH		9.493	-0.050	-0.14	9.527	-0.131	-0.40	MD
H3NM2R		9.222	-0.321	-0.89	9.530	-0.128	-0.39	MC
HMPKFD		9.747	0.204	0.57	9.878	0.220	0.66	MC
L63YTR		9.868	0.325	0.90	10.248	0.590	1.78	XX
LH43N7		8.873	-0.670	-1.86	9.148	-0.510	-1.54	MC
M3BM7R		9.530	-0.013	-0.04	9.442	-0.216	-0.65	MM
MX24AK		9.552	0.009	0.02	9.670	0.012	0.04	MD
NDLE87	*	9.930	0.387	1.08	10.323	0.665	2.01	MM
NVM7A8		9.525	-0.018	-0.05	9.740	0.082	0.25	MC
PNZVDH		9.302	-0.241	-0.67	9.475	-0.183	-0.55	MP
PXNQAD		9.287	-0.256	-0.71	9.378	-0.280	-0.85	MM
PYXREK		9.310	-0.233	-0.65	9.590	-0.068	-0.21	ME
QJ4LLG		9.380	-0.163	-0.45	9.673	0.015	0.05	ME
V8W642		9.460	-0.083	-0.23	9.508	-0.150	-0.45	MC
VDHZ2Y		9.682	0.139	0.39	9.750	0.092	0.28	MC



Rubber Interlaboratory Testing Program

Analysis 687

Report #213

3rd Qtr 2022

MDR Vulcanization-Cure Time 90% (minutes)

WebCode	Data Flag	Sample Y25-Y26			Sample Y27-Y28			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
VNHUT3		9.718	0.175	0.49	9.685	0.027	0.08	MC
W49VN9		9.758	0.215	0.60	9.743	0.085	0.26	MC
WC3ZGA	*	8.625	-0.918	-2.55	8.817	-0.841	-2.54	ME
WVGLYB		9.438	-0.105	-0.29	9.740	0.082	0.25	MC
X48J4P		9.798	0.255	0.71	9.723	0.065	0.20	MM
YY7ZGG		9.917	0.374	1.04	10.022	0.364	1.10	XX
ZD3EC6		9.577	0.034	0.09	9.435	-0.223	-0.67	MC

Grand Means		Summary Statistics	
		9.5430 minutes	9.6580 minutes
Stnd Dev Btwn Labs		0.3596 minutes	0.3308 minutes
Statistics based on 44 of 45 reporting participants			

Samples Y25-Y26: EPDM compound, batch #1 & Y27-Y28: EPDM compound, batch #2

Comments on Assigned Data Flags for Test #687

72VHVX (X) - Data for all samples are low. Possible Systematic Error.

Key to Instrument Codes Reported by Participants

MC	Alpha Technologies [Monsanto] MDR 2000 or 2000E	MD	Alpha Tech. Rubber Process Analyzer (RPA 2000)
ME	Alpha Tech. MDR Premiere	MM	MonTech MDR 3000
MP	Alpha Technologies [Monsanto] MDR 2000P	MR	MonTech D-RPA 3000
MX	Rebuilt MonTech Alpha	XX	Instrument model not specified by lab



Rubber Interlaboratory Testing Program

Analysis 687


Report #213

3rd Qtr 2022

MDR Vulcanization-Cure Time 90% (minutes)

Grand Mean Sample Y25-Y26 = 9.5430 minutes

Grand Mean Sample Y27-Y28 = 9.6580 minutes



**Rubber Interlaboratory Testing Program**

Report #213

Analysis 688

3rd Qtr 2022

MDR Vulcanization: Minimum Torque (lbf.in)

WebCode	Data Flag	Sample Y25-Y26			Sample Y27-Y28			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
2JUWC2		2.363	-0.327	-0.95	2.208	-0.322	-0.91	MC
2KZLB6		2.990	0.300	0.87	2.865	0.335	0.95	XX
2UPA8R		2.647	-0.043	-0.13	2.473	-0.057	-0.16	ME
2X9AJ2		2.723	0.033	0.10	2.577	0.047	0.13	MX
2XQBAB	*	3.717	1.027	2.99	3.643	1.113	3.16	MC
38PD7R		3.333	0.643	1.87	3.198	0.668	1.90	MC
3J3TUC		2.505	-0.185	-0.54	2.435	-0.095	-0.27	MC
3M4GRL		2.692	0.002	0.00	2.515	-0.015	-0.04	MC
3VZCUQ		2.515	-0.175	-0.51	2.383	-0.147	-0.42	MC
72VHVX		2.460	-0.230	-0.67	2.347	-0.183	-0.52	MM
7MNN4L		2.258	-0.432	-1.25	2.196	-0.333	-0.95	MC
7QU6H4		2.488	-0.202	-0.59	2.183	-0.347	-0.98	MC
86L7TF		3.028	0.338	0.98	2.744	0.214	0.61	MC
8ECRZZ		2.403	-0.287	-0.83	2.170	-0.360	-1.02	ME
ARTL6N		2.242	-0.448	-1.30	2.026	-0.504	-1.43	MC
C3837U		2.890	0.200	0.58	2.705	0.175	0.50	MC
CCEZWJ		2.530	-0.160	-0.47	2.383	-0.147	-0.42	MR
CL3NVR		2.400	-0.290	-0.84	2.310	-0.220	-0.62	MC
DEB7QE		2.757	0.067	0.19	2.620	0.090	0.26	MM
DLXVBP		2.286	-0.404	-1.17	2.157	-0.373	-1.06	ME
E7XANT		2.718	0.028	0.08	2.468	-0.062	-0.17	MC
EX7VJM		2.397	-0.293	-0.85	2.193	-0.337	-0.96	MR
G47U8H		2.182	-0.508	-1.48	2.020	-0.510	-1.45	ME
H36LBH		2.724	0.034	0.10	2.464	-0.066	-0.19	MD
H3NM2R		3.025	0.336	0.98	2.857	0.327	0.93	MC
HMPKFD		2.787	0.097	0.28	2.617	0.087	0.25	MC
L63YTR		3.210	0.520	1.51	3.172	0.642	1.82	XX
LH43N7		2.882	0.192	0.56	2.713	0.183	0.52	MC
M3BM7R		2.434	-0.256	-0.74	2.235	-0.295	-0.84	MM
MX24AK		2.060	-0.630	-1.83	1.932	-0.598	-1.70	MD
NDLE87		2.650	-0.040	-0.12	2.602	0.072	0.20	MM
NVM7A8		2.823	0.133	0.39	2.652	0.122	0.35	MC
PNZVDH		2.742	0.052	0.15	2.588	0.058	0.17	MP
PXNQAD		3.147	0.457	1.33	3.070	0.540	1.53	MM
PYXREK		2.765	0.075	0.22	2.732	0.202	0.57	ME
QJ4LLG		2.928	0.238	0.69	2.828	0.298	0.85	ME
V8W642		2.390	-0.300	-0.87	2.177	-0.353	-1.00	MC
VDHZ2Y		2.407	-0.283	-0.82	2.192	-0.338	-0.96	MC



Rubber Interlaboratory Testing Program

Analysis 688

Report #213

3rd Qtr 2022

MDR Vulcanization: Minimum Torque (lbf.in)

WebCode	Data Flag	Sample Y25-Y26			Sample Y27-Y28			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
VNHUT3		2.662	-0.028	-0.08	2.443	-0.087	-0.25	MC
W49VN9		2.870	0.180	0.52	2.682	0.152	0.43	MC
WC3ZGA		2.503	-0.187	-0.54	2.388	-0.142	-0.40	ME
WVGLYB		2.850	0.160	0.47	2.723	0.193	0.55	MC
X48J4P	*	3.402	0.712	2.07	3.078	0.548	1.56	MM
YY7ZGG		2.342	-0.348	-1.01	2.205	-0.325	-0.92	ME
ZD3EC6		2.922	0.232	0.67	2.678	0.148	0.42	MC

Grand Means		Summary Statistics	
Stnd Dev Btwn Labs	2.6900 lbf.in	2.5300 lbf.in	
	0.3439 lbf.in	0.3525 lbf.in	
Statistics based on 45 of 45 reporting participants			

Grand Means		Summary Statistics in SI Units	
Stnd Dev Btwn Labs	3.0393 dN.m	2.8585 dN.m	
	0.3885 dN.m	0.3982 dN.m	
Statistics based on 45 of 45 reporting participants			

Samples Y25-Y26: EPDM compound, batch #1 & Y27-Y28: EPDM compound, batch #2

Key to Instrument Codes Reported by Participants

MC	Alpha Technologies [Monsanto] MDR 2000 or 2000E	MD	Alpha Tech. Rubber Process Analyzer (RPA 2000)
ME	Alpha Tech. MDR Premiere	MM	MonTech MDR 3000
MP	Alpha Technologies [Monsanto] MDR 2000P	MR	MonTech D-RPA 3000
MX	Rebuilt MonTech Alpha	XX	Instrument model not specified by lab



Rubber Interlaboratory Testing Program

Analysis 688


Report #213

3rd Qtr 2022

MDR Vulcanization: Minimum Torque (lbf.in)

Grand Mean Sample Y25-Y26 = 2.6900 lbf.in

Grand Mean Sample Y27-Y28 = 2.5300 lbf.in



**Rubber Interlaboratory Testing Program**

Report #213

Analysis 689

3rd Qtr 2022

MDR Vulcanization: Maximum Torque (lbf.in)

WebCode	Data Flag	Sample Y25-Y26			Sample Y27-Y28			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
2JUWC2		12.27	-0.31	-0.44	12.22	-0.22	-0.32	MC
2KZLB6		13.02	0.43	0.62	12.72	0.28	0.40	XX
2UPA8R		11.98	-0.60	-0.85	12.18	-0.27	-0.39	ME
2X9AJ2	*	12.18	-0.40	-0.57	11.53	-0.92	-1.34	MX
2XQBAB		13.61	1.03	1.45	13.42	0.97	1.41	MC
38PD7R		13.70	1.12	1.59	13.42	0.97	1.41	MC
3J3TUC		13.09	0.51	0.72	13.02	0.57	0.83	MC
3M4GRL		12.40	-0.18	-0.26	12.15	-0.30	-0.43	MC
3VZCUQ		11.59	-0.99	-1.40	11.71	-0.74	-1.07	MC
72VHVX		11.60	-0.98	-1.39	11.63	-0.81	-1.18	MM
7MNN4L		11.59	-0.99	-1.40	11.63	-0.81	-1.18	MC
7QU6H4		11.84	-0.74	-1.05	11.80	-0.65	-0.94	MC
86L7TF		12.87	0.29	0.42	12.88	0.43	0.62	MC
8ECRZZ		12.18	-0.40	-0.56	12.06	-0.38	-0.56	ME
ARTL6N		12.31	-0.27	-0.38	12.04	-0.40	-0.59	MC
C3837U		13.25	0.67	0.95	13.01	0.56	0.81	MC
CCEZWJ		13.54	0.95	1.35	13.47	1.02	1.48	MR
CL3NVR		13.34	0.75	1.07	13.05	0.61	0.88	MC
DEB7QE		11.65	-0.93	-1.32	11.84	-0.61	-0.88	MM
DLXVBP		11.80	-0.78	-1.11	11.26	-1.18	-1.72	ME
E7XANT		13.43	0.84	1.20	13.15	0.70	1.02	MC
EX7VJM		12.57	-0.01	-0.02	12.78	0.33	0.48	MR
G47U8H		12.71	0.13	0.18	12.39	-0.06	-0.08	ME
H36LBH		13.40	0.82	1.16	13.24	0.79	1.15	MD
H3NM2R		12.66	0.08	0.11	12.70	0.26	0.37	MC
HMPKFD		12.41	-0.17	-0.24	12.43	-0.02	-0.02	MC
L63YTR		12.69	0.11	0.15	12.81	0.36	0.52	XX
LH43N7		13.24	0.66	0.93	13.15	0.70	1.02	MC
M3BM7R		12.21	-0.37	-0.53	11.89	-0.56	-0.81	MM
MX24AK	*	10.72	-1.86	-2.63	10.60	-1.85	-2.68	MD
NDLE87		11.82	-0.76	-1.08	12.00	-0.45	-0.65	MM
NVM7A8		12.60	0.02	0.02	12.61	0.16	0.23	MC
PNZVDH		12.80	0.22	0.31	12.41	-0.04	-0.05	MP
PXNQAD		14.13	1.55	2.19	14.16	1.71	2.48	MM
PYXREK		12.31	-0.27	-0.38	12.36	-0.09	-0.13	ME
QJ4LLG		12.62	0.03	0.05	12.68	0.24	0.34	ME
V8W642		12.20	-0.38	-0.54	11.97	-0.48	-0.69	MC
VDHZ2Y		12.66	0.08	0.12	12.42	-0.02	-0.03	MC



Rubber Interlaboratory Testing Program

Analysis 689

Report #213

3rd Qtr 2022

MDR Vulcanization: Maximum Torque (lbf.in)

WebCode	Data Flag	Sample Y25-Y26			Sample Y27-Y28			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
VNHUT3		13.15	0.57	0.81	12.78	0.33	0.48	MC
W49VN9		13.26	0.68	0.96	12.79	0.34	0.50	MC
WC3ZGA		11.63	-0.96	-1.35	11.22	-1.22	-1.77	ME
WVGLYB		13.38	0.79	1.13	13.09	0.64	0.93	MC
X48J4P		12.18	-0.40	-0.57	12.30	-0.15	-0.22	MM
YY7ZGG		12.69	0.11	0.15	12.48	0.03	0.05	XX
ZD3EC6		12.89	0.31	0.43	12.67	0.23	0.33	MC

Summary Statistics	
Grand Means	
12.580 lbf.in	12.447 lbf.in
Stnd Dev Btwn Labs	
0.706 lbf.in	0.690 lbf.in
Statistics based on 45 of 45 reporting participants	

Summary Statistics in SI Units	
Grand Means	
14.214 dN.m	14.063 dN.m
Stnd Dev Btwn Labs	
0.798 dN.m	0.779 dN.m
Statistics based on 45 of 45 reporting participants	

Samples Y25-Y26: EPDM compound, batch #1 & Y27-Y28: EPDM compound, batch #2

Key to Instrument Codes Reported by Participants

MC	Alpha Technologies [Monsanto] MDR 2000 or 2000E	MD	Alpha Tech. Rubber Process Analyzer (RPA 2000)
ME	Alpha Tech. MDR Premiere	MM	MonTech MDR 3000
MP	Alpha Technologies [Monsanto] MDR 2000P	MR	MonTech D-RPA 3000
MX	Rebuilt MonTech Alpha	XX	Instrument model not specified by lab



Rubber Interlaboratory Testing Program

Analysis 689


Report #213

3rd Qtr 2022

MDR Vulcanization: Maximum Torque (lbf.in)

Grand Mean Sample Y25-Y26 = 12.580 lbf.in

Grand Mean Sample Y27-Y28 = 12.447 lbf.in





Rubber Interlaboratory Testing Program

Analysis 690

Report #213

3rd Qtr 2022

RPA Rheological Properties: Part A - G' at 20Hz (kPa)

WebCode	Data Flag	Sample G21-G22			Sample G23-G24			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
72VHVX		590.9	32.9	0.51	560.2	24.5	0.38	RP
7QU6H4		495.3	-62.6	-0.97	468.3	-67.4	-1.04	PR
CL3NVR		486.1	-71.9	-1.11	470.1	-65.6	-1.01	RP
CN7L4Y		502.1	-55.9	-0.86	474.6	-61.1	-0.94	RP
DLXVBP		594.4	36.4	0.56	568.2	32.5	0.50	XX
L63YTR		689.0	131.1	2.03	669.5	133.8	2.07	XX
LH43N7		529.9	-28.1	-0.43	513.9	-21.8	-0.34	RP
M3BM7R		556.0	-2.0	-0.03	533.0	-2.7	-0.04	XX
MX24AK		519.1	-38.8	-0.60	500.9	-34.8	-0.54	RP
YY7ZGG		616.9	58.9	0.91	598.4	62.7	0.97	RP

Summary Statistics	
Grand Means	
	557.98 kPa
Stnd Dev Btwn Labs	
	64.62 kPa
64.78 kPa	
Statistics based on 10 of 10 reporting participants	

Samples G21-G22: EPDM compound, batch #1 & G23-G24: EPDM compound, batch #2

Key to Instrument Codes Reported by Participants

PR PRPA 2000

RP RPA 2000

XX Instrument model not specified by lab



Rubber Interlaboratory Testing Program

Analysis 690


Report #213

3rd Qtr 2022

RPA Rheological Properties: Part A - G' at 20Hz (kPa)

Grand Mean Sample **G21-G22** = 557.98 kPa

Grand Mean Sample **G23-G24** = 535.71 kPa



If fewer than 20 laboratories are included in an analysis, a control ellipse will not be drawn on the two-sample plot.



Rubber Interlaboratory Testing Program

Analysis 691

Report #213

3rd Qtr 2022

RPA Rheological Properties: Part A - G'' at 20Hz (kPa)

WebCode	Data Flag	Sample G21-G22			Sample G23-G24			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
72VHVX		212.8	-7.0	-0.33	202.2	-13.5	-0.65	RP
7QU6H4		206.9	-12.9	-0.62	202.1	-13.6	-0.65	PR
CL3NVR		196.8	-23.0	-1.10	195.6	-20.1	-0.96	RP
CN7L4Y		221.7	1.9	0.09	214.2	-1.5	-0.07	RP
DLXVBP		238.9	19.0	0.91	233.6	17.9	0.86	XX
L63YTR		263.1	43.3	2.06	259.6	44.0	2.11	XX
LH43N7		203.7	-16.1	-0.77	203.0	-12.7	-0.61	RP
M3BM7R		213.8	-6.0	-0.29	210.3	-5.4	-0.26	XX
MX24AK		201.8	-18.0	-0.86	199.6	-16.1	-0.77	RP
YY7ZGG		238.7	18.9	0.90	236.7	21.0	1.01	RP

Summary Statistics	
Grand Means	
219.83 kPa	215.68 kPa
Stnd Dev Btwn Labs	
20.97 kPa	20.85 kPa
Statistics based on 10 of 10 reporting participants	

Samples G21-G22: EPDM compound, batch #1 & G23-G24: EPDM compound, batch #2

Key to Instrument Codes Reported by Participants

PR PRPA 2000

RP RPA 2000

XX Instrument model not specified by lab



Rubber Interlaboratory Testing Program

Analysis 691


Report #213

3rd Qtr 2022

RPA Rheological Properties: Part A - G'' at 20Hz (kPa)

Grand Mean Sample **G21-G22** = 219.83 kPa

Grand Mean Sample **G23-G24** = 215.68 kPa



If fewer than 20 laboratories are included in an analysis, a control ellipse will not be drawn on the two-sample plot.



Rubber Interlaboratory Testing Program

Analysis 695

Report #213

3rd Qtr 2022

RPA Rheological Properties: Part B - G' at 1.0Hz (kPa)

WebCode	Data Flag	Sample G21-G22			Sample G23-G24			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
72VHVX		117.01	28.83	2.16	109.32	26.02	1.99	RP
7QU6H4		73.50	-14.68	-1.10	67.90	-15.40	-1.18	PR
CL3NVR		75.99	-12.19	-0.91	70.74	-12.56	-0.96	RP
CN7L4Y		77.54	-10.64	-0.80	71.73	-11.57	-0.88	RP
DLXVBP		88.09	-0.08	-0.01	83.19	-0.11	-0.01	XX
L63YTR		102.47	14.29	1.07	99.43	16.13	1.23	XX
LH43N7		89.09	0.91	0.07	83.69	0.39	0.03	RP
M3BM7R		91.44	3.26	0.24	87.37	4.07	0.31	XX
MX24AK		79.43	-8.75	-0.66	75.58	-7.72	-0.59	RP
YY7ZGG		87.21	-0.97	-0.07	84.04	0.74	0.06	RP

Summary Statistics	
Grand Means	
	88.178 kPa
Stnd Dev Btwn Labs	
	13.341 kPa
Statistics based on 10 of 10 reporting participants	

Samples G21-G22: EPDM compound, batch #1 & G23-G24: EPDM compound, batch #2

Key to Instrument Codes Reported by Participants

PR PRPA 2000

RP RPA 2000

XX Instrument model not specified by lab



Rubber Interlaboratory Testing Program

Analysis 695


Report #213

3rd Qtr 2022

RPA Rheological Properties: Part B - G' at 1.0Hz (kPa)

Grand Mean Sample **G21-G22** = 88.178 kPa

Grand Mean Sample **G23-G24** = 83.299 kPa



If fewer than 20 laboratories are included in an analysis, a control ellipse will not be drawn on the two-sample plot.



Rubber Interlaboratory Testing Program

Analysis 696

Report #213

3rd Qtr 2022

RPA Rheological Properties: Part B - G" at 1.0Hz (kPa)

WebCode	Data Flag	Sample G21-G22			Sample G23-G24			Instr Code
		Lab Mean	Diff from Grand Mean	CPV	Lab Mean	Diff from Grand Mean	CPV	
72VHVX		74.80	-0.80	-0.11	71.91	-1.66	-0.22	XX
7QU6H4		68.05	-7.55	-1.01	65.01	-8.56	-1.12	PR
CL3NVR		67.00	-8.59	-1.15	65.58	-7.98	-1.04	RP
CN7L4Y		67.71	-7.89	-1.06	65.44	-8.13	-1.06	XX
DLXVBP		83.40	7.80	1.04	81.18	7.61	1.00	XX
L63YTR		88.35	12.75	1.71	86.37	12.80	1.67	XX
LH43N7		72.23	-3.37	-0.45	70.70	-2.86	-0.37	RP
M3BM7R		75.78	0.18	0.02	73.38	-0.19	-0.02	XX
MX24AK		74.50	-1.10	-0.15	73.06	-0.51	-0.07	RP
YY7ZGG		84.16	8.57	1.15	83.05	9.49	1.24	RP

Summary Statistics	
Grand Means	
	75.597 kPa
Stnd Dev Btwn Labs	
	7.477 kPa
73.566 kPa	
7.647 kPa	
Statistics based on 10 of 10 reporting participants	

Samples G21-G22: EPDM compound, batch #1 & G23-G24: EPDM compound, batch #2

Key to Instrument Codes Reported by Participants

PR PRPA 2000

RP RPA 2000

XX Instrument model not specified by lab



Rubber Interlaboratory Testing Program

Analysis 696


Report #213

3rd Qtr 2022

RPA Rheological Properties: Part B - G'' at 1.0Hz (kPa)

Grand Mean Sample **G21-G22** = 75.597 kPa

Grand Mean Sample **G23-G24** = 73.566 kPa



If fewer than 20 laboratories are included in an analysis, a control ellipse will not be drawn on the two-sample plot.

-End of Report-